MIL-P-43038B(MR)
3 October 1973
SUPERSEDING
MIL-P-43038A(MR)
10 May 1968

MILITARY SPECIFICATION

PLASTIC MOLDING MATERIAL, POLYESTER, LOW-PRESSURE LAMINATING, HIGH-TEMPERATURE RESISTANT

1. SCOPE

1.1 This specification covers one type of polyester resin suitable for low pressure molding of strong-glass-laminated structures for use at high temperatures (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-C-96 - Cans, Metal, 28 Gage and Lighter
PPP-D-705 - Drum, Metal Shipping, Steel (Over and Under 55 Gallon)
PPP-D-729 - Drums, Shipping and Storage, Steel, 55-Gallon
PPP-P-704 - Pail, Shipping, Steel (1 Through 12 Gallons)

MILITARY

MIL-C-9084 - Cloth, Glass, Finished, For Polyester Resin Laminates

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:26Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized and Containerized Unit Loads 40 Inch X 48 Inch Pallets, Skids, Runners, or Pallet Type Base

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards:

D 70-70 - Specific Gravity of Road Oils, Road Tars, Asphalt Cements, and Soft Tar Pitches
D 618-61(1971)- Conditioning Plastics and Electrical Insulating Materials for Testing
D 635-72 - Flammability of Self-Supporting Plastics
D 638-71a - Tensile Properties of Plastics
D 648-72 - Deflection Temperature of Plastics Under Flexural Load
D 790-71 - Flexural Properties of Plastics
D 792-66(1970)- Specific Gravity and Density of Plastic by Displacement
D 2583-67(1972)-Indentation Hardness of Plastics by Means of a Barcol Impressor

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103).

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification

(Applications for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street N. W., Washington, D. C. 20036.)

Source: https://assist.dla.mil -- Downloaded: 202640-21T20:26Z •
Check the source to verify that this is the current version before use.

Uniform Classification Committee, Agent:

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606)

Interstate Commerce Commission

49 CFR 71-90 Interstate Commerce Commision Rules and Regulations for the Transportation of Explosives and Other Dangerous Articles

(The Interstate Commerce Commision Regulations are now a part of the Code of Federal Regulations (latest cumulatine packet supplement) available from the Superintendent of Documents, Government Printing Office, Washington, D. C. 20402. Orders for the above publication should cite "Code of Federal Regulations, 49 CFR 71-90 (Revised 1963)").

Manufacturing Chemists Association, Inc.

Manual L-1 Guide to Precautionary Labeling of Hazardous Chemicals (Sixth Edition - 1961)

(Application for copies should be addressed to the Manufacturing Chemists Association, Universal Building, 1825 Connecticut Avenue, Washington, D. C. 20009).

3. REQUIREMENTS

3.1 First article sample. When specified by the procuring activity (see 6.2), the resin furnished under this specification shall be a product which has been subjected to and has passed the first article sample inspection specified herein (see 4.2.2 and 4.2.3.2).

3.2 Material. The resin shall be of the low pressure laminating type with modified polyester base and suitable cross linking agents, and shall be suitable for the production of laminated panels such as those prepared under 4.3.1.2.

3.3 Code Number. The sppplier shall designate each resin composition by a code number identifying the resin. The code number may include trade name if desired. Any change in the kinds or proportions of components or in the manufacturing process shall necessitate use of a different code number and submission of the new product to preproduction inspection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z
Check the source to verify that this is the current version before use.

3.4 Physical and reactive properties (not applicable to laminate). The supplier shall furnish nominal values and tolerance limits for s ecific gravity, viscosity, and acid number of the liquid uncatalyzed resin; maximum gel time and peak exotherm of the catalyzed resin; and the Barcol hardness and specific gravity of the cured unfilled resin. These values and the methods of determination, when not specified herein, shall be included by the supplier in the instruction sheet (see 3.7) and shall be considered requirements of this specification for resin of the particular code number or designation concerned. In addition, unless otherwise specified (see 6.2), the following values, or tolerances from the stated nominal values, shall be as shown below.

Property	Value required
Specific gravity of uncatalysed resin	Nominal ± 0.05
Viscosity of uncatalyzed resin, poises	5000 maximum
Specific gravity of cured unfilled resin	Nominal ± 0.05
Barcol hardness of cured unfilled resin	45 minimum

3.5 Deflection temperature. The deflection temperature under load for the unfilled cured resin shall be not less than 215°C (419°F), when specimens are prepared and tested in accordance with 4.3.8.

3.6 Property values of the laminate. The property values of the glass cloth base plastic laminate, fabricated as specified in 4.3.1.2, shall conform to the values listed in table I.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:26Z
Check the source to verify that this is the current version before use.

Table I. Lengthwise property values of glass cloth base plastic laminate[1/]

Property	Value
Tested after normal conditioning (see 4.3.2.2)	
Tensile strength psi., min.	41,000
Flexural strength, psi., min.	47,000
Barcol hardness, min.	65
Flammability	SE (max)[2/]
Tested after three heat cycles (see 4.3.2.3)	
Tensile strength, psi., min.	35,000
Tested after one heat cycle (see 4.3.2.3)	
Flexural strength, psi., min.	44,000

1/ Lengthwise direction of test specimen is parallel to warp direction of the glass fabric.

2/ SE = Self Extinguishing.

The specific gravity and percent resin content of the glass cloth base plastic laminate, including method of test, shall be supplied to the procuring activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z
Check the source to verify that this is the current version before use.

3.7 Instruction sheet. At the time of submission of the preproduction sample, the supplier shall provide the procuring agency with instruction sheets (see 6.2). Each subsequent shipment of resin of the same code number shall be accompanied by copies of the approved instruction sheet (see 4.2.2.1.2 and 6.2). Instruction sheets shall contain the following:

(a) The number, title, and date of this specification,

(b) Resin code number (see 3.3).

(c) Limiting values required in 3.4 for the uncatalysed resin, and cured unfilled resin. Also the applicable test procedures when not specified herein.

(d) Maximum usable storage life of the uncatalysed resin, with recommeded storage conditions, and pot life of the catalysed resin.

(e) Recommended mixing and impregnating procedures, including recommended types, percentages, and manner of utilization of catalysts.

(f) Recommended method of preparing test specimens of unfilled cured resin.

(g) Recommended finishes to be used on glass fabric.

(h) Range of time, temperature, and pressure cycles recommended to affect the cure for laminates.

(i) Any other pertinent information, at the supplier's option, on storage and handling.

3.8 Workmanship. The material specified herein shall be homogeneous and free of contamination as determined by visual examination. The material shall be uniform from container to container as determined by visual examination.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z •
Check the source to verify that this is the current version before use.

4.2 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for examination and tests shall consist of all material submitted for delivery at one time.

4.2.1 Inspection of materials of components. In accordance with 4.1, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or if none, in accordance with this specification. In the event of conflict, this specification shall govern. A supplier's certificate of compliance with 3.1, 3.2, and 3.3 shall be furnished.

4.2.2 Inspection of material.

4.2.2.1 Examination of the material. Examination of the material shall be made in accordance with the list of defects, inspection levels and acceptable quality levels (AQL's) set forth below. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of 100 pounds for examination in 4.2.2.1.1, and in units of shipping containers for examination in 4.2.2.1.3.

4.2.2.1.1 Examination of the material for defects in appearance and workmanship. The sample unit for this examination, specified in table II, shall be approximately one pound.

Table II. Examination of the material for defects in appearance and workmanship

Examine	Defect
Appearance and workmanship	Material in each container not homogeneous, and not free of contamination. Not uniform from container to container.

4.2.2.1.2 Examination of instruction sheet. Instruction sheets must be furnished in accordance with 3.7, and must be acceptable to the procuring activity as part of the first article sample requirements (see 3.1 and 3.7). One sheet shall be examined as specified in table III.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:26Z
Check the source to verify that this is the current version before use.

Table III. Examination of instruction sheet

Examine	Defect
Instruction sheet	Not prepared in accordance with all requirements of 3.7.
	Specified test procedures not acceptable.

4.2.2.1.3 Examination of the preparation for delivery requirements (not applicable to preproduction inspection). An examination shall be made in accordance with table IV to determine that packaging, packing and marking comply with section 5 requirements. The sample unit for this examination shall be one shipping container fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z
Check the source to verify that this is the current version before use.

Table IV. Examination of preparation for delivery

Examine	Defect
Packing	Not level specified; not in accordance with contract requirements.
	Resin containers improperly closed.
	Any nonconforming component, component missing, damaged or otherwise defective affecting serviceability.
	Inadequate application of components such as: incomplete closures of case liners; container flaps, loose or inadequate strappings, bulged or distorted containers.
Quantity of material	Less than specified or indicated quantity.
Weight	Gross weight exceeds specified requirements.
Markings	Interior or exterior markings omitted, illegible, incorrect, incomplete, of improper size, location, sequence, method of application, or not in accordance with contract requirements.

4.2.2.1.4 Inspection levels and acceptable quality levels (AQL's) for examinations. The inspection levels for determining the sample size and the acceptable quality level (AQL) expressed as defects per 100 units shall be as follows:

Examination paragraph	Inspection level	AQL
4.2.2.1.1	II	2.5
4.2.2.1.2	S-2	2.5
4.2.2.1.3	S-2	2.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z
Check the source to verify that this is the current version before use.

4.2.3 Testing. The physical and reactive properties specified in 3.4 shall be tested in accordance with test methods specified herein. Plastic laminates shall be prepared from the material (see 4.3.1.2), and shall be tested for the characteristics listed in table I in accordance with the test methods specified herein. The lot size, for the purpose of determining the sample size for testing shall be expressed in units of 100 pounds of material. The sample unit shall consist of sufficient material to prepare all required specimens. The inspection level shall be S-1 with an acceptance number of 0. The results for each test shall be the averaged results of the specimens.

4.2.3.1 Classification of tests. All tests shall be classified as follows:

(a) Tests for first article sample (see 4.2.3.2).

(b) Tests for lot acceptance (see 4.2.3.3).

4.2.3.2 First article sample tests (see 3.1). The first article sample tests shall consist of all test specified herein (see section 3).

4.2.3.3 Lot acceptance tests. Lot acceptance tests shall be made on each lot of material and shall be the basis for acceptance or rejection of the lot, after first article sample inspection (see 3.1). Lot acceptance tests shall consist of all tests specified in table V.

Table V. Lot acceptance tests.

Test	Applicable test method paragraph
Uncatalyzed resin	
Specific gravity	4.3.3.1
Viscosity	4.3.4
Acid number	4.3.5
Catalyzed resin	
Gel	4.3.6
Peak exotherm	4.3.6
Cured unfilled resin	
Specific gravity	4.3.3.2
Barcol hardness	4.3.7
Deflection temperature	4.3.8
Laminate	
Flexural strength	4.3.9.2

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z
Check the source to verify that this is the current version before use.

4.3 Test Methods.

4.3.1 Specimen preparation.

4.3.1.1 Specimen preparation for testing other than that required by table I. Specimen preparation shall be in accordance with that specified in the applicable test procedure.

4.3.1.2 Specimen preparation for testing required by table I. The laminate sample shall be fabricated in the form of a sheet or sheets 0.125 ± 0.010 inch in thickness. The resin and 12 plies of 181 glass cloth shall be used. The 181 glass cloth shall conform to MIL-C-9084, except that the finish on the cloth shall be as specified by the procuring activity (see 6.2).

4.3.2 Conditioning prior to testing.

4.3.2.1 Resin. Uncatalyzed resin shall be brought to a temperature of 23° ± 1°C (73.4° ± 1.8°F) in the original sealed container, and shall be tested immediately after opening and stirring in the container. Testing shall be at 23° ± 1°C (73.4 ± 1.8°F).

4.3.2.2 Specimens. Unless otherwise specified, all specimens shall be conditioned in accordance with procedure A of ASTM D 618-61(1971) and tested at 23° ± 2°C (73.4° ± 3.6°F).

4.3.2.3 Temperature cycling. Each cycle shall consist of fifteen minutes in an electric oven at 315° ± 3°C (600° ± 5.4°F) followed by cooling for one hour at 23° ± 1°C (73° ± 1.8°F). The specimens shall be supported in the oven by a flat steel plate of 1/8 inch minimum thickness. The plate shall be sufficiently large that no part of any specimen shall extend beyond an edge of the plate. At the beginning of each cycle, the steel plate shall be at the temperature of the oven 315° ± 3°C (600 ± 5.4°F). After the required number of heating cycles, as specified in table I, the specimens shall be left overnight at 23° ± 1°C (73.4 ± 1.8°F). The specimens shall be tested the next day.

4.3.3 Specific gravity.

4.3.3.1 Liquid resin. The specific gravity of the liquid uncatalyzed resin shall be determined in accordance with ASTM D70-70.

Source: https://assist.dla.mil -- Downloaded: 202640-21T20:26Z
Check the source to verify that this is the current version before use.

4.3.3.2 Solid resin. The specific gravity of the unfilled cured resin shall be determined in accordance with ASTM D792-66(1970). Three determinations shall be made.

4.3.4 Viscosity of liquid resin. The viscosity of the liquid uncatalyzed resin shall be determined by a calibrated MacMichael viscosimeter or equivalent. The test procedure shall be submitted by the supplier in the instruction sheet (see 3.7). Three determinations shall be made.

4.3.5 Acid number of liquid resin. The acid number of a polyester is defined as the milligrams of potassium hydroxide required to neutralize 1 gram of polyester. The acid number of the liquid uncatalyzed resin shall be determined by titrating a suitable sample of the material as a solution in neutral acetone with 0.1 normal potassium hydroxide using phenolphthalein as an indicator. Other methods of determining acid number may be submitted for approval in the instruction sheet for the first article sample (see 3.1 and 3.7).

4.3.6 Gel time and peak exotherm. The gel time and peak exotherm shall be determined in the following manner:

(a) Apparatus:
Resin tubes: 19 by 150 mm.
Thermocouple: 1/8 inch maximum diameter (iron-constantan leads or stainless steel needle).
Potentiometer.
Constant-temperature circulating water baths.

(b) Method for gel time: A 200 gram sample of resin in a beaker surrounded by a water bath at 25° ± 0.5°C (77° ± 1°F) is catalyzed by adding exactly 1 percent of benzoyl peroxide and mixing at high speed for 5 minutes. Catalyzed resin is poured into the resin tube to a depth of 3 inches and the tube is suspended in a water bath controlled at 82.2° ± 0.3°C (180° ± 0.5°F), with the resin level below the water level of the bath. The thermocouple is positioned vertically in the tube, with the tip in the center of the resin. The gel time is determined as the time required for the temperature of the resin to rise from 65.6°C to 87.8°C (150°F to 190°F). The result shall be determined from an average of three tests.

(c) Method for peak exotherm: The peak exotherm is defined as the maximum temperature reached by the resin for the above-specified bath temperature. Peak exotherm is determined by the gel time method.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:26Z
Check the source to verify that this is the current version before use.

4.3.7 Barcol hardness of cured unfilled resin and of laminate. The Barcol hardness of cured unfilled resin specimens and of laminate resins shall be determined in accordance with ASTM D 2583-67(1972). The determination shall be made on three specimens for both the unfilled resin and laminate resin specimens. All specimens shall be at least 1 inch square.

4.3.8 Deflection temperature under load (for cured unfilled resin only). Deflection temperature under load shall be determined in accordance with ASTM D648-72. The determinations shall be made on three specimens cut from 0.125 ± 0.015 inch thick sheet of cured unfilled resin.

4.3.9 Lengthwise properties of the laminate.

4.3.9.1 Tensile strength. Tensile strength shall be determined in accordance with ASTM D638-71a. The determinations shall be made on five specimens prepared from 0.125 ± 0.015 inch thick laminate using speed A. Test specimens shall conform to dimensions of figure I of ASTM D638-71a.

4.3.9.2 Flexural strength. Flexural strength shall be determined in accordance with ASTM D790-71. The determinations shall be made on three specimens prepared from 1 by 4 inch laminate specimens.

4.3.9.3 Flammability. Flammability shall be determined in accordance with ASTM D635-72. The determination shall be made on ten specimens prepared in accordance with ASTM D635-72. Self extinguishing shall be defined as specified in ASTM D635-72.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A. The resin shall be packaged, as specified (see 6.2), in 1 gallon or smaller cans conforming to Type V, Class 2, round, of PPP-C-96, 5 gallon pails conforming to Type II, Class 3 of PPP-P-704, 16 gallon drums conforming to Type III of PPP-D-705, or 55 gallon drums conforming to Type III or Type IV of PPP-D-729.

5.1.2 Level C. The cans, pails or drums shall be packaged to afford adequate protection against deterioration and damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Resin packaged in containers comforming to PPP-C-96 shall be packed in accordance with the level A requirements of the appendix thereto. Resin packaged in containers conforming to PPP-P-704, PPP-D-705 or PPP-D-729 require no overpacking. When specified (see 6.2), 5 gallon pails and 16 gallon drums shall be palletized in accordance with MIL-STD-147.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:26Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. Resin packaged in containers conforming to PPP-C-96 shall be packed in accordance with the level B requirements of the appendix thereto. Resins packaged in containers conforming to PPP-P-704, PPP-D-705, or PPP-D-729 require no overpacking. When specified (see 6.2) 5 gallon pails and 16 gallon drums shall be palletized in accordance with MIL-STD-147.

5.2.3 Level C. Packing shall be in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking. In addition to any special marking required by the contract or order (see 6.2) or herein, interior packages, exterior shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129. The nomenclature shall include:

PLASTIC, MOLDING MATERIAL, POLYESTER, LOW-PRESSURE LAMINATING, HIGH TEMPERATURE RESISTANT, MIL-P-43038B(MR).

Code number (see 3.3)

Date of manufacture (month and year)

5.3.1 Hazardous chemicals. All packaged units of hazardous chemicals shall have affixed thereto such warning labels and markings as may be required by the Interstate Commerce Commission CFR, Title 49, Part 71-90, and the Manufacturing Chemists Association Manual L-1.

5.3.2 Warning markings. All packaged units shall be marked:

WARNING: USE WITH ADEQUATE VENTILATION - FLAMMABLE- The solvents contained in this compound may have flash points well below prevailing room temperatures. Do not heat by, or use near, an open flame. Heat preferably by means of a steam coil or other nonflame-producing heat source.

WARNING: Catalysts, promoters, and solvents to be used with this compound should be stored in original tight containers isolated from one another in cool locations. Never permit a catalyst to come in contact with any component except the base comouund.

Source: https://assist.dla.mil -- Downloaded: 202640-21T20:26Z
Check the source to verify that this is the currentversion before use.

6. NOTES

6.1 Intended use. This resin is intended for use with suitable glass fiber reinforcement in the manufacture of rifle handguards, and other similar applications.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) First article inspection, if required (see 3.1 and 4.2.3.2).
(c) Other values, or other tolerances from stated nominal values, for use in 3.4, if required.
(d) Additional copies of instruction sheet, with manner of submitting, if required (see 3.7).
(e) Minimum storage life for uncatalyzed resin, and minimum pot life for catalyzed resin, if required (see 3.7).
(f) Glass fabric finish (see 4.3.1.2).
(g) Levels of packaging and packing required (5.1 and 5.2).
(h) Size and type of containers required (5.1 and 5.2).
(i) Whether palletizing is required (5.2.1 and 5.2.2).
(j) Special marking, if required (5.3).
(k) Quantity of resin, pounds or gallons (6.2.1).

6.2.1 Purchase unit. The unit of purchase of resin is the pound.

Custodian:
Army - MR

Preparing activity:
Army - MR

Review interest:
Army - WC, MD

Project No. 9330-A470

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7, and send to preparing activity.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced documents(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-P-43038B (AR)	2. DOCUMENT DATE (YYYYMMDD) 3 OCTOBER 1973

DOCUMENT TITLE PLASTIC MOLDING MATERIAL, POLYESTER, LOW-PRESSURE LAMINATING, HIGH-TEMPERATURE RESISITANT

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME *(Last, First, Middle Initial)*	b. ORGANIZATION	
c. ADDRESS *(Include Zip Code)*	d. TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN *(If applicable)*	7. DATE SUBMITTED *(YYYYMMDD)*

8. PREPARING ACTIVITY

a. NAME U.S. Army TACOM-ARDEC Standardization Team	b. TELEPHONE *(Include Area Code)* (1) Commercial: (973) 724-5822 (2) DSN: 880-5822
c. ADDRESS *(Include Zip Code)* Attn; AMSTA-AR-QAW-E Picatinny Arsenal, NJ 07806-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman Road, Suite 2533 Fort Belvoir, Virginia 22060-6221 Telephone (703) 767-6888 DSN 427-6888

Source: https://assist.dla.mil -- Downloaded: 202640-21T20:26Z
Check the source to verify that this is the current version before use.