MIL-M-51231
INTERIM AMENDMENT 1 (MU)
10 NOVEMBER 1966

INTERIM AMENDMENT

MILITARY SPECIFICATION

MASK, GAS, ROCKET PROPELLANT, M26A1

This Interim Amendment is issued for use by Munitions Command with Military Specification MIL-M-51231, 1 June 1966.

Page 2, paragraph 2.2. Add the following:

"AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM Standard

D 257 — Electrical Resistance of Insulating Materials.

(Copies may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)"

Page 4, paragraph 3.1.3. Add "The hose shall have a surface resistivity of no more than 1×10^{11} ohms when tested as specified in 4.6.9 and it shall pass the nitric acid resistance test when tested as specified in 4.6.10."

Page 7, section 4. Add:

"4.6.9 *Surface resistivity*. The specimen shall be conditioned at 23° — 3°C and 50 — 5 percent relative humidity for no less than 40 hours and then tested in accordance with ASTM D257 with an applied voltage of no less than 500 volts dc for at least one minute. The voltage shall be applied to the specimen five times and an average value recorded."

"4.6.10 *Nitric acid resistance*. A 3-inch length of hose shall be placed in a container of nitric acid conforming to type IIIA of MIL-P-7254, for five minutes. If there is any evidence of decomposition of the coating material or the hose, it is unacceptable."

Custodian:

Army — MU

Preparing activity:

Army — MU (EA)

Project No. 4240-A267

FSC 4240

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:53Z
Check the source to verify that this is the current version before use.