MIL-N-51112A(EA)
AMENDMENT 2
18 July 1986
SUPERSEDING
AMENDMENT 1
14 March 1986

MILITARY SPECIFICATION

NOSECUP-DEFLECTOR, C11

This amendment forms a part of MIL-N-51112A(EA), dated 17 January 1977, and is approved for use within the Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

Add to paragraph 2.2 ASTM standards:

"D 1925 - Yellowness Index of Plastics".

PAGE 4

Replace paragraph 3.2.2 "Test Slabs" with the following:

"3.2.2 Test slabs and equivalent cure. Test slabs shall be molded from stock representative of the formulation used for preproduction sample and from each sublot during regular production of nosecups in accordance with ASTM D 3182. The slabs shall have a cure equivalent to that of regular production nosecups. Equivalent cure is established when physical properties are in conformance with table I at a given cure time and temperature and that the percent free sulfur of the slab and the part are equivalent. Objective evidence shall be submitted in accordance with 4.1.2.3. Once cure time and cure temperature are established, they may not change during production."

Paragraph 3.3.1: Delete "There shall be no visual discoloration of lenses" and replace with the following:

"The average yellowness index of the lenses, when tested in accordance with ASTM D 1925, shall be no more than 14. and no individual specimen shall be more than 16."

FSC 4240

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-22T20:50Z
Check the source to verify that this is the current version before use.

Add the following new paragraph 4.1.2.3:

"4.1.2.3 Equivalent cure. After date of award of contract, and prior to submission of preproduction, and without additional cost to the Government, the contractor shall submit the information listed below which will constitute evidence for establishing equivalent cure for a given formulation at optimal cure time and cure temperature for each mold used.

(a) Different combinations of cure time and temperature for slabs and parts, approaching and surpassing optimum cure shall be furnished.

(b) Percent free sulfur for slabs and parts shall be furnished for each time/temperature combinations.

(c) All physical property data from table I shall be generated for slabs and shall be furnished for each time/temperature combination. In addition, any physical property data from table I which can be generated for nosecups shall be furnished for each time/temperature combination.

(d) Any other information and data which substantiates the equivalency of cure at the established cure time and cure temperature."

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 4240-A854

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:50Z
Check the source to verify that this is the current version before use.