MIL-R-51283C(EA)
AMENDMENT 1
3 September 1986

MILITARY SPECIFICATION

RUBBER FABRICATED PRODUCTS FOR M17A1/Ml7A2 MASKS

This amendment forms a part of MIL-R-51283C(EA), dated 8 August 1983, and is approved for use within the Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1.1, Delete: "FED. STD. No. 601 - Rubber: Sampling and Testing."

PAGE 3

2.2:

Add: "ASTM D 471 - Rubber Property - Effects of Liquids".
ASTM D **395:** Delete current title and substitute "Rubber Property-Compression Set."
ASTM D 412: Delete current title and substitute "Rubber Properties in Tension."
ASTM D 572: Delete current title and substitute "Rubber-Deterioration by Heat and Oxygen."
ASTM D 573: Delete current title and substitute "Rubber-Deterioration In An Air Oven."
ASTM D 624: Delete current title and substitute "Rubber Property-Tear Resistance."
ASTM D **746:** Delete current title and substitute "Plastics and Elastomers, Brittleness Temperature Of, By Impact."
ASTM D 792: Delete current title and substitute "Plastics, Specific Gravity and Density Of, By Displacement."
ASTM D 797: Delete current title and substitute "Rubber Property-Young's Modulus at Normal and Subnormal Temperatures."
ASTM D **1149:** Delete current title and substitute "Rubber Deterioration-Surface Ozone Cracking in a Chamber (Flat Specimen)."
ASTM D 2240: Delete current title and substitute "Rubber Property-Durometer Hardness."

3.1, Delete "finished" and substitute "furnished",

FSC 4240

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:55Z
Check the source to verify that this is the current version before use.

3.2, Change ". . . make change in the formulation or manufacturing processes." to ". . . make a major change in the formulation, curing, or manufacturing processes."

303, Delete in its entirety and substitute the following:

"3.3 Manufacture. The piece parts shall be manufactured in accordance with the applicable drawings as listed in this specification."

PAGE 5

Table II, Delete in top row: "FED STD 601 or ASTM".
Delete near bottom: '[1]6211" and substitute "ASTM D 471 Section 10",

PAGE 6

3.6, Delete in its entirety and substitute the following:

"3.6 Resistance to deterioration by heat and oxygen. Molded parts shall show no cracking or increased hardness or tackiness after 72 hours of accelerated aging in oxygen in accordance with ASTM D 572."

4.1.2.1, In first sentence delete "of the rubber parts" and substitute "of the formulation of the rubber parts."

In second sentence delete "and parts are" and substitute "is".

PAGE 8

4.2.3, Delete "FED. STD. No. 601 Test Methods."

PAGE 13

6.3., Delete "Field" after M17A1 and M17A2.

6.5, Add new paragraph as follows:

"6.5 Major change. The term applies to any change in formulae, processing, or curing of currently approved rubber stocks which may induce toxic characteristics and cause casualties. The major change should be considered effected when one or more of the following conditions occur:

(a) Components of formulae are varied in excess of the limitations stated in the manufacturer's tolerance.

(b) The addition or deletion of one or more components of formulae.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:55Z
Check the source to verify that this is the current version before use.

(c) Substitutes-for one or more components of formulae without advance approval of the Government.

(d) Deviations from the submitted and approved factory mold cure, exceeding +5,F or -10,F even though equivalent cure is attained.

(e) Use of mold lubricants, dusting powders, or wet sprays not submitted with original information for toxicity approval."

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 1240-A861

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:55Z
Check the source to verify that this is the current version before use.