MILITARY SPECIFICATION

CALCIUM HYDRIDE CHARGES ML-304( )/TM and ML-305( )/TM and CHARGE, HYDROGEN GENERATOR ML-587( )/TM

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of calcium hydride charge, in three sizes, designated Calcium Hydride Charge ML-304( )/TM, Calcium Hydride Charge ML-305( )/TM, and Charge, Hydrogen Generator ML-587( )/TM (see 6.2).

1.2 Classification. The type classification shall be as follows:

Type I - Calcium Hydride Charge ML-304( )/TM.

Type II - Calcium Hydride Charge ML-305( )/TM.

Type III - Charge, Hydrogen Generator ML-587( )/TM.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-P-116	- Preservation, Methods Of.
MIL-M-13231	- Marking Of Electronic Items.
MIL-P-19602	- Primer, Size Coating, Baking, For Roller Coat Application.
MIL-E-19603	- Enamel, Baking, For Roller Coat Application.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Electronics Research and Development Command, ATTN: DELCS-PE, Fort Monmouth, NJ 07703-5304, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures And Tables For Inspection By Attributes.
MIL-STD-252 - Wired Equipment, Classification Of Visual And Mechanical Defects.

2.1.2 Other Government documents. The following Government documents form a part of this specification to the extent specified herein:

DRAWINGS

ELECTRONICS COMMAND

SC-D-7432 - Assembly And Details For Calcium Hydride Charges.
SC-DL-86428 - Container for Calcium Hydride Charge ML-304( )/TM.
SC-DL-86429 - Container For Calcium Hydride Charge ML-305( )/TM.
SC-DL-103454 - Container For Charge, Hydrogen Generator ML-587( )/TM.
SC-GL-57617 - Gages For Calcium Hydride Charge ML-304( )/TM.
SC-GL-57618 - Gages For Calcium Hydride Charge ML-305( )/TM.
SC-GL-57717 - Gages For Charge Hydrogen Generator ML-587( )/TM.
SPI 1G00409 - Special Packaging Instructions.

(Copies of specifications, standards, and drawings required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Description. Three distinct quantities of calcium hydride are encased in sealed metal canisters, having interrupted female threads for attachment to Hydrogen Generator ML-303( )/TM. The canisters have scored knock-out holes to permit the entrance of water and the escape of hydrogen gas during the generating process.

3.2 First article. Unless otherwise specified in the contract, the sample units shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.3 Material. The material shall be as specified herein and as shown on the applicable drawings. However, when a definite material is not specified, a material shall be used which will enable the calcium hydride charge to meet the performance requirements of this specification. Acceptance of approval of any constituent material shall not be construed as a guaranty of the acceptance of the finished product.

3.3.1 Recycled, virgin and reclaimed material. It is encouraged that recycled or reclaimed material, in lieu of virgin material, be used when practical provided it meets the requirements of this specification.

3.4 Design.

3.4.1 Construction. The calcium hydride charge shall consist of a container constructed in accordance with the applicable drawings listed below and filled with a quantity of calcium hydride as specified in 3.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

SC-DL-86428 - Calcium Hydride Charge ML-304( )/TM
SC-DL-86429 - Calcium Hydride Charge ML-305( )/TM
SC-DL-103454 - Charge, Hydrogen Generator ML-587( )/TM
SC-DL-7432 - Assembly and Details for Calcium Hydride Charges

3.4.2 Seams. The seams of the container shall be airtight, and shall not leak (see 4.6.1).

3.4.3 Knock-out holes. The knock-out holes shall be scored to a depth that shall break open when subjected to an applied force of not less than 30 lbf (13.6 kgf) and not more than 100 lbf (44.5 kgf) (see 4.6.2).

3.4.4 Interrupted threads. The interrupted threads on the container, for attachment to Hydrogen Generator ML-303( )/TM, shall be in accordance with SC-D-7432.

3.4.5 Soldering.

3.4.5.1 Soldering process. There shall be no sharp points or rough surfaces resulting from insufficient heating. The solder shall feather out to a thin edge indicating proper flowing and wetting action. The solder shall not be crystallized, indicating overheating or underheating. The soldering shall be accomplished that no flux remains on the seams or in the proximity thereof. Any means employed to remove an unavoidable excess of flux shall not incur the risk of loose particles of flux, brush bristles, or other foreign material remaining in the container, flux being spread over a larger area, or other resultant damage to the container.

3.4.5.2 Cleaning after soldering. After soldering of seams, the container shall be cleaned thoroughly and shall be free from particles of solder, flux, and other foreign material. Where acid or corrosive salts are used for cleaning, they shall be completely neutralized and removed immediately after use.

3.5 Calcium hydride. The hydrogen generating compound in the charge shall be calcium hydride. This calcium hydride shall be manufactured from metallic calcium, and shall assay not less than 90 percent purity. The bulk density and particle size of the calcium hydride shall be such that the following charge requirement will be met (see 4.6.4).

3.5.1 Charge for ML-304( )/TM. The calcium hydride charge for the ML-304( )/TM container shall be sufficient to inflate a 30-gram meteorological balloon within 6 minutes, to produce a minimum free lift of 155 grams. There shall be no violent or excessive blowback from the bottom of the generator body (see 4.6.5).

3.5.2 Charge for ML-305( )/TM. The calcium hydride charge for the ML-305( )/TM container shall be sufficient to inflate a 100-gram meteorological balloon within 20 minutes, to produce a minimum free lift of 650 grams. There shall be no violent or excessive blowback from the bottom of the generator body (see 4.6.5).

3.5.3 Charge for ML-587( )/TM. The calcium hydride charge for the ML-587( )/TM container shall be sufficient to inflate a 100-gram meteorological balloon within 30 minutes, to produce a minimum free lift of 1240 grams. There shall be no violent or excessive blowback from the bottom of the generator body (see 4.6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

3.6 Vibration. When tested as specified in 4.6.6, the calcium hydride charge shall show no leakage at the seams or damage to the container.

3.7 Finish. All exterior surfaces of the calcium hydride charge container shall be lithographed with a baked-on coating in accordance with MIL-P-19602 (primer) and MIL-E-19603 (enamel). In addition, a suitable type varnish shall be baked on to obtain the gloss required.

3.8 Marking. Identification and instruction marking shall be applied by the lithographic or silk screen method, using water-proof ink. Color shall be black. Printed matter shall be in accordance with SC-D-7432 and MIL-M-13231.

3.9 Government-loaned property. The following itmes of equipment, in the quantities specified (see 6.2), shall be provided to the contractor:

a. Hydrogen generator ML-303( )/TM.
b. Balloon nozzle ML-373( )/GM.
c. Hose ML-81( ). Standard garden hose, 0.5-inch (12.7mm) inside diameter, may be used for in-plant testing in lieu of hose ML-81( ).
d. Balloon, 30-gram: (i.e., ML-50( ), ML-51( ), ML-64( ), ML-155( ), or ML-1 5 6 ( ).).
e. Balloon, 100-gram: (i.e., ML-159( ), ML-160( ), or ML-161( ).)

3.10 Workmanship. The calcium hydride charge shall be manufactured and assembled in accordance with the applicable portions of the following paragraphs herein:

a. 3.4.1 Construction.
b. 3.4.2 Seams.
c. 3.4.3 Knock-out holes.
d. 3.4.4 Interrupted threads.
e. 3.4.5 Soldering.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classifications of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Inspections covered by subsidiary documents (see 4.4).
c. Quality conformance inspection (see 4.5).
d. Packaging inspection (see 4.8).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

4.3 First article.

4.3.1 First article units. The contactor shall furnish 20 first article units of each size calcium hydride charge specified in the contract.

4.3.2 First article inspection. The first article inspection shall consist of the inspections specified in subsidiary documents covering the items listed in 4.4, and the inspections specified for group A, group B and group C (see tables I, II, and III respectively). The inspection shall be performed in the following order: 4.4, group A and group B for all units; and group C as specified in 4.5.4.1. After completion of group C tests, conforming units shall be reinspected and shall pass all group A inspections. Failure of any inspection shall be cause for rejection.

4.4 Inspections covered by subsidiary documents. The following shall be inspected under the applicable subsidiary documents as part of the inspection required by this specification.

Item	Where required
Material	3.3
Finish	3.7
Marking	3.8

4.5 Quality conformance inspection.

4.5.1 Inspection. Quality conformance inspection shall be as specified in 4.4 and 4.5.2 through 4.5.4.2.

4.5.2 Group A inspection. Each unit shall be subjected to the inspections specified in table I. Discrete lots shall be formed from units that pass this inspection. Factors of lot composition not defined, or specified herein, shall be in accordance with MIL-STD-105.

TABLE I. Group A inspection.

Inspection	Requirement paragraph	Test method paragraph	AQL (percent defective) Major	AQL (percent defective) Minor
Visual and mechanical	3.10	4.7		
Construction	3.4.1	4.7		
Seams	3.4.2	4.6.1	2.5 for the group	10.0 for the group
Interrupted threads	3.4.4	4.6.3		
Soldering	3.4.5	4.7		

4.5.2.1 Group A lot sampling. Sampling of group A lots shall be in accordance with MIL-STD-105, inspection level II. Acceptable quality level(AQL) shall be as specified in table I.

4.5.2.2 Order of inspection within group A. Group A inspection shall be performed in any order satisfactory to the Government.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

4.5.3 Group B inspection. Group B inspection shall normally be perfomed on inspection lots that have passed group A inspection and on samples selected from units that have been subjected to and meet the group A inspection. This inspection shall be as specified in table II.

TABLE II. Group B inspection.

Inspection	Requirement paragraph	Test method paragraph	AQL (percent defective)
Knock-out holes	3.4.3	4.6.2	6.5
Hydrogen gas capacity:			
Charge ML-304( )/TM	3.5.1	4.6.5	6.5
Charge ML-305( )/TM	3.5.2	4.6.5	6.5
Charge ML-587( )/TM	3.5.3	4.6.5	6.5

4.5.3.1 Group B sampling. Sampling for group B shall be in accordance with MIL-STD-105, inspection level S-4 for normal and tightened inspection and S-3 for reduced inspection. AQL shall be as specified in table II.

4.5.3.2 Order of inspection. Inspection shall be performed in any order satisfactory to the Government.

4.5.4 Group C inspection. Group C inspection shall consist of the test specified in table III.

TABLE III. Group C inspection.

Inspection	Requirement paragraph	Test method paragraph
Calcium hydride purity	3.5	4.6.4
Vibration	3.6	4.6.6
Leakage	3.4.2	4.6.1

4.5.4.1 Sampling for group C inspection. Six samples shall be selected randomly from each batch of calcium hydride produced. A batach shall be defined as a production quantity produced at one time, or in one operation, under identical conditions.

4.5.4.2 Group C failures. Action requied relative to group C failures shall be as specified in 4.6.4.1.

4.6 Methods of inspection.

4.6.1 Leakage test (seams). The calcium hydride charge shall be submerged in water at a temperature of 131°F ±9°F (55° ±5°C) under a bell jar or equivalent and the pressure reduced to not more than 15 inches of mercury (50.7kPa), and held at that condition for not less than 5 minutes. Evidence of leakage or container rupture shall constitute failure of this test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

4.6.2 Knock-out holes. The top of the charge container shall be supported on an anvil with a scored knock-out hole centered over a 0.375 inch (9.5mm) diameter recess in the anvil. A 0.25 inch (6.4mm) test punch with a 0.125 inch (3.2mm) radius on the end, or a 0.5 inch (12.7mm) diameter test ball shall be centered on the scored knock-out. An increasing force shall be gradually applied to the test punch or test ball. The force requied to break open the knock-out hole shall be recorded. All of the scored knock-out holes on each sample container shall be tested. Nonconformance to 3.4.3 shall constitute failure of this test.

4.6.3 Interrupted threads. The top of the container shall be tested to determine that the interrupted threads are in accordance with the applicable gage (see SC-GL-57617, SC-GL-57618, or SC-GL-57717). Nonconformance to 3.4.4 shall constitute failure of this test.

4.6.4 Calcium hydride purity.

4.6.4.1 Test criteria. Each sample from the batch shall be subjected to the assay test of 4.6.4.2 and the acceptability determined as follows: (When more than one type of charge is being procured under the same order, sublots of calcium hydride charges (ML-304( )/TM, ML-305( )/TM, ML-587( )/TM may be combined to form one lot for acceptance inspection, provided that samples chosen from the sublots are in the same ratio as the sublot size to the lot size.)

a. The batch shall be considered acceptable if the test results of not more than one sample is outside the specified limits.

b. The batch shall be retested if more than one of the test values are outside of the test limits. Retesting shall be performed as follows:

(1) Twelve additional samples shall be selected at random from the batch. Each of these samples shall be subjected to the assay test specified in 4.6.4.2.

(2) If the results of each of the 12 retested samples are within the specified test limits, the batch shall be considered acceptable.

(3) If any one or more of the 12 retested samples are not within the specified test limits, the batch shall be rejected.

4.6.4.2 Purity assay. The purity of a sample of calcium hydride shall be measured in terms of its hydrogen yield, compared to the theoretical yield of 100 percent pure calcium hydride. A weighted sample of calcium hydride shall be reacted with water. The volume of hydrogen gas generated shall be measured and corrected to standard conditions of temperature and pressure. At standard temperature and pressure (15°C (59°F) and 1.0 atmosphere (101.3kPa), 1 gram of 100 percent pure calcium hydride will yield 1.122 liters of hydrogen gas. The purity shall be not less than 90 percent when computed using the following relationship:

$$\text{Percent Purity} = \frac{(100)(\text{Corrected yield of sample})}{\text{Theoretical yield of sample}}$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

4.6.5 Hydrogen gas capacity. The calcium hydride charge shall be tested for gas capacity using the following procedure:

a. To test the ML-304( )/TM, tie a 30-gram meteorological balloon to Balloon Nozzle ML-373/GM, with the valve of the nozzle in the open position. To test the ML-305( )/TM or the ML-587( )/TM, a 100-gram balloon shall be used.
b. Attach one end of Hose ML-81( ) to the outlet tube of the Hydrogen Generator ML-303( )/TM.
c. Punch out all knock-out holes on the top of the charge container.
d. Attach the charge container to Hydrogen Generator ML-303( )/TM.
e. Immerse the hydrogen generator in water to within two to three inches (50.8 to 76.2mm) of the top of the generator body. This water shall be at a temperature of 131°F ±9°F (55° ±5°C).
f. After two seconds, attach the other end of Hose ML-81( ) to the serrated inlet connection on Balloon Nozzle ML-373( )/GM.
g. When the vibration of the hydrogen generator ceases, the reaction shall be considered complete. The vibration is caused by the chemical reaction. At this time close the valve on the balloon nozzle.
h. Record the time from the immersion of the generator in water to completion of the reaction.
i. Remove Hose ML-81( ) from the balloon nozzle.
j. "Weigh-off" the inflated balloon to determine the free lift. Free lift shall be defined as the total lift of the balloon under standard conditions of atmosphere minus the weight of the balloon.

4.6.5.1 Failure criteria. Nonconformance to 3.5.1, 3.5.2, or 3.5.3, as applicable, shall constitute failure of this test.

4.6.6 Vibration. The calcium hydride charge shall be firmly clamped to a vibration table and tested for 30 minutes in a simple harmonic motion in the vertical plane at 15 Hertz with a total excursion of not less than 0.15 inch (3.8mm). Nonconformance to 3.6 shall consititue failure of this test.

4.7 Visual and mechanical. The equipment shall be examined for the defects listed in MIL-STD-252. Nonconformance to 3.10 shall constitute failure of this test.

4.8 Packaging inspection. Packaging inspection requirements specified herein are classified as follows:

a. First article inspection of packaging.
b. Quality conformance inspection of packaging.

4.8.1 First article inspection of packaging. Unless otherwise specified in the contract, first article inspection of packaging shall be in accordance with the unit pack design validation requirements of MIL-P-116.

4.8.2 Quality conformance inspection of packaging.

4.8.2.1 Materials inspection. All materials to be used in packaging shall be inspected in accordance with the applicable material specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

4.8.2.2 Preservation inspection. Inspection of preservation and interior markings shall be in accordance with group A and B quality conformance inspection requirements of MIL-P-116. Lot formation and sampling procedures shall be as specified therein.

4.8.2.3 Packing inspection. Inspection of packing and the marking for shipment and storage shall consist of the examinations specified in table IV "Packing inspection provisions." Lot formation shall consist of all packs made of the same materials during an identifiable period and submitted at one time for acceptance. Sampling procedures shall be in accordance with MIL-STD-105, using a single sampling plan and an acceptable quality level of 4.0 percent defective.

TABLE IV. Packing inspection provisions.

No.	Characteristic	Method of inspection
101	Intermediate container not as specified.	Visual
102	Improper closure of intermediate container.	Visual
103	Shipping containers not in accordance with specification.	Visual
104	Excessive cube.	Visual
105	Improper blocking and bracing.	Visual
106	Closure not in accordance with specification.	Visual
107	Weight and size exceed container limitations.	Weight & measure
108	Strapping not in accordance with specification, incorrectly applied, or omitted.	Visual
109	Marking omitted, incorrect, or illegible.	Visual

5. PACKAGING

5.1 Packaging requirements. The requirements for packaging shall be in accordance with SPI 1G00409.

6. NOTES

6.1 Intended use. The calcium hydride charge is used to produce hydrogen gas for inflating meteorological balloons.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Designation of calcium hydride charge required (see 1.1).
c. When a first article is required for inspection and approval (see 3.2).
d. Items of Government-loaned property and quantity of each required (see 3.9).
e. Action required relative to group C failure (see 4.5.4.2).
f. Level A or B preservation and packing (see section 5).
g. When first article inspection rough handling tests are not required.
h. When first article packaging inspection test reports require acquistion activity approval prior to production unit packing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

6.3 First article. When a first article inspection is required, the item will be tested and should be a preproduction sample. The first article should consist of 20 units. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, test, and approval of the first article.

6.4 Nomenclature. The parenthesis in the nomenclature will be deleted or replaced by a letter identifying the particular design; for example: ML-587W/TM. The contractor should apply for nomenclature in accordance with the applicable clause in the contract (see 1.1).

6.5 Level B preservation. When level B preservation is specified, this level of protection will only be used under known favorable conditions during transportation, storage and handling.

6.6 Data requirements. When this specification is used in an acquistion which incorporates a DD Form 1423, Contract Data Requirements List (CDRL), the data requirements identified below shall be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved CDRL incorporated into the contract. When the provisions of DAR 7-104.9 (n)(2) are invoked and the DD Form 1423 is not used, the data specified below shall be delivered by the contractor in accordance with the contract requirements. Deliverable data required by this specification is cited in the following paragraphs.

Paragraph 4.3 Data requirement title First Article test report Applicable DID no. UDA-T-23790

(Data item descriptions related to this specification, and identified in section 6 will be approved and listed as such in DoD 5000.19L., Vol. II, AMSDL. Copies of data item descriptions required by the contractors in connection with specific acquisiton functions should be obtained from the Naval Publications and Forms Center or as directed by the contracting officer.)

6.7 Environmental. Environmental pollution prevention measures are contained in the packaging material specifications referenced herein. Refer to material specifications or preparing activity for recommended disposability methods.

6.8 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - ER
Air Force - 99

Preparing activity:
Army - ER

Project 6660-0068

Review activities:
Air Force - 13
DLA - GS

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2 DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5 PROBLEM AREAS

a. Paragraph Number and Wording:

b Recommended Wording.

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8 DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Headquarters
US Army Combat Surveillance and
Target Acquisition Laboratory
ATTN: DELCS-PE
Fort Monmouth, New Jersey 07703

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:28Z
Check the source to verify that this is the current version before use.