MIL-I-3505C
13 OCTOBER 1960
SUPERSEDING
MIL-I-3505B
26 NOVEMBER 1954

MILITARY SPECIFICATION

INSULATION SHEET AND TAPE; ELECTRICAL, COIL AND SLOT, HIGH TEMPERATURE

This specification has been approved by the Department of Defense and is mandatory for use by the Departments of the Army, the Navy, and the Air Force.

1. SCOPE

1.1 Scope. This specification covers high temperature mica-glass electrical insulation used in the coils and slots of rotating electrical machinery.

1.2 Classification. High temperature coil and slot electrical insulation shall be of the following classes, forms, and types, as specified (see 6.2):

Class B — With organic varnish.

Class H — With silicone varnish.

Form S — Sheet (See 3.5.1).

Form T — Tape (See 3.5.2).

Type Mg. — Pasted mica laminated with one layer of glass fiber insulation.

Type Pmg. — Pasted mica laminated with one layer of paper insulation on one side and one layer of glass fiber insulation on the other side.

Type Gmg. — Pasted mica sandwiched between single layers of glass fiber insulation.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issue in effect on date of invitation for bids, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

UU-P-271	— Paper, Wrapping, Waterproofed Kraft.
PPP-B-566	— Boxes, Folding Paperboard.
PPP-B-585	— Boxes; Wood Wirebound.
PPP-B-591	— Boxes, Fiberboard, Wood-Cleated.
PPP-B-601	— Boxes, Wood, Cleated-Plywood.
PPP-B-621	— Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	— Box, Fiberboard.
PPP-B-676	— Boxes, Set-Up, Paperboard.

FSC 5970

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:07Z
Check the source to verify that this is the current version before use.

PPP-T-76 — Tape, Pressure-Sensitive Adhesive, Paper Water Resistant.

PPP-T-97 — Tape, Pressure-Sensitive Adhesive Filament Reinforced

MILITARY

MIL-P-116 — Preservation, Methods of.

MIL-A-140 — Adhesive, Water-Resistant, Waterproof Barrier-Material.

MIL-B-10377 — Box, Wood, Cleated, Veneer, Paper Overlaid.

MIL-L-10547 — Liners, Case, Waterproof

STANDARDS

MILITARY

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 — Marking for Shipment and Storage.

MIL-STD-130 — Identification Marking of U. S. Military Property.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

AMERICAN SOCIETY FOR TESTING MATERIALS

D-295—Tentative Methods of Test for Varnished Cloths and Tapes.

(Application for copies should be addressed to the American Society for Testing Materials, 1916 Race Street, Philadelphia 3, Pa.)

OFFICIAL CLASSIFICATION COMMITTEE

Uniform Freight Classification Rules.

(Application for copies should be addressed to the Official Classification Committee, 1 Park Avenue at 33rd Street, New York 16, New York.)

3. REQUIREMENTS

3.1 Mica splittings. The mica splittings shall be sound, clean, and free from mineral inclusions.

3.2 Binder. The binding material shall be a high-quality insulating material uniformly distributed and used in the minimum amount needed to obtain the specified properties. The binding material shall provide satisfactory adhesion between the mica splittings, and between the mica and reinforcing layers as indicated by the absence of delamination and flaking through normal handling. The binder shall not dry out or "set up" during normal storage so as to result in flaking of the mica or stiffening of the insulation.

3.3 Glass fiber insulation. In the case of form S material, the glass fiber insulation employed shall be varnish coated. In the case of form T material, the glass fiber insulation employed may or may not be varnish coated. The glass fiber insulation, when varnished, shall have a smooth, nontacky surface. A high quality baking varnish shall be used. The fabric before varnishing shall be glass-fiber fabric having the warp and filling threads at right angles to each other.

3.4 Classes.

3.4.1 *Class B.* Class B insulation shall conform to applicable requirements of table I, and shall be furnished in the types and thicknesses shown therein. When required (see 1.2 and 3.3). A high quality organic varnish shall be used as a binder and as a layer coating on the glass fiber component.

3.4.2 *Class H.* Class H insulation shall conform to the applicable requirements of table I, and shall be furnished in the types and thicknesses shown therein. A high quality baking silicone varnish shall be used as a binder, and as a layer on the glass fiber component, when required (see 1.2 and 3.3).

3.5 Forms.

3.5.1 *Form S (sheets).* Unless otherwise specified in the contract or order, sheets shall be furnished trimmed. Sheets shall be trimmed to a 36-inch square ±1 inch. Sheets shall be furnished in 36-inch lengths with a tolerance of ±1 inch.

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:07Z
Check the source to verify that this is the current version before use.

TABLE I. *Thicknesses and performance requirements*

Class	Form	Type	Nominal thickness as specified (see 6.2)	Tolerance (±) of average thickness from nominal thickness	Tolerance of individual thickness from nomina. thickness (±)	Tensile Strength		Dielectric Strength		Flexibility
						Condition C-96/25/50		Condition C-96/25/0	Condition C-96/25/96	Diameter of mandrel around which insulation shall be wound 360 degrees without chipping, cracking, or breaking Condition C-96/25/50
						Warp	Filler			
			Inch	Inch	Inch	Pounds per inch width (min. average)	Pounds per inch width (min. average)	Volts (min. average)	Volts (min. average)	Inch
B	S	Pmg	.007	.002	+.007-.002	65	35	4,550	2,730	½
		Mg	.008	.002	+.007-.002	65	35	5,200	3,300	½
		Mg	.010	.002	+.007-.002	65	35	6,500	3,900	½
		Gmg	.012	.002	+.007-.002	100	70	7,800	4,680	½
		Pmg	.015	.003	+.008-.003	250	200	9,750	5,850	½
B	T	Mg	.0035	.001	+.002-.001	40	...	1,575	945	½
		Pmg	.007	.002	+.007-.002	65	...	3,150	1,890	½
H	S	Mg	.007	.002	+.007-.002	65	35	3,500	2,100	½
		Gmg	.010	.002	+.007-.002	90	60	5,000	3,000	½
		Gmg	.012	.002	+.007-.002	100	70	6,000	3,600	½
		Gmg	.020	.003	+.007-.006	200	140	10,000	6,000	½
		Gmg	.025	.003	+.008-.005	250	175	12,600	7,500	½
H	T	Mg	.0035	.001	+.002-.001	40	...	1,400	840	½
		Mg	.007	.002	+.003-.002	65	...	2,800	1,680	½
		Gmg	.010	.002	+.004-.002	90	...	4,000	2,400	½

Source: https://assist.dla.mil -- Downloaded: 20264O-16T18:07Z
Check the source to verify that this is the current version before use.

3.5.2 *Form T (tape).* Unless otherwise specified in the contract or order, tape shall be furnished in rolls in accordance with table II. The tape shall not be spliced and not over two pieces shall be used in any one roll. The shorter of the two pieces shall not be less than 10 percent of the total length on the roll. The glass fiber layer shall be on the inside of the roll. Tape shall be furnished in widths of ½, ¾ and 1 inch, as specified (see 6.2), within a tolerance of $\pm\frac{1}{32}$ inch

TABLE II. *Length of rolls*

Tape thickness	Approximate rolled length
Inch	Yards
0.0035	50
.007	36
.010	20

3.6 Identification of individual sheets for stock. Form S sheets furnished for stock shall be marked with the class and stock number in accordance with Standard MIL-STD-130.

3.7 Type Pmg. A high quality of electrical paper insulation shall be used.

3.8 Workmanship. The workmanship for this product shall be such as to meet the requirements of the specification, when inspected in accordance with Section 4.

4. QUALITY ASSURANCE PROVISIONS

4.1 The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling for acceptance inspection.

4.2.1 *Inspection lot.* All material of the same class, form, type, and size manufactured in one production run and offered for delivery at one time shall be considered a lot for purposes of sampling and inspection.

4.2.2 *Sampling for examination.* A random sample of sheets or rolls shall be selected from each inspection lot offered for examination of visual and dimensional characteristics in accordance with Standard MIL-STD-105 at inspection level II. The Acceptable Quality Level shall be 1.5 percent defective.

4.2.3 *Sampling for tensile and dielectric tests.* A random sample of sheets or rolls shall be selected in accordance with the table for small sample inspection of Standard MIL-STD-105 at inspection level L-8 and shall be subjected to the tests specified in 4.6.3, 4.6.4, and 4.6.5. The largest sample to be used, however, shall be 15.

4.3 Acceptance inspection. Visual and dimensional examination.

4.3.1 *Visual and dimensional examination.* Each of the sample sheets or rolls selected in accordance with 4.2.1 shall be visually and dimensionally examined to verify compliance with this specification. Examination of the material of each sample roll shall be made on material remaining after several outer turns have been removed. Any sheet or roll in the sample containing one or more visual or dimensional defects shall be rejected, and if the number of defective sheets or rolls in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

4.3.2 *Acceptance tests.* Each of the sample sheets or rolls selected in accordance with 4.2.2 shall be tested to verify compliance with this specification. If any sheet or roll in the sample fails any test, the lot represented by the sample shall be rejected.

4.3.3 *Reports of acceptance inspection.* In addition to the copies required by the Government inspector, two copies of each acceptance examination and test report shall be forwarded to the bureau or agency concerned via the Government inspector for information purposes.

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:07Z
Check the source to verify that this is the currentversion before use.

4.4 Conditioning of test specimens.

4.4.1 *Nomenclature.* The following letter shall be used to indicate the respective general conditioning:

Condition C—Humidity conditioning

4.4.2 *Designation.* The designations indicating conditioning of test specimens shall be as follows:

First: A capital letter indicating the general condition of the specimen, that is, humidity, and temperature conditioning.

Second: A number indicating in hours the duration of the conditioning.

Third: A number indicating in degrees centrigrade the conditioning temperature.

Fourth: A number indicating relative humidity, whenever relative humidity is controlled. Relative humidity obtained over anhydrous $CaCl_2$ shall be taken as zero.

The numbers shall be separated from each other by slant marks and from the capital letter by a dash, examples:

Condition C-96/25/0—The specimen shall be conditioned for a period of not less than 96 hours at a temperature of 25° Centigrade (C.) 77° Fahrenheit (F.) over calcium chloride. The samples shall be tested immediately after removal from the conditioning chamber.

Condition C-96/25/50—The specimens shall be conditioned for a period of not less than 96 hours at a temperature of 25° C. (77° F.) and a relative humidity of 50 percent.

Condition C-96/25/96—The specimens shall be conditioned for a period of not less than 96 hours at a temperature of 25° C. (77° F.) and a relative humidity of 96 percent. The samples shall be tested immediately after removal from the conditioning chamber.

4.5 Examination and tests procedures.

4.5.1 *General examination.* The insulation sheet or tape shall be given a thorough examination to ascertain conformance to this specification.

4.5.2 *Dimensional examination.*

4.5.2.1 *Thickness.* The thickness shall be determined by the use of a dial type micrometer or alternatively with a 1-inch machinist's micrometer. The total thickness of the material, the thickness of the fiber glass component (including varnish, if varnish coated), and the thickness of the paper components shall be measured directly. The thickness of the pasted mica components shall be determined by difference. The thickness shall be determined as the average of at least 10 readings taken at intervals of approximately 1 foot along the length of the material. The maximum, minimum, and average values shall be recorded.

4.5.2.1.1 When a dial type micrometer is used, the lower or fixed anvil shall consist of a flat steel plate 2 inches in diameter; the upper or movable member shall consist of a foot or button having a flat steel face ¼ inch in diameter and arranged so as to move with its face at all times parallel to the face of the anvil. The movable member shall be of such weight and be attached to the operating rod of the micrometer in such a manner that the pressure exerted on the specimen shall be within the limits of 23 and 27 pounds per square inch (p. s. i.).

4.5.2.1.2 A 1-inch machinist's micrometer equipped with a ratchet may be used as an alternate to the dial type micrometer. The machinist's micrometer shall have ¼ inch diameter anvil and spindle surfaces. In case of dispute as to the thickness determined by the machinist's micrometer, an additional set of measurements shall be taken with the dial type micrometer and these measurements will be considered final.

4.5.2.2 *Width.* The width of tape shall be determined by the use of a standard steel scale graduated to read to 1/64 inch. The width of sheets may be measured by any suitable means. The material shall lie flat on a smooth surface at the time of measurement. In the case of tape, at least 10 measurements shall be made of width

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:07Z
Check the source to verify that this is the current version before use.

and the maximum, minimum, and average values recorded. The average value shall be taken as the tape width.

4.5.2.3 *Length.* The length of the sheet shall be measured. The length of tape on the sample rolls shall be suitably determined by unwinding and measuring. By suitable comparison of weights (sample rolls versus others) it shall be ascertained that the rolls contain not less than the specified quantity of tape.

4.5.3 *Flexibility.* The material shall be tested for flexibility by wrapping it 360 degrees around a mandrel of the proper size specified in table I after Condition C-96/25/50. The wrapped material shall be examined with the naked eye for chipping, cracking, or breaking. Tapes shall be wound so that the varnished glass component will be on the outside.

4.5.4 *Tensile strength.*

4.5.4.1 The tensile strength shall be determined on a pendulum typetesting machine. The machine shall preferably be power-driven and shall have a capacity not to exceed 500 pounds. It shall be graduated to read ½ pound or less per scale division.

4.5.4.2 Specimens cut from the full width sheet samples shall be 1 inch in width, having length not less than 2 inches in excess of the jaw clearance of the tensile tester. For tape, the specimens shall be of the original width and shall be of a length not less than 2 inches in excess of the jaw clearance of the tensile tester.

4.5.4.3 In the case of sheets, five specimens shall be cut with the sides paralleled to the warp threads and five with the sides parallel to the filling threads. In the case of tape, five specimens shall be cut from each sample roll.

4.5.4.4 The ratio of the clearance distance between jaws to the width of the specimen shall be not less than 5 to 1 nor more than 10 to 1.

4.5.4.5 The rate of travel of the movable jaw shall be constant and preferably 12 inches per minute, but it may be within the limits of 11 to 13 inches per minute provided it is constant. All readings obtained when the specimen breaks at or in the jaws shall be disregarded.

4.5.4.6 The tensile strength in pounds per inch width shall be determined from the average of the five tests in each direction.

4.5.5 *Dielectric strength.*

4.5.5.1 Any suitable, high-tension transformer connected to an alternating-current supply, having as nearly as true sine wave as possible, may be used. The transformer and the source of supply of energy shall be not less than 2 kilovolt-amperes (KVA). The frequency shall not exceed 100 cycles per second (c. p. s.).

4.5.5.2 Regulation shall be so controlled that the high-tension testing voltage taken from the secondary of the testing transformer can be raised gradually from any point, and in no case more than 500 volts at a step. Any method of regulating the voltage which will not distort the wave more than 10 percent from a sinusoidal shape will be satisfactory.

4.5.5.3 The voltage may be measured by any satisfactory method which will give root-mean-square values, preferably by means of a voltmeter connected to a suitable tertiary coil in the testing transformer, or to a separate step-down transformer.

4.5.5.4 For tests on form T (see 6.3), a special form of testing device using ¼-inch diameter electrodes, whereby the test specimen shall be clamped under 6 ounces of pressure in order to prevent flashover around the edges of the material shall be used.

4.5.5.5 The test specimens for form S may be of any sufficient size that will prevent flashover. The test electrodes shall be metal disks, 2 inches in diameter, and 1 inch in length with edges rounded to ¼-inch radius.

4.5.5.6 The total area of the specimens of each sample of material subjected to Conditions C-96/25/0 and C-96/25/96 shall be sufficient to permit making 10 tests after each condition. The specimen shall be representative of the material to be tested. The tests shall be made with the specimens in air at the conditioning temperature.

4.5.5.7 Starting at zero, the voltage shall be increased uniformly to breakdown at a rate of 500 volts per second. Ten tests shall be made for

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:07Z
Check the source to verify that this is the current version before use.

each condition and the average of these 10 readings in volts shall be taken.

4.6 Inspection of preparation for delivery. Sample items, packages, and packs shall be selected and inspected in accordance with Specification MIL-P-116 to verify conformance with the requirements of Section 5 herein

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 *Level A.*

5.1.1.1 Form S insulation sheets shall be stacked in alike thickness and size in quantities specified (see 6.2) with a sheet of fiberboard the same size as the insulation sheets, placed above and under the stack and secured in place with tape conforming to Specification PPP-T-76 of suitable width. The stacks shall be individually wrapped with waterproof barrier material conforming to type C-1 or C-2 of Specification UU-P-271 with all folds, seams, and laps sealed with water resistant adhesive conforming to Specification MIL-A-140.

5.1.1.2 Form T insulation tape shall be individually packaged in accordance with method 1A-8 of Specification MIL-P-116 and in folding or set-up paperboard boxes conforming to Specification PPP-B-566 or PPP-B-676. Each box shall be closed and sealed in accordance with the applicable box specification or appendix thereto.

5.1.1.2.1 *Intermediate packaging.* Form T insulation tape unit packaged as specified in 5.1.1.2 shall be intermediate packaged in boxes of like description and size in snug-fitting fiberboard boxes conforming to Specification PPP-B-636. Unit quantities in an intermediate container shall be as specified (see 6.2). The boxes shall be closed and sealed in accordance with appendix of the box specification.

5.1.2 *Level C.* Insulation sheet or tape shall be preserved and packaged in accordance with the manufacturer's commercial practice.

5.2 Packing.

5.2.1 *Level A.* Insulation sheet or tape, packaged as specified (see 6.2), shall be packed in overseas type, wood-cleated fiberboard, nailed wood, wirebound wood, fiber, wood-cleated veneer paper overlaid, or wood-cleated plywood boxes conforming to Specifications PPP-B-591 (overseas type), PPP-B-621, (overseas type), PPP-B-585, (overseas type), PPP-B-636, (class 3), MIL-B-10377, (overseas type), or PPP-B-601, (overseas type), respectively, at the option of the contractor. Shipping containers shall have caseliners conforming to Specification MIL-L-10547. Caseliners shall be closed and sealed in accordance with the appendix to Specification MIL-L-10547. Caseliners for boxes conforming to Specification PPP-B-636 may be omitted, provided all center and edge and manufacture joint of the boxes are sealed with minimum 1½-inch wide tape conforming to Specification PPP-T-76. Boxes shall be closed and strapped in accordance with the applicable box specification or appendix thereto except that fiber boxes shall be bonded with tape conforming to type IV of Specification PPP-T-97 and the appendix thereto. The gross weight of wood or wood cleated boxes shall not exceed 200 pounds; fiber boxes shall not exceed the weight limitations of the applicable box specification.

5.2.2 *Level B.* Insulation sheet or tape, packaged as specified (see 6.2), shall be packed in domestic type wood-cleated fiberboard, nailed wood, wirebound wood, wood-cleated plywood or wood-cleated paper overlaid boxes of class 2 or fiber boxes conforming to Specification PPP-B-591, (domestic type), PPP-B-621, (class 1), PPP-B-585, PPP-B-601, (domestic type), MIL-B-10377, (domestic type), or PPP-B-636, (class 2), respectively, at the option of the contractor. Box closures shall be as specified in the applicable box specification or appendix thereto. The gross weight of wood or wood-cleated boxes shall not exceed 200 pounds; fiber boxes shall not exceed the weight limitations of the applicable box specification.

5.2.3 *Level C.* Insulation sheet or tape, packaged as specified (see 6.2), shall be packed in containers which will insure acceptance by common carrier and safe delivery at destination. Shipping containers shall comply to the Uniform Freight Classification Rules or other regulations as applicable to the mode of transportation.

Source: https://assist.dla.mil -- Downloaded: 20260-16T18:07Z
Check the source to verify that this is the current version before use.

5.3 **Marking.** In addition to any special marking required by the contract or order or herein, interior and exterior shipping containers shall be marked in accordance with Standard MIL-STD-129.

6. NOTES

6.1 **Intended use.**

6.1.1 *Class B.* Class B material is used for generator, motor and transformer coils, slot liners and ground insulation, phase to phase insulation, phase and end insulation, primary secondary separation, coil exteriors cable splices, coil and cell-wrapper tapes, and similar uses. The highest temperature (limiting "hottest spot" temperature) to which class B insulation may be subjected to continuously with normal life expectancy is 130° C.

6.1.2 *Class H.* Class H material is used for applications as specified in 6.1.1 and where the highest temperature (limiting "hottest spot" temperature) is 200° C. for normal life expectancy.

6.2 **Ordering data.** Procurement documents should specify the following:

(a) Title, number, and date of this specification.

(b) Class, type, and form of material required (see 1.2).

(c) Nominal thickness required (see table I).

(d) Width of tape required (see 3.5.2).

(e) Quantities of sheets to be packaged (see 5.1.1.1).

(f) Level of preservation and packaging and level of packing required (see 5.1. and 5.2).

6.3 Two forms of testers are specified in the Appendix of ASTM Designation 295-Tentative Methods of Test for Varnished Cloths and Tapes.

Notice. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Custodians:

Army—SigC
Navy—Ships
Air Force—ARDC

Preparing activity:

Navy—Ships
(Project 5970-0001)

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:07Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATE

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding
Naval Ship Engineering Center
Attn: Code 6604.3B
Washington, DC 20360

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:07Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:07Z
Check the source to verify that this is the current version before use.