NOT MEASUREMENT SENSITIVE

MIL-PRF-3572B
AMENDMENT 1
30 September 2002

PERFORMANCE SPECIFICATION

LUBRICANT, COLLOIDAL GRAPHITE IN OIL

This amendment forms a part of MIL-PRF-3572B, dated 21 January 2000, and is approved for use by all departments and agencies of the Department of Defense.

PAGE 3

Table I: Delete and substitute:

TABLE I. Physical and chemical requirements.

Property	Grade A	Grade B	Grade C
Viscosity, cSt at 40 °C	19-25	--	--
Viscosity, cSt at 100 °C	--	22-27	57 (min.)
Flash point, °C min.	140	160	160
Pour point, °C max.	-46	-9	-9
Solids content, weight percent[1]	2.00 ± 0.05	10.00 ± 0.25	10.00 ± 0.25
Ash, weight percent (max.)[1]	0.75	0.75	0.75
Hiding power of lubricant containing two weight percent solids, sq. ft. per gallon (min.)	1,200	1,200	900

[1]Conversion must be made from weight percent to mass percent for application of verification test methods in section 4.

PAGE 4

4.3.8, line 2: Delete "10.00 ± 0.01 g" and substitute "10.00 ± 0.10 g".

Custodians:
Army - AT
Navy - OS
Air Force - 68

Preparing Activity:
DLA - GS3

(Project 9150-1275)

AMSC N/A 1 of 1 FSC 9150

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:13Z
Check the source to verify that this is the current version before use.