MIL-T-3508D

25 September 1970

SUPERSEDING
MIL-T-3508C
25 July 1967

MILITARY SPECIFICATION

TAGS, LAUNDRY MARKING, AND TAPE, PAPER, DRY CLEANING MARKING

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope.- This specification covers tags for identification of articles to be laundered or dry cleaned (see 6.1).

1.2 Classification.- Tags shall be of the following types, classes, and styles as specified (see 6.2).

Type I	- Cloth.
Class 1	- Resin coated on one side, with staples.
Class 2	- Sized, without staples.
Style A	- Rectangular.
Style B	- Slitted tab.
Class 3	- Heat sealable.
Type II	- Paper

2. APPLICABLE DOCUMENTS

* 2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

P-D-680	- Dry Cleaning Solvent.
TT-I-542	- Ink, Laundry, Indelible, Black, for Fabric.

FSC 8135

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Box, Fiberboard.
PPP-B-676 - Box, Set-up
PPP-T-45 - Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.

MILITARY

MIL-C-10296 - Cloth, Sateen, Cotton

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications, standards, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

DA Technical Manual TM-10-354 - Army Fixed Laundry Organization

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office, Washington, D.C. 20402.)

* Technical Association of the Pulp and Paper Industry

Testing Methods, Recommended Practices, Specifications of the Technical Association of the Pulp and Paper Industry.

T404 - Tensile Breaking Strength of Paper and Paperboard.
T410 - Weight Per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T414 - Internal Tearing Resistance of Paper.
T456 - Wet Tensile Breaking Strength of Paper and Paperboard.

Source: https://assist.dla.mil -- Downloaded: 202640-16T18:08Z
Check the source to verify that this is the current version before use.

(Copies of TAPPI testing methods may be obtained from the Technical Association of the Pulp and Paper Industry, 360 Lexington Avenue, New York, New York 10017.)

(Technical society and technical association specifications an standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal Agencies.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC.

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Association, ATTN: Tariff Order Section, 1616 P Street, N.W., Washington, D.C. 20036.)

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Type I cloth.-

3.1.1 Material.- The base fabric shall be white, natural, light blue, light green or yellow color, as specified (see 6.2). Cloth shall be cotton and shall comply with the requirements in table I when tested as specified in 4.2.1.1.

TABLE I.- Base fabric requirements

Weight per square yard, ounces (minimum)	Threads per inch (minimum)		Breaking strength, pounds (minimum)		Shrinkage, percent (maximum)	
	Warp	Filling	Warp	Filling	Warp	Filling
2.6	70	70	37	27	10	10

3.1.2 Finish and sizing.-

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

3.1.2.1 Class 1.- The base cloth for class 1 tags shall be evenly coated on one side with a clear resin compound when tested as specified in 4.2.1.1.

3.1.2.2 Class 2.- The weight of a desized class 2 tag shall be not less than 75 percent nor more than 85 percent of the original tag weight when tested as specified in 4.2.1.1.

* 3.1.2.3 Class 3, heat-sealable.- The base cloth for class 3 tags shall be evenly coated on one side with a heat-sealable coating for attaching the tag to the article to be laundered. The coating shall be a resinous compound. The coated cloth weight shall be 5.6 oz. per square yard minimum, when tested as specified in 4.2.1.1.

3.1.3 Construction.-

3.1.3.1 Class 1 tag.- Class 1 tags shall be formed from a rectangular strip of finished cloth, as specified in 3.1.2.1, by folding both edges inward with an overlap to the specified width. The coated side of the cloth shall be on the inside of the tag. Staples shall be fabricated from zinc strip (minimum 98 percent zinc) and shall be inserted perpendicular to the fold through both layers of cloth, not less than 1/8 inch from each end of the tag. The staples shall be not less than 0.015 inch thick and 14/16 to 15/16 inch in length, tapering to a point at each end. The crown of the staple shall be 4/16 to 5/16 inch long and not less than 3/32 inch wide when tested as specified in 4.2.1.1. Staples may be of "square" or elliptical design and shall not be clinched.

3.1.3.2 Class 2 tag.-

3.1.3.2.1 Style A.- Style A, class 2 tags shall be formed from a strip of sized cloth specified in 3.1.2.2 cut in a rectangular shape.

3.1.3.2.2 Style B.- Style B, class 2 tags shall be formed from a strip of sized cloth, specified in 3.1.2.2, cut in a slitted tab design. The slitted tab design shall be produced by cutting sections of one fourth of the total tag width from each edge for one-half the length of the tag. The narrow or tab part of the tag shall have a centered, $\pm$ 1/32 inch slit so that the wide part of the tag may be looped through the garment and the slit. The slit shall begin not less than 3/8 $\pm$ 1/16 inch from the end and shall extend not more than 1-3/4 $\pm$ 1/16 inches along its length.

3.1.4 Dimension.-

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

3.1.4.1 Class 1 tag.- Class 1 tags shall be 2-1/8 by 1/2 inches, with a tolerance of ± 1/16 inch for both dimensions.

3.1.4.2 Class 2 tag.-

3.1.4.2.1 Style A.- Style A, class 2 tags shall be 3 by 5 or 1 by 4 inches, as specified (see 6.2) with a ± 1/16 inch tolerance.

3.1.4.2.2 Style B.- Style B, class 2 tags shall have an overall length of 4-1/2 inches and shall be one inch wide for 2-1/4 inches of length, then becoming 1/2 inch wide. The 1/2 inch wide length shall be formed by cutting sections 2-1/4 inches long and 1/4 inch wide from each edge. A tolerance of ± 1/16 inch shall be permitted for all dimensions

* 3.1.4.2.3 Class 3 tags shall be 2-1/4 inches in length by 5/8 inch in width and shall have a ± 1/16 inch tolerance in both dimensions.

3.2 Type II, paper.-

3.2.1 Material.- The paper shall be white and shall comply with the requirements of table II when tested as specified in 4.2.1.1.

TABLE II.- Paper requirements

Basis weight, pounds 24 by 36-500	Tearing resistance, grams, (minimum) average		Tensile strength, pound per inch width (min.) average			
			Dry		Wet	
	Machine direction	Cross direction	Machine direction	Cross direction	Machine direction	Cross direction
75.0 (± 5 percent)	132	156	60	35	20	10

3.2.2 Form.- Type II tags shall be furnished in rolls of paper tape which may be cut into rectangular individual tags of any desired length.

3.2.2.1 Length.- Rolls shall be tightly wound and shall average 100 yards in length, except that no individual roll shall be less than 98 yards long. Rolls shall not telescope more than 1/8 inch and shall be suitably restrained to prevent unwinding prior to use. No more than two splices in any roll shall be permitted.

3.2.2.2 Width.- The width of the paper tape shall be 15/16 ± 1/16 inch.

3.3 Marking quality.-

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

3.3.1 Initial.- Cloth tags and paper tape shall show clear markings when marked with indelible ink as specified in 4.3.2. Type I, class 1 and class 3 tags shall be capable of being marked on the uncoated side. Type I, class 2 tags and type II, paper tape shall be capable of being marked on either side.

3.3.2 After laundering.- Cloth tags intended for use in laundering operations (see 6.2), marked in accordance with 3.3.1 shall retain clearly legible markings; that is, there shall be no question concerning the identification of any one character, after one laundering when tested as specified in 4.3.2.

3.3.3 After dry cleaning.- Paper tape and cloth tags intended for use in dry cleaning operations (see 6.2), marked in accordance with 3.3.1 shall retain clearly legible markings; that is, there shall be no question concerning the identification of any one character, after one dry cleaning when tested as specified in 4.3.2.

* 3.4 Adhesion.- When applied and tested as in 4.4.1.2, class 3 tags shall withstand laundering without separating from the test cloth and without lifting at the edges.

3.5 Workmanship.- The tags shall be clean, with clean cut edges and shall be free from wrinkles and tears.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance.- Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except when otherwise indicated hereinafter.

4.2.1 Inspection of materials and components.- In accordance with 4.1 above, components and material shall be inspected and tested in accordance

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended or qualified in this specification or applicable purchase documents.

* 4.2.1.1 Testing of components.- The component materials shall be tested for the applicable characteristics in table III. The methods of testing specified in FED-STD-191 and TAPPI, as applicable and as listed in table III, shall be followed. The lot of components shall consist of all the cloth, paper, or zinc strip used in fabricating all the end items offered for inspection at one time. The lot for determining the sample size shall be expressed in units of square yards of cloth for tests applicable to the cloth component; in pounds of paper for the paper component; and in feet of zinc strip for the staple component. The sample unit shall be one piece of cloth two yards long by one yard wide for the cloth component, a piece or pieces of paper with an aggregate area of 2,000 square inches and no dimension (excluding thickness) less than 10 inches for the paper component, and one foot of zinc strip for the staple component. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. When applicable, the supplier shall submit to the contracting officer or his authorized representative a certificate of compliance certifying the zinc content of the metal strip used in fabricating the staple component. The sample size shall be S-1.

4.3 Inspection of the end item.-

4.3.1 Examination of the end item.- The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) in 4.3.1.5. Random sample shall be drawn from each lot of end items of the same type, class and style, as applicable, for examination of visual, dimensional and preparation for delivery defects. The lot for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of finished rolls or tags, as applicable, for examination in 4.3.1.1, 4.3.1.2, and 4.3.1.3, and in units of shipping containers for examination in 4.3.1.4.

* 4.3.1.1 Examination of defects in appearance, construction, and workmanship.- The sample unit for this examination shall be one roll of paper or one cloth tag, as applicable.

Examine	Defect
Type I (cloth tag)	
Color	Not as specified.
Material	Holes, smashes, multiple floats, loose or weakening slubs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

Examine	Defect
Construction	
Class 1	Folded edges do not overlap. Coating not uniform. Coated side not on inside of tag. One or both staples missing. Staples not perpendicular to fold. Staples not penetrated through both layers of cloth. Staples not tapered to a point at both ends. Any part of staple broken. Staple clinched.
Class 2	Not style specified.
Style B	Slit missing.
Class 3	Resin missing; coated on both sides.
Workmanship	Presence of dirt, spots or stains. Ragged or frayed edges. Torn, wrinkled or cut (except for slit in class 2, style B).
Type II (paper tape)	
Appearance	Not white.
Construction of roll	Not suitably restrained to prevent unwinding before use. Fails to unwind after starting due to blocking or stray adhesive. More than two splices. Telescoping of roll by more than 1/8 inch.
Workmanship	Presence of tears, wrinkles, dirt, spots, or ragged edges.

* 4.3.1.2 Examination for defects in dimensions.- The sample unit for this examination shall be one cloth tag or one roll of paper tape, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

Examine	Defect
Type I	
Class 1	
Tag size	Varies from specified dimension by more than 1/16 inch.
Staples	
Placement	Less than 1/8 inch from each end.
Length	Less than 14/16 or more than 15/16 inch.
Crown	Less than 4/16 inch or more than 5/16 inch long. Less than 3/32 inch wide.
Thickness	Less than .015 inch.
Class 2	
Tag size, style A or B	Varies from specified dimensions by more than 1/16 inch.
Style B, slit	Not centered ± 1/32 inch. Begins less than 5/16 inch from end of tag. More than 1-13/16 inch or less than 1-11/16 inches in length.
Class 3	Less than 2-3/16 inch or more than 2-5/16 inches in length. Less than 9/16 inch or more than 11/16 inches in width.
Type II	
Width	More than 1 inch or less than 7/8 inch.

4.3.1.3 Examination for average length per roll (type II only).- The sample unit for this examination shall be one roll. The lot shall be unacceptable if the average length per roll is less than specified for all sample units. Any length of an individual roll less than 98 percent of the specified length shall be scored a defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

* 4.3.1.4 Examination of preparation for delivery.- An examination shall be made to determine that packaging, packing and marking comply with the requirements of section 5. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects. The lot shall be the number of shipping containers in the end item inspection lot.

Examine	Defect
Markings (exterior and interior)	Missing; incorrect; illegible; of improper size, location, sequence or method of application (see 5.3).
Materials	Any nonconforming component; component missing, damaged or otherwise defective.
Workmanship	Inadequate application of components such as: incomplete closure of container flaps, loose or inadequate strapping, sealing or stapling. Any bulged or distorted container.
Count	Less than specified or indicated count per package.
Contents	Number of interior packages, tags, or rolls, as applicable, per container is more or less than specified.
Weight	Weight of contents of each shipping container exceeds requirements.

4.3.1.5 Inspection levels and acceptable quality levels (AQLs) for examination.- The inspection levels for determining the sample size, and the acceptable quality levels (AQLs), expressed in defects per hundred units, shall be as follows:

Inspection paragraph	Inspection level	AQLs
4.3.1.1	I	2.5
4.3.1.2	S-2	2.5
4.3.1.3	S-2	2.5 1/
4.3.1.4	S-1	2.5

1/ Applies to individual roll length only.

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:08Z
Check the source to verify that this is the current version before use.

4.3.2 Testing of the end item.- The end item shall be tested for the characteristics in table IV for each lot of material. The lot for determining the sample size shall consist of all tags of the same type, class, style and color offered for inspection at one time. The sample unit shall be ten tags or ten six-inch lengths of paper tape, as applicable. No more than one sample unit shall be drawn from any intermediate package. The sample size shall be S-1. All test reports shall contain the individual values utilized in expressing the final results. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING THE COMPONENTS

TABLE ~~III~~

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations	Results Reported As		Inspect Level	AQL
	Requirement	Test Method	Individ Unit	Samp unit	Per sample unit	Pass or Fail	Numerically to Nearest		
Cloth component for type I tags									
Base fabric, classes 1 and 2									
Weight, ounces per sq. yd.	Table I	5041 1/		X	5		0.1 ounce		
Thread/inch									
Warp	Table I	5050 1/		X	5		4 threads		
Filling	Table I	5050 1/		X	5		4 threads		
Breaking strength, pounds, minimum									
Warp	Table I	5100 1/		X	5		pound		
Filling	Table I	5100 1/		X	5		pound		
Shrinkage, percent									
Warp	Table I	5550 1/		X	3		1/2 percent		
Filling	Table I	5550 1/		X	3		1/2 percent		
Coating, class 1 and 3	3.1.2.1	2/				X			
Sizing, class 2	3.1.3.1	2611 1/		X	2		percent		
Staples, composition	3.1.3.1	2/				X			
Basis weight, 24 x 36-500 pounds	3.2.1	T410		3/X	10	-	pound		
Tearing resistance	3.2.1	T414		X	10	-	gram		
Tensile, dry, pounds/inch width	3.2.1	T404		X	10	-	pound		

AMXRE Form 598
8 February 1965

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING THE COMPONENTS (cont'd)

TABLE III

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations	Results Reported As		Inspect Level	AQL
	Requirement	Test Method	Individ Unit	Samp unit	Per sample unit	Pass or Fail	Numerically to Nearest		
Tensile, wet, pounds/inch	3.2.1	T456		X	10	-	pound		

1/ Denotes test number of FED-STD-191.

2/ Supplier's certificate of compliance shall satisfy this requirement.

3/ Denotes TAPPI test standard numbers.

AMXRE Form 598
8 February 1965

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING THE END ITEM

TABLE IV

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations	Results Reported As		Inspect Level	AQL
	Requirement	Test Method	Sample unit	Lot Aver	Per sample unit	Pass or Fail 1/	Numerically to Nearest		
Marking quality									
Initial	3.3.1	4.4.1.1	X		1	X			
After laundering, as applicable	3.3.2	4.4.1.2	X		1	X			
After dry cleaning, as applicable	3.3.3	4.4.1.3	X		1	X			

1/ If failure is indicated, report description of failure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

AMXRE Form 590
8 February 1965

4.4 Test procedures.-

4.4.1 Marking.-

* 4.4.1.1 Initial.- Using ink conforming to TT-I-542, and a laundry marking machine, mark the specimen to be tested (one tag or one six-inch length of tape) with eight characters. For class 1 tags, marking shall be made on the uncoated side or the side normally on the outside after stapling to a garment. For class 2 tags, the markings shall be made on both sides of the tag, taking care not to blot or smear the markings made on the first side marked. For class 3 tags, the marking shall be on the uncoated side, prior to heat seal application. For paper tape, the initial marking shall be made on one side on a 3-inch length of tape; the tape shall then be reversed and marked on the remaining length, taking care not to blot or smear the initial markings. Not less than 15 minutes and not more than 20 minutes after affixing the last mark, the specimens shall be inspected for clarity of marking.

4.4.1.2 After laundering, as applicable (classes 1 and 2).- Immediately after the tags have been inspected in accordance with 4.4.1.1, they shall be subjected to one cotton laundering and drying in accordance with Method 5610 of FED-STD-191, followed by ironing or pressing in accordance with chapters 6 and 7 of TM-10-354. The laundered, rinsed, dried and ironed specimens shall be inspected for clarity of markings.

* 4.4.1.2.1 After laundering (class 3 only).- The marking on class 3 tags shall be examined for legibility after heat sealing and laundering as specified in 4.4.2.

4.4.1.3 After dry cleaning, as applicable.- Immediately after inspecting the tags, or tape as applicable, in accordance with 4.4.1.1, they shall be subjected to a dry cleaning operation as follows. Place the test specimen in a one pint jar containing 150 milliliters of dry cleaning solution conforming to P-D-680 and noncorroding steel balls of 3/8 inch diameter. Agitate in a Launderometer or similar machine described in Method 5610 of FED-STD-191, for 20 minutes. Remove the specimens from the jar, extract excess solvent in a centrifuge, and lay out to dry on horizontal surface at a temperature of 71° ± 2° C. for one hour. After the operations of treating, extraction, and drying, inspect the specimens for clarity of marking.

* 4.4.2 Laundering test (class 3 tag).-

* 4.4.2.1 Preparation of test specimens.-

Source: https://assist.dla.mil -- Downloaded: 202640-16T18:08Z
Check the source to verify that this is the current version before use.

4.4.2.2 Test cloth.- Test cloth to which class 3 tags shall be heat sealed shall be a 22 by 22 inch piece of cloth conforming to class 1, MIL-C-10296.

4.4.2.3 Marking of tags.- Tags for this test shall be marked as specified in 4.4.1.1 at least one hour prior to heat sealing of the tags.

* 4.4.2.4 Heat sealing.- Six tags marked as specified in 4.4.2.3, shall be attached, by heat sealing, to the filling effects side of the test cloth. The heat sealing device shall have a platen temperature of 275° ± 10° F. Dwell time shall be five to six seconds, and dwell pressure shall be 10 lbs. per square inch of platen area.

* 4.4.2.5 Laundering test.- One hour after attachment of tags as specified in 4.4.2.4, the test cloth shall be subjected to five cycles of laundering per Method 5556 of FED-STD-191 to include cotton laundering procedure, extraction, tumble drying, and flat bed pressing. At the end of five cycles the six tags shall be examined for extend of separation of the tags from the test cloth or lifting at the edges (see 3.1.2.3.1) and for legibility of the marking (see 3.3.2).

* 5. PREPARATION FOR DELIVERY.

5.1 Packaging.- Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.-

5.1.1.1 Type I.- One thousand type I tags, of one class and style only, shall be packaged in a snug-fitting, folding paperboard box conforming to variety 1, style III, type G, class 1 of PPP-B-566; or type I, variety 1, class A, style 3 or 4 of PPP-B-676. Each box shall be securely closed with 2-inch minimum width gummed paper tape conforming to type III, grade A or B or PPP-T-45, applied at the center of the length opening, along the bottom and up each side a minimum of one-half the depth of the box.

5.1.1.2 Type II.- Ten rolls of type II tags shall be evenly stacked and then completely wrapped in 30-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. The wrap shall be secured with 2-inch minimum width gummed paper tape conforming to type III, grade B of PPP-T-45.

5.1.2 Level C.- Tags shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing.- Packing shall be level A, B, or C as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:08Z
Check the source to verify that this is the current version before use.

5.2.1 Level A.- Tags of one description only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the appendix of the container specification. The weight of contents of each shipping container shall not exceed 65-pounds.

5.2.2 Level B.- Tags of one description only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class comestic, grade 275 of PPP-B-636. Each shipping container shall be closed in accordanc with method II as specified in the appendix of PPP-B-636. The weight of contents of each shipping container shall not exceed 65-pounds.

5.2.2.1 When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636, and closed in accordance with the appendix of the container specification.

5.2.3 Level C.- Tags, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.- In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use.- The identification markers are used in the marking of textile items to be laundered or dry cleaned.

6.2 Ordering data.- Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Type, class and style of tags required.
(c) Color of cloth required (see 3.1.1).
(d) Dimensions of type I, class 2, style A tags (see 3.1.4.2.1).
(e) Intended use of tag, i.e., laundering or dry cleaning (see 6.1).
(f) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(g) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T18:08Z
Check the source to verify that this is the current version before use.

6.3 The margins of this specification were marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Air Force - 69

Review activities:

Army - MD
Air Force - 45

User activity:

Navy - MC

Preparing activity:

Army - GL

Project No. 8135-0341

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:08Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:08Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

MIL-T-3508D - TAGS, LAUNDRY MARKING, AND TAPE, PAPER, DRY CLEANING MARKING

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202610-16T18:08Z
Check the source to verify that this is the current version before use.