INCH-POUND

MIL-DTL-17/190C
w/AMENDMENT 2
25 June 2024
SUPERSEDING
MIL-DTL-17/190C
w/AMENDMENT 1
26 June 2019

DETAIL SPECIFICATION SHEET

CABLE, RADIO FREQUENCY, FLEXIBLE, COAXIAL, 50 OHMS, M17/190-00001

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-17.




FIGURE 1. Configuration.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

TABLE I. Description.

Components	Construction details
Inner conductor	Seven strands of silver-coated copper wire, each strand .0296 inch diameter. Overall diameter: .0888 inch ± .0010.
Dielectric core	Type A-1: Solid polyethylene. Diameter: .285 inch ± .007.
Outer conductor	Double braid of AWG No. 34, silver-coated copper wire. Diameter: .355 inch maximum.
Inner	Coverage: 95.7% nominal Carriers: 24 Ends: 6 Picks/inch: 16.6 ± 10%
Outer	Coverage: 98.0% nominal Carriers: 24 Ends: 7 Picks/inch: 15.4 ± 10°
Barrier tape	A .001 inch thick polyester tape faced with a .002 inch thick layer of aluminum. The tape will be applied with a 50% lap, aluminum face toward the outer conductor. Diameter: .365 inch maximum.
Jacket	Type XIV, Cross-linked polyolefin. Diameter: .425 inch ± .007.

ENGINEERING INFORMATION

Continuous working voltage: 3,700 V rms, maximum.

Operating frequency: 11 GHz, maximum.

Velocity of propagation: 65.9 percent, nominal.

Power ratings: See figure 2.

Operating temperature range: -30°C to +85°C.

Inner conductor properties:

DC resistance (maximum at +20°C): 0.176 ohms per 100 feet.

Elongation: 25 percent, minimum.

Tensile strength: Not applicable.

REQUIREMENTS (See table II)

Dimensions, configuration, and descriptions: See figure 1 and table I.

Environmental and mechanical:

Visual and mechanical examination: Applicable.

Diameter: Applicable.

Out-of-roundness: Applicable.

Eccentricity: 10 percent maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

Adhesion of conductors: Inner conductor to core: 10 pounds, minimum; 50 pounds, maximum.

Electrical and mechanical:

Continuity: Applicable.

Spark test: 5,000 V rms, minimum.

Voltage withstanding: 10,000 V rms, minimum.

Insulation resistance: Not applicable.

Corona extinction voltage: 5,000 V rms, minimum.

Characteristic impedance: 50 ± 2 ohms.

RF transmission loss (attenuation): See figure 2.

Standing wave ratio (return loss): See figure 3.

Capacitance: 32.2 pF per foot, maximum.

Capacitance stability:	Not applicable.
Capacitance unbalance:	Not applicable.
Transmission unbalance:	Not applicable.
Inductance:	Not applicable
Mechanically induced noise voltage:	Not applicable.
Time delay:	Not applicable.

Aging stability: +98°C ± 2°C.

Stress crack resistance:	Not applicable.
Outer conductor integrity:	Not applicable.

Cold bend: -30°C ± 2°C.

Dimensional stability: +85°C ± 2°C.

Inner conductor from core:	.062 inch, maximum.
Inner conductor from jacket:	.125 inch, maximum.

Contamination:	Not applicable.
Bendability:	Not applicable.
Flammability:	Not applicable.

Flame propagation: Applicable.

Acid gas generation: 2.0 percent, maximum.

Halogen content: 0.2 percent, maximum.

Immersion test:

Tensile strength, percent of unaged minimum: 50

Elongation, percent of unaged minimum: 50

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

Smoke index: 25 maximum.

Toxicity index: 5 maximum.

Durometer hardness: (Type A) 80 minimum.

Weathering: Applicable.

Abrasion resistance: 75 cycles minimum (jacket only).

Tear strength: 35 pounds per inch minimum.

Heat distortion: 30 percent maximum distortion.

Physical tests on unaged jacket:

Tensile strength: 1,300 psi, minimum.

Elongation, 160 percent, minimum.

Physical tests on aged jacket:

Air oven:

Tensile strength, percent minimum: 60

Elongation, percent minimum: 60

Hot oil immersion:

Tensile strength, percent minimum: 50

Elongation, percent minimum: 50

Tensile strength and elongation: 1,300 psi, 160 percent minimum.

Weight: 15.4 pounds per 100 feet maximum.


Marking: Applicable.

Marking Durability: 125 cycles (250 strokes), 1 pound.

Workmanship: Applicable.

Part or Identifying Number (PIN): M17/190-00001.


Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.



Attenuation	
MHz	dB
50	1.7
400	6.8
3000	28
11000	60

FIGURE 2. Power rating and attenuation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.



Tabulated values are for reference only.
The values on the graph represent the Requirement.

Structural Return Loss	
GHz	dB
1	23
1	20
3	19
5	18
11	17

FIGURE 3. Structural return loss.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification and Group A, B, and C Table.

Group	Qualification inspection	Requirement paragraph	Test paragraph	Qual- # of Specimens	Conf - # of Specimens	Conformance inspection
I	In-process inspection:		4.5	Entire sample		
	Continuity	3.7.1	4.8.2	Entire sample		
	Spark test	3.7.2	4.8.3	Entire sample		
	Voltage withstanding	3.7.3	4.8.4	Entire sample		
	Insulation resistance	N/A				
	Visual and mechanical inspection	3.6	4.8.1	Entire sample	Per Table VIII	A
	Diameter measurements.	3.6.1	4.8.1.1	Entire sample	Per Table VIII	A
	Out-of-roundness	3.6.2	4.8.1.2	Entire sample	Per Table VIII	A
	Eccentricity of inner conductor	3.6.3	4.8.1.3	2	Per Table VIII	A
	Adhesion of conductors	3.6.4	4.8.1.4	4	Per Table VIII	A
	Marking	3.8	4.8.1	Entire sample	Per Table VIII	A
	Marking Durability	3.8.2	4.8.39	3	Per Table VIII	A
	Workmanship	3.10	4.8.1	Entire sample	Per Table VIII	A
II	Corona extinction voltage	3.7.5	4.8.6	1	Per Table VIII	B
	Characteristic impedance	3.7.6	4.8.7	1	Per Table VIII	A
	RF transmission loss (attenuation)	3.7.7	4.8.8	2	Per Table VIII	A
	Standing wave ratio (return loss)	3.7.8	4.8.9	2	Per Table VIII	A
	Capacitance	3.7.9	4.8.10	1	Per Table VIII	B
	Capacitance stability	N/A				
	Capacitance unbalance	N/A				
	Transmission unbalance	N/A				
	Inductance	N/A				

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification and Group A, B, and C Table - Continued.

Group	Qualification inspection	Requirement paragraph	Test paragraph	Qual- # of Specimens	Conf - # of Specimens	Conformance inspection
II	Mechanically induced noise voltage	N/A				
	Time delay	N/A				
	Aging stability	3.7.15	4.8.16	4	Per Table VIII	C
	Stress crack resistance	N/A				
	Outer conductor integrity	N/A				
	Cold bend	3.7.18	4.8.19	3	Per Table VIII	B
	Dimensional stability	3.7.19	4.8.20	1	Per Table VIII	C
	Contamination	N/A				
	Bendability	N/A				
	Flammability	N/A				
	Flame propagation	3.7.23	4.8.25	1		
	Acid gas generation	3.7.24	4.8.26	1		
	Halogen content	3.7.25	4.8.27	1		
	Immersion tests	3.7.26	4.8.28	1		
	Smoke index	3.7.27	4.8.29	1		
	Toxicity Index	3.7.28	4.8.30	1		
	Durometer hardness	3.7.29	4.8.31	1		
	Weathering	3.7.30	4.8.32	1		
	Abrasion resistance	3.7.31	4.8.33	5		
	Tear strength	3.7.32	4.8.34	6	Per Table VIII	B
	Heat distortion	3.7.33	4.8.35	1	Per Table VIII	C
	Physicals (aged)	3.7.34	4.8.36	1	Per Table VIII	C
	Tensile strength and elongation	3.7.35	4.8.37	1	Per Table VIII	C
	Weight	3.9	4.8.24	1	Per Table VIII	B

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

Amendment notations: The margins of this specification are marked with vertical lines to indicate where modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Referenced documents. This document references MIL-DTL-17.

CONCLUDING MATERIAL

Custodians:
Army – CR
Navy – EC
Air Force – 85
DLA - CC

Preparing activity:
DLA-CC

Review activities:
Army – AR, AT, CR4
Navy – AS, MC, OS
Air Force – 19

(Project 6145-2024-015)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.