INCH-POUND

MIL-DTL-17/191B
w/AMENDMENT 3
24 September 2025
SUPERSEDING
MIL-DTL-17/191B
w/AMENDMENT 2
3 April 2020

DETAIL SPECIFICATION SHEET

CABLE, RADIO FREQUENCY, FLEXIBLE, COAXIAL, 75 OHMS, M17/191-00001

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-17.




FIGURE 1. General configuration.

TABLE I. Description.

Components	Construction details
Inner conductor	Seven strands of tinned copper wire at .0159 inch each. Overall diameter: .0477 inch ± .0020.
Dielectric core	Type A-1: Solid polyethylene. Diameter: .285 inch ± .007.
Outer conductor	Double braid of AWG No. 34, copper wire. Diameter: .355 inch maximum.
Inner braid	Coverage: 95.4% nominal Carriers: 24 Ends: 9 Picks/inch: 6.5 ± 10%
Outer braid	Coverage: 93.6% nominal Carriers: 24 Ends: 8 Picks/inch: 10.3 ± 10%

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

TABLE I. Description – Continued.

Components	Construction details
Barrier tape	A .001 inch thick polyester tape faced with a .002 inch thick layer of aluminum. The tape will be applied with a 50% lap, minimum. Aluminum face toward the outer conductor. Diameter: .365 inch, maximum.
Jacket	Cross-linked polyolefin. Diameter: .425 inch ± .007.

ENGINEERING INFORMATION:

Continuous working voltage: 3,700 V rms, maximum.

Operating frequency: 3 GHz, maximum.

Velocity of propagation: 65.9 percent, nominal.

Power ratings: See figure 2.

Operating temperature range: -30°C to +85°C.

Inner conductor properties:

DC resistance (maximum at 20°C): 0.66 ohm per 100 feet.

Elongation: 15 percent, minimum.

Engineering notes: This cable is useful in general purpose, medium low temperature applications. (See connector series “N” in accordance with MIL-PRF-39012.) These cables were redesigned to meet the vertical flame test.

REQUIREMENTS:

Dimensions, configuration, and descriptions: See figure 1 and table I.

Environmental and mechanical:

Visual and mechanical examination: Applicable.

Diameter: Applicable.

Out of roundness: Applicable.

Eccentricity: 10 percent maximum.

Adhesion of conductors:

Inner conductor to core: 7 pounds, minimum; 50 pounds, maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

Electrical and mechanical:

Continuity: Applicable.

Spark test: 5,000 V rms, +25, -0 percent.

Voltage withstanding: 10,000 V rms, minimum.

Insulation resistance: Not applicable.

Corona extinction voltage: 5,000 V rms, minimum.

Characteristic impedance: 75 ohms ± 3.

RF transmission loss (attenuation):

6.5 dB per 100 feet, maximum at .4 GHz.

26.5 dB per 100 feet, maximum at 3 GHz.

Standing wave ratio (return loss): Not applicable.

Capacitance: 22 pF per foot, maximum.

Capacitance stability:	Not applicable.
Capacitance unbalance:	Not applicable.
Transmission unbalance:	Not applicable.
Inductance:	Not applicable.
Mechanically induced noise:	Not applicable.
Time delay:	Not applicable.

Aging stability: +98° ± 2°C.

Stress crack resistance:	Not applicable.
Outer conductor integrity:	Not applicable.

Cold bend: -30° ± 2°C.

Dimensional stability: +85°C ± 2°C.

Inner conductor from core: .062 inch, maximum.

Inner conductor from jacket: .125 inch, maximum.

Contamination:	Not applicable.
Bendability:	Not applicable
Flammability:	Not applicable.

Flame propagation: Applicable.

Acid gas generation: 2.0 percent, maximum.

Halogen content: 0.2 percent, maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

Immersion test:

Tensile strength, percent of unaged minimum: 50.

Elongation, percent of unaged minimum: 50.

Smoke index: 25 maximum.

Toxicity index: 5 maximum.

Durometer hardness: (Type A) 80 minimum.

Weathering: Applicable.

Abrasion resistance: 75 cycles, minimum (jacket only).

Tear strength: 35 pounds per inch minimum.

Heat distortion: 30 percent maximum distortion.

Physical tests on unaged jacket:

Tensile strength: 1,300 psi. minimum.

Elongation: 160 percent minimum.

Physical tests on aged jacket:

Air oven:

Tensile strength, percent minimum: 60.

Elongation, percent minimum: 60.

Hot oil immersion:

Tensile strength, percent minimum: 50.

Elongation, percent minimum: 50.

Tensile strength and elongation: 1,300 psi, 160 percent minimum.

Weight: 13.9 pounds per 100 feet maximum.

Marking: Applicable.


Marking Durability: 125 cycles (250 strokes), 1 pound.

Workmanship: Applicable.

Qualification: Shall consist of the inspections specified in table II.

Part or Identifying Number (PIN): M17/191-00001.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.



Maximum power at 25ºC, sea level.

MHz	Watts
100	650
400	270
1000	150
2000	90
3000	70

FIGURE 2. Power rating.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification and Group A, B, and C Table.

Group	Qualification inspection	Requirement paragraph	Test paragraph	Qual- # of Specimens	Conf - # of Specimens	Conformance inspection
I	In-process inspection:		4.5 (MIL-DTL-17 Table III tests)	Entire sample		
	Continuity	3.7.1	4.8.2	Entire sample	Entire sample	In-process inspection
	Spark test	3.7.2	4.8.3	Entire sample	Entire sample	In-process inspection
	Voltage withstanding	3.7.3	4.8.4	Entire sample	Entire sample	In-process inspection
	Visual and mechanical inspection	3.6	4.8.1	Entire sample	Per Table VIII	A
	Diameter measurements.	3.6.1	4.8.1.1	Entire sample	Per Table VIII	A
	Out-of-roundness of jacket measurements	3.6.2	4.8.1.2	Entire sample	Entire sample	A
	Eccentricity of inner conductor	3.6.3	4.8.1.3	2	Per Table VIII	A
	Adhesion of conductors	3.6.4	4.8.1.4	4	Per Table VIII	A
	Physical dimensions	3.6	4.8.1	Entire sample	Per Table VIII	A
	Marking	3.6	4.8.1	Entire sample	Per Table VIII	A
	Marking Durability	3.8.2	4.8.39	3	Per Table VIII	A
	Workmanship	3.10	4.8.1	Entire sample	Per Table VIII	A
II	Characteristic impedance	3.7.6	4.8.7	1	Per Table VIII	A
	RF transmission loss (attenuation)	3.7.7	4.8.8	2	Per Table VIII	A
	Corona extinction voltage	3.7.5	4.8.6	1	Per Table VIII	B
	Capacitance	3.7.9	4.8.10	1	Per Table VIII	B
	Cold bend	3.7.18	4.8.19	3	Per Table VIII	B
	Weight	3.9	4.8.24	1	Per Table VIII	B
	Tear strength	3.7.32	4.8.34	6	Per Table VIII	B

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification and Group A, B, and C Table – Continued.

Group	Qualification inspection	Requirement paragraph	Test paragraph	Qual- # of Specimens	Conf - # of Specimens	Conformance inspection
II	Aging stability	3.7.15	4.8.16	4	Per Table VIII	C
	Dimensional stability	3.7.19	4.8.20	1	Per Table VIII	C
	Heat distortion	3.7.33	4.8.35	1	Per Table VIII	C
	Tensile strength and elongation	3.7.35	4.8.37	1	Per Table VIII	C
	Physicals (aged)	3.7.34	4.8.36	1	Per Table VIII	C
	Flame propagation	3.7.23	4.8.25	1	----------	----------
	Acid gas generation	3.7.24	4.8.26	1	----------	----------
	Halogen content	3.7.25	4.8.27	1	----------	----------
	Immersion	3.7.26	4.8.28	1	----------	----------
	Smoke index	3.7.27	4.8.29	1	----------	----------
	Toxicity index	3.7.28	4.8.30	1	----------	----------
	Durometer hardness	3.7.29	4.8.31	1	----------	----------
	Weathering	3.7.30	4.8.32	1	----------	----------
	Abrasion resistance	3.7.31	4.8.33	5	----------	----------

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.

Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Referenced documents. In addition to MIL-DTL-17, this document references the following:

MIL-PRF-39012

CONCLUDING MATERIAL

Custodians:
Army – CR
Navy – EC
Air Force – 85
DLA - CC

Preparing activity:
DLA - CC

(Project 6145-2025-017)

Review activities:
Army – AR, AT, CR4
Navy – AS, MC, OS, SH
Air Force – 19, 71

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:28Z
Check the source to verify that this is the current version before use.