INCH-POUND

MIL-DTL-17/194C
w/AMENDMENT 1
22 March 2017
SUPERSEDING
MIL-DTL-17/194C
12 June 2014

DETAIL SPECIFICATION SHEET

CABLE, RADIO FREQUENCY, FLEXIBLE, COAXIAL, 50 OHMS, M17/194-00001

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-17.




FIGURE 1. Configuration.

TABLE I. Description.

Components	Construction details
Inner conductor	Solid silver-coated copper wire. Diameter: .035 inch ± .001.
Dielectric core	Type A-1: Solid polyethylene. Diameter: .116 inch ± .004.
Outer conductor	Double braid of AWG No. 36, silver-coated copper wire. Diameter: .170 inch, maximum.
Inner braid	Coverage: 95.0% nominal Carriers: 16 Ends: 7 Picks/inch: 11.5 ± 10%
Outer braid	Coverage: 94.2% nominal Carriers: 16 Ends: 7 Picks/inch: 15.0 ± 10%

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:29Z
Check the source to verify that this is the current version before use.

TABLE I. Description – Continued.

Components	Construction details
Barrier tape	A .001 inch thick polyester tape faced with a .002 inch thick layer of aluminum. The tape will be applied with a 50% lap, aluminum face toward the outer conductor. Diameter: .180 inch maximum.
Jacket	Cross-linked polyolefin. Diameter: .212 inch ± .004. Jacket thickness: .014 inch minimum.

REQUIREMENTS:

Continuous working voltage: 1,400 V rms, maximum.

Operating frequency: 12.4 GHz, maximum.

Velocity of propagation: 65.9 percent, nominal.

Power ratings: See figure 2.

Operating temperature range: -30°C to +85°C.

Inner conductor properties:

DC resistance (maximum at +20°C): 0.897 ohm per 100 feet.

Elongation: 25 percent, minimum.

Dimensions, configuration, and descriptions: See figure 1 and table I.

Environmental and mechanical:

Visual and mechanical examination: Applicable.

Eccentricity: 10 percent maximum.

Adhesion of conductors:

Inner conductor to core: 2 pounds, minimum; 20 pounds, maximum.

Aging stability: +98°C ± 2°C.

Cold bend: -30°C ± 2°C.

Dimensional stability: +85°C ± 2°C.

Inner conductor from core: .062 inch, maximum.

Inner conductor from jacket: .125 inch, maximum.

Contamination: Not applicable.

Flame propagation: Applicable.

Acid gas generation: 2.0 percent, maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:29Z
Check the source to verify that this is the current version before use.

Halogen content: 0.2 percent, maximum.

Immersion test:

Tensile strength, percent of unaged minimum: 50

Elongation, percent of unaged minimum: 50

Smoke index: 25 maximum.

Toxicity index: 5 maximum.

Durometer hardness: (Type A) 80 minimum.

Weathering: Applicable.

Abrasion resistance: 75 cycles minimum (jacket only).

Tear strength: 35 pounds per inch minimum.

Heat distortion: 30 percent maximum distortion.

Physical tests on unaged jacket:

Tensile strength: 1,300 psi, minimum.

Elongation, 160 percent, minimum.

Physical tests on aged jacket:

Air oven:

Tensile strength, percent minimum: 60

Elongation, percent minimum: 60

Hot oil immersion:

Tensile strength, percent minimum: 50

Elongation, percent minimum: 50

Tensile strength and elongation: 1,300 psi, 160 percent minimum.

Weight: 4 pounds per 100 feet, maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:29Z
Check the source to verify that this is the current version before use.





FIGURE 2. Power rating and attenuation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:29Z
Check the source to verify that this is the current version before use.



* At 12,400

FREQUENCY IN MHz

SWR	REFLECTION COEFFICIENT	RETURN LOSS dB	SWR	REFLECTION COEFFICIENT	RETURN LOSS dB
17.3910	.8913	1	1.3767	.1585	16
8.7242	.7943	2	1.3290	.1413	17
5.8480	.7079	3	1.2880	.1259	18
4.4194	.6310	4	1.2528	.1122	19
3.5698	.5623	5	1.2222	.1000	20
3.0095	.5012	6	1.1957	.0891	21
2.6146	.4467	7	1.1726	.0794	22
2.3229	.3981	8	1.1524	.0708	23
2.0999	.3548	9	1.1347	.0631	24
1.9250	.3162	10	1.1192	.0562	25
1.7849	.2818	11	1.1055	.0501	26
1.6709	.2512	12	1.0935	.0447	27
1.5769	.2239	13	1.0829	.0398	28
1.4985	.1995	14	1.0736	.0355	29
1.4326	.1778	15	1.0653	.0316	30

FIGURE 3. Structural return loss.Electrical:

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:29Z
Check the source to verify that this is the current version before use.

Spark test: 3,000 V rms, minimum.

Voltage withstanding: 5,000 V rms, minimum.

Corona extinction voltage: 1,900 V rms, minimum.

Characteristic impedance: 50 ± 2 ohms.

Attenuation: See figure 2.

Structural return loss: See figure 3.

Capacitance: 32.2 pF per foot, maximum.

Part or Identifying Number (PIN): M17/194-00001.

Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Referenced documents. This document references MIL-DTL-17.

CONCLUDING MATERIAL

Custodians:
Army – CR
Navy – EC
Air Force – 85
DLA - CC

Preparing activity:
DLA-CC

Review activities:
Army – AR, AT, CR4, MI
Navy – AS, MC, OS, SH
Air Force – 19, 99

(Project 6145-2017-007)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:29Z
Check the source to verify that this is the current version before use.