INCH-POUND
MIL-DTL-44031G
25-AUG-2022
SUPERSEDING
MIL-DTL-44031F
28 July 2017

DETAIL SPECIFICATION

CLOTH, CAMOUFLAGE PATTERN: COTTON AND NYLON

This specification is approved for use by all Departments and Agencies of the Department of Defense (DoD).

1. SCOPE

1.1 Scope. This specification covers the following classes as specified.

1.2 Classification. The cloth is furnished in the following classes as specified.

1.2.1 Classes.

Class 1 - Camouflage Printed (Woodland Camouflage Print)
Class 2 - Camouflage Printed and Quarpel Treated (Woodland Camouflage Print)
Class 3 - Universal Camouflage Print (UCP), Static Dissipative Fiber
Class 4 - Universal Camouflage Print (UCP), Water Repellent Treated
Class 5 - Woodland Camouflage Print, Static Dissipative Fiber
Class 6 - Universal Camouflage Print (UCP)
Class 7 - Operation Enduring Freedom Camouflage Pattern (OEF-CP)
Class 8 - Operation Enduring Freedom Camouflage Pattern (OEF-CP), Water Repellent Treated
Class 9 - Operational Camouflage Pattern (OCP)
Class 10 - Operational Camouflage Pattern (OCP), Water Repellent Treated
Class 11 - Operational Camouflage Pattern (OCP) Static Dissipative
Class 12 - Operational Camouflage Pattern (OCP) –Six (6) color

Comments, suggestions, or questions regarding this document should be addressed to: Attn: DLA Troop Support, Clothing & Textiles, John McCarrick (john.mccarrick@dla.mil). Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 8305

DISTRIBUTION STTATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

COMMERCIAL ITEM DESCRIPTIONS

A-A-50199	-	Thread, Polyester Core, Cotton or Polyester-Covered

(Copies of these documents are available online at https://quicksearch.dla.mil.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation or contract.

DRAWINGS

U.S. ARMY NATICK SOLDIER RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

2-1-1516	-	Woodland Camouflage Pattern
2-1-2519	-	Universal Camouflage Pattern
2-1-2592	-	Operational Camouflage Pattern (OCP)
2-1-2594	-	Operational Camouflage Pattern (OCP-Six (6) - Color)

(Copies of drawings are available from the U.S. Army Natick Soldier Research Development and Engineering Center, Natick Soldier Center, ATTN: RDNS-SEW-EWC, 10 General Greene Avenue. Natick, MA 01760.)

ENVIRONMENTAL PROTECTION AGENCY

Federal Insecticide, Fungicide and Rodenticide Act (FIFRA)

(40 CFR Part 162) State Registration of Pesticide Products

(Copies of this document are available online at https://www.epa.gov/pesticides.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

FEDERAL ACQUISITION REGULATIONS (FAR)

52.209-4	-	First Article Approval – Government Testing

(Copies are available online at https://acquisition.gov/far/index.html.)

FEDERAL TRADE COMMISSION

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies of this document available online at https://www.ftc.gov.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

AATCC Evaluation Procedure 1	-	Gray Scale for Color Change
AATCC Evaluation Procedure 2	-	Gray Scale for Staining
AATCC Evaluation Procedure 8	-	AATCC 9-Step Chromatic Transference Scale
AATCC Evaluation Procedure 9	-	Visual Assessment of Color Difference of Textiles
AATCC Test Method 8	-	Colorfastness to Crocking: AATCC Crockmeter
Method AATCC Test Method 15	-	Colorfastness to Perspiration
AATCC Test Method 16.2	-	Colorfastness to Light: Carbon-Arc
AATCC Test Method 16.3	-	Colorfastness to Light: Xenon-Arc
AATCC Test Method 20	-	Fiber Analysis: Qualitative
AATCC Test Method 20A	-	Fiber Analysis: Quantitative
AATCC Test Method 22	-	Water Repellency – Spray Test
AATCC Test Method 61	-	Colorfastness to Laundering: Accelerated
AATCC Test Method 70	-	Water Repellency: Tumble jar Dynamic Absorption Test

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

AATCC Test Method 81	-	pH of the Water-Extract from Wet Processed Textiles
AATCC Test Method 96	-	Dimensional Changes in Commercial Laundering of Woven and Knitted Fabrics Except Wool
AATCC Test Method 118	-	Oil Repellency: Hydrocarbon Resistance Test
AATCC Test Method 127	-	Water Resistance: Hydrostatic Pressure Test

(Copies of these documents are available online at https://www.aatcc.org.)

AMERICAN SOCIETY FOR QUALITY (ASQ)

ANSI/ASQ Z1.4	-	Sampling Procedures and Tables for Inspection by Attributes

(Copies are available online at https://www.asq.org.)

ASTM INTERNATIONAL

ASTM D276	-	Standard Test Methods for Identification of Fibers in Textiles
ASTM D737	-	Standard Test Method for Air Permeability of Textile Fabrics
ASTM D1424	-	Standard Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf) Apparatus
ASTM D1683/D1683M	-	Standard Test Method for Failure in Sewn Seams of Woven Fabrics
ASTM D3775	-	Standard Test Method for Warp (End) and Filling (Pick) Count of Woven Fabrics
ASTM D3776/D3776M	-	Standard Test Method for Mass per Unit Area (Weight) of Fabric
ASTM D5034	-	Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)
ASTM D3990	-	Standard Terminology Relating To Fabric Defects

(Copies of these documents are available on line at https://www.astm.org.)

OTHER PUBLICATIONS

Repeat Insult Patch Test - Modified Draize Procedure –

Principles and Methods of Toxicology, A Wallace Hayes (editor).

(Copies are available online at https://www.crcpress.com.)

Fabric Defect Replica Scales

(Fabric Defect Replica Scales are available online at https://www.sdlatlas.com.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.2.

3.2 Standard sample. The finished cloth shall match the standard sample for shade, appearance, colorfastness and spectral reflectance and shall, unless otherwise indicated, be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 Recycled, recovered, environmentally preferable, or biobased materials. Recycled, recovered, environmentally preferable, or biobased materials should be used to the maximum extent possible, provided at the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

3.4 Materials.

3.4.1 Cotton. The cotton shall be carded.

3.4.2 Nylon. The nylon shall be first quality, high tenacity, semi-dull staple having a nominal cut length of 1-½-inches and a round cross section with a nominal denier of 2.25 to 2.50. No form of nylon waste shall be used, such as undrawn fiber, mixtures of deniers, lusters or cross sections, and waste from any stage of fiber production: whether drawn, un-drawn, or mixed or garneted fiber. Testing shall be as specified in 4.4.3.

3.4.3 Static dissipative fiber (Classes 3, 5 and 11). The fiber shall have carbon core and nylon sheath and shall be 3 to 3.8 nominal denier per filament and a cut length of 1-½ to 2-inches in staple length (see 6.8).

3.4.4 Yarns. The warp and filling yarn shall be singles made from a blend of 50 (± 5) percent nylon and the remaining percentage cotton based on the dry weight of the desized cloth when tested as specified in 4.4.3. The yarn for the Class 3, Class 5 and Class 11 shall contain 2 percent static dissipative fiber.

3.5 Color.

3.5.1 Classes 1, 2 and 5 Woodland Camouflage. The cloth shall be dyed to a ground shade either matching or approximating Light Green 354 and then shall be overprinted with the camouflage pattern. When the ground shade is dyed to match Light Green 354, the remaining (3) colors shall be printed as appropriate for the Dark Green 355, Brown 356, and Black 357 areas of the pattern. When the ground shade is not dyed to approximate Light Green 354, all four (4) colors of the camouflage pattern shall be printed to match all four (4) colors of the pattern.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

3.5.2 Classes 3, 4 and 6 Universal Camouflage Pattern (UCP). The cloths shall be dyed to a ground shade either matching or approximating Desert Sand 500 and then overprinted with the camouflage pattern. When the ground shade is dyed to match Desert Sand 500, the remaining two (2) colors shall be printed as appropriate, for the Urban Gray 501 and Foliage Green 502 areas of the pattern. When the ground shade is not dyed to approximate Desert Sand 500, all three (3) colors of the camouflage pattern shall be printed to match all three (3) colors of the pattern.

3.5.3 Classes 7 and 8, Operation Enduring Freedom Camouflage Pattern (OEF-CP). The cloth(s) shall be dyed to a ground shade either matching or approximating Cream 524 and then shall be overprinted with the camouflage pattern. When the ground shade is dyed to match Cream 524, the remaining colors shall be as appropriate for the Tan 525, Pale Green 526, Olive 527, Dark Green 528, Brown 529 and Dark Brown 530 areas of the pattern. When the ground shade is not dyed to approximate Cream 524 all seven (7) colors of the camouflage pattern shall be printed to match all seven (7) colors.

3.5.4 Classes 9, 10 and 11, Operational Camouflage Pattern (OCP). The cloth(s) shall be dyed to a ground shade either matching or approximating Dark Cream 559 and then shall be Overprinted with the camouflage pattern. When the ground shade is dyed to match Dark Cream 559, the six (6) remaining colors shall be printed as appropriate, for the Tan 525, Light Sage 560, Olive 527, Dark Green 528, Brown 529 and Bark Brown 561 areas of the pattern. When the ground shade is not dyed to approximate Dark Cream 559 all seven (7) colors of the camouflage pattern shall be printed to match all seven (7) colors of the pattern.

3.5.5 Class 12, Operational Camouflage Pattern (OCP) – six (6) color. The cloth(s) shall be dyed to a ground shade either matching or approximating Dark Cream 559 and then shall be overprinted with the camouflage pattern. When the ground shade is dyed to match Dark Cream 559, the five (5) remaining colors shall be printed as appropriate, for the Tan 525, Olive 527, Dark Green 528, Brown 529 and Bark Brown 561 areas of the pattern. When the ground shade is not dyed to approximate Dark Cream 559 all six (6) colors of the camouflage pattern shall be printed to match all six (6) colors of the pattern.

3.5.6 Labile sulfur. Dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid shall not be used.

3.5.7 Visual shade matching (all Classes). The color and appearance of the camouflage printed cloth shall match the standard sample when tested as specified in 4.4.3.

3.5.8 Colorfastness (all Classes). The finished cloth shall conform to the colorfastness requirements listed below in Tables I, I.A and I.B when tested as specified in 4.4.3 and 4.5.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

TABLE I
Colorfastness requirements (Classes 1 - 6).

Colors Evaluation	Laundering (3 cycles) Color Change and Staining (min.)	Light (40 AFU or 170kJ/(m^{2}nm) @ 420 nm) (min.) 1/	Perspiration (acid & alkaline) Color Change and Staining (min.)	Crocking (Dry and Wet) (min.)
Black 357	3	3-4	3-4	1
Dk. Green 355, Brown 356, Lt. Green 354, Desert Sand 500, Urban Gray 501, Foliage Green 502	3-4	3	3-4	3.5

1/ AFU: AATCC Fading Units

TABLE II
Colorfastness requirements (Classes 7 and 8).

Colors Evaluation	Laundering (3 cycles) Color Change and Staining (min.)	Light (40 AFU or 170kJ/(m^{2}nm) @ 420 nm) (min.) 1/	Perspiration (acid & alkaline) Color Change and Staining (min.)	Crocking (Dry and Wet) (min.)
All colors	3-4	----	3-4	3.5
Dk. Green 528, Brown 529, Dark Brown 530	----	3-4	----	----
Cream 524, Tan 525, Pale Green 526, Olive 527	----	3	----	----

1/ AFU: AATCC Fading Units

TABLE III
Colorfastness requirements (Classes 9, 10, 11 and 12).

Colors Evaluation	Laundering (3 cycles)	Light	Perspiration (acid & alkaline)	Crocking

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

	Color Change and Staining (min.)	(40 AFU or 170kJ/(m^{2}nm) @ 420 nm) (min.) 1/	Color Change and Staining (min.)	(Dry and Wet) (min.)
All colors	3-4	----	3-4	3.5
Dk. Green 528, Brown 529, Bark Brown 561	----	3-4	----	----
Dark Cream 559, Tan 525, Light Sage 560, Olive 527 2/	----	3	----	----

1/ AFU: AATCC Fading Units
2/ Class 12 the Light Sage 560 will not apply

3.5.9 Pattern execution. The pattern on the printed finished cloth(s) shall reproduce the standard sample in respect to design, colors and registration of the respective areas. The pattern repeat of Class 1, 2 and 5 shall be 27.25 (+1.25, -2.50) inches in the warp direction. The pattern repeat of Class 3, 4 and 6 shall be 36.00 (+1.25, -2.50) inches in the warp direction. The pattern repeat of Class 7, 8, 9, 10, 11, and 12 shall be 25.255 (+1.25, -2.50) inches in the warp direction. The various areas of the pattern shall be properly registered in relation to each other and shall present definite sharp demarcations with a minimum of feathering or spew. Each pattern area shall show solid coverage; skitteriness exceeding that shown on the standard sample in any of the printed areas will not be acceptable. When the standard sample is not referenced for pattern execution, a pattern drawing will be provided; Class 1, 2 and 5 shall match Drawing 2-1-1516, Class 3, 4 and 6 shall match Drawing 2-1-2519, and Class 9, 10 and 11 shall match Drawing 2-1-2592 (see 2.2.2, 6.2, 6.4 and 6.7). Class 12 shall match Drawing 2-1-2594.

3.5.9.1 Pattern width (filling direction for OCP, Classes 9, 10, 11 and 12). The maximum width for the camouflage printed area for Classes 9, 10, 11 and 12 shall be 68-inches in the filling direction.

3.5.10 Spectral reflectance.

3.5.10.1 Spectral reflectance Classes 1, 2 and 5. The spectral reflectance values for each color in the Woodland Camouflage printed cloth shall conform to the requirements specified in Table II, when tested as specified in 4.4.3.

TABLE IV
Spectral reflectance requirements, Classes 1, 2 and 5.

Reflectance values (percent) - Woodland Camouflage						
Wavelength Nanometers (nm)	Black 357		Light Green 354		Dark Green 355 and Brown 356	
	Min.	Max.	Min.	Max.	Min.	Max.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

600	-	10	8	18	3	9
620	-	10	8	18	3	9
640	-	10	8	18	3	9
660	-	10	8	18	3	12
680	-	10	10	22	3	14
700	-	10	18	33	5	18
720	-	10	22	45	7	20
740	-	10	30	55	12	28
760	-	10	35	65	18	36
780	-	10	40	75	26	44
800	-	10	45	80	34	52
820	-	10	50	86	42	60
840	-	10	55	88	50	68
860	-	10	60	90	56	74

3.5.10.2 Spectral reflectance Classes 3, 4 and 6. The spectral reflectance values for each color in the Universal Camouflage Pattern printed cloth shall conform to the requirements specified in Table III, when tested as specified in 4.4.3.

TABLE V
Spectral reflectance requirements, Classes 3, 4 and 6.

Reflectance values (percent) – Universal Camouflage Pattern (UCP)						
Wavelength Nanometers (nm)	**Desert Sand 500**		**Urban Gray 501**		**Foliage Green 502**	
	Min.	**Max.**	**Min.**	**Max.**	**Min.**	**Max.**
600	28	40	12	26	8	18
620	30	42	14	26	8	18
640	34	48	14	28	8	20
660	38	56	14	30	10	26
680	44	60	18	34	10	26
700	46	66	24	38	12	28
720	48	68	26	42	16	30
740	48	72	30	46	16	30
760	50	74	32	48	18	32
780	54	76	34	48	18	34
800	54	76	34	50	20	36
820	54	76	36	54	22	38
840	56	78	38	54	24	40
860	56	78	40	56	26	42

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

3.5.10.3 Spectral reflectance, Classes 7 and 8. The spectral reflectance values for each color in the Operation Enduring Freedom Camouflage Pattern (OEF-CP) cloth shall conform to the requirements specified in Table IIIA, when tested as specified in 4.4.3.

TABLE VI
Spectral reflectance requirements, Classes 7 and 8.

Reflectance values (percent) – Operation Enduring Freedom Camouflage Pattern (OEF-CP)						
Wavelength, Nanometers (nm)	**Cream 524 & Tan 525**		**Pale Green 526, Olive 527 and Brown 529**		**Dark Green 528 and Dark Brown 530**	
	Min.	**Max.**	**Min.**	**Max.**	**Min.**	**Max.**
600	22	44	12	30	3	11
620	24	45	12	30	3	12
640	24	45	12	32	4	13
660	25	45	12	32	4	14
680	28	45	14	34	4	17
700	28	48	14	36	6	23
720	30	52	16	39	6	23
740	32	55	18	41	10	25
760	36	56	20	43	14	30
780	38	57	22	45	18	35
800	40	57	22	45	21	40
820	44	58	24	46	24	42
840	46	59	26	47	26	43
860	48	60	28	48	28	45

3.5.10.4 Spectral reflectance, Classes 9, 10, 11 and 12. The spectral reflectance values for each color in the Operational Camouflage Pattern cloth shall conform to the requirements specified in Table III.B, when tested as specified in 4.4.3.

TABLE VII
Spectral reflectance requirements, Classes 9, 10, 11, and 12.

Reflectance values (percent) – Operational Camouflage Pattern (OCP)						
Wavelength, Nanometers (nm)	**Dark Cream 559 & Tan 525**		**Light Sage 560, Olive 527 and Brown 529** 1/		**Dark Green 528 and Bark Brown 561**	
	Min.	**Max.**	**Min.**	**Max.**	**Min.**	**Max.**
600	22	44	12	30	3	11
620	24	45	12	30	3	12
640	24	45	12	32	4	13

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

660	25	45	12	32	4	14
680	28	45	14	34	4	17
700	28	48	14	36	6	23
720	30	52	16	39	6	23
740	32	55	18	41	10	25
760	36	56	20	43	14	30
780	38	57	22	45	18	35
800	40	57	22	45	21	40
820	44	58	24	46	24	42
840	46	59	26	47	26	43
860	48	60	28	48	28	45

1/ Class 12 the Light Sage 560 will not apply

3.6 Physical requirements. The finished cloth shall conform to the requirements in Table IV when tested as specified in 4.4.3.

TABLE VIII
Physical requirements.

Characteristic	**Classes 1, 3, 5, 6 ,7, 9, 11, and 12**	**Classes 2, 4, 8 & 10**
Weight (oz./sq. yd.), min.	6.8	7.0
Construction, (yarns per inch), min. Warp Filling	 86 54	 86 54
Breaking strength (pounds), min. Warp Filling	 200 125	 190 115
Tearing strength (pounds), min. Warp Filling	 11 8	 10 7
Air permeability cu. ft./minute/sq. ft.), max.	25.0	10.0
Electrostatic decay (Class 3, 5 and 11 only) Initial and after five (5) launderings	 See 3.10	 See 3.10

3.6.1 Weave. The weave shall be a 2/1 left hand twill.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

3.6.2 Width. For Government procurements only, the width of the cloth shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of the selvage when fly-shuttle looms or shuttleless with tuck-in selvage are used. For all other shuttleless looms, the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe(s).

3.7 Finish. The cloth shall be dyed and printed with the warp effect side as the face. The cloth shall be, desized, scoured, dyed, and printed. The Class 2, 4, 8, and 10 cloths shall be given a water repellent treatment as specified in 3.7.1.

3.7.1 Water repellency (Classes 2, 4, 8, and 10). The cloth shall be given a fluorocarbon water repellent treatment meeting the requirements specified in Table V and 3.9. Testing shall be as specified in 4.4.3.

TABLE IX
Water repellency (Classes 2, 4, 8, and 10).

	Dynamic absorption (percent) (Max.) 1/	**Hydrostatic height (centimeters) (Min.)**	**Spray rating (Min.)**
Initial	20	18.0	100, 100, 90
After 15 launderings	20	18.0	----

1/ No individual specimen shall exceed the specified maximum.

3.8 pH. The pH value of the water extract of the finished cloth shall be not less than 5.0 and not greater than 8.5 when tested as specified in 4.4.3.

3.9 Liquid repellency (Classes 2, 4, 8 and 10). The treated finished Classes 2, 4, 8, and 10 cloth shall show no wetting by n-dodecane after 30 seconds and no wetting by tri-ethyl phosphate, di-methyl phosphonate, and bis (2ethyl hexyl) hydrogen phosphate after eight (8) hours when tested as specified in 4.4.3.

3.10 Electrostatic decay (Classes 3, 5, and 11). The finished Classes 3, 5, and 11 cloths when tested as specified in 4.4.3 shall dissipate 90 percent of the charge in less than or equal to ½ second. The average warp results and average filling results shall meet this requirement before and after five (5) launderings when tested as specified in 4.4.3.

3.11 Dimensional stability. The shrinkage or elongation both in the warp and in the filling of the finished cloth shall be not greater than 3.5 percent for the individual sample unit and not greater than 3.0 percent for the lot average when tested as specified in 4.4.3. The preshrinkage process used shall not be identified by name or trademark on the cloth, ticket, or package.

3.12 Seam efficiency. The finished cloth shall have a seam efficiency of no less than 80 percent when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

3.13 Toxicity. The finished cloth shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 4.4.3. Chemicals recognized by the Environmental Protection Agency (EPA) as human carcinogens shall not be used.

3.14 Length and put-up. For Government procurements only, unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put-up on a roll as specified (see 6.2).

3.15 Fiber identification. Each roll shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.16 Workmanship. The finished cloth shall conform to the quality of product established by this specification. The demerit points per 100 square yards when calculated as specified in Section 4 shall not exceed the applicable established maximum point values.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2).
b. Conformance inspection (see 4.3).

4.2 First article inspection. A first article, submitted in accordance with 3.1, shall be inspected, examined for appearance, color and finished defects listed in Table VII and tested for the characteristics as specified in Table VIII. Unless otherwise specified in the contract, the sample unit shall be one (1) continuous 5-yard length of full width, finished cloth (see 6.3).

4.3 Conformance inspection. In accordance with 4.1, the material shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this specification or applicable procurement documents. Conformance inspection shall include the examination of 4.4 and 4.5 through 4.6 (see 6.2).

4.3.1 Conformance inspection samples. Sampling for finished cloth testing shall be performed in accordance with Table VI. Unless otherwise specified in the contract, the sample unit shall be five (5) continuous yards full width of the finished cloth per roll of cloth.

TABLE X
Lot sample size.

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

4.4 Yard by yard examination. Each roll in the sample shall be examined yard-by-yard on the printed side only. When the total yardage in the roll does not exceed 100-yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100-yards, only 100-yards shall be examined. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards examined exceeds 20.0 points. The lot shall be unacceptable if the points per 100 square yards of two (2) or more individual rolls exceeds 30.0 points. If one (1) roll in the sample exceeds 30.0 points per 100 square yards, a second sample of 20 rolls shall be examined for individual roll quality only. The lot shall be unacceptable if one (1) or more rolls in the second sample exceed 30.0 points per 100 square yards. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{Total yards inspected}} = \text{Points per 100 square yards}$$

All defects as defined in ASTM D3990 that are clearly noticeable at normal inspection distance (3-feet) shall be scored and assigned demerit points as listed in 4.4.1

Except as follows:

a. Only coarse yarns that exceed twice the normal diameter shall be scored.
b. Mixed filling (shade bar shall be scored only when resulting from wrong ply, wrong twist in the yarn, or off shade yarn.
c. Only knots and slubs that exceed limits shown on Fabric Defect Scale (see 2.3) “F” for slubs and “D” for knots shall be scored.

The defects found shall be counted regardless of their proximity to each other, except where two (2) or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one (1) defect for each warpwise yard or fraction thereof in which it occurs. No linear yard (increments of 1-yard on the measuring device of the inspection machine) from any one (1) roll within the sample shall be penalized more than four (4) points.

4.4.1 Demerit points. Demerit points shall be assigned as follows:

For defects up to 3-inches in any dimension	-	one (1) point
For defects exceeding 3-inches, but not exceeding 6-inches in any dimension	-	two (2) points
For defects exceeding 6-inches, but not exceeding 9-inches in any dimension	-	three (3) points
For defects exceeding 9-inches in any dimension		four (4) points

All defects as specified in Table VII shall be scored four (4) points for each yard in which they occur:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

TABLE XI
Defects.

Defect Description
Any hole, cut, pinhole, tear, scratch or abrasion mark 1/
Edge ravels when pulled outward
Uneven weaving throughout
Pattern design not equal to the standard sample
Incorrect color in any part of the pattern
Pattern repeat not equal to the standard sample
Pattern repeat less than 24.75-inches or more than 28.50-inches in the warp direction (Classes 1, 2 and 5)
Pattern repeat less than 33.50-inches or more than 37.25-inches in the warp direction (Classes 3, 4 and 6)
Pattern repeat less than 22.755-inches or more than 26.505-inches in the warp direction (Classes 7, 8, 9, 10,11 and 12)
Pattern width more than 68-inches in the filling direction.(Classes 9, 10, 11 and 12)
Skitteriness (mottled, uneven color) of pattern exceeds that shown by the standard sample
Excessive feathering or spew (fuzziness at color boundaries) of pattern as compared to the standard sample
Excessive grinning (off register, gap where ground shade shows through) of pattern as compared to the standard sample
Excessive haloing or trapping (overlapping of colors) of pattern as compared to the standard sample
Overall application of water repellent not uniform (Classes 2, 4, 8 and 10)
Tackiness (sticky to touch) (Classes 2, 4, 8 and 10)
Design not printed on face side of cloth
Any spot, stain or streak more than 1 inch in combined directions. 2/
Any objectionable odor 3/
Width not as specified within a tolerance of ± ½-inch.
Broken or missing yarn. 2/
Any embedded foreign matter or uncleanness. 2/
Color not as specified
Slack or tight selvages 4/
Edges rolled folded, scalloped or corded, baggy, ridgy or wavy cloth.

1/ The same yardage shall be given a through –lighting inspection for pinholes and thinly coated areas.

2/ Clearly visible at normal inspection distance - (3 feet) by either direct viewing or through-lighting.

3/ Odors of chemicals commonly used in coating compounds shall not be considered objectionable.

4/ To determine the presence of unacceptable selvage conditions, the following procedure shall be observed: During the visual examination, the perch shall be stopped a minimum of three (3)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

times for each roll in the sample, the tension removed, and the finished cloth examined for the selvage conditions. A waviness in the selvage or significant ripples diagonally across the width of the fabric is an indication of slack or tight selvages.

4.4.1.1 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2-yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets.

4.4.2 Shade and appearance examination. The shade and appearance examination sampling procedure shall be followed as written below.

a. Sampling: a 12-inch by full width swatch (header) will be cut by the contractor from each piece or roll in the lot. The header will be cut in half to form Set A and Set B. The Government representative will select samples in accordance with the following:

b.

Lot size (pieces)	**pieces to be sampled**
1 to 5	each piece
6 to 25	5
26 to 90	10
91 to 160	16
over 160 pieces	1 of every 10 pieces

c. The swatches shall be identified and submitted to the DLA Troop Support Laboratory for shade evaluation. If one (1) or more of the shade swatches are found unacceptable, the entire lot shall be rejected. Any end items made from the component lot shall also be rejected. A lot that was rejected for shade shall, without cost to the Government, be screened and all defective pieces in the lot shall be removed before such a lot is resubmitted. Resubmitted lots shall again be subjected to the sampling and shade evaluation prescribed herein. This requirement does not negate the contractor's responsibility to perform shade evaluation prior to the submittal of a lot to the Government.

d. When Section 3 of the fabric specification contains a specific requirement for uniformity of shade, the swatches submitted in accordance with (a) above shall also be evaluated for uniformity of shade.

e. If the contractor reworks and resubmits pieces originally rejected for shade or finish, the contractor shall not combine the rejected pieces with normal production or with lots rejected for other causes. Such pieces shall be combined to form one resubmitted lot. Each piece shall retain its original piece number, suffixed with an "x". The lot number shall also be suffixed with an "x".

f. Shade sampling procedures are detailed further in DLA Troop Support Manual, Quality Requirements, DPSCM 4155.3, Part 1, which is incorporated by reference. The swatches shall be submitted to the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

Commander
DLA Testing Center
Naval Support Station Philadelphia
700 Robbins Ave (Building 5 D)
Philadelphia. Pa. 19111-5098

4.4.3 End item testing. The cloth shall be tested for the characteristics listed in Table VIII. The methods of testing as specified wherever applicable and as listed in Table VIII shall be followed. All test reports shall contain the individual values utilized in expressing the final results. The lot shall be unacceptable if one (1) or more sample units or the lot average for dimensional stability fail to meet any requirement specified.

TABLE XII
End item tests.

Characteristic	Requirement Reference	Test Method
Fiber Identification	3.4.1-3.4.3	AATCC-20 or ASTM D276[1/]
Fiber content %	3.4.4	AATCC-20A [2/]
Yarn Ply	3.4.4	Visual
Color	3.5 -3.5.5	Visual
Labile sulfur	3.5.6	4.5.1
Visual shade matching	3.5.7	AATCC Evaluation Procedure 9, Option A, [3/]
Colorfastness: Laundering (after three (3) cycles) Light (after 40 AFU. or 170kJ/(m^2nm) @ 420 nm) Perspiration (acid & alkaline) Crocking (dry and wet)	3.5.8 Tables I, I.A & I.B Tables I, I.A & I.B Tables I, I.A & I.B Tables I, I.A & I.B	(see 4.5.2) AATCC-61 Test 3A [4/,5/,6/] AATCC-16.2 or 16.3[5/,7/] AATCC-15[5/,6/] AATCC-8[5/,8/]
Pattern execution	3.5.9 - 3.5.9.1	Visual
Spectral reflectance: Classes 1, 2 and 5 Classes 3, 4 and 6 Classes 7 and 8 Classes 9, 10, 11 and 12	3.5.10 3.5.10.1, Table II 3.5.10.2, Table III 3.5.10.3, Table III.A 3.5.10.4, Table III.B	 4.5.3 4.5.3 4.5.3 4.5.3
Weight	3.6, Table IV	ASTM D3776/D3776M
Yarns per inch	3.6, Table IV	ASTM D3775
Breaking strength	3.6, Table IV	ASTM D5034
Tearing strength	3.6, Table IV	ASTM D1424
Air Permeability	3.6, Table IV	ASTM D737
Weave	3.6.1	Visual
Water repellent treatment [9/]		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

(Classes 2, 4 , 8 & 10)	3.7 - 3.7.1 & Table V	
Dynamic absorption		
Initial	Table V	AATCC-70
After 15 Launderings	Table V	AATCC-96[9/,10/,1/] and AATCC-70
Hydrostatic Pressure		
Initial	Table V	AATCC-127
After 15 Launderings	Table V	AATCC-96[9/,10/,1/] and AATCC-127
Spray rating:		
Initial	Table V	AATCC-22
pH	3.8	AATCC-81
Liquid repellency (Classes 2,4 & 8)		
Initial	3.9	AATCC-118
After 15 launderings	3.9	AATCC-96[9/,10/,11/] and AATCC-118 & 4.5.5
Electrostatic decay (Classes 3, 5 & 11)		
Initial	3.10	See 4.5.4
After five (5) launderings	3.10	AATCC-96, [9/] & 4.5.4[12/]
Dimensional stability		
After one (1) cycle	3.11	AATCC-96, [9/]
Seam efficiency	3.12	ASTM 1683/D1683M[13/]
Toxicity	3.13	See 4.5.6

1/ In case of dispute, the ASTM method prevails.
2/ The cotton content shall be calculated as follows: Cotton content, percent = R/S x 100 R = Weight of residual fibers S = Weight of dry desized specimen
3/ The color and appearance of the camouflage printed cloth shall match the standard sample when viewed using the AATCC Evaluation Procedure 9, Option A, with sources simulating artificial daylight D75 illuminant with a color temperature of 7500K (± 200) illumination of 100 (±20) foot candles, and shall be a good match to the standard sample under incandescent A illuminant with a color temperature of 2856K (± 200).
4/ Only the stain on the nylon and cotton fibers of the color transfer cloth shall be evaluated.
5/ When testing for colorfastness properties, each color shall be evaluated, whenever possible, separately and reported as such. In cases where the print pattern does not allow for the evaluation of each color separately, the test results should indicated which colors were evaluated together.
6/ Rated using the AATCC Evaluation Procedure 1, Gray Scale for Color Change and AATCC Evaluation Procedure 2, Gray Scale for Staining.
7/ Rated using the AATCC Evaluation Procedure 1, Gray Scale for Color Change
8/ Rated using the AATCC Evaluation Procedure 8, AATCC 9-Step Chromatic Transference Scale
9/ AATCC 96 with conditions; Washing Temperature 60 (±3)°C and Tumble Dry

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

10/ Specimens shall be subjected to 15 complete cycles (wash and dry) prior to determinations of dynamic absorption and resistance to organic liquid after laundering. The last two (2) wash cycles shall be performed without the addition of detergent.
11/ Immediately after tumble drying the specimens shall be laid out, without tension or pressing, on a flat surface in standard atmosphere until moisture equilibrium is reached.
12/ The last wash cycle shall be performed without the use of detergent. Specimens shall be dried after each laundering.
13/ The needle shall measure 0.040 (± 0.001) inch across the blade at the eye. The thread for all tapes shall be cotton or polyester covered in accordance with A-A-50199 Tex size 36-45, for the needle and top thread and Tex size 31-35 for the looper.

4.5 Methods of inspection.

4.5.1 Presence of labile sulfur test. In the determination of presence of labile sulfur in textile materials with lead acetate, two (2) 1.50 (± 0.01) gram samples from each material submitted for evaluation shall be tested. Each of the two (2) samples shall be cut into very small pieces and placed into separate test tubes. The samples shall be submersed in a stannous chloride solution that contains 100 grams of stannous chloride crystals ACS in 100 milliliters of hydrochloric acid ACS (35 percent concentration) and 50 milliliters of distilled water. A filter paper wet out with a 5.0 percent lead acetate solution shall be placed over top of the test tube. The lead acetate solution contains 5.0 grams of lead acetate CP reagent grade and enough distilled water to make up a 100 milliliter solution; if the solution is not clear, add a few drops (one at a time) of glacial acetic acid until the solution is clear. The test tube containing the textile sample, stannous chloride and wet filter paper shall be heated over a low flame until the solution is boiling. The solution should not be heated for more than 15 seconds. A brown to black stain on the filter paper should be evaluated as follows:

Free - The filter paper shows no discoloration or staining of any kind.
Slight - The filter paper shows a light tan to light brown discoloration stain.
Moderate - The filter paper shows a dark brown discoloration stain.
Severe - The filter paper shows a black color stain.

4.5.2 Colorfastness evaluation testing. When testing for colorfastness properties, each color shall be evaluated, whenever possible, separately and reported as such. In cases where the print pattern does not allow for the evaluation of each color separately, the test results should indicated which colors were evaluated together. All color evaluations to include visual, and colorfastness for Classes 7 and 8 shall be performed on the solid color area and not the tonal area.

4.5.3 Spectral reflectance test. Spectral reflectance data shall be obtained from 600 to 860 nanometers (nm) at 20 nm intervals for all classes on a spectrophotometer relative to the polytetrafluoroethylene (PTFE) family of compounds, the preferred white standard. Other white reference materials may be used provided they are calibrated to absolute white, e.g. magnesium oxide or vitrolite tiles. The spectral band width shall be less than 20 nm at 860 nm. Reflectance measurements shall be made by either the monochromatic or polychromatic mode of operation. When the polychromatic mode of operation is used, the spectrophotometer shall operate with the

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

specimen diffusely illuminated with the full emission of a continuous source that simulates either CIE Source A or CIE Source D65. Measurements shall be taken on a minimum of two (2) different areas and the data averaged. The measured areas should be at least 6-inches away from the selvage. Specimens shall be oriented in different directions during testing. When possible, the specimens tested shall not contain the same warp or filling yarns when presented to the sample port. The specimen shall be measured as a single layer backed with three (3) layers of the same fabric and shade. The specimen shall be viewed at an angle no greater than 10° from normal, with the specular component included Photometric accuracy of the spectrophotometer shall be within 1 percent and wavelength accuracy within 2 nm. The diameter for standard aperture size used in the color measurement device shall be 1.0 to 1.25 inches for Classes 1, 2 and 5 unless otherwise specified and. 0.3725 inches or larger for Classes 3, 4, 6, 7, 8, 9, 10, 11 and 12. (NOTE: Always use the largest aperture possible). Any color having spectral reflectance values falling outside the limits at four (4) or more of the wavelengths specified shall be considered a test failure. The spectral reflectance for Classes 7, 8, 9, 10, 11 and 12, shall be performed on the solid color area and not the tonal area.

4.5.4 Electrostatic decay test (Class 3, 5 and 11 only). The specimen shall be tested according to the method specified in 4.5.4.1 through 4.5.4.3 initially and after five (5) laundering cycles according to conditions in Table VIII.

4.5.4.1 Specimen preparation. The specimen shall be a 3-inch by 6-inch rectangular piece of material. The warp or filling yarns shall run parallel to the 6-inch length of the specimen. The direction of test (warp or filling) shall be along the length of the specimen and each specimen shall be labeled accordingly in one (1) corner. Test specimens shall be cut so that no two (2) contain the same set of warp and filling yarns. Six (6) specimens, three (3) warp and three (3) filling, shall be tested, face and back sides inclusive.

4.5.4.2 Testing equipment. The test equipment shall consist of a meter for measuring relative humidity (RH) and temperature, a faraday cage, a source capable of outputting 5000 volts, and voltage meters to display the applied voltage and the voltage detected by the sensor. The faraday cage shall contain two (2) parallel electrodes on which specimens may be mounted and charged, and a sensor that will detect voltage on the specimen surface. The faraday cage and specimens to be tested shall be pre-conditioned at 10 (±2) percent relative humidity overnight, and conditioned at 20 (± 2) percent relative humidity for a minimum of 24 hours at approximately 75 (± 5)°F. The specimens shall be tested at 20 (± 2) percent relative humidity and 75° (± 5)°F. A bench top size chamber may be used as an option to achieve the conditions and to do the testing in, or any area capable of maintaining these conditions may be used. An air ionizing blower may be used while conditioning, although the blower must be turned off once testing begins. A static master may also be used to eliminate residual charges before testing.

4.5.4.3 Testing procedure. Allow the test equipment 1-hour of warm-up time. Adjust the voltage source for a charging voltage of 5000 volts by mounting a 3-inch by 5-inch aluminum plate across the electrodes in the faraday cage such that it is centered in front of the voltage sensor opening. Apply a charge of 5000 volts, and adjust/calibrate the voltage meter designated to indicate detected voltage on the sample equal to 5000 volts. Remove the aluminum plate. Mount

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

a specimen tautly across the electrodes, centering it over the sensor opening. The surface of test specimen (back or front) shall face the sensor. The CUT-OFF must be set to 10 per cent. With the high voltage off, depress the CHG button to measure initial charge on the test specimen. If it is not reading zero, turn CHG button off and use the static master or blower to attempt to eliminate the residual charge. With high voltage off, depress the CHG button again and record any remaining measurable residual charge. Turn off CHG button. Apply 5000 volts to the electrodes for a period of 20 seconds. To do this, depress the + button on the right (the reading on CHARGING VOLTAGE meter must read 5000 volts); then depress the CHG button. Wait 20-second; record the highest reading on the SAMPLE CHARGE meter. Then depress the TEST button and from the readout under DECAY TIME-SEC, record how long it took for the charge to decay from maximum voltage to 10 per cent of the maximum level. Depress the ZERO/STBY button after the test. The high voltage (5000 volts) shall be turned off and the specimen immediately grounded. If the DECAY TIME-SEC is less than 0.5 seconds, the specimen is acceptable; otherwise it is not. Also, the specimen must accept a charge of at least 4000 volts during the 20 second charging period to be acceptable.

NOTE. The reason for failure shall be noted. Recalibrate periodically, at the minimum between each set of six (6) specimens. Report the test method used and any alterations to the method shall be reported. Test conditions, including relative humidity, temperature and conditioning time shall be stated.

4.5.5 Liquid repellency test. Place a small specimen of the treated finished camouflage cloth (comprised of all colors in the pattern) on a smooth horizontal surface, face-up. Using a pipette or eye dropper, gently deposit a drop of each liquid specified (see 3.9) on the surface of each shade of the camouflage pattern. After 30-seconds, examine each color of the specimen under light at an angle. Absence of light reflectance at the cloth-drop interface for the n-dode-cane drop shall be taken as evidence of wetting. The test shall be continued for 8-hours for the drops of tri-ethyl phosphate, di-methyl methyl phosphonate, and bis (2 ethyl hexyl) hydrogen phosphite. Absence of light reflectance at the cloth-drop interface for the three liquids after the 8 hour period shall be taken as evidence of wetting. Three (3) specimens taken at various locations across the sample unit shall be tested. Evidence of wetting on any color of one (1) or more specimens shall be considered cause of rejection of the lot represented by the sample.

4.5.6 Toxicity test. When required, (see 6.2), an acute dermal irritation study and a skin sensitization study shall be conducted on laboratory animals. When the results of these studies indicate the finished cloth is not a sensitizer or irritant, a Repeat Insult Patch Test shall be performed in accordance with the Modified Draize Procedure (see 2.3). If the toxicity requirement (see 3.13) can be demonstrated with historical use data, toxicity testing may not be required (see 6.2).

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The cloth is intended for use in combat camouflage uniforms. Classes 3, 5 and 11 contain a static dissipative fiber in the fiber blend and are not water repellent treated. Classes 2, 4, 8, and 10 are water repellant treated and Classes 1, 6, 7 and 9 are untreated. Class 12 is untreated and is for combat helmet covers.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of Specification.
b. Class of cloth required (see 1.2).
c. The specific issue of individual documents referenced (see 2.2).
d. Woodland, Universal or Operational Camouflage Pattern drawing if required (2.2.2).....
e. When first article is required (see 3.1 and 4.2).
f. Width of cloth required (see 3.6.2).
g. When toxicity testing is required (see 3.13 and 4.5.6).
h. Length and put up required if other than specified (see 3.14).
i. Conformance Inspection conditions (see 4.3).
j. Packaging (see 5.1).

6.3 First article. When a first article inspection is required (see 3.1), it will be inspected and approved under the appropriate provisions of FAR 52.209-4. The first article should be a pre-production sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4. For access to samples and pattern drawings, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Heat setting. The contractors are cautioned to insure that the cloth prior to printing has been properly heat set in order that the final dimensions of the pattern will be within the limits set forth in 3.5.6.

6.6 Changes from previous issue. Marginal notations were not used to indicate revisions, due to overall changes in format per MIL-STD-961. Section 3.2 wording and Table VIII were revised per comments received, Section 5 packaging instructions were updated to reflect current direction, web addresses were updated, and general formatting issues were corrected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

6.7 Static dissipative fiber. Static dissipative fiber also known as P140 is premixed in bale form in a 96% T-420 Nylon /4% P-140 fiber blend and referred to as T420A from the INVISTA, 3 Little Falls Centre, 2801 Centerville Road, Wilmington, DE 19808. The T420A bale is blended with cotton in the yarn formation process.

6.8 Known suppliers of equipment suitable for conducting the Electrostatic Decay Test.

Electro-Tech Systems, Inc. (ETS)
3101 Mt. Carmel Ave
Glenside, PA 19038
https://electrotechsystems.com

Cole-Parmer Instrument
625 East Bunker Court
Vernon Hills, IL 60061-1844
https://www.coleparmer.com

Solomat Corporation
Glenbrook Industrial Park
652 Stamford Road
Stamford, CT 06906

6.9 Operation Enduring Freedom Camouflage Pattern (OEF-CP). Operation Enduring Freedom Camouflage Pattern (OEF-CP) has previously been referred to as MultiCam® Camouflage Pattern.

6.10 Subject term (key word)listing.

Cover, Helmet
Coveralls,
Mechanic
Operational Camouflage Pattern (OCP)
Operation Enduring Freedom Camouflage Pattern (OEF-CP) Static Dissipative Fiber
Water repellent treated
Woodland Camouflage
Pattern
Universal Camouflage Pattern (UCP)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.

Custodian:

Army – GL

Navy – NU

Air Force – 11

Preparing activity:

DLA – CT

(Project 8305-2022-038)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:27Z
Check the source to verify that this is the current version before use.