MIL-B-20390B (AR)
AMENDMENT 2
10 June 1988
SUPERSEDING
AMENDMENT 1
20 February 1976

MILITARY SPECIFICATION

BOARD, AMMUNITION CONTAINER

This Amendment forms a part of Military Specification MIL-B-20390B (PA) dated 20 March 1972, and is approved for use within the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.1 First sentence: Delete "two types" and substitute "one type".

1.2 and 1.2.1 Delete in their entirety.

PAGE 2

* Delete in its entirety and substitute the following:

"2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the non-government documents which is current on the date of this solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM-D641	- Conditioning Paperboard, Fiberboard and Paperboard Containers for Testing
ASTM-D646	- Basis Weight of Paper and Paperboard
ASTM-D685	- Conditioning Paper and Paper Products for Testing
ASTM-D2529	- Bursting Strength of Paperboard and Linerboard

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:44Z
Check the source to verify that this is the current version before use.

Technical Association of the Pulp and Paper Industry (TAPPI)

TAPPI-T208	- Moisture in Wood, Pulp, Paper and Paperboard by Toluene
TAPPI-T412	- Moisture in Paper and Paperboard

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 1 Dunwoody Park, Atlanta, Georgia 30341.)"

3.1.1 Delete in its entirety.

PAGE 3

3.4 Table I: for board thickness "0.016 to 0.036", change the tolerance of "0.002" to "0.0010". For board thickness "0.036 to 0.042" add a tolerance of "±0.0015". Table II and related information: Delete in its entirety.

PAGE 5

4.1.1 Delete "f. Type (I or II) board submitted."

PAGE 10

* Table III For the Moisture Content test method, delete "Method 5024 FED. Test method std. 101." and substitute "Procedure T208 or T412 of TAPPI test standard".

PAGE 11

6.1 Delete "k Type of board required (I or II)".

PAGE 12

6.2.1 Delete in its entirety and substitute

6.2.1 Previously specified "Type I or II" board is not required."

The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:44Z
Check the source to verify that this is the current version before use.

Custodian
Army - AR

Preparing activity
Army - AR

(Project 8140-A764)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:44Z
Check the source to verify that this is the current version before use.