MIL-C-20312
26 November 1951

MILITARY SPECIFICATION

CORD, COTTON, BRAIDED
(FOR PYROTECHNIC PARACHUTES)

This specification was approved by the Departments of the Army, the Navy, and the Air Force for use of procurement services of the respective Departments, and supersedes the following specification:

Army 50-11-52
8 September 1938

This specification consists of this cover sheet, Specification 50-11-52, dated 8 September 1938, and Amendment -1, dated 1 April 1942, attached hereto, without modification.

When a request for this specification is received by a supplying activity it will be necessary to attach this cover sheet to the pertinent specification before issue.

Copies of specifications required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.

Custodian:
Army- O

Structures.ihtsdtools.mil - Downloaded: 2026-10-19T07:36Z
Check the source to verify that this is the current version before use.

THIS DOCUMENT CONTAINS 4 PAGES.

U. S. ARMY
SPECIFICATION

No. 50-11-52

SEPTEMBER 8, 1933

CORD, COTTON, BRAIDED

(For Pyrotechnic Parachutes)

A. APPLICABLE SPECIFICATIONS.

A–1. United States Army Specification No. 100–2, Standard Specification for Marking Shipments, of the issue in effect on the date of invitation for bids, forms a part of this specification.

B. GRADES.

B–1. This specification covers one grade of Cord, Cotton, Braided.

C. MATERIALS AND WORKMANSHIP.

C–1. Braided cotton cord shall be made by braiding uniformly cotton threads or cords.

D. GENERAL REQUIREMENTS.

D–1. See section E.

E. DETAIL REQUIREMENTS.

E–1. *Number of threads or cords.*—Sixteen.
E–2. *Breaking strength, pounds, minimum.*—Ninety-five.
E–3. *Elongation, percent, minimum.*—Fifteen.
E–4. *Yards per pound, minimum.*—One hundred and seventy.
E–5. *Area of cross-section, sq. mm, maximum.*—Six.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. *Inspection.*—Inspection shall be at the point of delivery unless otherwise specified in the contract.

F–2. *Size of lots.*—Maximum, 1,000 pounds.

F–3. *Sampling* shall be done as follows: Ten percent, but in no case more than 10 of the spools comprising the lot shall be selected by the inspector. Approximately 15 yards of cord shall be cut from each of the selected spools. The sample composed of these portions shall represent the lot in all tests and shall be marked with the name of the material, manufacturer, plant, purchase order, and number of pounds in the lot.

F–4. *Laboratory* examination shall be made as follows after conditioning the sample cord for at least 4 hours at 65% relative humidity and a temperature of 70–80° F.

F–4a. *Breaking strength.*—Cut one or more test specimens thirty-six inches in length from each piece of the sample. Test these specimens by means of an inclination-balance (pendulum) type machine of such capacity that the arm makes an angle between 4° and 45° with the vertical when rupture occurs, and having a rate of separation of the grips of 12 inches per minute under no load. Use smooth grips of the drum type 2 inches in diameter. At the beginning of the test the distance between the grips shall be not less than 6 inches. In case a specimen breaks less than ½ inch from the point at which it touches the drum grip or at any point touching the grip, disregard the result and test another specimen from the same piece. Calculate the average of the results.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:36Z
Check the source to verify that this is the current version before use.

F-4b. *Elongation.*—Cut one or more test specimens 20 inches in length from each piece of the sample. Test these specimens by means of the same equipment used for determining breaking strength, except that flat grips shall be used. Measure the distance between the grips before the test is begun, fasten the test specimen so that it will be under a tension of about 0.5 pound, and increase the load to 90 pounds. Stop the movement of the grips at this point and measure the distance between the grips. Calculate the increase in distance between the grips as percentage of the distance before tension was applied. Calculate the average of the results.

F-4c. *Yards per pound.*—Cut from each piece of the sample a specimen 10 yards in length, measured when subjected to only sufficient tension to keep the line taut. Weigh simultaneously all of the specimens so obtained, and calculate the number of yards per pound.

F-4d. *Area of cross-section.*—Measure the undistorted maximum and minimum thickness of each piece of the sample by means of a measuring microscope having a scale graduated in 0.1-mm divisions and employing a magnification of 12.7. Average the two measurements made and calculate the area as that of a circle of that diameter. Calculate the average area for all of the pieces comprising the sample.

G. PACKAGING, PACKING, AND MARKING.

G-1. *Packaging.*—

G-1a. Braided cotton cord shall be wound on commercial-size spools so as to hold from 2 to 4 pounds of material.

G-1b. Braided cotton cord shall be so wound that each turn and layer shall be free of entanglement.

G-2. *Packing.*—Unless otherwise specified, braided cotton cord shall be packed in commercial containers, so constructed as to insure acceptance by common or other carrier, for safe transportation, at the lowest rate, to the point of delivery.

G-3. *Marking.*—Each container shall be marked as prescribed by United States Army Specification No. 100-2.

H. NOTES.

H-1. This specification covers braided cotton cord used in making shroud lines for pyrotechnic parachutes.

NOTICE.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation or conveying any rights or permission to manufacture, use, or sell any patented invention that may be in any way related thereto.

NOTE.—Copies of this specification may be obtained from the Office, Chief of Ordnance, Washington, D. C.

[No. 50-11-52]

MIL-C-2312

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:36Z
Check the source to verify that this is the current version before use.

U. S. ARMY
SPECIFICATION

No. 50-11-52
September 8, 1938
Amendment-1
April 1, 1942

CORD, COTTON, BRAIDED
(For Pyrotechnic Parachutes)

The following change shall be made in Specification No. 50-11-52 dated September 8, 1938:

Page 2, Paragraph F-4d. Delete the first sentence and substitute the following:

"By means of a measuring microscope having a scale graduated in 0.1 mm. divisions and adjusted so as to have a magnification of 12.7, measure the maximum and minimum thicknesses of each piece of the sample when the cord is under a tension of 1 pound."

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:36Z
Check the source to verify that this is the current version before use.