U. S. ARMY
SPECIFICATION

No. 50-11-65A
19 August 1941
Amendment - 2
17 October 1944
Superseding Amendment
- 1

CLOTH, COTTON, CARTRIDGE

* Page 1, paragraph C-1b. Delete the paragraph and substitute the following:

"C-1b. Grade A cloth shall be manufactured from commercial type 140 sheeting, narrow or wide, slit to the correct width. It shall be free of starch and shall be calendered to facilitate handling, cutting and sewing."

* Page 1, Section C. Add the following paragraphs:

"C-1c. Grade B cloth shall be manufactured from commercial print cloth. It shall be free of starch and shall be calendered to facilitate handling, cutting, and sewing".

C-1d. Grade C cloth shall be manufactured from commercial combed lawn cloth. It shall be lightly sized with starch and shall be calendered to facilitate handling, cutting and sewing. The starch used shall be undegraded (e.g. no gums or dextrines) to prevent sticking of the edges of the cloth when cut on punch presses."

C-1e. Grade D cloth shall be manufactured from commercial material of a four hardness twill weave to the right, three up and one down. It shall be free of starch and shall be calendered to facilitate handling, cutting and sewing. It shall be pre-shrunk and mercerized."

* Page 1, paragraph C-2a. Delete the last sentence.

* Page 1, paragraphs C-2c, C-2d, and C-2e. Delete the paragraphs and substitute the following:

"C-2c. Cotton Cartridge Cloth shall be furnished in rolls weighing between 200 and 250 pounds. Lengths of cloth comprising a roll shall be not less than 90 per cent of lengths, 40 yards and over. No length shall be less than 20 yards. Lengths shall be sewn together to give a continuous length using a stitch which will not cause the cloth to ravel when passing through a slitting machine.

C-2d. The stretch and breaking strength in either direction should be as near equal as possible. The former should be as low and the latter as high as possible."

Page 1, footnote at bottom of page. Delete the footnote and substitute the following:

"1 desired width 40 inches."

Source: https://assist.dla.mil -- Downloaded: 2026-10-19107:37Z
Check the source to verify that this is the current version before use.

	Grade A	Grade B	Grade C	Grade D
weight per sq. yd.: Hex., Oz	5.0	3.1	2.1	8.2
Thread count:				
Warp. Minimum	74		87	116
" Maximum			93	
Fill, minimum	66		76	56
Fill, Maximum			82	
Breaking Strength:				
Warp, minimum, pounds	70	30	28	180
Fill, minimum, pounds	70	30	25	130
Stretch:				
Warp, maximum, per cent	12.0			12.5
Fill, maximum, per cent	20.0			12.5
Water extract; max., per cent	0.5	0.5	2.0	0.5

* Page 3, paragraph 4g, second sentence, delete "one inch" and substitute "three inches".

* Page 3, paragraph 4g, line 7. Delete "50" and substitute "40".

* Page 3, paragraph G-1, delete all reference to "bolts" and add "rolls".

* Page 4, paragraph G-1, last sentence. Delete "200 pounds" and add "250 pounds or less than 200 pounds".

* Asterisks indicate changes in addition to or differing from previous amendments.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:37Z
Check the source to verify that this is the current version before use.