INCH-POUND
MIL-W-16878/35A(NAVY)
11 September 1992
SUPERSEDING
MIL-W-16878/35(NAVY)
25 June 1982

MILITARY SPECIFICATION SHEET

WIRE, ELECTRICAL, POLYTETRAFLUOROETHYLENE (PTFE) INSULATED, 260°C, 1000 VOLTS, DOUBLE WRAPPED INSULATION

This specification is approved for use by the Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-W-16878.




FIGURE 1. Construction.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:33Z
Check the source to verify that this is the current version before use.

TABLE I. Construction details.

PIN 1/	Wire size	Strand-ing	Conductor		Conductor diameter (nominal) (inch)	Finished wire diameter (inch)	
			Material	Coating		Min	Max
M16878/35-BAB*	32	7 X 40	Copper	Nickel	0.010	0.036	0.044
M16878/35-BBB*	30	7 X 38	Copper	Nickel	.012	.038	.046
M16878/35-BCB*	28	7 X 36	Copper	Nickel	.015	.041	.049
M16878/35-BDB*	26	7 X 34	Copper	Nickel	.019	.045	.053
M16878/35-BEB*	24	7 X 32	Copper	Nickel	.024	.050	.058
M16878/35-BFB*	22	7 X 30	Copper	Nickel	.030	.056	.064
M16878/35-BGB*	20	7 X 28	Copper	Nickel	.038	.064	.072
M16878/35-BHB*	18	7 X 26	Copper	Nickel	.048	.074	.084
M16878/35-BJE*	16	19 X 29	Copper	Nickel	.057	.083	.095
M16878/35-BKE*	14	19 X 27	Copper	Nickel	.072	.098	.114
M16878/35-BLE*	12	19 X 25	Copper	Nickel	.091	.117	.133
M16878/35-BMG*	10	37 X 26	Copper	Nickel	.111	.137	.153
M16878/35-BNL*	8	133 X 29	Copper	Nickel	.169	.199	.219
M16878/35-BPL*	6	133 X 27	Copper	Nickel	.213	.253	.273
M16878/35-BRL*	4	133 X 25	Copper	Nickel	.257	.287	.307

1/ PIN stands for part or identifying number.

ADDITIONAL REQUIREMENTS:

Construction: The wire shall be insulated with two spirally-wrapped layers of 0.005-inch (nominal) thick PTFE tape. The first layer of tape shall be applied in the opposite direction to the lay of the conductor, and the second layer of tape shall be applied in the opposite direction of the first layer. Then the two layers shall be heatbonded and fused.

Visual and mechanical examination: Required.

Spark test: 5.0 kV.

Impulse dielectric test: 8.0 kV.

Dielectric withstanding voltage: 3.0 kV.

Insulation resistance: $IR = K \log_{10} D/d$.

Where: IR = Minimum insulation resistance in megohms per 1000 feet at 20°C.
K = 50,000.
D = Maximum average diameter of finished wire.
d = Conductor diameter.

Conductor resistance: See table I.

Cold bend: Condition 4 hours at minus 65 ± 1°C (See table II).


Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:33Z
Check the source to verify that this is the current version before use.

TABLE II. Cold bend mandrel sizes.

Wire size	Cold bend mandrel (maximum diameter in inches)
32 through 16	1
14, 12	2
10, 8	3

Concentricity: 70 percent (minimum).
Surface resistance: Not required.
Wrap back: Required.
Heat resistance: Condition at 290°C.
Flammability: Meets requirements of UL VW1 Flame Test.
Toxicity: Meets requirements of concentration levels specified in MIL-E-917.
Shrinkage: Required.
Heat aging: Not required.
Insulation tensile strength: 4000 pounds force per square inch (minimum).
Insulation elongation: 150 percent (minimum).
Marking and stripe durability: Required.
Fungus resistance: Not required.
Maximum dc resistance of finished wire: See table I of MIL-W-16878.
Wire length requirements: See appendix B.
Identification of product: Required for wire sizes 22 AWG and larger.

PIN example (see MIL-W-16878):



Revision letters are not used to denote changes due to the extensiveness of the changes.

Preparing activity:
Navy - SH
(Project 6145-N330-34)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:33Z
Check the source to verify that this is the current version before use.