A-A-53926
26 June 1989

COMMERCIAL ITEM DESCRIPTION

SCALER, DENTAL, Double-ended

The General Services Administration has authorized the use of this Commercial Item Description.

Salient characteristics:

This commercial item description covers double-ended dental scalers suitable for use in periodontal procedures. The scalers shall be of the following styles as specified below:

Style 1. - No. U15 and 30

Style 2. - No. U15 and 33

Style 3. - Jaquette No. 31 and 32

Style 4. - Jaquette No. 34 and 35

Material.

Operative ends. The operative ends shall be fabricated of class 4, type 440A, 440B or 440C martensitic stainless steel as specified in ASTM Designation F899 for composition only.

Handles.

Style 1 and 2. Handles A and C shall be fabricated of brass. The brass shall conform to C26000 or C33000 as specified in ASTM Designation B135 for composition only. The brass handles shall be chromium over nickel plated. Handle B shall be fabricated of Class 4, type 416 or 410 martensitic stainless steel or Class 6, type 430F ferritic stainless steel as specified in ASTM Designation F899 for composition only. Handle D shall be fabricated of Class 3, type 303 austenitic stainless steel as specified in ASTM Designation F899 for composition only.

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Style 3 and 4. Handles A and D shall be fabricated of brass. The brass shall conform to C26000 or C33000 as specified in ASTM Designation B135 for composition only. The brass handles shall be chromium over nickel plated. Handle B shall be fabricated of Class 4, type 416 or 410 martensitic stainless steel or Class 6, type 430F ferritic stainless steel as specified in ASTM Designation F899 for composition only. Handle C shall be fabricated of Class 3 type 303 austenitic stainless steel as specified in ASTM Designation F899 for composition only.

Hardness. After proper stress relieving, the Rockwell hardness of the operative ends shall be C52 to C56 for type 440A, C54 to C58 for type 440B and C56 to C60 for type 440C, as specified in ASTM Designation E18 (Rockwell) or E92 (Vickers) and E140. The handles and shanks shall be of the proper temper and shall have a hardness suitable for the intended purpose.

Style, design and dimensions. The scalers shall be double-ended and shall be suitable for use in periodontal procedures for scaling teeth.

Style 1 and 2. The scalers shall be of Jaquette-Towner design. The style, design and dimensions of the scalers shall conform to Defense Personnel Support Center (DPSC) Drawing No. 24412 for the applicable style.

Style 3 and 4. The scalers shall be of Jaquette design. The style, design and dimensions of the scalers shall conform to Defense Personnel Support Center (DPSC) Drawing No. 24450 for the applicable style.

The scalers shall be furnished in the applicable style, specified. The scalers shall be furnished with the handle and shank design of either Handle A, B, C or D.

Construction. The scalers shall be of three-piece construction (one operative end at each end and a handle). The handle shall be of solid or hollow construction as specified on the drawing for the operative handle. Knurled or serrated portions of handle shall be as specified on the drawing for the respective handle. The operative ends shall be permanently secured to the handle. There shall be no movement, loosening, or separation between the operative end and the handle when the operative end is subjected to an 85 pound (minimum) pull out force when tested as specified herein. The interface of the shank and handle shall be smoothly blended with no crevices evident.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Finish. The operative ends, including shanks, shall have a bright finish, except for the surfaces forming the scaling edges (blade) which shall have a fine honed finish such as that produced with FF emery on a leather wheel. The scaling edges shall be sharp. Handles shall have a bright finish, except for the serrated or knurled portion of the handle.

Corrosion resistance. The copper sulfate test requirements of ASTM Designation F1089 shall apply to the operative ends, martensitic stainless steel handles and ferritic stainless steel handles. The boil test requirements of ASTM Designation F1089 shall apply to the operative ends and all the handles.

Workmanship. The operative end (blade portion) shall be free from coarse grind marks, cracks, burrs, pits, feathers, or any other defects and the serrated or knurled portion of the handle shall be free of barbs or slivers or any other defects.

Unit. Each (EA). One scaler of the style specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Certificates of quality. Certificates of quality for raw material, supplied by the manufacturer of the steel, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more inspection, examination and test characteristics. The unit of product for inspection, examination and test purposes shall be one scaler. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, except for dimensions which shall be conducted at inspection level S-1, AQL 2.5 (percent defective) and sampling for tests (when applicable) shall be conducted at inspection level S-2 and acceptance number shall be zero (0) for all sample sizes.

Examination. Examination shall include, but shall not be limited to the following:

Defects
Style and design not as specified for the applicable style number of the instrument.
Finish of entire instrument not as specified.
Identification marking not present, not properly located, illegible, or incomplete.
Handle serrations or knurling missing, not uniform, or not complete.
Dimensions not as specified.

Examination under magnification. The instruments shall be examined under four power (4X) magnification for the following defects:

Defects
Cutting edge of operative end rounded or not sharp.
Cutting edge not free from coarse grind marks, cracks, burrs, pits, feathers, or other irregularities.

Tests.

Chemical analysis. In the absence of certificates of quality, the chemical analysis of the instrument shall be determined in accordance with method 111 or method 112 of FED-STD-151. In the event of a conflict, method 111 shall govern.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Pull test. The handle and shank of the operative end shall be securely held in separate chucks or other holding devices. A slowly increasing pull out force, increasing from zero to 85 pounds (minimum), shall be applied to the shank of the operative end. The force shall be maintained at the high value for a minimum of 1 second. The instrument shall then be examined for movement, looseness, or separation of the operative end with respect to the handle. The test shall be repeated for each operative end of the double-ended instrument.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pounds units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

National Stock Number	Item Identification	Style
6520-01-046-7331	SCALER, DENTAL, No. U15 and 30, Double-ended	1
6520-01-046-7332	SCALER, DENTAL, No. U15 and 33, Double-ended	2
6520-01-125-6611	SCALER, DENTAL, Jaquette No. 31 and 32, Double-ended	3
6520-01-125-6613	SCALER, DENTAL, Jaquette No. 34 and 35, Double-ended	4

Ordering data. Intermediate/exterior package quantities, labeling and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

PREPARING ACTIVITY:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

PROJECT NO. 6520-2279
LOCATION: NCR DISK 2

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 3, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4968 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
Attn: DPSC-RSTE
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.