A-A-53933
31 July 1989

COMMERCIAL ITEM DESCRIPTION

PROBE, PERIODONTAL

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-P-37928 (DM) which is cancelled.

Salient characteristics:

This commercial item description covers probes suitable for diagnosing and measuring the depth of periodontal pockets. Probes shall be of the following types and styles, as specified below:

Type I. - Single-ended

Style 1. - Glickman, No. 26G
Style 2. - No. 4

Type II. - Double-ended

Style 1. - Nabers, No. 2N

Material.

Operative ends. The operative ends shall be fabricated of class 3, type 302, 303 or 304 austenitic stainless steel. As an alternate for type I, style 2 and type II, style 1 class 4, type 440A martensitic stainless steel or as an alternate for type I, style 1 class 5, type 630 (17-4PH) precipitation hardening stainless steel as specified in ASTM Designation F899 for composition only.

Handles. The handles shall be fabricated of class 3, type 303 austenitic stainless steel or class 4, type 416 martensitic stainless steel, or class 6, type 430F ferritic stainless steel as specified in ASTM Designation F899 for composition only, or number C36000 free-cutting brass as specified in ASTM Designation B16 for composition only. As an alternate to C36000, the handles shall be fabricated of C26000 or C33000 as specified in ASTM Designation B135 for composition only. The brass handles shall be chromium over nickel plated.

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Corrosion resistance. The boil test requirements of ASTM Designation F1089 shall apply for the entire probe, (operative ends and all handles). The copper sulfate requirements of ASTM Designation F1089 shall apply to the operative ends if fabricated of martensitic stainless steel, and the handles if fabricated of martensitic or ferritic stainless steel only.

Hardness. After proper stress relieving, the Rockwell hardness of the operative ends shall be C45 to C50, except if 630 precipitation hardening stainless steel is used for type I, style 1 shall be C39 to C45, as specified in ASTM Designation E18 (Rockwell) or ASTM Designation E92 (Vickers) and E140.

Style, design and dimensions. Type I probes shall be suitable for use in measuring the depth of periodontal pockets and type II probes shall be suitable for diagnosing and evaluating periodontal pockets and abnormalities in bifurcation areas. The style, design and dimensions of the probes shall conform to Defense Personnel Support Center (DPSC) Drawing No. 24405 for the applicable type and style.

Construction.

Type I. The probes shall be single-ended, two piece construction, consisting of an operative end and a handle. The operative ends shall be permanently secured to the handles. The finger grip portion of the handles shall be finely serrated or fine diamond knurled.

Style 1. The operative end shall have millimeter (mm) markings. The millimeter markings shall be legible, sharply defined lines, of uniform width and depth. Markings shall be calibrated in 1mm, 2mm, 3mm, 5mm, 7mm, 8mm, 9mm and 10mm increments extending around the periphery of the measuring tip.

Style 2. The operative ends shall be color-coded and calibrated in 3mm, 6mm, 9mm and 12mm increments extending around the periphery of the measuring tip.

Type II, style 1. The probe shall be double-ended, three-piece construction, consisting of two operative ends and a handle. The operative ends shall be permanently secured in the handles. Operative ends shall be finely serrated or fine diamond knurled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Finish. The operative ends shall have a bright finish. The handles shall have a bright or satin finish, except for the serrated or knurled portion.

Identification marking. Type I, style 1, Glickman probe shall be marked "26G"; type I, style 2 probe shall be marked "4"; type II, style 1, Nabers probe shall be marked "2N". All markings shall be on the smooth portion of the handles and shall be legible and permanent. As an alternate to the word "stainless", the use of a registered trade name identifying the steel as stainless is acceptable, provided prior approval is received from the cognizant contracting officer. If the probes are of foreign manufacture, the instruments shall be marked with the country of origin.

Workmanship. The operative ends and the handle of the probes shall be free from defects such as coarse grind marks, cracks, burrs, or pits which may detract from their appearance or impair their serviceability, proper functions or intended use.

Unit. Each (EA). One probes of the type and style specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Certificates of quality. Certificates of quality for raw material, supplied by the manufacturer of the steel, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more inspection, examination and test characteristics. The unit of product for inspection, examination and test purposes shall be one probe. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, except for dimensions which shall be conducted at inspection level S-1, and sampling for tests (when applicable) shall be conducted at inspection level S-2 and acceptance number shall be zero (0) for all sample sizes.

Examination. Examination shall include, but shall not be limited to the following:

Defects

Style and design not as specified for the applicable type and style.
Instrument not constructed as specified.
Instrument finish not as specified.
Instrument marking not properly located, permanent or legible.
Dimensions not as specified.

Microscopic examination. Examination of probe defects not readily perceptible to the naked eye shall be made using a microscope at 10 power (10X) magnification.

Defects

Operative end not free from cracks, burrs, feathers or pits.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Tests. Tests shall be conducted to determine compliance with the item description requirements.

Chemical analysis. In the absence of certificates of quality for the raw material, chemical analysis shall be conducted in accordance with method 111 or method 112 of FED-STD-151. In case of dispute, method 111 shall govern.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pounds units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

National Stock Number	Item Identification
6520-01-046-7329	PROBE, PERIODONTAL, Glickman, 26G
6520-01-047-0646	PROBE, PERIODONTAL, No. 4
6520-01-047-5629	PROBE, PERIODONTAL, Bifurcation, Nabers, 2N

Ordering data. Intermediate/exterior package quantities, labeling and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

PREPARING ACTIVITY:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

PROJECT NO. 6520-2276
LOCATION: NCR DISK 2

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide sti ons. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and ed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
Attn: DPSC-RSTE
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
A-A-53933	PROBE, PERIODONTAL

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.