FF-N-105B
March 17, 1971
SUPERSEDING
Fed. Spec. FF-N-105A
July 26, 1963
(See Sec. 6)

# FEDERAL SPECIFICATION

# NAILS, BRADS, STAPLES AND SPIKES: WIRE, CUT AND WROUGHT

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

## 1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers wire and cut nails and spikes, wire brads and staples, and wrought spikes

1.2 Classification.

1.2.1 Types and styles. Nails, brads, staples and spikes shall be of the following types and styles, as specified (see 6.2).

Type I - Brads

Type II - Nails
- Style 1 - Asbestos Shingle
- 2 - Barrel
- 3 - Boat
- 4 - Box
- 5 - Broom
- 6 - Casing
- 7 - Coolers
- 8 - Sinkers
- 9 - Corkers
- 10 - Common
- 11 - Concrete
- 12 - Double-Headed
- 13 - Fine
- 14 - Finishing
- 15 - Flooring

FSC 5315

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

Style 16 - Lath
17 - Masonry
18 - Pallet
19 - Gypsum Wallboard
20 - Roofing
21 - Shingle
22 - Siding
23 - Slating
24 - Rubber Heel
25 - Underlayment
26 - Square Barbed
27 - Masonry Drive
28 - Escutcheon

Type III - Staples
Style 1 - Fence
2 - Poultry Netting
3 - Flat Top Crown
3a - Round or "V" Crown
4 - Preformed

Type IV - Cut Nails
Style 1 - Common
2 - Basket
3 - Clout
4 - Trunk
5 - Cobblers
6 - Extra-Iron Clinching
7 - Hob

Type V - Spikes
Style 1 - Common (Cut)
2 - Gutter
3 - Round
4 - Barge and Boat

1.2.2 Sizes. Nails, brads, staples and spikes shall be of the sizes listed herein or as otherwise specified (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

NN-P-71 - Pallets; Materials-Handling, Wood (General Construction Requirements).
QQ-Z-325 - Zinc Coating, Electrodeposited, Requirements For.
MMM-A-250 - Adhesive, Water-Resistant (For Closure of Fiberboard Boxes).
PPP-B-566 - Boxes, Folding Paperboard.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Box, Fiberboard.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from the established distribution points in their agencies.)

Military Specification:

MIL-C-87562 - Coating, Cadmium or Zinc (Mechanically Deposited).

Military Standards:

MIL-STD-109 - Quality Assurance Terms and Definitions.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-147 - Palletized and Containerized Unit Loads - 40" x 48" Pallets. Skids, Runners or Pallet-Type Base.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards:

ASTM A90 - Weight of Coating on Zinc Coated (Galvanized) Iron or Steel Articles.
ASTM A153 - Zinc Coating (Hot Dip) on Iron and Steel Hardware.
ASTM B211 - Specification for Aluminum Alloy Bars and Wire.
ASTM D1761 - Testing Metal Fasteners in Wood.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA. 19103.)



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Tariff Publishing Officer, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, IL 60606.)

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc., Agent, 1616 P Street, N.W., Washington, DC 20036.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Material. Nails, brads, staples and spikes shall be of the following materials, as specified (see 6.2).

3.1.1 Steel wire. Steel wire shall be of good commercial quality, entirely suitable for the purpose and sufficiently ductile to insure that the finished product shall withstand, without fracture, cold bending through 180 degrees over a diameter not greater than the diameter of the wire. Except as specified in 3.1.2, the cold bend test will not be applied to barbed nails, or nails having mechanically formed or deformed shanks.

3.1.2 Hardened steel. Hardened steel nails shall be heat treated to a minimum hardness of Rockwell C37. The finished product shall withstand, without fracture, cold bending through 20 degrees over a diameter not greater than the diameter of the wire.

3.1.3 Medium-carbon steel sheet. Cut nails (Type IV) and cut spikes (Type V, style 1) shall be sheared from medium-carbon steel sheet of good commercial quality, entirely suitable for the purpose. The finished product shall withstand, without fracture, cold bending through 90 degrees over a diameter not greater than the thickness of the sheet.

3.1.4 Copper. Copper nails shall contain a minimum of 98 percent pure copper. Copper nails shall withstand, without fracture, cold bending through 120 degrees over a diameter not greater than the diameter or thickness of the nail.

3.1.5 Copper-clad steel wire. Copper-clad steel wire shall be not less than 30 percent copper by weight. The average thickness of the copper shall be not less than 10 percent of the radius of the finished wire; the minimum thickness shall be not less than 7 percent of the radius of the finished wire. The finished product shall withstand cold bending through 180 degrees over a diameter not greater than the diameter of the wire without fracture and without separation of the copper from the steel.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.1.6 Aluminum alloy wire. Aluminum alloy wire shall conform to alloy 5056 having a minimum ultimate tensile strength of 60,000 PSI or alloy 6061 having a minimum ultimate tensile strength of 63,000 PSI. Smooth shank nails shall be chemically treated to remove all grease, oil and foreign matter and to microscopically roughen the surface. Barbed and mechanically deformed nails shall be cleaned to remove all grease and foreign matter. Finished, smooth shank nails shall withstand, without fracture, cold bending through 90 degrees over a diameter not greater than the diameter of the wire.

3.1.7 Wrought iron and steel. Wrought iron and steel used in the manufacture of spikes shall be of good commercial quality, entirely suitable for the purpose. The finished product shall withstand, without fracture, cold bending through 180 degrees over a diameter not greater than the square dimension of the spike being tested.

3.1.8 Brass wire. Brass wire shall be of good commercial quality, entirely suitable for the purpose. The finished product shall withstand, without fracture, cold bending through 180 degrees over a diameter not greater than the diameter of the wire.

3.2 Protective coatings and finishes. When specified (see 6.2), protective coatings and finishes shall be as follows.

3.2.1 Zinc coating.

a. Hand driven staples shall be cut from galvanized wire, mechanically deposited zinc coated wire or electrodeposited zinc coated wire, or cut from uncoated wire and galvanized after forming.

b. Mechanically driven staples and nails required to be zinc coated shall be manufactured from hot dip (galvanized ) steel wire which shall not vary in diameter by more than the amount indicated in Table 7-26 of the American Iron and Steel Institute's Steel Products Manual-Wire and Rods, Carbon Steel for the size (gage) of wire specified or from mechanically deposited zinc coated wire or electrodeposited zinc coated wire.

3.2.1.1 Galvanizing. Hot-Dip galvanizing shall be in accordance with ASTM A153, Class D.

3.2.1.2 Mechanically deposited. Mechanically deposited zinc coating shall be in accordance with MIL-C-81562, Type II and shall have a coating weight of not less than 0.25 ounces per square foot of surface area.

3.2.1.3 Electrodeposited. Electrodeposited zinc coating shall be in accordance with QQ-Z-325, Type II, Class 2.

3.2.2 Cement coating. Cement coating shall be applied by tumbling, mechanical dispensing device or immersion in resin, shellac or other similar material and shall not be tacky or gummy. Cement coated nails having nominal diameters of 0.135 inch (10 gage) or less shall produce a minimum



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

increase in immediate holding power, above that of an identical bright nail before cleaning, of not less than 50 percent. Cement coatings on mechanically driven nails and staples shall be uniform and may be applied before, during or after the fasteners are cohered into strips, clips or coils. This minimum increase in holding power is not applicable to mechanically deformed nails.

3.2.3 Chemical etching. Chemical or acid etching shall remove the polish of fabrication and microscopically roughen the surface to produce a nail of increased holding power

3.2.4 Blued nails. Blued nails shall be heated to form a thin, bluish oxide on the surface.

3.2.5 Other finishes. When required, tin plating, brass plating and copper plating shall be as specified (see 6.2).

3.3 Altered shapes and power driven nails and staples.

3.3.1 Mechanically formed or deformed shanks. Mechanically formed shanks shall have barbs, flutes, angular serrations, etc., formed onto the wire from which the nail is made. Mechanically deformed shanks shall have vertical or helical flutes or screw type or annular ring type deformations rolled or twisted on the shank. The deformations shall pass entirely around the body resulting in expanded ridges and depressions. (For the purpose of this specification these deformations are not to be considered as threads.) Nails with formed or deformed shanks may be fabricated from round or square wire as specified (see 6.2).

3.3.2 Mechanically driven nails. Mechanically driven nails shall be either "T" headed or with or without altered round heads. These nails shall be suitable for use in the make and model of gun specified (see 6.2). Unless otherwise specified (see 6.2), the dimensions shall correspond to the dimensions for styles 4, 7, 8, 10, 14 or 18.

3.3.3 Power driven staples. Power driven staples shall conform to Tables IV-A, IV-B and IV-C and shall fit the make and model of staple gun specified (see 6.2).

3.4 Dimensions. Unless otherwise specified (see 6.2), dimensions shall be in accordance with the applicable table or paragraph (see 3.6).

3.4.1 Lengths. Nails and spikes with flat heads or square shoulders under the heads shall be measured from under the head or shoulder to the tip of the point. Unless otherwise specified, all other brads, nails, and spikes shall be measured overall.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.4.2 Tolerances.

3.4.2.1 Shank diameters. Tolerances on shank diameters shall be ± .004 inch for diameters .076 inch and larger, and ± .002 inch for diameters smaller than .076 inch. Tolerances shall apply before application of protective coatings or finishes. Diameters of pointed nails shall be measured directly below the gripper marks. Diameters of mechanically deformed shanks shall be measured before deformation.

3.4.2.2 Lengths. Tolerances on lengths shall be ± 1/32 inch for lengths up to and including 1 inch; ± 1/16 inch for lengths over 1 inch up to and including 2-1/2 inches; ± 3/32 for lengths over 2-1/2 inches up to and including 7 inches and ± 1/8 inch for lengths over 7 inches.

3.4.2.3 Head diameters.

3.4.2.3.1 Hand driven. Tolerances on head diameters of roofing nails shall be plus 0, minus 10 percent of the nominal head diameter (mean of two readings 90 degrees apart). For other brads, nails and spikes the tolerance shall be ± 10 percent of the nominal head diameter (individual measurement). The difference in diameter across the long axis of a roofing nail shall not exceed that across the short axis by more than 20 percent. For other brads, nails and spikes the difference in diameter across the long axis shall not exceed that across the short axis by more than 10 percent. A fillet shall be provided under the head; an angle or radius will be acceptable. Heads shall be well centered.

3.4.2.3.2 Mechanically driven. Tolerances on head diameters of mechanically driven nails shall comply with the manufacturer's specifications and shall be suitable for use in the make and model of gun specified (see 6.2).

3.5 Workmanship. Items covered by this specification shall be true to shape, well finished, reasonably free from imperfections, clean and free of corrosion. Mechanically driven colored items shall be uniform and properly alligned in their assembled form.

3.6 In the following paragraphs, the various dimensions and other data are indicated as follows:

S = Nominal size or trade designation
L = Nominal length in inches
H = Nominal diameter or width of head in inches
D = Nominal wire diameter in inches
No./lb. - Approximate number per pound (bright finish, round shank)




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.1 Type I - Brads. Steel wire, brad head, diamond point, round smooth shank, bright finish. When specified (see 6.2), brads shall have a modified brad head with blunt or chisel point for use with mechanical drivers.




| L | D | NO./LB | S | L | D | NO./LB | S | L | D | NO./LB |
|---|---|---|---|---|---|---|---|---|---|---|
| 3/8 | .035 | 9,520 | -- | 1-1/4 | .054 | 1,208 | -- | 2-1/4 | .080 | 320 |
| 1/2 | .035 | 7,060 | -- | 1-1/4 | .062 | 940 | 7d | 2-1/4 | .113 | 160 |
| 1/2 | .048 | 3,990 | 3d | 1-1/4 | .080 | 568 | -- | 2-1/2 | .080 | 290 |
| 5/8 | .035 | 5,680 | -- | 1-1/2 | .054 | 1,040 | 8d | 2-1/2 | .131 | 107 |
| 5/8 | .048 | 3,200 | -- | 1-1/2 | .080 | 470 | 9d | 2-3/4 | .131 | 97 |
| 3/4 | .035 | 4,800 | 4d | 1-1/2 | .099 | 316 | 10d | 3 | .148 | 70 |
| 3/4 | .048 | 2,620 | -- | 1-3/4 | .062 | 372 | 12d | 3-1/4 | .148 | 65 |
| 3/4 | .062 | 1,550 | -- | 1-3/4 | .080 | 400 | 16d | 3-1/2 | .162 | 50 |
| 7/8 | .035 | 4,220 | 5d | 1-3/4 | .099 | 270 | 20d | 4 | .192 | 31 |
| 7/8 | .048 | 2,220 | -- | 2 | .062 | 580 | 30d | 4-1/2 | .207 | 24 |
| 7/8 | .062 | 1,280 | -- | 2 | .080 | 350 | 40d | 5 | .225 | 18 |
| 1 | .054 | 1,500 | 6d | 2 | .113 | 181 | 50d | 5-1/2 | .244 | 14 |
| 1 | .062 | 1,120 | | | | | 60d | 6 | .262 | 11 |
| 1 | .072 | 904 | | | | | | | | |

3.6.2 Type II, style 1 - Asbestos shingle nails. Aluminum alloy wire, flat or casing head, diamond point, round, smooth or mechanically deformed shank, as specified (see 6.2).



| L | D | CASING HEAD | | FLAT HEAD | | THICKNESS OF |
|---|---|---|---|---|---|---|
| | | H | NO./LB | H | NO./LB | |
| 1-1/8 | .099 | .141 | 1,046 | .312 | 988 | 1/8 |
| 1-1/4 | .113 | .141 | 787 | .312 | 785 | 3/16 |
| 1-1/4 | .135 | .156 | 516 | .438 | 491 | 1/4 |

3.6.3 Type II, style 2 - Barrel nails. Steel wire, flat head, diamond point, round smooth shank, bright or cement coated, as specified (see 6.2).




| L | D | H | NO./LB | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 5/8 | .067 | .148 | 1,347 | 1-1/8 | .076 | .177 | 670 |
| 3/4 | .067 | .148 | 1,297 | 1-1/4 | .090 | .188 | 542 |
| 7/8 | .076 | .177 | 852 | 1-3/4 | .092 | .219 | 383 |
| 1 | .076 | .177 | 750 | 1-1/2 | .092 | .219 | 352 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.4 Type II, style 3 - Boat nails. Steel wire, oval countersunk head, chisel point, round smooth shank, bright or zinc coated, as specified (see 6.2).



| S | L | LIGHT | | | HEAVY | | |
|---|---|---|---|---|---|---|---|
| | | D | H | NO./LB | D | H | NO./LB |
| 4d | 1-1/2 | .188 | .406 | 82 | .250 | .500 | 47 |
| 6d | 2 | .188 | .406 | 62 | .250 | .500 | 36 |
| 8d | 2-1/2 | .188 | .406 | 50 | .250 | .500 | 29 |
| 10d | 3 | .250 | .500 | 24 | .375 | .750 | 11 |
| 12d | 3-1/4 | .250 | .500 | 22 | .375 | .750 | 10 |
| 16d | 3-1/2 | .250 | .500 | 20 | .375 | .750 | 9 |
| 20d | 4 | .250 | .500 | 18 | .375 | .750 | 8 |


3.6.5 Type II, style 4 - Box nails. Steel wire, flat head, diamond point, round, barbed or smooth shank, bright or cement coated, as specified (see 6.2). When specified (see 6.2), box nails shall have an altered or T-head with a diamond, blunt or chisel point for use with mechanical drivers.





| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .067 | .188 | 940 | 9d | 2-3/4 | .113 | .297 | 124 |
| 3d | 1-1/4 | .076 | .219 | 588 | 10d | 3 | .128 | .312 | 90 |
| 4d | 1-1/2 | .080 | .219 | 453 | 12d | 3-1/4 | .128 | .312 | 83 |
| 5d | 1-3/4 | .080 | .219 | 389 | 16d | 3-1/2 | .135 | .344 | 69 |
| 6d | 2 | .099 | .266 | 225 | 20d | 4 | .148 | .375 | 50 |
| 7d | 2-1/4 | .099 | .266 | 200 | 30d | 4-1/2 | .148 | .375 | 45 |
| 8d | 2-1/2 | .113 | .297 | 136 | 40d | 5 | .162 | .406 | 34 |

3.6.6 Type II, style 5 - Broom nails. Steel wire, flat or star head, diamond point, round smooth shank, bright finish, as specified (see 6.2).



| L | D | H | NO./LB | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 5/8 | .072 | .203 | 1,480 | 3/4 | .072 | .203 | 1,175 |
| 5/8 | .080 | .219 | 992 | 3/4 | .080 | .219 | 945 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.7 Type II, style 6 - Casing nails. Steel wire, flat countersunk cupped head, diamond point, round smooth shank, bright finish.



| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .067 | .099 | 1,090 | 8d | 2-1/2 | .113 | .155 | 147 |
| 3d | 1-1/4 | .076 | .113 | 654 | 9d | 2-3/4 | .113 | .155 | 133 |
| 4d | 1-1/2 | .080 | .120 | 489 | 10d | 3 | .128 | .170 | 96 |
| 5d | 1-3/4 | .080 | .120 | 414 | 12d | 3-1/4 | .128 | .170 | 88 |
| 6d | 2 | .099 | .142 | 244 | 16d | 3-1/2 | .135 | .177 | 74 |
| 7d | 2-1/4 | .099 | .142 | 215 | | | | | |


3.6.8 Type II, style 7 - Cooler nails. Steel wire, flat head, diamond point, round smooth shank, cement coated. When specified (see 6.2), coolers shall have an altered or T-head for use with mechanical drivers.



| S | * L | D | H | NO./LB | S | * L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .062 | .172 | 1,110 | 7d | 2-1/8 | .099 | .266 | 212 |
| 3d | 1-1/8 | .067 | .188 | 839 | 8d | 2-3/8 | .113 | .281 | 144 |
| 4d | 1-3/8 | .080 | .219 | 493 | 9d | 2-5/8 | .113 | .281 | 131 |
| 5d | 1-5/8 | .086 | .234 | 366 | 10d | 2-7/8 | .120 | .297 | 105 |
| 6d | 1-7/8 | .092 | .250 | 278 | | | | | |

* Overall length

3.6.9 Type II, style 8 - Sinker nails. Steel wire, flat countersunk head, diamond point, round smooth shank, cement coated. When specified (see 6.2), sinkers shall have an altered or T-head for use with mechanical drivers.




| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 3d | 1-1/8 | .067 | .172 | 923 | 12d | 3-1/8 | .135 | .312 | 91 |
| 4d | 1-3/8 | .080 | .203 | 527 | 16d | 3-1/4 | .148 | .344 | 64 |
| 5d | 1-5/8 | .086 | .219 | 387 | 20d | 3-3/4 | .177 | .375 | 40 |
| 6d | 1-7/8 | .092 | .234 | 293 | 30d | 4-1/4 | .192 | .406 | 30 |
| 7d | 2-1/8 | .099 | .250 | 223 | 40d | 4-3/4 | .207 | .438 | 23 |
| 8d | 2-3/8 | .113 | .266 | 153 | 60d | 5-3/4 | .244 | .500 | 14 |
| 10d | 2-7/8 | .120 | .291 | 111 | | | | | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.10 Type II, style 9-Corker nails. Steel wire, flat countersunk head, diamond point, round smooth shank, cement coated. When specified (see 6.2), corkers shall have an altered or T-head for use with mechanical drivers.



| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .062 | .156 | 1,217 | 10d | 2-7/8 | .135 | .312 | 89 |
| 3d | 1-1/4 | .072 | .188 | 720 | 12d | 3-1/8 | .135 | .312 | 81 |
| 4d | 1-1/2 | .086 | .219 | 419 | 16d | 3-3/8 | .148 | .344 | 62 |
| 5d | 1-5/8 | .086 | .219 | 387 | 20d | 3-7/8 | .177 | .375 | 38 |
| 6d | 1-7/8 | .099 | .250 | 253 | 30d | 4-3/8 | .192 | .406 | 29 |
| 7d | 2-1/8 | .099 | .250 | 223 | 40d | 4-7/8 | .207 | .438 | 22 |
| 8d | 2-3/8 | .120 | .281 | 135 | 50d | 5-3/8 | .226 | .469 | 17 |
| 9d | 2-5/8 | .120 | .281 | 122 | 60d | 5-7/8 | .244 | .500 | 13 |

3.6.11 Type II, style 10 - Common nails. Aluminum alloy wire, flat head, diamond point, round smooth shank or, when specified (see 6.2), square-barbed shank.



| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 4d | 1-1/2 | .099 | .250 | 825 | 10d | 3 | .162 | .312 | 170 |
| 6d | 2 | .120 | .266 | 430 | 16d | 3-1/2 | .177 | .344 | 120 |
| 8d | 2-1/2 | .148 | .281 | 220 | 20d | 4 | .199 | .406 | 78 |

3.6.11.1 Type II, style 10 - Common nails. Copper wire, flat head, diamond point, round smooth shank.

| L | D | NO./LB | L | D | NO./LB | L | D | NO./LB |
|---|---|---|---|---|---|---|---|---|
| 5/8 | .065 | 1,380 | 1-1/2 | .109 | 208 | 3 | .148 | 56 |
| 3/4 | .065 | 1,160 | 1-3/4 | .109 | 180 | 3-1/2 | .165 | 40 |
| 3/4 | .072 | 956 | 1-3/4 | .120 | 144 | 4 | .203 | 23 |
| 7/8 | .072 | 808 | 2 | .120 | 130 | 4-1/2 | .220 | 18 |
| 1 | .072 | 704 | 2 | .134 | 106 | 5 | .235 | 14 |
| 1-1/4 | .083 | 424 | 2-1/2 | .134 | 86 | 6 | .294 | 9 |

3.6.11.2 Type II, style 10 - Common nails. Steel wire, flat head, diamond point, round smooth shank, bright, zinc or cement coated, as specified (see 6.2).

| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .072 | .172 | 847 | 10d | 3 | .148 | .312 | 66 |
| 3d | 1-1/4 | .080 | .203 | 543 | 12d | 3-1/4 | .146 | .312 | 61 |
| 4d | 1-1/2 | .099 | .250 | 294 | 16d | 3-1/2 | .162 | .344 | 47 |
| 5d | 1-3/4 | .099 | .250 | 254 | 20d | 4 | .192 | .406 | 30 |
| 6d | 2 | .113 | .266 | 167 | 30d | 4-1/2 | .207 | .438 | 23 |
| 7d | 2-1/4 | .113 | .266 | 150 | 40d | 5 | .226 | .469 | 17 |
| 8d | 2-1/2 | .131 | .291 | 101 | 50d | 5-1/2 | .244 | .500 | 14 |
| 9d | 2-3/4 | .131 | .291 | 92 | 60d | 6 | .262 | .531 | 11 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.11.3 Type II, style 10 - Common nails. Aluminum alloy wire, bright or zinc coated steel wire, altered or T-head, diamond or chisel point, round smooth shank, as specified (see 6.2). For use with mechanical drivers.




| L | D | L | D | L | D | L | D | L | D | L | D |
|---|---|---|---|---|---|---|---|---|---|---|---|
| 1-1/4 | .080<br>.086<br>.092<br>.099 | 1-1/2 | .099<br>.113 | 1-3/4 | .080<br>.086<br>.092<br>.099<br>.113 | 1-7/8 | .080<br>.086<br>.092<br>.099<br>.113 | 2 | .080<br>.086<br>.092<br>.099<br>.113<br>.148 | 2-1/4 | .092<br>.099<br>.113 |
| 1-1/2 | .080<br>.086<br>.092 | 1-5/8 | .080<br>.086<br>.092<br>.099 | | | | | | | 2-1/2 | .092<br>.099<br>.113<br>.131 |
| | | | | | | | | | | 3-1/2 | .131 |

3.6.12 Type II, style 11 - Concrete nails. Hardened steel, flat countersunk head, diamond point, smooth or mechanically deformed shank formed from round or square stock, as specified (see 6.2), bright finish.




| L | D | H | NO./LB |
|---|---|---|---|
| 1/2 | .148 | .312 | 450 |
| 5/8 | .148 | .312 | 350 |
| 3/4 | .148 | .312 | 290 |
| 7/8 | .148 | .312 | 250 |
| 1 | .148 | .312 | 215 |



| L | D | H | NO./LB |
|---|---|---|---|
| 3/4 | .181 | .284 | 240 |
| 1 | .181 | .284 | 204 |
| 1-1/2 | .181 | .284 | 116 |
| 1-3/4 | .181 | .284 | 112 |
| 2 | .181 | .284 | 93 |
| 2-1/2 | .181 | .284 | 68 |
| 2-3/4 | .181 | .284 | 60 |
| 3 | .181 | .284 | 52 |

3.6.13 Type II, style 12 - Double-headed nails. Steel wire, flat heads, diamond point, round smooth shank, bright finish.




| S | L* | D | BETWEEN HEADS | NO./LB | S | L* | D | BETWEEN HEADS | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 6d | 1-3/4 | .113 | 1/4 | 156 | 16d | 3 | .162 | 3/8 | 45 |
| 8d | 2-1/4 | .131 | 1/4 | 90 | 20d | 3-1/2 | .192 | 3/8 | 28 |
| 10d | 2-3/4 | .148 | 5/16 | 59 | 30d | 4 | .207 | 7/16 | 22 |

3.6.14 Type II, style 13 - Fine nails. Steel wire, flat head, diamond point, round smooth shank, bright finish.



| S | L | D | H | NO./LB |
|---|---|---|---|---|
| 3d | 1-1/4 | .072 | .172 | 757 |




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.15 Type II, style 14 - Finish nails. Steel wire, brad head, altered or clipped T-head for use with mechanical drivers, diamond or chisel point, smooth or barbed shank formed from round or square stock, as specified (see 6.2), bright finish.




| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .058 | .086 | 1,473 | 8d | 2-1/2 | .099 | .142 | 190 |
| 3d | 1-1/4 | .067 | .099 | 880 | 9d | 2-3/4 | .099 | .142 | 178 |
| 4d | 1-1/2 | .072 | .106 | 630 | 10d | 3 | .113 | .155 | 124 |
| 5d | 1-3/4 | .072 | .106 | 535 | 12d | 3-1/4 | .113 | .155 | 113 |
| 6d | 2 | .092 | .135 | 288 | 16d | 3-1/2 | .120 | .162 | 93 |
| 7d | 2-1/4 | .092 | .135 | 254 | 20d | 4 | .135 | .177 | 65 |

3.6.16 Type II, style 15 - Flooring nails. Hardened steel or steel wire, casing head or flat cupped countersunk head, diamond or blunt point, round, smooth or mechanically deformed shank, dark (hardened), bright (steel wire) or cement coated, as specified (see 6.2).




| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .072 | .141 | 840 | 7d | 2-1/4 | .113 | .203 | 158 |
| 3d | 1-1/4 | .072 | .141 | 669 | *8d | 2-1/2 | .135 | .177 | 105 |
| 4d | 1-1/2 | .090 | .156 | 426 | 8d | 2-1/2 | .113 | .203 | 142 |
| 4d | 1-1/2 | .092 | .156 | 369 | 10d | 3 | .135 | .250 | 82 |
| 5d | 1-3/4 | .092 | .156 | 313 | 12d | 3-1/4 | .135 | .250 | 75 |
| 6d | 2 | .113 | .203 | 177 | 16d | 3-1/2 | .148 | .281 | 58 |

* smooth shank only.

3.6.17 Type II, style 16 - Lath nails. Steel wire, flat head, diamond point, round smooth shank, blued finish.



| S | L | D | H | NO./LB |
|---|---|---|---|---|
| 2d | 1 | .058 | .141 | 1,280 |
| 3d (Light) | 1-1/8 | .062 | .156 | 984 |
| 3d | 1-1/8 | .072 | .172 | 757 |

3.6.17.1 Type II, style 16 - Lath nails. Steel wire, flat hook-head, diamond point, round smooth shank, blued or zinc coated, as specified (see 6.2).



| L | D | H (LENGTH) | NO./LB |
|---|---|---|---|
| 1-1/8 | .106 | .438 | 279 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.18 Type II, style 17 - Masonry nails. Hardened steel, flat or flat countersunk head, diamond point, mechanically deformed shank, bright finish.



STANDARD

| L | D | H | NO./LB |
|---|---|---|---|
| 1/2 | | | 339 |
| 3/4 | | | 280 |
| 1 | | | 173 |
| 1-1/4 | | | 145 |
| 1-1/2 | | | 129 |
| 1-3/4 | .148 | .312 | 113 |
| 2 | | | 98 |
| 2-1/4 | | | 84 |
| 2-1/2 | | | 76 |
| 2-3/4 | | | 70 |
| 3 | | | 67 |
| 3-1/4 | | | 60 |
| 3-1/2 | .162 | .344 | 48 |
| 3-3/4 | .162 | .344 | 45 |
| 4 | .177 | .375 | 35 |

HEAVY

| L | D | H | NO./LB |
|---|---|---|---|
| 1 | | | 63 |
| 1-1/4 | | | 47 |
| 1-1/2 | | | 43 |
| 1-3/4 | .250 | .562 | 39 |
| 2 | | | 34 |
| 2-1/2 | | | 27 |
| 3-1/2 | | | 19 |
| 3 | | | 24 |

3.6.19 Type II, style 18 - Pallet nails. Hardened steel or steel wire (for mechanical drivers), flat head, altered or T-head (for mechanical drivers), diamond point, round, mechanically deformed shank, bright finish (steel wire) or dark (hardened), as specified (see 6.2).



| L | D | H | NO./LB |
|---|---|---|---|
| 1-1/2 | .120 | .281 | 188 |
| 1-5/8 | .120 | .281 | 175 |
| 2 | .120 | .281 | 144 |
| 2-1/4 | .120 | .281 | 129 |
| 2-1/2 | .120 | .281 | 117 |
| 2-1/2 | .135 | .312 | 93 |
| 3 | .120 | .281 | 98 |
| 3 | .135 | .312 | 79 |
| 3 | .148 | .312 | 66 |
| 3-1/4 | .135 | .312 | 73 |
| 3-1/4 | .148 | .312 | 61 |
| 3-1/2 | .148 | .312 | 57 |
| 3-1/2 | .162 | .375 | 47 |
| 3-1/2 | .177 | .438 | 38 |
| 4 | .177 | .438 | 35 |
| 4** | .177 | .375 | 35 |
| 5** | .177 | .375 | 27 |
| 6** | .177 | .375 | 23 |
| 7** | .207 | .500 | 15 |
| 8** | .207 | .500 | 13 |

Note: The shank of the nails shall have helical twists extending from the point at least 2/3 of the shank length.

** Formerly Type II, style 10.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.20 Type II, style 19 - Gypsum wallboard nails. Steel wire flat head, diamond point, round smooth shank, blued finish.



| L | D | H | NO./LB |
|---|---|---|---|
| 1-1/8 | .092 | .297 | 473 |
| 1-1/8 | .092 | .375 | 449 |
| 1-1/4 | .092 | .297 | 425 |
| 1-1/4 | .106 | .375 | 310 |
| 1-3/4 | .092 | .375 | 294 |

3.6.20.1 Type II, style 19 - Gypsum wallboard nails. Steel wire, flat slightly countersunk head, long diamond point, round mechanically deformed shank, bright or blued finish.



| L | D | H | NO./LB | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 1-1/8* | .099 | .250 | 380 | 1-1/2 | .099 | .250 | 290 |
| 1-1/4* | | | 345 | 1-5/8 | | | 270 |
| 1-3/8* | | | 320 | | | | |

* Recommended sizes

3.6.21 Type II, style 20 - Roofing nails. Aluminum alloy wire, flat head, diamond point, round smooth shank or, when specified (see 6.2), square-barbed shank.



| L | D | H | NO./LB | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 3/4 | .120 | | 936 | 1-1/4 | .120 | | 616 |
| 3/4 | .135 | | 746 | 1-1/4 | .135 | | 491 |
| 7/8 | .120 | | 832 | 1-1/2 | .120 | | 523 |
| 7/8 | .135 | .438 | 663 | 1-1/2 | .135 | .438 | 417 |
| 1 | .120 | | 759 | 1-3/4 | .135 | | 368 |
| 1 | .135 | | 605 | 2 | .135 | | 336 |
| 1* | .135 | .562 | 580 | 2-1/2 | .145 | | 227 |

* For prepared felt roofing.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.21.1 Type II, style 20 - Roofing nails. Steel wire, flat head, diamond point, round, smooth or barbed shank, bright or zinc coated, as specified (see 6.2).




| D | H | LENGTH & NO./LB | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | 3/4 | 7/8 | 1 | 1-1/8 | 1-1/4 | 1-1/2 | 1-3/4 |
| .106 | .281 | --- | --- | 384 | --- | --- | --- | --- |
| .106 | .375 | 464 | 406 | 361 | 325 | 295 | 249 | 216 |
| .120 | .312 | --- | --- | --- | --- | 240 | --- | --- |
| .120 | .438 | 340 | 300 | 267 | 241 | 220 | 187 | 162 |
| .120 | .500* | --- | 246 | 223 | --- | 189 | 164 | 145 |
| .135 | .469 | 274 | 241 | 215 | 194 | 176 | 150 | 130 |
| .142 | .484 | 241 | 212 | 189 | 171 | 156 | 133 | 116 |
| .148 | .500 | 222 | 195 | 174 | 158 | 144 | 122 | 106 |
| .162 | .500 | 197 | 172 | 153 | 138 | 125 | 106 | 92 |

* Checkered flat head

3.6.21.2 Type II, style 20 - Roofing nails. Copper-clad wire, flat head, diamond point, round smooth shank.


| S | L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | .120 | .375 | 280 | 5d | 1-3/4 | .120 | .375 | 160 |
| 3d | 1-1/4 | | | 220 | 6d | 2 | | | 140 |
| 4d | 1-1/2 | | | 190 | 7d | 2-1/4 | | | 130 |

3.6.21.3 Type II, style 20 - Roofing nails. Steel wire, leak resistant convex head, diamond point, round smooth shank, zinc coated.



| L | D | H | NO./LB |
|---|---|---|---|
| 1-3/4 | .135 | .500 | 105 |
| 2 | .135 | .500 | 98 |

3.6.21.4 Type II, style 20 - Roofing nails. Steel wire, flat reinforced head, needle or diamond point, round smooth shank, bright or zinc coated, as specified (see 6.2). (For prepared felt roofing)



| D | H | NO./LB | | | | |
|---|---|---|---|---|---|---|
| | | L-3/4 | L-7/8 | L-1 | L-1-1/8 | L-1-1/4 |
| .106 | .625 | 195 | 180 | 170 | 165 | 160 |
| .120 | .625 | 175 | 165 | 153 | 140 | 136 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.21.5 Type II, style 20 - Roofing nails. Steel wire one-inch flat integral steel cap, diamond point, round mechanically deformed shank, bright finish. (For roofing felts.)

| L | D | NO./LB | L | D | NO./LB |
|---|---|---|---|---|---|
| 1/2 | .106 | 128 | 1-1/4 | .106 | 104 |
| 5/8 | | 124 | 1-1/2 | .106 to .120 | 96 to 84 |
| 3/4 | | 115 | 1-3/4 | .106 to .120 | 94 to 78 |
| 7/8 | | 112 | 2 | .106 to .120 | 90 to 74 |
| 1 | | 110 | 2-1/2 | .106 to .120 | 80 to 61 |
| 1-1/8 | | 106 | 3 | .106 | 71 |

3.6.21.6 Type II, style 20 - Roofing nails. Steel wire, cast lead head, diamond point, round, barbed or ringed shank, bright finish.



| L | D | NO./LB | L | D | NO./LB |
|---|---|---|---|---|---|
| 1-1/2 | .148 | 98 | 1-1/2 | .135 | 115 |
| 1-3/4 | | 87 | 1-3/4 | | 106 |
| 2 | | 79 | 2 | | 93 |

3.6.21.7 Type II, style 20 - Roofing nails. Aluminum alloy wire, flat head with neoprene washer (for aluminum roofing sheet), diamond point, round, smooth or mechanically deformed shank, as specified (see 6.2).



| | SMOOTH SHANK | | | DEFORMED SHANK | | |
|---|---|---|---|---|---|---|
| L | D | H | NO./LB | D | H | NO./LB |
| 1-3/4 | .135 | .438 | 318 | .145 | .438 | 290 |
| 2 | .135 | | 285 | | | 259 |
| 2-1/4 | .135 | | 243 | | | 235 |
| 2-1/2 | .145 | | 208 | | | 215 |

3.6.22 Type II, style 21 - Shingle nails. Aluminum alloy wire, flat head, diamond point, round, smooth or mechanically deformed shank, as specified (see 6.2).



| DEFORMED SHANK | | | | SMOOTH SHANK | | | |
|---|---|---|---|---|---|---|---|
| L | D | H | NO./LB | L | D | H | NO./LB |
| 1-1/4 | .101 | .191 | 1,057 | 7/8 | .099 | .281 | 1,313 |
| 1-1/2 | .101 | .191 | 856 | 1-1/4 | .080 | .219 | 1,480 |
| 1-3/4 | .105 | .191 | 722 | 1-1/4 | .099 | .281 | 1,010 |
| 2 | .105 | .191 | 609 | 1-1/4 | .113 | .312 | 785 |
| 2-1/4 | .113 | .200 | 477 | 1-1/2 | .113 | .312 | 660 |
| 2-1/2 | .113 | .200 | 427 | 1-3/4 | .113 | .312 | 644 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.22.1 Type II, style 21 - Shingle nails. Steel wire, flat head, diamond point, round, smooth (standard) or barbed (for asbestos shingles) shank, bright or zinc coated, as specified (see 6.2).



| S | L | D | N | NO./LB |
|---|---|---|---|---|
| 3d | 1-1/4 | .092 | .250 | 411 |
| 3-1/2d | 1-3/8 | .099 | .281 | 312 |
| 4d | 1-1/2 | .106 | .281 | 257 |



| L | D | H | NO./LB |
|---|---|---|---|
| 1-1/4 | .113 | .406 | 247 |
| 1-1/2 | | | 210 |
| 1-3/4 | | | 183 |
| 2 | | | 162 |


3.6.23 Type II, style 22 - Siding nails. Aluminum alloy wire, flat head (insulated), casing or countersunk head (wood), as specified (see 6.2), diamond point, round smooth shank or, when specified (see 6.2), square-barbed shank.






| L | D | H | NO./LB | S | L | D | H | | NO./LB |
|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | CASING | CSK | |
| 1-1/2 | .113 | .219 | 701 | 6d | 1-7/8 | .106 | .141 | .266 | 604 |
| 1-1/2 | .113 | .312 | 659 | 7d | 2-1/8 | .113 | .141 | .266 | 468 |
| 2 | .113 | .219 | 495 | 8d | 2-3/8 | .128 | .156 | .297 | 319 |
| 2-1/2 | .135 | .219 | 295 | 10d | 2-7/8 | .148 | .189 | .312 | 197 |

3.6.24 Type II, style 23 - Slating nails. Aluminum alloy, copper or steel wire as specified (see 6.2). Aluminum and copper nails shall have a flat head (.312 to .375 dia.), diamond point and round smooth shank or, when specified (see 6.2), square-barbed shank. Steel nails shall have a flat, slightly countersunk head, diamond point, round smooth shank and bright finish.







| L | ALUMINUM | | COPPER | | STEEL | | | |
|---|---|---|---|---|---|---|---|---|
| | D | NO./LB | D | NO./LB | S | D | H | NO./LB |
| 7/8 | .106 | 1,170 | -- | -- | -- | -- | -- | -- |
| 1 | .106 | 1,050 | .109 | 292 | 2d | .106 | .312 | 425 |
| 1-1/4 | .106 | 867 | .109 | 240 | 3d | .128 | .375 | 229 |
| 1-1/4 | .120 | 618 | .120 | 208 | -- | -- | -- | -- |
| 1-1/4 | .135 | 519 | .135 | 164 | -- | -- | -- | -- |
| 1-1/2 | .120 | 529 | .109 | 204 | 4d | .128 | .375 | 190 |
| 1-1/2 | .135 | 435 | .120 | 164 | -- | -- | -- | -- |
| 1-1/2 | -- | -- | .135 | 132 | -- | -- | -- | -- |
| 1-3/4 | -- | -- | .135 | 116 | 5d | .135 | .406 | 144 |
| 2 | -- | -- | .135 | 104 | 6d | .148 | .438 | 104 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.25 Type II, style 24 - Rubber heel nails. Steel wire, flat or countersunk head, as specified (see 6.2), needle point, round smooth shank and bright finish.






| L | D | H | L | D | H |
|---|---|---|---|---|---|
| 5/8<br>3/4<br>7/8 | .080 | .154 | 1<br>1-1/8<br>1-1/4 | .080 | .154 |

3.6.26 Type II, style 25 - Underlayment nails. Steel wire, flat or flat, slightly countersunk head, diamond point, round, mechanically deformed shank and bright finish.



| L | D | H | NO./LB | S | L | D | H | NO./LB |
|---|---|---|---|---|---|---|---|---|
| 1 | .080 | .188 | 766 | -- | 1-1/2 | .099 | .250 | 328 |
| 1-1/4 | .080 | .188 | 600 | -- | 1-5/8 | .099 | .250 | 302 |
| 1-1/4 | .099 | .250 | 399 | -- | 1-3/4 | .099 | .250 | 279 |
| 1-3/8 | .080 | .188 | 545 | 6d | 1-7/8 | .106 | .266 | 175 |
| 1-3/8 | .099 | .250 | 360 | 7d | 2-1/8 | .109 | .266 | 171 |
| 1-1/2 | .080 | .188 | 496 | 8d | 2-3/8 | .113 | .297 | 141 |

3.6.27 Type II, style 26 - Square barbed nails. Steel wire, flat head, diamond point, square barbed shank and bright finish.




| S | L | DIAGONAL | SQ. DIM | H | NO./LB |
|---|---|---|---|---|---|
| 6d common | 2 | .113 | .080/.102 | .250 | 201 |
| 8d common | 2-1/2 | .131 | .092/.120 | .266 | 118 |
| 10d common | 3 | .148 | .105/.135 | .281 | 94 |
| 16d common | 3-1/2 | .162 | .113/.149 | .312 | 59 |
| 20d common | 4 | .192 | .135/.170 | .375 | 39 |
| 6d box | 2 | .099 | .072/.089 | .250 | 256 |
| 8d box | 2-1/2 | .113 | .080/.102 | .266 | 152 |
| 6d finish | 2 | .092 | .062/.083 | .124 | 320 |
| 8d finish | 2-1/2 | .099 | .072/.089 | .131 | 235 |
| 1-1/2 truss | 1-1/2 | .131 | .092/.120 | .281 | 191 |




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.6.28 Type II, style 27 - Masonry drive nails. Hardened steel, flat head, cone pilot point, round, high pitch, multiple-start threaded shank, bright finish. When specified (see 6.2), masonry drive nails shall be proof load tested in accordance with 4.4.6.



| S | L | THREAD DIA | S | L | THREAD DIA |
|---|---|---|---|---|---|
| 3/32 | 3/4 | .125 | 3/16 | 1-1/4 | .215 |
| 1/8 | 3/4 | .156 | 1/4 | 1-1/2 | .268 |
| 5/32 | 1 | .188 | 5/16 | 2 | .330 |

3.6.29 Type II, style 28 - Escutheon nails. Steel or brass wire, as specified (see 6.2), oval head, diamond point and round smooth shank.



| D | LENGTH | | | | | | |
|---|---|---|---|---|---|---|---|
| .035 | 1/4 | 1/2 | | | | | |
| .048 | 1/4 | 1/2 | 3/4 | 1 | | | |
| .062 | 1/4 | 1/2 | 3/4 | 1 | 1-1/4 | | |
| .072 | 1/4 | 1/2 | 3/4 | 1 | | | |
| .080 | 1/4 | 1/2 | 3/4 | 1 | 1-1/4 | 1-1/2 | 2 |
| .092 | | 1/2 | 3/4 | 1 | 1-1/4 | 1-1/2 | 2 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE I

STEEL WIRE GAGE
SPLIT GAGE NUMBERS AND DECIMAL EQUIVALENTS

| | | | | | | | |
|---|---|---|---|---|---|---|---|
| 7/0 | 1/4 | .490 | 6 | 1/4 | .192 | 18 | 1/4 | .0475 | 30 | 1/4 | .014 |
| | 1/2 | .481 | | 1/2 | .188 | | 1/2 | .0459 | | 1/2 | .0138 |
| | 3/4 | .476 | | 3/4 | .185 | | 3/4 | .0443 | | 3/4 | .0136 |
| | | .469 | | | .181 | | | .0426 | | | .0134 |
| 6/0 | 1/4 | .4615 | 7 | 1/4 | .177 | 19 | 1/4 | .0410 | 31 | 1/4 | .0132 |
| | 1/2 | .454 | | 1/2 | .173 | | 1/2 | .0394 | | 1/2 | .0131 |
| | 3/4 | .446 | | 3/4 | .170 | | 3/4 | .0379 | | 3/4 | .0130 |
| | | .438 | | | .166 | | | .0363 | | | .0129 |
| 5/0 | 1/4 | .4305 | 8 | 1/4 | .162 | 20 | 1/4 | .0348 | 32 | 1/4 | .0128 |
| | 1/2 | .421 | | 1/2 | .159 | | 1/2 | .0340 | | 1/2 | .0126 |
| | 3/4 | .413 | | 3/4 | .155 | | 3/4 | .0332 | | 3/4 | .0123 |
| | | .407 | | | .152 | | | .0325 | | | .0121 |
| 4/0 | 1/4 | .3938 | 9 | 1/4 | .1483 | 21 | 1/4 | .0317 | 33 | 1/4 | .0118 |
| | 1/2 | .386 | | 1/2 | .145 | | 1/2 | .0309 | | 1/2 | .0115 |
| | 3/4 | .379 | | 3/4 | .142 | | 3/4 | .0301 | | 3/4 | .0111 |
| | | .370 | | | .138 | | | .0294 | | | .0108 |
| 3/0 | 1/4 | .3625 | 10 | 1/4 | .135 | 22 | 1/4 | .0286 | 34 | 1/4 | .0104 |
| | 1/2 | .355 | | 1/2 | .131 | | 1/2 | .0279 | | 1/2 | .0102 |
| | 3/4 | .347 | | 3/4 | .128 | | 3/4 | .0272 | | 3/4 | .0100 |
| | | .339 | | | .124 | | | .0265 | | | .0097 |
| 2/0 | 1/4 | .331 | 11 | 1/4 | .1205 | 23 | 1/4 | .0258 | 35 | 1/4 | .0095 |
| | 1/2 | .325 | | 1/2 | .117 | | 1/2 | .0251 | | 1/2 | .0094 |
| | 3/4 | .319 | | 3/4 | .113 | | 3/4 | .0244 | | 3/4 | .0093 |
| | | .313 | | | .109 | | | .0237 | | | .0091 |
| 1/0 | 1/4 | .3065 | 12 | 1/4 | .1055 | 24 | 1/4 | .0230 | 36 | 1/4 | .0090 |
| | 1/2 | .301 | | 1/2 | .102 | | 1/2 | .0224 | | 1/2 | .0089 |
| | 3/4 | .295 | | 3/4 | .099 | | 3/4 | .0217 | | 3/4 | .0087 |
| | | .289 | | | .095 | | | .0211 | | | .0086 |
| 1 | 1/4 | .283 | 13 | 1/4 | .0915 | 25 | 1/4 | .0204 | 37 | 1/4 | .0085 |
| | 1/2 | .279 | | 1/2 | .089 | | 1/2 | .0199 | | 1/2 | .0084 |
| | 3/4 | .273 | | 3/4 | .086 | | 3/4 | .0193 | | 3/4 | .0083 |
| | | .268 | | | .083 | | | .0187 | | | .0081 |
| 2 | 1/4 | .2625 | 14 | 1/4 | .080 | 26 | 1/4 | .0181 | 38 | 1/4 | .0080 |
| | 1/2 | .258 | | 1/2 | .079 | | 1/2 | .0179 | | 1/2 | .0079 |
| | 3/4 | .253 | | 3/4 | .076 | | 3/4 | .0177 | | 3/4 | .0078 |
| | | .248 | | | .074 | | | .0174 | | | .0076 |
| 3 | 1/4 | .2437 | 15 | 1/4 | .072 | 27 | 1/4 | .0173 | 39 | 1/4 | .0075 |
| | 1/2 | .239 | | 1/2 | .070 | | 1/2 | .0170 | | 1/2 | .00737 |
| | 3/4 | .235 | | 3/4 | .067 | | 3/4 | .0168 | | 3/4 | .00725 |
| | | .230 | | | .064 | | | .0165 | | | .00712 |
| 4 | 1/4 | .2253 | 16 | 1/4 | .0625 | 28 | 1/4 | .0162 | 40 | 1/4 | .007 |
| | 1/2 | .221 | | 1/2 | .060 | | 1/2 | .0159 | | 1/2 | .0069 |
| | 3/4 | .216 | | 3/4 | .058 | | 3/4 | .0156 | | 3/4 | .0068 |
| | | .212 | | | .056 | | | .0153 | | | .0067 |
| 5 | 1/4 | .207 | 17 | 1/4 | .054 | 29 | 1/4 | .0150 | 41 | 1/4 | .0066 |
| | 1/2 | .203 | | 1/2 | .052 | | 1/2 | .0148 | | 1/2 | .0065 |
| | 3/4 | .200 | | 3/4 | .051 | | 3/4 | .0146 | | 3/4 | .0064 |
| | | .196 | | | .0491 | | | .0143 | | | .0063 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

3.7 Detail requirements, type III, staples. The requirements for each style staple shall be in accordance with the following tables, as specified (see 6.2).

3.7.1 In the following tables the various dimensions and other data are indicated as follows:

Hand driven staples


L - Inside leg length in inches
D - Wire diameter in inches
W - Inside width in inches
No./lb. - Approximate number per pound

Mechanically driven staples

L - Outside leg length in inches +1/32, -1/64
C - Outside crown width in inches ±1/32
T - Leg thickness in inches
W - Leg width in inches

TABLE II


Type III, Style 1 - Fence Staples. Steel wire, bright finish or zinc coated, as specified (see 6.2).




| L | D | NO./LB | L | D | NO./LB | L | D | NO./LB |
|---|---|---|---|---|---|---|---|---|
| 7/8 | .1483 | 122 | 1-1/8 | .1483 | 97 | 1-1/2 | .1483 | 72 |
| 1 | .1483 | 106 | 1-1/4 | .1483 | 87 | 1-3/4 | .1483 | 61 |

TABLE III

Type III, Style 2 - Poultry Netting Staples. Steel wire, zinc coated.



| L | D | NO./LB |
|---|---|---|
| 3/4 | .080 | 500 |




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE IV-A

Type III, Style 3 - Flat Top Crown Staples.

Steel wire, aluminum alloy wire or copper-clad wire; bright finish, zinc coated, cement coated or chemically etched, as specified (see 6.2). (For use in pneumatic or mechanical guns for fastening wood, and other materials to wood.)




| C CROWN WIDTH | 3/16 | 3/8 | 7/16 | 1/2 | 3/4 | 7/8 | 15/16 or 1 | 1-3/8 or 1-17/32 | 2-1/8 |
|---|---|---|---|---|---|---|---|---|---|
| * WIRE GAGE (T & W) | 18 | 14-16 -18 | 14-15 -16 | 14-15 -16 | 14-16 | 14-16 | 14-16 | 12 | 10 |
| L LEG LENGTH | 3/8 | 3/8 | 3/8 | -- | -- | -- | -- | -- | -- |
| | 1/2 | 1/2 | 1/2 | 1/2 | 1/2 | 1/2 | 1/2 | -- | -- |
| | 5/8 | 5/8 | 5/8 | 5/8 | 5/8 | 5/8 | 5/8 | -- | -- |
| | 3/4 | 3/4 | 3/4 | 3/4 | 3/4 | 3/4 | 3/4 | 3/4 | -- |
| | 7/8 | 7/8 | 7/8 | 7/8 | 7/8 | 7/8 | 7/8 | -- | -- |
| | 1 | -- | 1 | 1 | 1 | 1 | 1 | | 1 |
| | 1-1/8 | 1-1/8 | 1-1/8 | 1-1/8 | 1-1/8 | 1-1/8 | 1-1/8 | | |
| | 1-1/4 | 1-1/4 | 1-1/4 | 1-1/4 | 1-1/4 | 1-1/4 | 1-1/4 | | |
| | | 1-3/8 | 1-3/8 | 1-3/8 | 1-3/8 | 1-3/8 | 1-3/8 | | |
| | | 1-1/2 | 1-1/2 | 1-1/2 | 1-1/2 | 1-1/2 | 1-1/2 | | |
| | | 1-5/8 | 1-5/8 | 1-5/8 | 1-5/8 | 1-5/8 | | | |
| | | 1-3/4 | 1-3/4 | 1-3/4 | 1-3/4 | 1-3/4 | | | |
| | | | 1-7/8 | 1-7/8 | 1-7/8 | 1-7/8 | | | |
| | | | 2 | 2 | 2 | 2 | | | |
| | | | 2-1/4 | 2-1/4 | | | | | |
| | | | 2-1/2 | 2-1/2 | | | | | |

* Tolerances for round or round flattened wire.

| | | | |
|---|---|---|---|
| 18 Gage (.0475) | [.0435 +.0040 -.0060 T] | X | [.0475 +.0060 -.0020 W] |
| 16 Gage (.0625) | [.0570 +.0055 -.011 T] | X | [.0625 +.0075 -.0025 W] |
| 15 Gage (.0720) | [.0690 +.0030 -.0086 T] | X | [.0720 +.0086 -.0030 W] |
| 14 Gage (.0800) | [.0775 +.0025 -.0096 T] | X | [.0800 +.0096 -.0025 W] |
| 12 Gage (.1055) | [.1015 +.0040 -.0126 T] | X | [.1055 +.0126 -.0040 W] |
| 10 Gage (.1350) | [.1300 +.0050 -.0162 T] | X | [.1350 +.0162 -.0050 W] |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE IV-B

Type III, Style 3 - Flat Top Crown

Steel wire, chisel point, tin plated, zinc coated or lacquer finish, as specified (see 6.2); cohered together in strips. (For use in staple tackers or machines.) Number per strip shall be as specified (see 6.2) and shall be suitable for use in make and model of gun specified (see 6.2).

| CROWN WIDTH | .500 ±.015 | | | | .437 ±.010 | | .164 ±.015 | |
|---|---|---|---|---|---|---|---|---|
| WIRE ** SIZE | .020T x .030W | | .020T x .050W | | .020T x .050W | | .030T x .050W | |
| LEG LENGTH | 3/16 | +1/32 -1/64 | 1/4 | +1/32 -1/64 | 3/8 | +1/64 -0 | 3/8<br>1/2<br>5/8<br>3/4<br>7/8 | ±1/64 |
| | 1/4 | +1/32 -1/64 | 5/16 | +1/32 -1/64 | 1/2 | +1/64 -0 | | |
| | 5/16 | ±1/64 | 3/8 | +1/32 -1/64 | 9/16 | +1/64 -0 | 1<br>1-1/8<br>1-1/4 | |
| | | | 1/2 | ±1/64 | | | | |

* Inside dimension.

** Tolerances for thickness (T) and width (W) of wire are +.002, -.003.

TABLE IV-C

Type III, Style 3a - Round or "V"-Crown

Steel wire or copper-clad wire, bright finish, zinc coated, cement coated or chemically etched, as specified (see 6.2). (For use in pneumatic or mechanical guns for fastening wood and other materials to wood.)



| CROWN WIDTH | .346 +.015 -.000 | | .435 +.015 -.000 | |
|---|---|---|---|---|
| WIRE GAGE | 16 (.062) | | 16 (.062) | |
| LEG LENGTH | 1/2<br>9/16<br>5/8<br>3/4<br>7/8<br>1 | ±1/64 | 1/2<br>9/16<br>5/8<br>3/4<br>7/8<br>1 | ±1/64 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE V
Type III, Style 4 - Preformed Staples

Steel wire, zinc or cement coated, as specified (see 6.2). Copper-clad wire, tinned or other plated finish, as specified (see 6.2). (Hand driven)



CHISEL POINT STAPLES (COMMON)

| NO. | L | W | D | FLATTEN TO | POINT LENGTH | POINT ANGLE | NO./LB |
|---|---|---|---|---|---|---|---|
| 5 | 3/8 | 7/32 | .054 | .040 | 3/16 | 13° | 1,920 |
| 8 | 13/32 | 3/16 | .067 | .048 | 3/16 | 12° | 1,376 |
| 9 | 7/16 | 7/32 | .067 | .048 | 1/4 | 12° | 1,248 |
| 10 | 1/2 | 1/4 | .072 | .057 | 1/4 | 12° | 864 |
| 11 | 9/16 | 9/32 | .072 | .057 | 5/16 | 12° | 800 |
| 12 | 5/8 | 5/16 | .072 | .057 | 5/16 | 12° | 672 |
| 14 | 11/16 | 5/16 | .083 | .060 | 11/32 | 12° | 544 |
| 16 | 3/4 | 3/8 | .083 | .060 | 11/32 | 12° | 410 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

## ELECTRICAL STAPLES
(Insulated or uninsulated, as specified (see 6.2)

| L | W | D | FLATTEN TO | POINT LENGTH | POINT ANGLE | NO./LB |
|---|---|---|---|---|---|---|
| 3/8 | 5/32 | .067 | .048 | 1/4 | 12° | 1,440 |
| 1/2 | 3/16 | .072 | .057 | 1/4 | 12° | 992 |
| 5/8 | 1/4 | .072 | .057 | 5/16 | 12° | 736 |
| 3/4 | 3/16 | .083 | .060 | 11/32 | 12° | 480 |
| 3/4 | 1/4 | .083 | .060 | 11/32 | 12° | 450 |
| 7/8 | 1/4 | .083 | .060 | 11/32 | 12° | 400 |
| 7/8 | 7/16 | .083 | .060 | 11/32 | 12° | 375 |
| 1<br>1-1/4 | 1/2<br>5/8 | .120 | .050T x .215W | 3/8 | 18° | -- |

## HOOP STAPLES
(Inside dimensions)

### 1/2 Inch Wide

| L | D | FLATTEN TO | NO./LB | L | D | FLATTEN TO | NO./LB |
|---|---|---|---|---|---|---|---|
| 1/2 | .072 | .057 | 720 | 5/8 | .083 | .060 | 432 |
| 1/2 | .083 | .060 | 467 | 3/4 | .072 | .057 | 494 |
| 5/8 | .072 | .057 | 576 | 3/4 | .083 | .060 | 375 |

### 5/8 Inch Wide

| L | D | FLATTEN TO | NO./LB | L | D | FLATTEN TO | NO./LB |
|---|---|---|---|---|---|---|---|
| 1/2 | .072 | .057 | 628 | 5/8 | .083 | .060 | 400 |
| 1/2 | .083 | .060 | 471 | 3/4 | .072 | .057 | 460 |
| 5/8 | .072 | .057 | 532 | 3/4 | .083 | .060 | 340 |

### 3/4 Inch Wide

| L | D | FLATTEN TO | NO./LB | L | D | FLATTEN TO | NO./LB |
|---|---|---|---|---|---|---|---|
| 1/2 | .072 | .057 | 576 | 3/4 | .072 | .057 | 432 |
| 1/2 | .083 | .060 | 432 | 3/4 | .083 | .060 | 324 |
| 1/2 | .109 | .083 | 256 | 3/4 | .109 | .083 | 192 |
| 5/8 | .072 | .057 | 493 | 1 | .072 | .057 | 346 |
| 5/8 | .083 | .060 | 370 | 1 | .083 | .060 | 259 |
| 5/8 | .109 | .083 | 219 | 1 | .109 | .083 | 154 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

7/8 Inch Wide

| L | D | FLATTEN TO | NO./LB | L | D | FLATTEN TO | NO./LB |
|---|---|---|---|---|---|---|---|
| 1/2 | .072 | .057 | 531 | 3/4 | .072 | .057 | 406 |
| 1/2 | .083 | .060 | 400 | 3/4 | .083 | .060 | 305 |
| 5/8 | .072 | .057 | 461 | 7/8 | .072 | .057 | 364 |
| 5/8 | .083 | .060 | 345 | 7/8 | .083 | .060 | 273 |

1 Inch Wide

| L | D | FLATTEN TO | NO./LB | L | D | FLATTEN TO | NO./LB |
|---|---|---|---|---|---|---|---|
| 5/8 | .083 | .060 | 324 | 7/8 | .083 | .060 | 259 |
| 5/8 | .109 | .083 | 198 | 7/8 | .109 | .083 | 158 |
| 3/4 | .083 | .060 | 288 | 1 | .083 | .060 | 236 |
| 3/4 | .109 | .083 | 176 | 1 | .109 | .083 | 143 |

1-1/4 Inch Wide

| L | D | FLATTEN TO | NO./LB | L | D | FLATTEN TO | NO./LB |
|---|---|---|---|---|---|---|---|
| 3/4 | .083 | .060 | 216 | 1 | .083 | .060 | 179 |
| 3/4 | .109 | .083 | 130 | 1 | .109 | .083 | 120 |

3.8 Detail requirements, type IV, cut nails. Unless otherwise specified, cut nails shall be sheared from medium carbon sheet steel and shall have a wedge-shaped shank with a sheared-square point and narrower than the up-set head end. Other requirements shall be in accordance with the following tables, as specified (see 6.2).

3.8.1 In the following tables the various dimensions and other data are indicated as follows:

S - Commercial size designation
L - Length in inches
T - Thickness in inches
H - Head diameter in inches
No./Lb - Approximate number per pound.




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE VI

Type IV, Style 1 - Common Cut Nails

Steel or copper, flat head, bright finish or zinc coated, as specified (see 6.2).




| S | L | S | L | S | L | S | L | S | L |
|---|---|---|---|---|---|---|---|---|---|
| 2d | 1 | 5d | 1-3/4 | 9d | 2-3/4 | 16d | 3-1/2 | 40d | 5 |
| 3d | 1-1/4 | 6d | 2 | 10d | 3 | 20d | 4 | 50d | 5-1/2 |
| 3-1/2d | 1-3/8 | 7d | 2-1/4 | 12d | 3-1/4 | 30d | 4-1/2 | 60d | 6 |
| 4d | 1-1/2 | 8d | 2-1/2 | | | | | | |

TABLE VII

Type IV, Style 2 - Basket Cut Nails

Steel, flat head, bright finish




| L | T | H | NO./LB | L | T | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 5/8 | .049 | .180 | 2,080 | 7/8 | .058 | .203 | 1,056 |
| 3/4 | .049 | .180 | 1,504 | 1 | .058 | .220 | 928 |

TABLE VIII

Type IV, Style 3 - Clout Cut Nails

Steel, flat head, bright finish, blued or zinc coated, as specified (see 6.2).




| L | T | H | NO./LB | L | T | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 3/4 | .065 | .220 | 960 | 1 | .072 | .259 | 576 |
| 7/8 | .0685 | .238 | 768 | 1-1/4 | .0775 | .284 | 384 |

TABLE IX

Type IV, Style 4 - Trunk Cut Nails

Steel, oval head, bright finish, blued, brass or copper plated, as specified (see 6.2).



| L | T | H | NO./LB | L | T | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 3/4 | .072 | .2485 | 672 | 1 | .083 | .2715 | 448 |
| 7/8 | .072 | .2485 | 608 | 1-1/4 | .083 | .2715 | 352 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE X

Type IV, Style 5 - Cobblers Cut Nails

Steel, casing head, clinch point, bright finish or brass plated, as specified (see 6.2).



| L | T | H | NO./LB |
|---|---|---|---|
| 1/2 | .065 | .109 | 1,952 |
| 5/8 | .065 | .109 | 1,504 |
| 3/4 | .065 | .109 | 1,344 |

TABLE XI

Type IV, Style 6 - Extra-Iron Clinching Cut Nails

Steel, casing head, clinch point, bright finish or blued, as specified (see 6.2).



| L | T | H | NO./LB | L | T | H | NO./LB |
|---|---|---|---|---|---|---|---|
| 3/8 | .049 | .093 | 4,128 | 11/16 | .049 | .093 | 2,000 |
| 7/16 | | | 3,488 | 3/4 | .0535 | .101 | 1,640 |
| 1/2 | | | 3,040 | 13/16 | .0535 | .101 | 1,600 |
| 9/16 | | | 2,864 | 7/8 | .0535 | .101 | 1,520 |
| 5/8 | | | 2,256 | | | | |

TABLE XII

Type IV, Style 7 - Hob Cut Nails

Steel, square grooved head, clinch point, bright finish or blued, as specified (see 6.2).



| L | T | H | NO./LB |
|---|---|---|---|
| 7/16 | .134 | .380 | 268 |
| 1/2 | .134 | .380 | 264 |

3.9 Detail requirements, type V, spikes. The requirements for each style spike shall be in accordance with the following tables, as specified (see 6.2).

3.9.1 In the following tables the various dimensions and other data are indicated as follows:

S - Commercial size designation
L - Length in inches
H - Head diameter in inches
D - Wire diameter in inches



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE XIII

Type V, Style 1 - Common Cut Spikes

These spikes shall be sheared from medium carbon sheet steel and shall have a wedge-shaped shank with a square point end narrower than the upset head end. They shall have a flat head, bright finish or zinc coated, as specified (see 6.2).





| S | L | S | L | S | L |
|---|---|---|---|---|---|
| 20d | 4 | 50d | 5-1/2 | 80d | 7 |
| 30d | 4-1/2 | 60d | 6 | 100d | 8 |
| 40d | 5 | | | | |

TABLE XIV

Type V, Style 2 - Gutter Spikes

Steel wire, oval head, chisel point; flat head, diamond point; bright finish or zinc coated, as specified (see 6.2).






| L | D ±.004 | H FLAT | H OVAL |
|---|---|---|---|
| 6-1/2, 7, 8, 8-1/2, 9, 10, 10-1/2 | .250 | .562 | .531 |

TABLE XV

Type V, Style 3 - Round Spikes

Steel wire, oval countersunk head, chisel point; flat head, diamond point; bright finish or zinc coated, as specified (see 6.2).





| S | L | D ±.004 | H | L | D ±.004 | H |
|---|---|---|---|---|---|---|
| 40d | 5 | .2625 | .531 | 8 | .312 | .625 |
| 50d | 5-1/2 | .283 | .562 | 8 | .375 | .750 |
| 60d | 6 | .283 | .562 | 9 | .375 | .750 |
| -- | 7 | .312 | .625 | 10 | .375 | .750 |




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE XVI

Type V, Style 4 - Barge and Boat Spikes

Wrought iron, hot rolled steel rod or steel wire; square, diamond or oval head; chisel point; bright finish or zinc coated; as specified (see 6.2).



| D-SQUARE | H | L |
|---|---|---|
| 1/4 | 17/32 | 3, 3-1/2, 4, 5, 6, 7, 8 |
| 5/16 | 19/32 | 3-1/2, 4, 5, 6, 7, 8 |
| 3/8 | 11/16 | 3, 3-1/2, 4, 5, 6, 7, 8, 9, 10, 11, 12 |
| 7/16 | 13/16 | 6, 7, 8, 9, 10, 11, 12 |
| 1/2 | 1 | 6, 7, 8, 9, 10, 11, 12 |
| 5/8 | 1-1/8 | 8, 9, 10, 11, 12 |

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Quality assurance terms and definitions. Quality assurance terms and definitions used herein are in accordance with MIL-STD-109.

4.2 Inspection provisions.

4.2.1 Lot. A lot shall consist of all brads, nails, staples or spikes of the same type, style, size, material, finish, head style, shank style and point produced under essentially like conditions and offered for acceptance at any one time.

4.2.2 Sampling.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

4.2.2.1 Sampling for examination. A random sample of items shall be selected from each lot in accordance with Table XVII for examination. The acceptance number shall be as specified in the table.

TABLE XVII

Sampling for Examination

| Lot size - Number of kegs, pkgs. or containers in lot | Sample size - Number of kegs, pkgs. or containers in sample | Sample size - Number of items | Acceptance number of defectives |
|---|---|---|---|
| 2 to 15 | 2 | 14 | 1 |
| 16 to 40 | 3 | 24 | 3 |
| 41 to 110 | 5 | 35 | 5 |
| 111 to 300 | 7 | 49 | 6 |
| 301 to 500 | 10 | 70 | 9 |
| 501 to 1300 | 15 | 120 | 12 |
| 1301 to 3200 | 25 | 150 | 17 |
| 3201 to 8000 | 35 | 215 | 24 |
| 8001 and over | 50 | 300 | 32 |

4.2.2.2 Sampling for test of ductility, zinc coating, cement coating and proof load. A random sample of items shall be selected from each lot in accordance with Table XVIII for testing. The acceptance number shall be as specified in the table.

TABLE XVIII

Sampling for Tests

| Lot size - Number of kegs, pkgs. or containers in lot | Sample size - Number of kegs, pkgs. or containers in sample | Sample size - Number of items for each test | Acceptance number of defectives for each test |
|---|---|---|---|
| 2 to 15 | 2 | 4 | 0 |
| 16 to 40 | 3 | 6 | 0 |
| 41 to 110 | 5 | 10 | 0 |
| 111 to 300 | 7 | 14 | 1 |
| 301 to 500 | 10 | 20 | 1 |
| 501 to 1300 | 15 | 30 | 2 |
| 1301 to 3200 | 25 | 50 | 3 |
| 3201 to 8000 | 35 | 70 | 5 |
| 8001 and over | 50 | 100 | 6 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

4.2.2.3 Sampling for test of copper-clad wire. If the contract or order includes copper-clad items, the supplier shall furnish with the items five wire specimens, each not less than 12 inches long, certified to be representative of the wire used in the production of the items.

4.2.2.4 Sampling for test of aluminum wire. If the contract or order includes aluminum nails, the supplier shall furnish with the nails five wire specimens, each not less than 12 inches long, certified to be representative of the wire used in the production of the nails.

4.2.3 Material certification. When specified in the contract or order (see 6.2), the contractor shall furnish a certificate of the chemical composition of the aluminum alloy and copper used in the contract or order. Material thus certified shall be representative of the material used in the production of the items included in the contract or order.

4.3 Examination. Each item taken as specified in 4.2.2.1 shall be examined to determine conformance to this specification. Examination shall be conducted in accordance with Table XIX. Any item in the sample containing one or more defects shall be rejected, and if the number of defective items exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

TABLE XIX

Classification of Defects

| Categories | Defects | Inspection Method |
|---|---|---|
| Critical | None defined | |
| Major | | |
| 101 | Type, style and size not as specified (1.2.1) | Visual |
| 102 | Material and finish not as specified (3.1 and 3.2) | Visual |
| 103 | Length not as specified (3.4) | SIE* |
| 104 | Wire diameter (gauge) not as specified (Table I) | SIE |
| Minor | | |
| 201 | Other dimensions not as specified (3.4) | SIE |
| 202 | Workmanship (3.5) | Visual |
| 203 | Protective coating or finish missing or incomplete. Evidence of fins or lumps (3.2) | Visual |

* SIE = Standard Inspection Equipment



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

4.4 Tests.

4.4.1 Ductility. Samples selected in accordance with 4.2.2.2 shall be subjected to a ductility (bending) test to determine conformance to 3.1.1, 3.1.2, 3.1.3, 3.1.4, 3.1.5, 3.1.6, 3.1.7, or 3.1.8, as applicable. Items shall be bent by any suitable means available.

4.4.2 Zinc-coating (weight). Samples selected in accordance with 4.2.2.2 shall be tested for weight of the zinc coating to determine conformance to 3.2.1.1 and 3.2.1.2. The heads and points shall be cut from the samples and the weight of the zinc coating on the remaining lengths shall be determined in accordance with ASTM A90.

4.4.2.1 Zinc coating (electrodeposited). Examination and test of electrodeposited zinc coating shall be conducted in accordance with QQ-Z-325.

4.4.3 Cement coating (holding power). Samples selected in accordance with 4.2.2.2 shall be tested for holding power of cement coating in accordance with ASTM D1761 (Nail Withdrawal Test), except as modified herein. The nails shall be driven, perpendicular to the grain, into sound, dry western yellow pine, hemlock, fir or larch. Evidence of less than a 50 percent average increase in holding power, above that of an identical bright nail before cleaning, shall be cause for failure of the test. Nails shall be tested within 24 hours after driving.

4.4.4 Copper-cladding. Samples selected in accordance with 4.2.2.3 shall be subjected to tests of the thickness and weight of the copper-cladding to determine conformance to 3.1.5. The tests shall be as follows:

4.4.4.1 Thickness. Measurements of thickness of copper-cladding shall be made either by (a) accurately measuring the diameter of the wire before and after removing the cladding by any suitable means, (b) cutting off the wire, grinding smooth and etching the exposed cross section to differentiate between core and cladding, and measuring under suitable magnification or (c) using electrical indicating instruments of suitable accuracy.

4.4.4.2 Weight. The percentage of copper shall be determined by chemical analysis of a representative sample of the wire or by chemically stripping the copper and accurately weighing the sample of wire before and after stripping.

4.4.5 Aluminum (tensile strength). Samples of aluminum wire selected in accordance with 4.2.2.4 shall be subjected to a tensile strength test in accordance with ASTM B211 to determine conformance to 3.1.6.

4.4.6 Proof load (Type II, style 27 - masonry drive nails). When specified (see 6.2), samples selected in accordance with 4.2.2.2 shall be subjected to a proof load test. Proof loads shall be as specified below. The samples being tested shall not be removable when driven into



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

concrete of 3,000 p.s.i. compressive strength and subjected to the specified proof loads in an axial direction. The concrete shall show no evidence of failure attributable to the masonry nail itself.

| * Size (Inch) | Proof Loads (Lbs) |
|---|---|
| 5/32 | 240 |
| 3/16 | 400 |
| 1/4 | 1,200 |
| 5/16 | 1,300 |

Note: Recommended safe working load is one-fourth the proof load.
* Larger sizes shall have proof loads as specified (see 6.2).

4.5 Inspection of preparation for delivery. Preservation, packaging, packing and marking shall be examined to determine conformance to Section 5 of this specification.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be Level A, B or C, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit packaging.

5.1.1.1.1 Staples. Unless otherwise specified (see 6.2), staples of like sizes and description shall be packaged in quantities of 25 or 50 pounds, as specified (see 6.2). The containers shall conform to PPP-B-636, class weather resistant, V3C or V3S, style RSC, with liner and top and bottom pads. The liner shall be secured to the sides of the container with water resistant adhesive conforming to MMM-A-250, Type I or II as applicable. Closure shall be in accordance with the box specification. Optional containers shall conform to PPP-B-636, class weather resistant, V3C or V3S, style FTC and closed in accordance with the box specification.

5.1.1.1.2 Nails. Unless otherwise specified (see 6.2), nails of like size and description shall be packaged in quantities of 5 or 50 pounds, as specified (see 6.2). The 5 pound containers shall conform to PPP-B-636, class domestic, variety SW, grade 200, style optional and closed in accordance with the box specification. The 50 pound containers shall conform to PPP-B-636, class weather resistant, V3C or V3S, style RSC with liner and top and bottom pads. The liner shall be secured to the sides of the container with water resistant adhesive conforming to MMM-A-250, type I or II as applicable. Closure shall be in accordance with the box specification. Optional containers shall conform to PPP-B-636, class weather resistant, V3C or V3S, style FTC and closed in accordance with the box specification.

5.1.1.1.3 Brads. Brads of like size and description shall be packaged in quantities of 1/4 pound or 1 pound, as specified (see 6.2). Containers



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

shall conform to PPP-B-566, variety 1, style I or II, type and class optional and closed in accordance with the box specification.

5.1.1.1.4 Spikes. Spikes of like size and description shall be packaged in quantities of 50 pounds. Containers shall be as specified in 5.1.1.1.2.

5.1.1.1.5 Cohered staples, nails and brads. Cohered staples, nails and brads as used in pneumatic or mechanical guns shall be packaged as specified in (see 6.2).

5.1.1.2 Intermediate packaging.

5.1.1.2.1 Five pound packages. Five pound packages of nails of like size and description shall be intermediate packaged in quantities of 10 packages each. Containers shall conform to PPP-B-636, class weather resistant, V3C or V3S, style RSC and closed in accordance with the box specification.

5.1.1.2.2 Brads. Brads of like size and description shall be intermediate packaged in quantities of 100 each or 40 each of the 1/4 pound packages or 25 each or 10 each of the 1 pound packages, as specified (see 6.2). Containers shall conform to PPP-B-636, class weather resistant, W5C, style optional and closed in accordance with the box specification.

5.1.2 Level B.

5.1.2.1 Unit packaging.

5.1.2.1.1 Staples, nails and spikes. Staples, nails and spikes shall be packaged in accordance with 5.1.1.1.1, 5.1.1.1.2 or 5.1.1.1.4 respectively, except that the boxes and liners shall conform to PPP-B-636, class domestic, Grade 275.

5.1.2.1.2 Brads. Brads shall be packaged as specified in 5.1.1.1.3.

5.1.2.1.3 Cohered staples, nails and Brads. Cohered staples, nails and brads as used in pneumatic or mechanical guns shall be packaged as specified in (see 6.2).

5.1.2.2 Intermediate packaging.

5.1.2.2.1 Five pound packages. Five pound packages of nails of like size and description shall be intermediate packaged in accordance with 5.1.1.2.1, except that the boxes shall conform to PPP-B-636, class domestic, Grade 275.

5.1.2.2.2 Brads. Brads of like size and description shall be intermediate packaged as specified in 5.1.1.2.2, except that the boxes shall conform to PPP-B-636, class domestic, Grade 275.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

5.1.3 Level C (bulk). Bulk nails, brads, staples and spikes of like size and description shall be packaged in the quantities specified in 5.1.1. Packaging shall afford adequate protection against damage during direct shipment from supply source to first receiving activity. The supplier's standard practice may be used provided it fulfills the above requirements.

5.1.3.1 Level C (cohered). Cohered nails, brads and staples as used in pneumatic or mechanical guns shall be packaged in quantities according to the manufacturer's specifications (unless otherwise specified). Packaging shall afford adequate protection against damage during direct shipment from supply source to first receiving activity.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 Level A. Nails, brads, staples and spikes of like sizes and description, packaged as specified in 5.1, shall be packed in close-fitting wood cleated plywood boxes conforming to PPP-B-601, overseas type, style A, B, I or J, or in wood boxes conforming to PPP-B-621, class 2, style optional, type 2 load, as specified (see 6.2), up to the weight limitation of the container. Closure shall be in accordance with the appendix to the box specification. Strapping shall be zinc coated.

5.2.2 Level B. When specified (see 6.2), nails, brads, staples and spikes of like size and description, packaged as specified in 5.1, shall be palletized. The pallets shall conform to MH-P-71, type optional, size 2 and unitized in accordance with MIL-STD-147, load type I, except the horizontal top course strap shall not be required. For cohered nails and staples, pallets conforming to size 1 (32" x 40") of MH-P-71 may be used.

5.2.3 Level C. Nails, brads, staples and spikes of like size and description, packaged as specified in 5.1, shall be packed or palletized to afford adequate protection against damage during direct shipment from supply source to first receiving activity. Containers and packing shall comply with Uniform Freight Classification or National Motor Freight Classification.

5.3 Marking.

5.3.1 Civil agencies. Interior packages and shipping containers shall be marked in accordance with FED. STD. NO. 123.

5.3.2 Military agencies. Interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use.

6.1.1 Nails, brads and staples. Nails, brads and staples are intended for use in fastening wood and wood products. However, special



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

types of nails and staples are specifically intended for certain purposes; i.e. masonry fasteners, fastening roofing, electrical wiring and fences.

6.1.2 Cut and round spikes. Cut and round spikes are for general use in medium to heavy construction.

6.1.3 Gutter spikes. Gutter spikes are for use in installing roof gutters and eaves troughs.

6.1.4 Barge and boat spikes. Barge and boat spikes are for use in general marine construction.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Type and style required (see 1.2.1).
(c) Material (see 3.1).
(d) Protective coating or finish, if require and type of zinc coating, when required (see 3.2 and 3.2.1).
(e) Shape wire for formed or deformed shanks, when required (see 3.3.1).
(f) Make and model gun to be used for power driven nails or staples (see 3.3.2 or 3.3.3).
(g) Type and diameter of head and shank, type of point, width of staple, when required, and thickness of cut nails, when required (see 3.4, 3.6, 3.7 and 3.8).
(h) Length required (see 3.4, 3.6, 3.7 and 3.8).
(i) Whether insulated or uninsulated electrical staples are required (see Table V).
(j) Material certification, when required (see 4.2.3).
(k) When proof load test of masonry nails is required (see 4.4.6).
(l) Proof loads of masonry nails, when required (see 4.4.6).
(m) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(n) Weight per unit package, when required (see 5.1.1).
(o) Quantity per intermediate package, when required (see 5.1.1.2.2).
(p) Packaging requirements for cohered nails, brads and staples (see 5.1.1.1.5 and 5.1.2.1).
(q) When palletization is required (see 5.2.2).

6.3 Supersession data. This specification includes the requirements of FF-S-606 dated August 29, 1958; FF-N-103C in part, dated 24 July 1964; and FF-S-325 in part, dated September 10, 1957.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

6.4 Cross reference data. Cross reference between types, styles and groups of FF-S-606, FF-N-103C and FF-S-325 and the types and styles of this specification are as follows:

| FF-S-606 | FF-N-105B |
|---|---|
| Common cut spikes | Type V, Style 1 |
| Common cut nails | Type IV, Style 1 |
| Wire gutter spikes | Type V, Style 2 |
| Round wire spikes | Type V, Style 3 |
| Wrought Barge and boat spikes | Type V, Style 4 |

| FF-N-103C | FF-N-105B |
|---|---|
| Type I, Style 1 | Type IV, Style 2 |
| Type I, Style 2 | Type IV, Style 3 |
| Type I, Style 3 | Type IV, Style 4 |
| Type II, Style 5 | Type III, Style 4 |
| Type III, Style 1 | Type IV, Style 5 |
| Type III, Style 2 | Type IV, Style 6 |
| Type III, Style 3 | Type IV, Style 7 |

| FF-S-325 | FF-N-105B |
|---|---|
| Group VII | Type II, Style 17 |

MILITARY CUSTODIANS:

Army - MC
Navy - YD
Air Force - 82

Reviewer activities:

Army - GL
Navy - SA
Air Force - None
DSA - IS, GS
NSA

User activities:

Army - AV, CE, ME, MI
Navy - AS, MC, SH
Air Force - None

Preparing activity:

Army - MC

CIVIL AGENCIES INTEREST:
CSA
IC
JUS
Agr

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| | |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR<br>☐ USER<br>☐ MANUFACTURER<br>☐ OTHER *(Specify)*: |
| b. ADDRESS *(Street, City, State, ZIP Code)* | |
| | |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |
| | |

DD FORM 32 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.