MIL-C-3372E
13 September 1982
SUPERSEDING
MIL-C-3372D
20 March 1973

MILITARY SPECIFICATION

CASE, TENTAGE REPAIR KIT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type and size tentage repair kit case made of cotton duck and webbing.

2. APPLICABLE DOCUMENTS

2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

C-F-206	-	Felt Sheet: Cloth, Felt, Wool, Pressed.
T-T-881	-	Twine, Cotton, Seine.
V-T-285	-	Thread, Polyester.
KK-L-271	-	Leather, Cattlehide, Strap, Vegetable Tanned.
CCC-C-419	-	Cloth, Duck, Cotton, Unbleached, Plied-Yarns, Army and Numbered.
CCC-D-950	-	Dyeing and Aftertreating Processes for Cotton Cloths.
DDD-L-20	-	Label; For Clothing, Equipage and Tentage, (General Use).
PPP-B-636	-	Boxes, Shipping, Fiberboard.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Natick Research and Development Laboratories, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8340

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-C-496	-	Clips, End, Strap.
MIL-W-530	-	Webbing, Textile, Cotton, General Purpose, Natural or in Colors.
MIL-B-543	-	Buckles, Tongueless and Web strap.
MIL-F-2312	-	Felt, Hair or Wool: Mildew Resistant, and Moisture Resistant, Treatment for.
MIL-R-3390	-	Rings, Dee.
MIL-F-10884	-	Fasteners, Snap.
MIL-T-43566	-	Tape, Textile, Cotton, General Purpose, Natural or in Colors.

STANDARDS

FEDERAL

FED-STD-751	-	Stitches, Seams and Stitchings.

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.
MIL-STD-1188	-	Commercial Packaging of Supplies and Equipment.

DRAWINGS

US ARMY NATICK RESEARCH AND DEVELOPMENT LABORATORIES

5-7-54	-	Case, Tentage Repair Kit; Illustration, Assemblies and Details.
5-7-55	-	Assemblies and Details.
5-7-56	-	Details.

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

* 2.2 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

* 3.1 First article. When specified, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

* 3.2 Materials (see 6.5) and components.

3.2.1 Cloth, duck, cotton. Cloth, before finishing, shall conform to type I, No. 6, hard texture of CCC-C-419 for the body of the case and to type III, 8.25 ounces per square yard of CCC-C-419 for pockets "D" and bags for rings and grommets.

3.2.1.1 Color and treatment. The finished cloth shall conform to type I, class B of CCC-D-950, shade Olive Drab 7.

3.2.2 Tape, textile, cotton. Cotton tape shall conform to type I, class 4 of MIL-T-43566, 1-inch width, shade Olive Drab 7.

3.2.3 Webbing, textile, cotton. Cotton webbing shall conform to type II and type IIb, class 4 of MIL-W-530, shade Olive Drab 7. Type II webbing shall be 2-inch width and type IIb shall be one inch width.

3.2.4 Thread, polyester. The thread shall conform to type I, class 1, sub-class B, dyed to match shade Olive Drab S-1 (CA 66022) of V-T-285. Dyed thread shall show fastness to chlorine bleaching equal to or better than the standard shade sample. If no standard shade sample is available, the thread shall show good fastness to weathering. Thread sizes shall be as follows:

For all stitching except overedge stitching	Size FF for needle and bobbin
For overedge stitching	Size E

3.2.5 Felt. The pressed wool felt shall conform to type I, classification number 9R5, of C-F-206 and shall be mildew resistant treated to conform to type I of MIL-F-2312.

3.2.6 Leather. The leather shall conform to any type, class 1 of KK-L-271, 6 ounce color russet. Application of a finish to the grain side is not required.

3.2.7 Twine, cotton, seine. The cotton seine twine shall conform to type II, size number 120 of T-T-881.

3.2.8 Buckle, tongueless, 2-bar. The buckles shall conform to type II, style 1, class 1 of MIL-B-543.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

3.2.9 Clip, end, strap. The end clips shall conform to type I, class 1, size 1-inch of MIL-C-496.

* 3.2.10 Fasteners, snap. The snap fasteners shall conform to style 1, finish 2, regular prong socket and stud, eyelet base with washer, size 1; and style 2, finish 2, button, 24 line, size 1, of MIL-F-10884.

3.2.11 Ring, dee. The dee ring shall conform to configuration K, class 1 or 2, size 1-inch of MIL-R-3390.

3.3 Construction. The construction of the case and bags for rings and grommets shall conform to the drawings listed in section 2 and as specified herein.

3.3.1 Stitching, machine.

3.3.1.1 Types of stitching. All stitch types shall conform to FED-STD-751 as follows:

For all stitching except overedge stitching	Type 301, 6 to 8 stitches per inch
For overedge stitching	Type 304, 14 to 16 stitches per inch; types 502, 504 or 505, 6 to 8 stitches per inch

3.3.1.2 Thread breaks. Thread breaks in stitching shall be overstitched not less than 1 inch at each break on stitch type 301 and not less than 3/4 inch at each break on stitch types 304, 503, 504 or 505. Thread breaks noted during inspection shall be repaired by starting the overstitching at least 1 inch before the break and ending it at least 1 inch beyond the break. The ends of repair stitching are not required to be backstitched.

3.3.1.3 Stitching ends. The ends of type 301 stitching shall be overstitched not less than 1 inch except where ends are turned under in a hem or held down by other stitching. Where 301 stitching is performed automatically on stitch patterns such as box, box with cross-stitch, "W" stitching or straight line tacking, at least 3 or more tying, overlapping or backstitches shall be used to secure the ends of stitching. The ends of type 304, 503, 504 or 505 stitching shall be firmly secured by backstitching or overstitching or by increasing the number of stitches per inch at the ends for a minimum of 1/4 inch.

3.3.1.4 Skipped stitches. Two or more consecutively skipped stitches occurring in type 301, 304, 503, 504 or 505 stitching shall be overstitched not less than 1 inch. Skipped stitches noted during inspection shall be repaired in the same manner as specified under thread breaks.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

3.3.1.5 Lubrication of thread. The addition of any lubricant to the polyester thread prior to or during the sewing operation is prohibited.

3.3.2 Setting of end clips. The webbing shall be inserted the full depth of the clip. Clips shall be securely attached without cutting the webbing and the webbing shall lie flat at the point of entrance.

3.3.3 Setting of snap fasteners.

* 3.3.3.1 Style 1. The hole for the male part of the snap fastener shall be formed when the fastener is driven into the material. The hole punched before insertion of the female part of the fastener shall be no larger than that made by a standard number 10 round drive punch (5/16 inch diameter hole). Fasteners shall be securely clinched. Not more than one score or split shall be allowed on the roll of the eyelet base of the stud.

* 3.3.3.2 Style 2. When a hole is punched before insertion of the male or female part of the fastener it shall be smaller than the outside diameter of the fastener tube so that the tube must be forced through the hole. Fasteners shall be securely clinched. Not more than one score or split shall be allowed on the roll of the eyelet of either male or female half of the fastener.

3.4 Marking. Identification marking shall be applied in the location shown on the drawing and shall conform to type IV, class 5 labels of DDD-L-20. The letters "U.S.", the item name, list of contents, pocket numbers and bag markings shall be located and applied in the size characters indicated on the drawings and shall conform to type IV, class 9 labels of DDD-L-20. Fastness of class 9 marking shall be as specified for the class 5 labels.

* 3.4.1 List of contents. The list of contents shall be as follows:

List of contents

Pocket No.	Item	Quantity
1	Cloth, duck, cotton, OD 9.85 ounce, FWWMR, 29-1/2 inch	8 yd
1	Grommet, metallic, black chemical finish, rolled rim w/washer, spur type, No. 4 (in bag)	1 gr
1	Grommet, metallic, black chemical finish, rolled rim w/washer, spur type, No. 5 (in bag)	1 hd

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

List of contents (cont'd)

Pocket No.	Item	Quantity
1	Mallet, rawhide, 2-3/4 inch face	1 ea
1	FM 10-16, Field Manual General Repair for Tents, Canvas and Webbing	1 ea
1	Palm, sewing	1 ea
1	Punch and die, inserting, spur grommet No. 4 (in bag)	1 ea
1	Punch and die, inserting, spur grommet No. 5 (in bag)	1 ea
1	Ring, connecting, round, galvanized, 1/2 inch (in bag)	50 ea
1	Ring, connecting, round, galvanized, 3/4 inch (in bag)	25 ea
1	Ring, connecting, round, galvanized, 1 inch (in bag)	10 ea
1	Sling, carrying, bag and case	1 ea
1	Slip, tent line, magnesium casting	10 ea
1	Twine, cotton, wrapping, 5-ply, MRT	1 lb
2	Thread, polyester, type I or II, class 1, size FF	1 tu
2, 3	Adhesive, nitrile butadiene rubber, tent patching (1/2 pt. cans)	8 cn
4	Needle, sailmaker's, No. 14	12 ea
5	Brush, wire, scratch	1 ea
6	Punch, cutting, for No. 4 grommet	1 ea
7	Awl, sadler's sewing	1 ea

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

List of contents (cont'd)

Pocket No.	Item	Quantity
8	Lubricant, slide fastener	1 bx (24 sticks)
9	Punch, cutting, for No. 5 grommet	1 ea
10	Shears, bent trimmers, length overall, 10 inches	1 ea

3.5 Workmanship. Cloth components shall be clean and free of holes, cuts, tears or cloth defects such as multiple floats or broken or missing yarns. Webbing and tape shall not have frayed or scalloped edges. Thread tension shall be maintained so that there will be no loose stitching and seam allowances shall be maintained with seams properly sewed so that no runoffs, twists, pleats or open seams shall result. Care shall be taken in sewing to see that no needle chews occur. All thread ends shall be trimmed to 1/2 inch or less. Metal components shall be free of burrs, sharp edges, or corroded areas and shall not be broken or malformed.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for defects listed in 4.4.3.1 and dimensions specified. The presence of any defect not within the specified requirements shall be cause for rejection of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this document or applicable purchase document.

* 4.4.2 In-process inspection. Inspection shall be made during the manufacturing process to insure that no lubrication of polyester thread prior to or during sewing operations for compliance with 3.3.1.5. In addition, inspection shall be made to insure that holes punched to receive female part of style 1 snap fasteners or male and female part of style 2 snap fasteners shall be smaller in diameter than the tube of the parts to be inserted for compliance with 3.3.3. Whenever nonconformance is noted, corrections shall be made to the parts affected and lot in-process. Components which cannot be corrected shall be removed from production.

* 4.4.3 End item inspection. Defects found during the examination shall be classified in accordance with the list shown in 4.4.3.1. The lot size shall be expressed in units of repair kit cases with parts bags. The sample size shall be one completely fabricated repair kit case with parts bags. The inspection level shall be II and the acceptable quality levels (AQLs) shall be 2.5 major, 6.5 major and minor A and 15.0 total (major and minor combined) defects per hundred units.

* 4.4.3.1 Visual examination.

Examine	Defect	Classification Major	Minor A	Minor B
Fabric	Any hole, cut or tear	X		
	Broken or missing yarn, multiple floats clearly visible at normal inspection distance (approximately 3 feet)		X	
Felt	Any hole, cut or tear		X	
Leather (shears scabbard)	Hole, cut or tear	X		
	Loose, spongy, flanky, weak or thin spot		X	
	Scabbard not removable from pocket; corners not clipped as specified			X
	Fabricated with flesh side on inside		X	
	Not color specified			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor A	Minor B
Hardware	Broken	X		
	Malformed:			
	-fails to perform intended function	X		
	-will perform intended function		X	
	Corroded area			X
	Burr or sharp edge which may cause injury in handling or damage to fabric	X		
End clips	Webbing not flat at point of entrance into clip			X
	Clinched tight, cutting webbing	X		
Seams and stitching	Open seam on stitch type 301:			
	-for more than 1 inch	X		
	-for more than 1/2 inch but not more than 1 inch		X	
	-for more than 1/4 inch but not more than 1/2 inch			X
	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken, or when one or more skipped or runoff stitches occur. On double stitched seams, a seam shall be classified as open when either one or both sides of a seam are open.			
	Raw edges caught in stitching (except end of inside binding):			
	-more than 1 inch		X	
	-more than 1/2 inch but not more than 1 inch			X
	Thread breaks:			
	-overstitched less than 1 inch on stitch type 301			X
	-overstitched less than 3/4 inch on stitch type 304			X
	NOTE: Thread breaks not overstitched shall be classified as open seams.			

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor A	Minor B
Seams and stitching (cont'd)	Needle chew resulting in hole, cut or tear	X		
	Skipped stitches overstitched less than 1 inch on stitch type 301, 304, 503, 504, or 505 when 2 or more skipped stitches occur consecutively			X
	NOTE: Skipped stitches not overstitched shall be classified as open seams.			
	One or more required rows of stitching omitted (except on boxstitching)	X		
Boxstitching	Incomplete:			
	-one row of stitching omitted			X
	-two or more rows of stitching omitted		X	
	Any boxstitching less than specified length by more than 1/8 inch			X
Stitching ends	Overstitched less than 1 inch on stitch type 301 (except where ends are held down by other stitching, turned under in a hem, or where stitching is performed automatically)		X	
	Secured with less than 3 tying, overlapping or backstitches where automatic stitching is performed			X
	Secured with less than 1/4 inch of backstitching, overstitching or by an increased number of stitches at the end of stitch type 304, 503, 504 or 505			X
Seam type	Wrong seam type	X		
Stitch type	Wrong stitch type		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor A	Minor B
Stitch tension	Loose, resulting in exposed bobbin or top thread for more than 2 inches			X
	Tight, as evidenced by puckering of fabric for more than 2 inches		X	
Stitches per inch	Less than minimum specified:			
	-one stitch			X
	-two or more stitches		X	
	More than maximum specified:			
	-one stitch			X
	-two or more stitches		X	
	NOTE: Variation in the number of stitches per inch caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy seams or heavy places or in turning corners shall be classified as follows:			
	a. Within the minor B defect classification -no defect			
	b. Within the minor A defect classification -minor B defect			
Stitching margin	Larger than specified by more than 1/8-inch:			
	-for more than 1 inch but not more than 2 inches in length			X
	-for more than 2 inches in length		X	
	Less than specified:			
	-for more than 1 inch but not more than 2 inches in length			X
	-for more than 2 inches in length		X	
Components and assembly	Any component part not fabricated of applicable referenced material	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor A	Minor B
Construction details				
Facing	Ends of facing A or B not caught in binding stitching		X	
Pockets and bags	Fold of pocket piece B not formed as specified, or not stitched through body and handle where applicable		X	
	Stitching across bottom of pockets 6 through 9 omitted, or interferes with clearance in pockets 5 or 10		X	
Drawstring	Drawstring cut or abraded		X	
	Drawstring caught in hem stitching causing failure to draw freely		X	
	Drawstring hem improperly formed, badly puckered, twisted or pleated			X
Binding	Loosely or improperly applied: -badly pleated			X
	-ends of binding not finished as specified			X
Buckle chape and strap	Buckle reversed		X	
	Misplaced; i.e. failing to effect a smooth and secure closure		X	
	Chape reinforcement improperly applied	X		
Handles	Set beyond location indicated on drawing by more than 1/4 inch		X	
	Edges of grip section overlapped; edges not folded or not stitched as indicated on drawing		X	
	Ends of carrying strap not finished as specified		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor A	Minor B
Snap fasteners	Not functioning properly	X		
	Not securely clinched, allowing components to separate	X		
	Clinched excessively tight, cutting surrounding fabric	X		
	Two or more splits on roll of any eyelet		X	
Marking: "U.S.", nomenclature, identification, list of contents, numbering of pockets	Omitted, incorrect, illegible or size of characters not as specified		X	
Cleanness	Grease or oil stains			X
	Thread ends not trimmed to 1/2 inch or less throughout			X
	Ink spots or stains		X	

4.4.3.2 Dimensional examination. The repair kit case with included parts bags shall be examined for compliance with dimensions specified on drawings. Any dimension that is not within the specified requirements shall be classified as a defect. The inspection level shall be S-3 and the AQL shall be 10.0, expressed in terms of defects per hundred units.

* 4.4.4 Packaging inspection. An examination shall be made to determine that preservation, packing and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully packaged. The lot size shall be the number of shipping containers offered in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

Examine	Defect
Marking	Omitted, incorrect, illegible, of improper size, location, sequence or method of application
Materials	Any component missing, damaged or not as specified
Workmanship	Bulging or distortion of containers
Content	Number per container is more, or less, than required

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

5. PACKAGING

* 5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each case shall be laid out flat with flaps extended. The two cotton bags shall be placed within the large pocket and the pocket then pressed flat by hand. The "A" billets shall be laid out flat, the "B" billets shall be folded over and laid flat, and the flaps snap fastened. The case shall then be folded in half and securely closed by buckling the "C" billets. The case shall again be folded in half with the U.S. facing up. The folded case shall measure 16-1/2 inches in length, 9-3/4 inches in width and 2-1/4 inches in depth.

* 5.1.2 Commercial. Each complete tentage repair kit case shall be preserved in accordance with MIL-STD-1188.

* 5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

* 5.2.1 Level A packing. Twenty cases preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container, conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Level A unit packs shall be packed on end 10 in length, 2 in width, and 1 in depth within a shipping container. Inside dimensions of each container shall approximate 22-1/2 inches in length, 19-1/2 inches in width, and 16-1/2 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

* 5.2.2 Level B packing. Twenty cases, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Level A unit packs shall be packed on end 10 in length, 2 in width and 1 in depth within a shipping container. Inside dimensions of each container shall approximate 22-1/2 inches in length, 19-1/2 inches in width, and 16-1/2 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

* 5.2.2.1 Weather-resistant fiberboard container. When specified, (see 6.2) the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of the container specification, except the inspection shall be in accordance with 4.4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

* 5.2.3 Commercial. Cases, preserved as specified in 5.1, shall be packed in accordance with MIL-STD-1188.

* 5.3 Marking. In addition to any special marking required by the contract, or purchase order, shipping containers shall be marked in accordance with MIL-STD-129 or MIL-STD-1188, as applicable.

6. NOTES

6.1 Intended use. The case covered by this document is designed to contain tools, materials, and components used in the repair of tentage items.

6.2 Ordering data. Aquisition documents should specify the following:

(a) Title, number and date of this document.
(b) When a first article is required (see 3.1, 4.3 and 6.4).
(c) Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
(d) When weather-resistant fiberboard is required for level B shipments (see 5.2.2.1).

6.3 For access to a standard shade sample of thread, address the procuring activity issuing the invitation for bids.

* 6.4 First article. When a first article sample is required, it shall be inspected and approved under the appropriate provisions of DAR 7-104.55. The first article should be a preproduction sample, consisting of one tentage repair kit case. The contracting officer should include specific instructions in all acquisition documents regarding arrangements for inspection and approval of the first article.

* 6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the document (see 3.2).

* 6.6 International standardization agreements. Certain provisions of this document are the subject of international standardization agreement as cited in NATO, STANAG No. 2882, relative to camouflage requirements for tents, shelters and subsidiary components. When amendment, revision, or cancellation of this document is proposed which will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

6.7 Changes from previous issue. The margins of this document have been marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content as written irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - MC
Air Force - 99

Preparing activity:

Army - GL

Project No. 8340-0435

Review activity:

Army - MD

User activity:

Air Force - 45

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T17:35Z
Check the source to verify that this is the current version before use.