MILITARY SPECIFICATION SHEET

TUBING, ELASTOMERIC, RUBBER, ELECTRICALLY INSULATING, ABRASION RESISTANT, POLYCHLOROPRENE, FLEXIBLE, HEAT SHRINKABLE: SHRINK RATIO 1.75 TO 1.

The complete requirements for procuring the rubber tubing described herein shall consist of this document and the issue in effect of MIL-K-81786(AS).

REQUIREMENTS: The tubing shall meet the requirements of MIL-R-46846

Sizes - See table I
Type - tubular
Material - Polychloroprene Rubber
Color - Black
Length - 48 inches

TABLE I

Part No.	Dimensions(inches)			
	As Supplied	After Heating		
	ID, min	ID, max	Nominal Wall Thickness	Wall Thickness Tolerance
M81786 /4-1	.250	.143	.035	± .010
M81786 /4-2	.375	.214	.040	± .010
M81786 /4-3	.500	.286	.048	± .015
M81786 /4-4	.625	.357	.052	± .015
M81786 /4-5	.750	.428	.057	± .015
M81786 /4-6	.875	.500	.065	± .015
M81786 /4-7	1.000	.570	.070	± .020
M81786 /4-8	1.250	.714	.087	± .020
M81786 /4-9	1.500	.857	.095	± .020
M81786 /4-10	1.750	1.000	.107	± .020

Preparing Activity:
Navy-AS

FSC-4940

☆ U. S. GOVERNMENT PRINTING OFFICE: 1974-713-154/6018

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:09Z
Check the source to verify that this is the current version before use.