The documentation and process conversion measures necessary to comply with this document shall be completed by 19 July 2025.

INCH-POUND

MIL-PRF-19500/627C
w/AMENDMENT 2
19 February 2025
SUPERSEDING
MIL-PRF-19500/627C
w/AMENDMENT 1
29 October 2019

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER, ULTRA-FAST RECOVERY, TYPES 1N6688 AND 1N6689, QUALITY LEVELS JANTX, JANTXV, AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for a silicon, ultra-fast recovery, semiconductor power rectifier diode. Three levels of product assurance (JANTX, JANTXV, and JANS) are provided for each device type as specified in MIL-PRF-19500.

1.2 Package outlines. The device package for the encapsulated device type are as follows: Axial leaded DO-41 in accordance with figure 1 and surface mount US in accordance with figure 2 (surface mount).

1.3 Maximum ratings. Unless otherwise specified, T_A = +25°C.

1.3.1 Ratings applicable to all types. Ratings applicable to all Part or Identifying Numbers (PIN): T_{STG} and T_J = -65°C to +175°C.

1.3.2 Ratings applicable to individual types.

Col. 1	Col. 2	Col. 3 (1)	Col. 4	Col. 5	Col. 6	Col. 7
Device type	V_{RWM}	$I_{O(L)}$ at T_L = +55°C L = .375 inch (9.52 mm)	I_{FSM} at t_p = 8.3 ms	t_{rr}	$R_{\theta JL}$ at L = .375 inch (9.52 mm)	$R_{\theta JEC}$ (2)
	V dc	A	A pk	ns	°C/W	°C/W
1N6688, US	300	20	375	40	4	3.5
1N6689, US	400	20	375	40	4	3.5

(1) Derate linearly at 267 mA/°C from +100°C to +175°C.
(2) US devices only.

Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A
DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

FSC 5961

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics. Primary electrical characteristics are not applicable for this document.

1.5 PIN. The PIN is in accordance with MIL-PRF-19500, and as specified herein. See 6.4 for PIN construction example and 6.5 for a list of available PINs.

1.5.1 JAN certification mark and quality level. The quality level designators for encapsulated devices that are applicable for this specification sheet from the lowest to the highest level are as follows: The base quality level "JANTX", "JANTXV", and "JANS".

1.5.2 Device type. The designation system for the device types of diodes covered by this specification sheet are as follows.

1.5.2.1 First number and first letter symbols. The diodes of this specification sheet use the first number and letter symbols "1N".

1.5.2.2 Second number symbols. The second number symbols for the diodes covered by this specification sheet are "6688" and "6689".

1.5.3 Suffix symbols. The following suffix letters are incorporated in the PIN in the order listed in the table as applicable:

	A blank first suffix symbol indicates an axial through-hole mount package (see figure 1).
US	Indicates a surface mount, square endcap, package (see figure 2).

1.5.4 Lead finish. The lead finishes applicable to this specification sheet are listed on QPDSIS-19500.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Copies of these documents are available online at https://quicksearch.dla.mil).

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.




FIGURE 1. Physical dimensions and configuration for axial leaded devices (1N6688 and 1N6689).




FIGURE 2. Physical dimensions for surface mount devices (1N6688US and 1N6689US).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML-19500) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows:

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500 and figures 1 and 2 herein.

3.4.1 Lead finish. Unless otherwise specified, lead or end-cap finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. When solder alloy is used for finish, the maximum lead temperature is limited to +175°C maximum. Where a choice of finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Diode construction. These devices shall be constructed utilizing non-cavity double plug construction with high temperature metallurgical bonding between both sides of the silicon die and terminal pins (see MIL-PRF-19500). Metallurgical bond shall be in accordance with the requirements of category I in MIL-PRF-19500. US version devices shall be structurally identical to the non-surface mount devices except for lead terminations.

3.5 Marking. Devices shall be marked as specified in MIL-PRF-19500.

3.5.1 Marking for US devices. For US version devices only, all marking may be omitted from the device except for the cathode marking. All marking which is omitted from the body of the device shall appear on the label of the initial container.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3 and table I herein.

3.7 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I herein.

3.8 Polarity. The polarity of all types shall be indicated with a contrasting color band to denote the cathode end.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and table I).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or requalification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed by the first inspection lot to this revision to maintain qualification.

4.3 Screening (JANS, JANTX, and JANTXV levels only). Screening shall be in accordance with table E-IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen	Measurement for JANS level	Measurement for JANTXV and JANTX level
(1) 3c	Thermal impedance (see 4.3.1)	Thermal impedance (see 4.3.1)
5	Not applicable	Not applicable
9	Required I_{R1} and V_{FM1}	Not required
10	Method 1038 of MIL-STD-750, condition A	Method 1038 of MIL-STD-750, condition A
11	I_{R1} and V_{FM1}	I_{R1} and V_{FM1}
12	Required, see 4.3.2	Required, see 4.3.2
13 (2)	Subgroups 2 and 3 of table I herein: V_{F1} and I_{R1}; ΔV_{F1} = ±100 mV (pk); ΔI_{R1} = ±5 µA dc or 100 percent from the initial value, whichever is greater. Scope display evaluation (see 4.5.4)	Subgroup 2 of table I herein: V_{F1} and I_{R1}; ΔV_{F1} = ±100 mV (pk); ΔI_{R1} = ±5 µA dc or 100 percent from the initial value, whichever is greater. Scope display evaluation (see 4.5.4)

(1) Thermal impedance shall be performed any time after sealing provided temperature cycling is performed in accordance with MIL-PRF-19500, screen 3 prior to this thermal test.
(2) $Z_{\theta JX}$ is not required in screen 13, if already previously performed.

4.3.1 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3101, as applicable, of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, and K factor. See table II, group E, subgroup 4 herein.

4.3.2 Power burn-in conditions. Power burn-in conditions are as follows (see 4.5.3), T_A = +55°C maximum. Test conditions shall be in accordance with method 1038 of MIL-STD-750, condition B. Adjust I_O to achieve the required T_J. Use method 3100 of MIL-STD-750 to measure T_J. T_J = +115°C minimum and +150°C maximum.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIA (JANS) and E-VIB (JANTX and JANTXV) of MIL-PRF-19500 and 4.4.2.1 and 4.4.2.2 herein. Delta measurements shall be in accordance with table III herein.

4.4.2.1 Quality level JANS (table E-VIA of MIL-PRF-19500). For B5, if a failure occurs, resubmission shall be at the test conditions of the original sample.

Subgroup	Method	Condition
B3	1056	-0°C to +100°C, 25 cycles.
B3	1051	-55°C to +175°C, 100 cycles.
B3	4066	Condition A, I_{FSM} = rated I_{FSM} (see 1.3, column 4); ten surges of 8.3 ms each at 1 minute intervals, superimposed on I_O = 0, V_{RWM} = 0.
B4	1037	I_O = I_O rated minimum (see 1.3, column 3); V_R = rated V_{RWM} (see column 2 of 1.3, and 4.5.3).
B5	1027	I_O = I_O rated minimum (see 1.3, column 3 and 4.5.3); adjust T_A and or I_O to achieve T_J = +150°C minimum. t = 1,000 hours. Temporary leads may be added for surface mount devices. n = 45, c = 0. Delta shall not exceed 60 percent of initial reading.
B6	4081	See 4.5.5, +25°C ≤ T_A ≤ +35°C (recorded before test is performed); For axial leaded devices, $R_{\theta JL}$ (maximum) ≤ 4°C/W; L = .375 inch (9.53 mm). For surface mount devices (US version), $R_{\theta JEC}$ = 3.5°C/W maximum.
B8	4065	Peak reverse power, P_{RM} ≥ 318 W for square wave in accordance with method 4065 of MIL-STD-750 (P_{RM} ≥ 500 W for half-sine wave). Test shall be performed on each sublot; sampling plan n = 10, c = 0, end-points, see 4.4.2.

4.4.2.2 Quality levels JANTX and JANTXV (table E-VIB of MIL-PRF-19500).

Subgroup	Method	Condition
B2	1056	-0°C to +100°C, 10 cycles.
B2	1051	-55°C to +175°C, 25 cycles.
B3	1027	I_O = rated I_O (see column 3 of 1.3) minimum; adjust I_O to achieve required T_J of +125°C minimum; apply V_R = rated V_{RWM} (see column 2 of 1.3), f = 50 to 60 Hz (see 4.5.3.1). Delta shall not exceed 25 percent of initial reading.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and herein. See table III for delta measurements when applicable.

Subgroup	Method	Condition
C2	1056	-0°C to +100°C, 10 cycles.
C2	1051	-55°C to +175°C, 25 cycles.
C2	2036	Axial devices only. Tension: Test condition A; weight = 12 pounds (5.44 kg); t = 30 seconds. Lead fatigue: Test condition E; weight 2 pounds (0.91 Kg), t = 15 seconds. NOTE: Lead fatigue is not applicable for US devices.
C2	2038	US devices only. Condition B, 12 pounds (5.44 kg), t = 30 seconds.
C5	4081	See 4.5.5, +25°C ≤ T_A ≤ +35°C (recorded before test is performed); For axial leaded devices, $R_{\theta JL}$ (maximum) ≤ 4°C/W; L = .375 inch (9.53 mm). For surface mount devices (US version), $R_{\theta JEC}$ ≤ 3.5°C/W.
C6	1027	I_O = rated I_O (see column 3 of 1.3) minimum; adjust I_O to achieve T_J of +125°C minimum; apply V_R = rated V_{RWM} (see column 2 of1.3), f = 50 to 60 Hz (see 4.5.3.1). Delta shall not exceed 25 percent of initial reading.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table E-IX of MIL-PRF-19500 and as specified herein. See table III for delta measurements when applicable.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Inspection conditions. Unless otherwise specified, all inspections shall be conducted at T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5).

4.5.3 Burn-in and life tests. These tests shall be conducted with a half-sine waveform of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectified current. The forward conduction angle of the rectified current shall be neither greater than 180 degrees, nor less than 150 degrees.

4.5.3.1 Free air burn-in. The use of a current limiting or ballast resistor is permitted provided that each DUT still sees the full P_T (minimum) and that the minimum applied voltage, where applicable, is maintained through-out the burn-in period. T_J = +115°C minimum and +150°C maximum for screening, and T_J = +125°C minimum for 4.4.2.2 and 4.4.3 life tests. Accelerated life test in 4.4.2.1 shall be T_J = +150°C minimum.

4.5.4 Scope display evaluation. Scope display evaluation shall be condition A (stable only) in accordance with method 4023 of MIL-STD-750. Scope display may be performed on ATE (automatic test equipment) for screening only with the approval of the qualifying activity. Scope display in table I, subgroup 4 shall be performed on a scope. Reverse current (I_{BR}) over the knee shall be 500 µA peak.

4.5.5 Thermal resistance. Thermal resistance measurement shall be performed in accordance with method 4081 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, and t_{MD}. See table E-IX of MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2 2/						
Thermal impedance	3101	See 4.3.1	$Z_{\theta JX}$			°C/W
Breakdown voltage 1N6688, 1N6688US 1N6689, 1N6689US	4022	I_R = 100 A dc; pulsed (see 4.5.1)	V_{BR}	 300 400		V
Forward voltage	4011	Condition B, Duty cycle < 2 percent (pulsed) (see 4.5.1); t_p = 8.3 ms (maximum) I_F = 5 A I_F = 20 A I_F = 70 A	 V_{F1} V_{F2} V_{F3}		 0.90 0.97 1.2	V V V V
Reverse current leakage	4016	Condition A, V_{RM} = column 2 (peak) of 1.3; pulsed (see 4.5.1)	I_{R1}		50	µA
Subgroup 3						
High temperature operation:		T_C = +100°C				
Reverse current leakage	4016	Condition A, V_{RM} = column 2 (peak) of 1.3; pulsed (see 4.5.1)	I_{R2}		10	mA
Low temperature operation:		T_A = -65°C				
Forward voltage	4011	Condition B, I_F = 5 A (pk); pulsed (see 4.5.1)	V_{F4}		1.0	V
Subgroup 4						
Scope display	4023	Condition A (stable only). See 4.5.4, n = 116, c = 0				
Reverse recovery time	4031	Condition B; I_F = .5 A, I_R = 1 A; I_{RR} = .25 A	t_{rr}		40	ns
Junction capacitance	4001	V_R = 10 V dc; f = 1 MHz; V_{SIG} = 50 mV (p-p) (maximum)	C_J		400	pF

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 5 Not applicable						
Subgroup 6 Forward surge current	4066	Condition A. I_{FSM} = rated I_{FSM} (see 1.3, column 4); ten surges of 8.3 ms each at 1 minute intervals, superimposed on I_O = 0, V_{RWM} = 0. T_A = +25°C				
Electrical measurement		See table I, subgroup 2.				
Subgroup 7 Not applicable						

1/ For sampling plan, see MIL-PRF-19500.
2/ For end-point measurements, this test is required for the following subgroups:
Group B, subgroups 3, 4 and 5 (JANS).
Group B, subgroups 2 and 3 (JANTX and JANTXV).
Group C, subgroups 2 and 6.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification and requalification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			45 devices, c = 0
Thermal shock (glass strain)	1056	20 cycles, condition D except low temperature shall be achieved using liquid nitrogen (-195°C). Visual for cracked glass.	
Temperature cycling	1051	500 cycles, -65°C to +175°C.	
Hermetic seal	1071	Gross leak.	
Delta measurement		See table III herein, steps 1 and 2.	
Subgroup 2			22 devices, c = 0
Blocking life	1048	T_A = +150°C; t = 1,000 hours +65, -0 hours; dc = 80 to 85 percent rated V_R.	
Subgroup 4			
Thermal impedance curves		See MIL-PRF-19500.	
Subgroup 5			
Insulation resistance	1016	V_R = rated V_{RWM} (see 1.3, column 2); pressure = 33 mm H_g; t = 1 minute (minimum), R_{ISO} = 2.0 x 10^6 Ω maximum.	5 devices, c = 0
Subgroup 8 1/			
Peak reverse power	4065	Peak reverse power (P_{RM}) shall be characterized by the supplier and this data shall be available to the Government. Test shall be performed on each sublot.	n = 45
Subgroup 9 2/			
Resistance to glass cracking	1057	Test condition B. Step stress to destruction by increasing cycles or up to a maximum of 25 cycles.	n = 45
Subgroup 10			
Forward surge current	4066	Condition A, I_{FSM} = rated I_{FSM} (see 1.3, column 4); ten surges of 8.3 ms each at 1 minute intervals, I_O = 0, V_{RWM} = 0.	22 devices, c = 0
Electrical measurement		See table I, subgroup 2.	

1/ The sample size for this step stress requirement shall be determined by the supplier. A statistically significant sample size is required.
2/ Also applies US suffix versions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

TABLE III. Groups B, C, and E delta measurements. 1/ 2/ 3/ 4/

Step	Inspection	MIL-STD-750		Symbol	Limit	Limit	Unit
		Method	Conditions		Min	Max	
1.	Forward voltage change	4011	Condition B, I_F = 5 A, pulsed (see 4.5.1)	ΔV_{F1}	±100 mV change from previous measured value		
2.	Reverse current change	4016	Condition A, V_R = rated V_{RWM} (see 1.3, column 2)	ΔI_{R1}		±5	µA

1/ Devices which exceed table I, subgroup 2 (group A) limits for this test shall not be accepted.
2/ The delta measurements for group B inspection, table E-VIA (JANS) of MIL-PRF-19500 shall be as follows: In addition to the measurements specified for subgroup 5, the measurements of steps 1 and 2 of this table shall also be taken.
3/ The delta measurements for group E inspection, table E-IX of MIL-PRF-19500 shall be as follows: In addition to the measurements specified for subgroup 1, the measurements of steps 1 and 2 of this table shall also be taken.
4/ Also applies to US suffix versions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.


b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. The complete PIN, see 1.5 and 6.4.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML-19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://qpldocs.dla.mil.

6.4 PIN construction example. The PINs for encapsulated devices are constructed using the following form.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.

6.5 List of PINs. The following is a list of possible PINs for encapsulated devices available on this specification sheet.

PINs for types1N6688 and 1N6689

JANTX1N6688	JANTXV1N6688	JANS1N6688
JANTX1N6688US	JANTXV1N6688US	JANS1N6688US
JANTX1N6689	JANTXV1N6689	JANS1N6689
JANTX1N6689US	JANTXV1N6689US	JANS1N6689US

6.6 Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army − CR
Navy − SH
Air Force − 85
NASA − NA
DLA − CC

Review activities:
Army − AR, MI, SM
Navy − AS
Air Force − 19

Preparing activity:
DLA − CC

(Project 5961−2025−019)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:19Z
Check the source to verify that this is the current version before use.