A-A-54010
28 February 1990

COMMERCIAL ITEM DESCRIPTION

SPREADER, GUTTA-PERCHA, DENTAL

The General Services Administration has authorized the use of this Commerical Item Description as a replacement for MIL-S-36377B which is cancelled.

Salient characteristics:

This commercial item description covers spreaders suitable for use in manipulating gutta-percha into dental pulp chambers and root canals.

Classification. Spreaders shall be furnished in the following numbers, as specified (See Notes):

No. D11
No. D11T
No. MA57
No. 3

Materials.

Spreader point. The spreader operative end shall be fabricated of class 5, type 631 (17-PH), precipitation hardening stainless steel or class 3, type 302, austenitic stainless steel as specified in ASTM F899 for composition.

Solid handles. Solid handles shall be fabricated of class 3, type 303 austenitic stainless steel, type 303 stainless steel with a maximum of 3.50 percent of manganese and 0.25 percent of copper, or class 4, type 416, martensitic stainless steel as specified in ASTM B899 for composition.

Hollow handles. Hollow handles shall be fabricated of chromium over nickel plated brass. Brass shall conform to copper alloy No. 260 or 330 as specified in ASTM B135 for composition.

Hardness. After proper stress relieving and passivation, the Rockwell hardness of the spring tempered operative end shall be C45 to C58 for operative ends fabricated of type 631 stainless steel and C40-C50 for operative ends fabricated of type 302 stainless steel. Hardness shall be determined as specified in ASTM E18 (Rockwell) or E92 (Vickers).

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

Design and dimensions. The spreader shall be suitable for manipulating gutta-percha into pulp chambers and root canals. The spreader shall be single-ended and of two-piece construction consisting of a spreader operative end, and a handle. The spreader operative end shall be firmly and permanently secured in the handle.

The handle shall be straight, solid, and of one piece construction. The finger grip portion of the handle shall be finely serrated or fine diamond knurled. Spreader No. D11 and D11T shall conform to Defense Personnel Support Center (DPSC) Drawing No. 24424; No. MA57 shall conform to DPSC Drawing No. 24437; and No. 3 shall conform to DPSC Drawing No. 20892 for design and dimensions.

Corrosion resistance. The copper sulfate test shall apply to martensitic stainless steel components. The boil test shall apply to the entire spreader (operative ends and all handles). Corrosion tests shall be as specified in ASTM F1089.

Joint strength. There shall be no movement, loosening, or separation between the operative end and handle when the operative end is subjected to the pull test as specified herein.

Ductility. The operative end of the spreader shall withstand a minimum of two 90 degree cold bends with no signs of rupture or fracture, when subjected to the ductility test as specified herein.

Finish. The spreader operative end shall have a smooth, bright or mirror finish and shall be free of defects such as coarse grind marks, cracks, nicks, gouges and burrs when examined under four power (4x) magnification. The handle shall have a smooth, mirror or bright polished finish, except for the serrated or knurled finger grip portion. Serrated or knurled finger grip portions shall be free of barbs and shall provide adequate finger grip during use. The interface of the shank and handle shall be smoothly blended with no crevices evident.

Identification markings. Each spreader shall be marked withe the applicable instrument number, country of origin and name or trademark of the manufacturer if different from that of the contractor. The word "stainless" or letters "SS" shall also be marked on all instruments. As an alternate to the word "stainless", the use of a registered trademark identifying the steel as stainless shall be acceptable, provided prior approval is received from the cognizant contracting officer. All markings shall be permanent and legible.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

Workmanship. The spreaders shall be free from all defects which detract from their appearance or impair their serviceability, proper functioning or intended use.

Unit. Each (EA). One gutta-percha spreader, as specified, constitutes one unit.

Unit package. Each spreader shall be blister-packed or wrapped in neutral tissue or other suitable anti-corrosive material and in a close fitting container to prevent damage to the operative end.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, with an AQL (percent defective) of 2.5 and inspection level of II. The unit of product for examination purposes shall be one spreader as specified in this description.

Examination. Examination shall be as specified herein. Examination shall include, but shall not be limited to the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

Defects.

Design not as specified.
Finish on spreader operative end not as spreader.
Spreader operative end not free of coarse grind marks, cracks, nicks, gouges, burrs or other imperfections.
Spreader operative end bent or distorted.
Spreader operative end taper not smooth.
Handle not straight.
Finish on handle not as specified.
Instrument identification not present, not legible or not permanent.
Instrument not permanently and legibly marked with name or trade mark of manufacturer.
Instrument not free of dirt, oil, polishing compound, or foreign matter.
Interface of the shank and the handle not smoothly blended; shows crevices.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as specified below. The unit of product for test purposes shall be one spreader, as specified in this description.

Test criteria

Characteristic	Inspection level	AQL
Chemical composition	*	**
Hardness	S-2	1.5
Dimensions	S-2	2.5
Corrosion resistance	S-2	1.0
Pull test	S-2	**
Ductility test	S-2	1.5

*A sufficient quantity of each lot of metal used in the construction of the spreader may be selected for chemical analysis provided lot identity has been maintained and can be demonstrated to the Government.

**Acceptance number shall be zero for all sample sizes.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

Chemical analysis. In the absence of certificates of quality, chemical analysis of the individual components of the spreaders shall be determined in accordance with method 111 of FED-STD-151.

Dimensions. Dimensions shall be measured using an optical comparator, shadowgraph, or other suitable device capable of measuring the spreader dimensions with the accuracy specified in the drawing.

Pull test. The handle and shank of the operative end shall be securely held in separate chucks or other holding devices. A slowly increasing pull out force, increasing from zero to 85 pounds (minimum), shall be applied to the shank of the operative end. The force shall be maintained at the high value for a minimum of 1 second. A pull out force of 100 pounds (minimum), shall be applied quickly to the shank of the operative end of No. 3 spreaders and held for a minimum of 2 seconds.

Ductility test. The first 1/4 inch of the operative end (operative tip) shall be clamped in a vise or other suitable device, the jaws of which shall be rounded to a radius to 1/16 inch. The spreader operative end shall be bent back and forth over this radius at a uniform rate. Each 90 degrees of travel in one direction shall be considered one bend. Test shall be conducted at room temperature. Examination for rupture or fracture shall be under a minimum of 30 power (30x) magnification.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pounds units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and of regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document.

National Stock Number	Item Identification
6520-00-890-1386	SPREADER, GUTTA-PERCHA, DENTAL, No. 3
6520-01-061-6452	SPREADER, GUTTA-PERCHA, DENTAL, No. D11T
6520-01-064-8981	SPREADER, GUTTA-PERCHA, DENTAL, No. D11
6520-01-126-4033	SPREADER, GUTTA-PERCHA, DENTAL, No. MA57

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:
Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:

DoD-MB

AGENT:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:
VA-OSS
PHS
FDA-MPQAS

PROJECT NO. 6520-2318
LOCATION: NCR - DISK 8

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
Attn: DPSC-BSTE
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
A-A-54010	SPREADER, GUTTA-PERCHA, DENTAL

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)* _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:28Z
Check the source to verify that this is the current version before use.