MILITARY SPECIFICATION

IGNITER, PRIMER, ELECTRIC, M74
LOADING, ASSEMBLING AND PACKING

This amendment forms a part of Military Specification MIL-I-46521D (AR), dated 25 July 1979, and is approved for use within the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.3 Delete in its entirety and substitute:

"3.3 Moisture content of ignition element. The moisture content of the ignition element after drying shall not exceed 0.02 percent."

PAGE 5

Table I Heat Seal Test, Paragraph Reference Column: Delete "4.4.3.7" and substitute "4.4.3.6".

PAGE 7

4.4.2.1 Critical 1, Inspection Method Column: Delete "/Straight Edge".

PAGE 13

4.4.3.1 Delete in its entirety and substitute:

"4.4.3.1 Chemical analysis sample. After the mixing cycle is complete, transfer approximately 5 grams of the wet ignition charge composition to a tared medium porosity crucible for transfer to the Chemical Laboratory for drying to establish sample weight and subsequent ingredient analysis."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:10Z
Check the source to verify that this is the current version before use.

4.4.3.2 Delete in its entirety and substitute:

"4.4.3.2 Moisture content of ignition charge composition. Three samples minimum shall be selected from each drying oven after completion of the drying cycle. If the moisture content of any sample exceeds the requirement, that quantity of material represented by the sample shall be either redried until acceptable results are achieved, or rejected. The selected samples must not be dried more than any other unit which could be selected."

PAGE 14

4.5.2 Delete in its entirety and substitute:

"4.5.2 Moisture content of igniter charge composition. The moisture content of the igniter charge composition shall be determined as in Method 102.211 of MIL-STD-1234, except that the electric ignition element loading assembly and only a two hour drying time shall be used. The upper insulator may be removed from the electric element loading assembly prior to analysis."

PAGE 15

4.5.6 Delete:

"Potassium chlorate	44.5 plus or minus 2
Lead thiocyanate	35.5 plus or minus 2
Charcoal	20.0 plus or minus 1.5
Lacquer solids (added)	1.6 plus or minus 0.2".

and substitute:

"Charcoal	19.7 $\pm$ 1.5
Lead thiocyanate	34.9 $\pm$ 2.0
Potassium chlorate and gum solids	45.4 $\pm$ 2.1".

4.5.6.1 Delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:10Z
Check the source to verify that this is the current version before use.

PAGE 16

4.5.6.2 Delete in its entirety and substitute:

"4.5.6.2 Charcoal content. Transfer approximately 2 grams of the igniter charge composition into a tared medium porosity crucible. Place in 70°C oven overnight to dry. Remove crucible from oven and place in desiccator to cool and then weigh to establish sample weight. Wash the sample with ten successive portions of 25 mls of 5% potassium nitrate solution followed by 50 mls of distilled water. Use a small glass rod to break up lumps in the sample during the extraction procedure. Preserve the filtrate for the determination for lead thiocyanate. Place the sample in 100°C oven for 2 hours. Remove from oven and place in desiccator to cool, then weigh. Calculate the percent charcoal as follows:

$$\text{Percent charcoal} = \frac{(100)\ (C - B)}{A - B}$$

Where:
A - Sample weight before the washing (including crucible)
B - Weight of empty crucible
C - Sample weight after washing (including crucible)".

4.5.6.4 Delete in its entirety and substitute:

"4.5.6.4 Potassium chlorate and gum solids. The percentage of potassium chlorate and gum solids is determined by subtracting the total percentage of charcoal and lead thiocyanate from one hundred percent."

PAGE 18

6.6 Delete in its entirety.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1390-A741)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:10Z
Check the source to verify that this is the current version before use.