MILITARY SPECIFICATION

PACKING, PREFORMED, HYDROCARBON FUEL RESISTANT

This amendment forms a part of Military Specification MIL-P-5315B, 2 December 1964, and has been approved by all Departments and Agencies of the Department of Defense.

Page 2, table I:

(a) Item 7, under "Property": Delete "Shore "A"", and substitute "durometer".

(b) Item 8, under "Requirements": Delete "0-50", and substitute "25 max."

Page 3, table II: Delete, and substitute:

TABLE II. Permissible production variation in physical properties from the qualification values

Item	Property	Variation
1	Tensile stress at 100 percent elongation, psi.	±15 percent
1/ 2	Tensile strength, psi.	±15 percent
1/ 3	Ultimate elongation, percent.	±20 percent
4	Specific gravity, points.	±0.02 points
1/ 5	Volume change due to type I test fluid aging, percent.	±2 units of percent
1/ 6	Volume change due to type III test fluid aging, percent.	±3 units of percent
1/ 7	Hardness, durometer, points.	±3 points
1/ 8	Compression set (permanent set), percent	±5 units of percent
1/ 9	Temperature retraction, °F.	±2° F
10	Corrosion and adhesion.	None

1/ All values obtained shall be within the numerical limits specified in table I.

Page 5, paragraph 4.4.3: Delete items (d), (e), and (f).

Custodians:
Army - AV
Navy - AS
Air Force - 11

Reviewer activities:
Army - AV, AT, MI, WC
Navy - AS
Air Force - 11, 69

User activities:
Navy - SH, MC

Preparing activity:
Air Force - 11

Project No. 5330-0319

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T04:29Z
Check the source to verify that this is the current version before use.