MIL-T-26089(USAF)
AMENDMENT 3
5 October 1979
SUPERSEDING
AMENDMENT 2
1 August 1972

MILITARY SPECIFICATION

TAPE, TEXTILE, NYLON, LOOP

This amendment forms a part of Military Specification MIL-T-26089(USAF) dated 11 March 1957.

PAGE 1

Paragraph 2.1: Under SPECIFICATIONS, delete "Federal, CCC-T-191 Textile Test Methods". Under Military, delete "MIL-P-6065 Packaging, Packing, and Marking of Cloth, Fabric, and Webbing" and substitute "MIL-W-43334 Webbing and Tape, Textile, Packaging and Packing Of".

Under STANDARDS, add "Federal, FED-STD-191 Textile Test Methods".

Paragraph 3.1.1, line 5: Delete "4.3.2.1" and substitute "4.3.2".

PAGE 2

Paragraph 3.1.2 and Table I. Delete and substitute:

"3.1.2 Loop cord. The loop cord used in the manufacture of the lacing loop tape shall be constructed in such a manner and with such yarn tension that the core yarns are held firmly in place to prevent puckering of the core yarns when released from stress. This cord shall conform to the requirements of the core or coreless construction of table I when tested as specified in 4.3.

FSC 8315

Source: https://assist.dla.mil -- Downloaded: 202610-20T07:51Z
Check the source to verify that this is the current version before use.

TABLE I. Cord requirements.

	Core Construction			Coreless Construction
	Sleeve	Core	Cord	
Yarn size, denier	210	210	-	210
Yarn ply (min)	3	2 or 3	-	6
Yarn twise, turns per inch (min)	8S 6Z	8S 6Z	- -	2.5S 2.5Z
Number of carriers	20	-	-	16
Ends per carrier	1	-	-	1
Number of ends	20	6 or 9	-	16
picks per inch	26 - 28	-	-	15
Weave	plain (1 up 1 down	-		basket
Thickness, inch ±0.010	-	-	0.075	
Breaking strength, pounds (min)	-	-	150	150
Yarns per pound (min)	-	-	180	180

Table II: Opposite "Breaking strength, pounds (min)", delete "375" and substitute "175".

PAGE 3

Paragraph 3.2.2, line 2: Delete "45 ± 1 inch" and substitute "41 inches, minimum".

Paragraphs 3.5 and 3.6: Delete and substitute:

"3.5 Length and put-up. Unless otherwise specified, the tape shall be furnished on double headed spools, or tubes, containing 500 ± 10 yards. No spool shall contain more than 5 pieces, and no piece shall be less than 10 yards in length.

3.6 Identification ticket or label. Each spool or tube shall have an identification ticket or label attached in accordance with MIL-W-43334."

Source: https://assist.dla.mil -- Downloaded: 202610-20T07:51Z
Check the source to verify that this is the current version before use.

PAGE 9

Paragraph 4.3.2, first sentence: Change to read, "The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table IV and 4.3.2.1 shall be followed."

Table IV: Under "test", insert "Melting point" between "Thread count" and "Colorfastness to laundering". Under "Method No.", insert "1534" between "5050" and "5614".

PAGE 10

Paragraph 4.3.2.1: Delete in its entirety.

Paragraph 4.3.2.2: Change to read "4.3.2.1".

Custodian:
Air Force - 11

Review activity:
DLA - CT

Preparing activity:
Air Force - 11

Project No. 8315-F288

Source: https://assist.dla.mil -- Downloaded: 202610-20T07:51Z
Check the source to verify that this is the currentversion before use.