INCH-POUND

A-A-55243

October 27, 1993

COMMERCIAL ITEM DESCRIPTION

TAPE, TEXTILE, NYLON OR POLYESTER (FOR NAME TAPES)

The General Services Administration has authorized the use of this commercial item description in preference to MIL-T-43664.

Abstract. The tape is intended for use as a name tape for uniforms and field clothing.

Classification. The tape shall be in the following types:

Type I - Nylon
Type II - Polyester

Salient characteristics. The color of the tape shall be Olive Drab 7, Light tan 389 or Camouflage Green 483. The weave for both types of tape shall be plain weave 1-up and 1-down. The filling yarn for type I shall traverse the full width of the tape with one filling yarn per shed. The filling yarn for type I shuttleless and type II shall traverse the full width of the tape with two filling yarns per shed and shall be held at the edge by a catch cord yarn interlacing with the filling yarn. The water-soluble and chloroform-soluble materials of the tape shall be no more than 2.0 percent as specified in the end item testing section. The shrinkage of the tape in the warp or lengthwise direction shall be no more than 5.0 percent when tested in accordance with the end item testing section. The pH value of the water extract of the finished tape shall be no less than 5.0 nor more than 8.5 when tested in accordance with the end item testing section. The tape shall conform to the requirements specified in table I.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8315

DISTRIBUTION STATEMENT A.

Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

ed shipping containers must be ... The fully package

The dyed tape shall show fastness to light, perspiration, and laundering (after 3 cycles) equal to or better than a rating of good. The dyed tape shall show fastness to crocking or shall have an AATCC Chromatic Transference Scale rating not lower than 3.5.

Table I.
Physical Requirements

Requirements	Type I (Nylon)	Type II (Polyester)
Width (inches)	1 ± 1/32	1-1/16 ± 1/32
Thickness (inches)	0.015 to 0.025	0.006 to 0.012
Weight (oz/yd), maximum	0.30	0.20
Warp ends (face & back), minimum	200	125
Picks per inch, minimum	33, (66 1/)	80 1/
Yarn numbers: Warp (nominal) Filling (nominal)	 210 (den) 420 (den), (210 den 1/	 170 (den) 40/1 (spun polyester)

1/ Two picks per shed for shuttleless loom tape.

Material

Nylon yarn (type I). The yarn for type I shall not be subjected to any type of bleaching process. The yarn shall be a bright, high tenacity, light and heat resistant polyamide prepared from either hexamethylene diamine and adipic acid with a minimum melting point of 472°F when tested.

Polyester yarn (type II). The yarn for type II tape shall be semi-dull or bright, regular or high tenacity fiber prepared from polyethylene glycol terephthalate with a minimum melting point of 472°F when tested.

Length and put-up. Unless otherwise specified, the tape for type I shall be furnished in rolls of 72 yards ± 1 yard. The tape for type II shall be furnished in rolls of 200 yards ± 1 yard. No roll shall contain more than two pieces, and no piece shall be less than 5 yards. Ends of pieces may be butted and fastened with adhesive tape. Overlapping pieces and sewing is prohibited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Label/tag. Each item shall be individually bar-coded with the type VII or VIII, class 17 label/tag of DDD-L-20. This label/tag shall be located so that it is completely visible on the items, and causes no damage to the items.

Workmanship. The finished tape shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

Product Demonstration Model. When required, offerers shall submit samples of their intended production. The product demonstration model will consist of units independently developed. Product demonstration models will be analyzed and evaluated by the government. Evaluation criteria and basis for award are contained in the solicitation. Product demonstration models will be retained by the Government. One (1) product demonstration model approved by DPSC under the resultant contract will serve as a manufacturing standard for the corresponding production items delivered under this contract. Offerers are advised that the product demonstration model does not relieve the successful offerer of his responsibility to perform in accordance with the commercial item description specified above.

Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Quality assurance

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for, under the provisions of the contract. Reliance on contractor quality assurance systems shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract.

Examination

Visual examination. The tape shall be examined for the defects listed below. The lot size shall be expressed in units of tape. The sample unit is one tape.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Defects. The tape shall be examined for the following defects: any hole, cut, tear, color not as specified; any spot or stain (outside); thread ends not removed; label missing, incorrect, or illegible; measurement of item not as specified; bar code omitted or not readable by scanner, human-readable interpretation (HRI) omitted or illegible; bar-coded type not as specified, code density not as specified.

Dimensional examination. The finished tape shall conform to the dimensions specified. Any dimension that is not within the established tolerance shall be classified as a defect. The sample unit shall be one tape.

Packaging examination. The fully packaged shipping containers shall be examined in accordance with defects listed below. The lot size shall be the number of shipping containers in the inspection lot.

Examination	Defect
Marking (Exterior and interior)	Omitted; incorrect; illegible; of improper size location, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose strapping, inadequate stapling, or improper taping
Content	Number of items in container is more or less than required.
	NSN shown on one or more items is not as specified on shipping container
Palletization	Length, width, or height exceeds specified maximum requirements
	Pallet type not as specified
	Load not bonded as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

End item performance testing. The tape shall be tested for the characteristics listed in table II. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table II shall be followed. The physical and chemical values specified in the salient characteristics section apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing the final result. The sample unit shall be 6 yards of tape. The sample size shall be as follows:

Lot size (yards)	Sample size (sample unit)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more sample units fail to meet any requirement specified.

Table II.
End Item Performance Testing

Characteristic	Test Method
Material (yarn):	
Nylon:	
Material identification	ASTM D 276-87 1/
Melting point	ASTM D 276-87 1/
Yarn number	ASTM D 1907 1/
Polyester:	
Material identification	ASTM D 276-87 1/
Melting point	ASTM D 276-87 1/
Yarn number	ASTM D 1907 1/
Colorfastness to:	
Light	AATCC 16A-1988
Perspiration	AATCC 15-1988
Crocking	AATCC 8-1988
Laundering (after 3 cycles)	AATCC 61-1986 2/
Thickness	ASTM D 1777-64
Weight	ASTM D 3776-85
Warp ends (face and back)	Visual
Picks per inch	Visual
Weave	Visual

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Table II.
End Item Performance Testing - (Cont.)

Characteristic	Test Method
Nonfibrous material	ASTM D 629-88
Dimensional stability	AATCC D 99-1988
pH	ASTM 2165

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.
2/ The specimens must be dried after each of the 3 laundering cycles. On the color transfer cloth, the stain on the nylon, cotton, polyester, and wool fibers shall be evaluated.

Preservation, packing, and marking. The preservation, packing, and marking shall be as specified in the contract or order.

Source of Government documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Sources of Nongovernment Documents

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

(Applications for copies should be addressed to the American Association of Textile Chemists and Colorists, AATCC, P.O. Box 12215, Triangle Park, NC 27709-2215.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

Custodian:
Army - GL

Civil Agency Coordinating Activity:
GSA - FSS

Review Activity:
Army - MD

Preparing Activity:
DLA - CT

Project No.
8315-0366

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-55243	93-10-27

3. DOCUMENT TITLE

TAPE, TEXTILE, NYLON OR POLYESTER (FOR NAME TAPES)

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
Defense Personnel Support Center ATTN: DPSC-FSSD (12-3-D)	(1) Commercial	(2) AUTOVON
c. ADDRESS (Include Zip Code) 2800 South 20th Street P. O. Box 8419 Philadelphia, Pennsylvania 19101-8419	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89

Source: https://assist.dla.mil -- Downloaded: 2026/0-28T09:45Z
Check the source to verify that this is the current version before use.