|INCH-POUND|
MIL-B-22036D(AS)
20 September 1991
SUPERSEDING
MIL-B-22036C(AS)
6 November 1972

MILITARY SPECIFICATION

BRIDLE AND PENDANT ASSEMBLIES AIRCRAFT LAUNCHING

This specification has been approved by the Naval Air Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers requirements for the procurement of aircraft launching bridle and pendant wire rope assemblies of the types and part numbers shown in 1.2.

* 1.2 Classification. The bridles and pendants shall be classified as follows:

TYPE	PART NUMBER	AIRCRAFT APPLICATION	BASIC CABLE DIA (INCHES)
Type I Endless grommet bridles	Not required, used on obsolete aircraft		
Type II Forged eye pendants	Not required, used on obsolete aircraft		
Type III Forged eye bridles	NAEC 608503-1 NAEC 608976-1 NAEC 608932-6	A-3 series A-4 series T-2 series	2 1 3/8 3/4
Type IV Sleeve and poured zinc socket pendants	Not required, used on obsolete aircraft		
Type V Forged eye bridles (reinforced apex)	NAEC 616710-1	F-4 series	1 1/2

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Naval Air Engineering Center, Systems Engineering and Standardization Department, (Code 53), Lakehurst, NJ 08733-5100, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 1720
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

MILITARY

MIL-P-116 - Preservation, Methods of
MIL-H-6875 - Heat Treatment of Steel, Process for

STANDARDS

MILITARY

MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-1949 - Inspection, Magnetic Particle
MIL-STD-2073-1 - DOD Materiel Procedures for Development and Application of Packaging Requirements

(Unless otherwise indicated, copies of federal and military specifications, standards and handbooks are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

* 2.1.2 Other Government Documents and Drawings. The following other Government documents and drawings form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

MATERIALS PROCESSING REPORT (NAEC)

MPR 1705 Identification Symbols Assigned to Manufacturing of Launching Bridles and/or Pendants

DRAWINGS

Naval Air Engineering Center

608503 Bridle, Launching, A-3 Series Aircraft

616710 Bridle, Launching, F-4 Series Aircraft

608976 Bridle, Launching, A-4 Series Aircraft

608932 Bridle, Launching, T-2 Series Aircraft

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

Commanding Officer, Naval Supply Depot (Code 1051) 5801 Tabor Avenue, Philadelphia, PA 19120. All other documents should be obtained from the procuring activity or as directed by the contracting officer.

* 2.2 Non-government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

ASTM E 8 — Standard test methods of tension testing of metallic materials

(Application for copies should be addressed to the AMERICAN SOCIETY FOR TESTING AND MATERIALS, 1916 Race Street, Philadelphia, PA 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Qualification. Bridle and pendant assemblies furnished under this specification shall be products which are authorized by the qualifying activity for listing on the applicable qualified products list at the time of award of contract (see 4.4 and 6.3).

3.2 Materials. Materials shall be as specified on the applicable drawings. Materials which are not covered by applicable specifications shall be of aircraft quality and suitable for the purpose intended.

* 3.3 Design and construction. The design and construction of the assemblies shall be in accordance with applicable assembly drawings and this specification. While in service these bridles and pendant are used to launch military aircraft and are classified as critical. Their design shall be made with a minimum margin of safety as they are subject to impact and dynamic loads. Their construction shall be of a uniformly excellent quality since a failure could result in the loss of an airplane, the lives of its crew and ships personnel.

3.3.1 Wire rope. Wire rope shall conform to the requirements specified on the applicable drawing.

3.3.2 Terminals. Terminal shanks shall be swaged, cold forged, pressed, or zinc socketed on the wire rope until the dimensions conform to those specified on the applicable assembly drawings.

Source: https://assist.dla.mil - Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

3.3.3 Heat treatment. The equipment requirements of Section 3 and the inspection and the test procedures of Section 6 relating to the heat treating equipment of MIL-H-6875 shall apply.

3.4 Identification of product.

3.4.1 Metal identification tag. The metal identification tag shall be attached securely to the wire rope immediately upon separation from the shipping reel or master reel and in such a manner as not to damage or interfere with subsequent operations. The tag shall be located on a straight portion of the bridle or pendant as shown on the applicable drawings. The tag shall be fixed in position so as to prevent accidental detachment. The letters shall be metal stamped or electric etched and shall be not less than 3/32 inches high. Identification tags shall contain the information shown on the applicable drawings.

3.4.1.1 Different manufacturer's wire rope. If wire rope of different manufacturers is used during production, the metal identification tags shall include an identification symbol specified by MPR 1705. Mechanical splice sleeves and terminals shall be legibly and durably marked with the contractor's identifying symbol and code in such a manner that the strength and performance characteristics are not impaired.

3.5 Vendors. The contractor shall notify NAVAIR (copy to NAEC) prior to any change in vendors of component parts or assemblies from original vendors represented in bridles or pendants passing the qualification test.

3.6 Performance. Bridle and pendant assemblies and test specimens shall satisfactorily pass performance and mechanical properties tests specified in Section 4.

* 3.7 Workmanship. The assemblies specified herein shall be uniform in quality and shall be free from any irregularities or defects which might adversely affect its performance or serviceability. Component parts shall be free from burrs, fins, nicks, sharp edges, laps, seams, cracks, or other detrimental defects. Bridles and pendants covered by this specification are used in launching military aircraft and are considered critical. Excellent quality cannot be overemphasized. Manufacturing, processing, and assembly methods shall conform to those recognized by the industry as of highest quality.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

* 4.1.2 Inspection conditions. Unless otherwise specified, all inspections shall be performed in accordance with the test conditions specified in (applicable test method document or applicable paragraph(s) in the specification).

4.2 Classification of inspections. The inspection and testing of the bridle and pendant assemblies shall be classified as follows:

(a) Qualification inspections. Qualification inspections (see 4.3) are examinations and test performed on samples submitted by a prospective qualifier for approval as qualified products in accordance with the NAVAIR letter of authorization (see 6.3). The cost of these tests shall be borne by the prospective qualifier.

(b) Quality conformance inspection:

(1) Quality conformance inspections. Quality conformance inspections (see 4.4) are examinations and tests performed on samples submitted under contract to determine conformance of the products or lots with requirements set forth in the specification prior to acceptance.

(2) Production control inspections. Production control inspections are examinations and tests performed at a test laboratory designated by the Government on random samples of assemblies produced under any contract. Samples shall be selected by the Government inspector.

4.3 Qualification inspections. Qualification inspections shall consist of the examinations and tests listed in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification inspections

SAMPLE ASSEMBLIES 1 THROUGH 5	SAMPLE ASSEMBLIES 6 THROUGH 10	TENSION TEST SPECIMENS 11 AND 12
Examination (4.5.1) Magnetic particle inspection (4.5.3) Hardness (4.5.4) Proof load (4.5.5) Dynamic (4.3.2) (4.5.9)	Examination (4.5.1) Magnetic particle inspection (4.5.3) Hardness (4.5.4) Proof load (4.5.5)	Examination (4.5.1) Magnetic particle inspection (4.5.3) Hardness (4.5.4) Tension (4.5.6)

4.3.1 Requalification. Qualification inspections in accordance with 4.3 shall be repeated every two years or as directed by the qualifying activity.

4.3.2 Samples for qualification inspection. Qualification samples shall be accompanied by prospective qualifier's drawings, test reports, and certification letters of materials signed by the Government inspector. Qualification inspection samples shall consist of the number of assemblies listed in Table I for the applicable type. The inspection schedule listed in Table I shall be used for qualification inspections. The overall length of the assembly for each tension test specimen shall not exceed ten feet. Samples shall be forwarded to the test laboratory designated in the letter of authorization (see 6.3). The samples shall be plainly identified by securely attached durable tags marked with the following information:

> Samples submitted by (Name, Date) for Qualification Inspection in accordance with the requirements of MIL-B-22036 under authorization reference (NAVAIR letter authorizing the tests) Contractor's part no.

4.3.3 Prospective qualifier's actions prior to forwarding qualification samples. Prior to forwarding qualification samples, the prospective qualifier shall have:

a. Submitted a request for qualification to NAVAIR.

b. Tested twelve samples in his own test facility, or at a testing facility approved by the procuring activity, in accordance with Table I, except repeated load tests (4.5.7) shall be substituted for the dynamic tests (4.5.9).

c. Prepared a test report on the samples tested in (b) above and submitted copies to NAVAIR, NAEC, and the test laboratory designated in the letter of authorization.

4.3.3.1 Prospective qualifier's test report. This report shall include but not be limited to the following.

a. Name of parts, materials, and processes used on all components not specifically covered by this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

b. Wire rope specification, manufacturer's name and commercial designation.

c. Heat treatment, physical and chemical properties of materials.

d. List of commercial designations and vendor's names and addresses.

e. Results of all tests including a detail statement indicating compliance with each requirement of this specification, referring specifically to the applicable paragraph numbers.

f. Outline and description of tests and test conditions.

g. copies of test log sheets.

4.3.4 Failure. Failure to meet any qualification test will result in rejection of the entire assembly and cessation of further tests.

4.3.4.1 Failure after qualification. If samples fail to pass tests subsequent to qualification approval, the listing of the contractor's product for that type bridle or pendant qualified will be considered for deletion from the Qualified Products List.

4.4 Quality conformance inspections. Quality conformance inspections performed by the contractor for production assemblies shall consist of the examinations and tests listed in Table II. Assemblies and components not meeting the specified requirements shall be rejected.

TABLE II. Contractor's quality conformance inspections

TESTS	PARA	ASSEMBLIES
Examination	4.5.1	All
Magnetic particle inspection	4.5.3	All
Hardness	4.5.4	All
Proof load	4.5.5	All
Tension test	4.5.6	Two (See 4.4.2)
Destruction test	4.5.8	First 5 on each contract and then one from each lot (See Notes 1, 2 and 3)

NOTE 1: A full report shall be submitted to NAVAIR (copy to NAEC). In event of premature failure or unsatisfactory performance, cause of failure and remedial action shall be determined prior to further production.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

NOTE 2: Prior approval of NAVAIR (copy to NAEC) shall be obtained for any change in the source, type, grade, commercial designation, or specification of the wire rope during production. After approval, the first five production assemblies manufactured shall be subjected to the destruction test (4.5.8).

NOTE 3: If any one of the assemblies fails to meet the specified requirements, five additional samples shall be selected at random by the Government inspector for subjection to the destruction test (4.5.8). Failure of any one of these five sample assemblies to meet specified requirements shall result in rejection of the entire lot from which the samples were taken.

4.4.1 Inspection lot. The inspection lot shall consist of 250 assemblies or part thereof of the same part number produced under essentially the same manufacturing conditions. The unit of inspection shall be one assembly. All assemblies in any lot shall be made with wire rope from the same shipping reel or master reel.

4.4.2 Tension tests. The tension tests under qualification testing shall consist of the test given in 4.5.6 and shall be conducted on each tension test specimen as specified in 4.4.2.1 and 4.4.2.3.

4.4.2.1 Integrity of terminal-wire rope connector (Types II, III, and V only. Terminal tension test specimens shall be made by assembling a production terminal on each end of a length of wire rope taken from the same reel of rope as used in production. The assembly shall not exceed ten feet. Type V does not require reinforcing of the apex for tension specimens. Before a production run is made on a die and also after a die is redressed, a tension test specimen shall be made and tested. Thereafter, tension test specimens shall be made and tested as follows:

a. Terminals swaged in rotary swaging machine. Tests shall be made at intervals of every 200th swaging up to the 600th swaging and at every 100th swaging thereafter.

b. Terminals cold forged or pressed. Tests shall be made at intervals of every 300th forging or pressing up to the 1000th and at every 150th thereafter.

c. Tension test. A tension test specimen shall be made after production of the last assembly of a shipment, whenever the number of terminals since the last satisfactory test exceeds 20.

4.4.2.2 Tension test failure. If the wire rope tension specimen fails to meet 92 percent of the specified minimum breaking strength, a second specimen may be prepared and tested. If the second specimen fails to meet the specified requirements the production run between the last satisfactory test specimen and the failed specimen shall be rejected. Production terminals shall be identified by etching a serial number on the flat of eye end terminals and on the end of round terminals after cold working. The serial numbers shall run consecutively and continuously in accordance with the sequence of production.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

4.4.2.3 Mechanical splice sleeve or poured zinc socket test specimens (Types I, II and IV only). For Types I and II, two representative mechanical splice specimens shall be tension tested to failure prior to the production run. For Type IV, each of two representative specimens with mechanical splice on one end and poured zinc socket on the other end shall be tension tested to failure prior to the production run. The wire rope, splicing medium, and method employed to manufacture test splices and poured zinc sockets shall be the same as that utilized in production. The overall length of the wire rope test specimen shall not exceed ten feet. Should either sample of mechanical splice sleeve fail to meet 92 percent of the specified minimum breaking strength of the wire rope, or either sample of poured zinc socket fail to meet 100 percent of the specified minimum breaking strength of the wire rope, cause of failure shall be determined and corrective action shall be made before production run begins. This test shall be repeated with one specimen during each production lot. Failure of splice during production run shall result in rejection of the lot represented.

4.4.3 Production control inspections. Upon completion of qualification inspections the Government inspector shall immediately select two random samples from each lot of assemblies. Samples shall be forwarded to a Government designated test laboratory for the tests listed in Table III. Rejection of any sample for noncompliance with this specification or applicable drawings shall result in rejection of the lot represented. Shipment of lots under consideration from contractor's facility shall be contingent on satisfactory completion of the tests of this paragraph.

TABLE III. Production control inspections

Sample No. 1		Sample No. 2	
Examination	(4.5.1)	Examination	(4.5.1)
Magnetic particle inspection	(4.5.3)	Magnetic particle inspection	(4.5.3)
Hardness	(4.5.4)	Hardness	(4.5.4)
Proof load	(4.5.5)	Proof load	(4.5.5)
Destruction	(4.5.8)	Dynamic	(4.5.9)
		Destruction	(4.5.8)

* 4.4.4 Forging integrity. One forging from each heat treated lot shall be sectioned for the purpose of preparing tensile test specimens by the supplier. At least two specimens shall be taken and machined to conform to the largest types which can be accommodated and are described in ASTM E 8, Figure 8, Standard 0.500-in. Round Tension Test Specimen with 2-in. Gage Length and Examples of Small-Size Specimens Proportional to the Standard Specimen which can be accommodated. The supplier shall identify the location on the parent forging from which the marked specimens are taken in a sketch. One specimen shall be parallel to forging flow direction and a second at another identifiable angle. Conformance to strength requirements stated on apex fitting and grab hook drawings shall be accomplished in supplier performed tensile tests. All forging data shall be documented in supplier certification of material composition and strength.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

4.5 Test methods.

4.5.1 Examination. Each assembly shall be carefully inspected for conformance with applicable drawings and requirements of this specification not covered by tests.

4.5.2 Preparation for delivery. The inspector shall ascertain that the preparation for delivery of the bridles and pendants conforms to this specification.

* 4.5.3 Magnetic particle inspection. Magnetic particle inspection on terminals and mechanical splice sleeves shall be conducted in accordance with MIL-STD-1949 and the applicable drawings. There shall be no evidence of any cracks, seams, laps, or other detrimental defects.

* 4.5.4 Hardness. Each terminal shall be tested for hardness in accordance with the applicable drawing. When a portable Rockwell Hardness Tester is used, any hardness readings outside the range specified on the applicable drawing shall be rechecked with a standard Rockwell Hardness Tester after the bridle/pendant breaking load tests have been completed. The hardness readings obtained with the standard tester shall determine the acceptability of the bridle terminals.

4.5.5 Proof load. Each assembly shall be loaded at a maximum rate of 300,000 pounds per minute by applying the proof load as shown in the Proof Load diagrams in the applicable drawings. Reduce the load to 25,000 pounds and repeat the cycle until the proof load has been applied three times. Each load shall be held for a minimum of 15 seconds. Inspect the assembly during test and after the load has been released. There shall be no defects beyond the limits set forth in the applicable drawing. See the applicable drawing for allowable amount of wire rope stretch or zinc socket settling. Each assembly which passes the proof load test shall have "Accepted" electric etched on the identification tag. Any assembly which fails in the proof load test shall be rejected. The noises heard during proof loading that sound like wires breaking shall not be considered as cause for rejection.

4.5.6 Tension. This test applies to all bridles and pendants. The tension test specimens shall be tested in straight tension pull until failure occurs. The test specimens shall have a breaking strength not less than 92 percent of the minimum value given in the wire rope specification. There shall be no defects beyond limits set forth in the applicable drawing.

4.5.7 Repeated load. The bridle or pendant shall be tested by 200 applications of proof load (see 4.5.5) and then loaded at a maximum rate of 300,000 pounds per minute, as shown in the Destruction Test diagram on the applicable drawings. Failing load of the assembly shall equal or exceed the minimum breaking strength specified on the applicable drawing. There shall be no defects beyond limits set forth in the applicable drawing.

4.5.8 Destruction. The bridle or pendant shall be tested by application of loading, at a maximum rate of 300,000 pounds per minute, as shown in the Destruction Test diagram on the applicable drawings. Failing load of the assembly shall equal or exceed the minimum breaking strength specified on the applicable drawing. There shall be no defects beyond limits set forth in the applicable drawing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

4.5.9 Dynamic. The dynamic test shall consist of satisfactory overall performance when any individual assembly is used in a maximum of 200 repeated launchings. A spectrum of loading shall be used consisting of 80, 90 and 100 percent limit load application then repeating until a maximum of 200 launches are made or service life is reached. Launchings shall be made using catapults and service type aircraft or simulated by testing in devices of a Government designated test laboratory. There shall be no defects beyond limits set forth in the applicable drawing.

* 4.6 Test reports. The contractor shall submit in duplicate test reports on all tests required on the applicable drawings and this specification to NAVAIR (copy to NAEC), via the cognizant Government inspector within one month after completion of each lot (see 4.4.1 and 6.4). These reports shall indicate:

a. part number for the assembly tested
b. serial number
c. Contract number
d. lot number
e. code number
f. notation of failure location
g. photographs showing failures
h. certification of test equipment calibration

* 4.7 Inspection of packaging. Except when commercial packaging is specified, the sampling and inspection of the preservation and interior package marking shall be in accordance with groups A and B quality conformance inspection requirements of MIL-P-116. The sampling and inspection of the packing for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification shown in Section 5. The inspection of marking for shipment and storage shall be in accordance with MIL-STD-129. The inspection of commercial packaging shall be as specified in the contract (see 6.2).

5. PACKAGING

5.1 Cleaning and preservation. Terminals shall be cleaned in accordance with process C-1 of MIL-P-116 and the entire assembly coated with P-1 preservative in accordance with MIL-P-116, Method I.

5.2 Packing. Packing shall be Level A, B or C as specified (see 6.2).

5.2.1 Assembly packing. The assemblies shall be packed in accordance with MIL-STD-2073-1. Boxes shall be designed and constructed to provide a compact non-shifting load for safe transportation to destination at the lowest freight classification rate.

5.3 Marking. Containers shall be marked in accordance with MIL-STD-129.

5.3.1 Additional marking. The following marking shall also be added:

a. Identification symbol (see 3.4.1.1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. This specification covers bridle and pendant wire rope assemblies intended to be used in military aircraft launchings.

* 6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of the specification.

b. Issue of Department of Defense Index of Specifications and Standards (DODISS) to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1).

c. The contractor should affirm, on bid submittal, that the mechanical splice sleeves utilized develop 92 percent of the full rated breaking strength of the wire rope without slippage and without damage or deformation of the mechanical splice sleeves.

d. The test laboratory to perform qualification and acceptance testing should be designated by the Government.

e. Selection of applicable levels of preservation and packing.

f. No deviation from any of the requirements of this specification and applicable drawings shall be permitted unless specifically authorized in writing by the Naval Air Systems Command, Code AIR-551, Department of the Navy, Washington, D.C. 20361-0001. A copy of the letter requesting the deviation shall be forwarded to the Naval Air Engineering Center, Code 50, Lakehurst, NJ 08733-5000.

* 6.3 Data requirements. The following Data Item Description (DIDs) must be listed, as applicable, on the Contract Data Requirements List (DD Form 1423) when this specification is applied on a contract, in order to obtain the data, except where DOD FAR Supplement 27.475-1 exempts the requirement for a DD Form 1423.

Reference Paragraph	DID Number	DID Title	Suggested Tailoring
4.3.3.1 & 4.6	VDI-T-20266	Test Reports	Wherever possible, use the contractors standard test report format.

The above DIDs were those cleared as of the date of this specification. The current issue of DOD 5010.12-L, Acquisition Management Systems and Data Requirements Control List (AMSDL), must be researched to ensure that only current, cleared DIDs are cited on the DD Form 1432.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

6.4 Samples, tests and transportation costs. The cost of the qualification samples and their transportation to the testing laboratory are to be paid by the prospective qualifier. The cost of the production samples and their tests are to be paid by the Government but the transportation of these samples to the test facility are to be paid by the manufacturer.

* 6.5 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contact, qualified for inclusion in Qualified Products List QPL No. 22036 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or purchase orders for the products covered by this specification. The activity responsible for the Qualified Products List is:

Commander
Naval Air Systems Command
Code AIR-551
Department of the Navy
Washington, DC 20361-0001

and information pertaining to qualification of products may be obtained from that activity. Requests should specifically itemize the type and part numbers of the assemblies upon which qualification is desired.

6.5.1 Qualification of specific types of bridles or pendants. Contractors who qualify for a specific bridle (or pendant) are considered qualified suppliers of all bridles (or pendants) included in that general type; e.g., qualification of NAEC 608503-1 forged eye bridles constitutes qualification of all Type III items. Contractors who may qualify for Type V bridles are also qualified for Type III bridles; however, qualification for Type III bridles is not considered qualification for Type V bridles.

6.5.2 Contractor-NAEC conferences prior to qualification. The prospective contractor shall confer with NAEC during the early stages of qualification in order to take advantage of exchange of engineering and design information. The first conference should take place prior to manufacturing the qualification test samples. Other conferences can take place during the production of qualification samples of the assembly.

6.6 Facility survey. As a preliminary to the qualification procedure and at any time during production, the NAEC will survey manufacturing facilities to ascertain ability to fabricate, process, test bridles and pendants and meet Service production needs. Manufacturing facilities considered unsatisfactory to the NAEC will be cause for rejection of the contractor's request for qualification (or cancellation of the contract where production is involved).

* 6.7 Definitions.

6.7.1 Data. For the information of Contractors and Contracting Officers, any of the data specified in (a) subparagraphs below, (b) applicable documents listed in Section 2 of this specification, or (c) referenced lower-tier

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

documents need not be prepared for the Government and shall not be furnished to the Government unless specified in the contract or order. The data to be furnished shall be listed on DD Form 1423 (Contractor Data Requirements List), which shall be attached to and made a part of the contract or order.

* 6.7.1.2 Drawings and data list. Drawings, engineering and associated lists of the test equipment should be in accordance with DOD-D-1000.

* 6.7.1.3 Test reports submitted prior to qualification. Test reports submitted prior to qualification should be as specified in 4.3.3.1.

6.7.1.4 Qualification test reports. Test reports for qualification should be submitted as specified in 4.3.3.1 and 4.6.

6.7.1.5 Inspection lot test reports. Test reports for acceptance should be submitted as specified in 4.4.1. (Note 1) and 4.6.

6.7.1.6 Production control test reports. Test reports should be submitted for production control inspections as specified in 4.4.3 and 4.6.

* 6.7.2 NAVAIR and NAEC. Where reference is made in this specification to NAVAIR correspondence, where required, it should be addressed to:

Commander
Naval Air Systems Command
Code AIR-551
Department of the Navy
Washington, DC 20361-0001

Where NAEC is to be contacted the address should be:

Commanding Officer
Naval Air Engineering Center
Code 50
Lakehurst, NJ 08733-5100

6.7.3 Production items. The production items supplied under contract shall be identical in every respect to the corresponding Government approved qualification sample and drawings, except for changes which have been previously approved by the NAVAIR. Evidence of unauthorized change from the Government approved sample or drawings will constitute cause for rejection.

* 6.8 Subject term (key word) listing.

Airplane Catapult
Catapult Equipment
Forged eye bridles
Launching Equipment, Shipboard
Wire rope assemblies, Catapult
Reinforced Apex or forged eye catapult equipment

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.

* 6.9 Marginal indicia. The outside margins of this specification has been marked with an asterisk to indicate where changes form the previous issue have been made. This has been done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content as written irrespective of the marginal notations and relationship to the previous issue.

Preparing activity
Navy - AS
Project No. 1720-NO16

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:57Z
Check the source to verify that this is the current version before use.