MILITARY SPECIFICATION

PLASTIC STRIP, DENTURE TRIAL PACK

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers polyethylene strips suitable for use in the trial packing and processing of dentures.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

SPECIFICATIONS

Federal

L-P-378	Plastic Film (Polyethylene Thin Gage)
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Box, Setup.

Military

MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

FSC 6520

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:38Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, and drawings required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing Materials:

D-882-61T	Tests for Tensile Properties of Thin Plastic Sheeting (Tentative)
D-1505-63T	Method of Test for Density of Plastics by the Density-Gradient Technique.

(Application for copies should be addressed to the American Society for Testing Materials, 1916 Race Street, Philadelphia 3, Pa.

3. REQUIREMENTS

3.1 Material. The plastic strip shall be fabricated from type 1, class L and grade 1, 2 or 3 polyethylene containing a lubricant, if necessary, and formulated to meet the requirements of L-P-390. The finished plastic strip shall be flexible unsupported polyethylene film.

3.1.1 Color. The film shall be transparent and natural in color.

3.2 Dimensions. Strips shall be 4 ± 1/8 inches by 4 ± 1/8 inches square, and 0.001 ± 0.00045 inch thick. The overall variation in thickness per strip shall not exceed 0.0008 inch.

3.3 Physical properties. The polyethylene plastic strips shall conform to the physical properties specified in table I, and shall pass the tests specified in 4.2.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:38Z
Check the source to verify that this is the current version before use.

Table I. Physical properties.

Characteristics	Requirements	Units
Density	.910 - .925	g/cm^3
Tensile strength		
a. Machine direction	1700	Minimum psi
b. Traverse direction	1200	Minimum psi
Ultimate elongation		
a. Machine direction	225	Minimum Percent
b. Traverse direction	350	Minimum Percent

4 Performance. The strip shall be suitable for use in the trial packing dentures and as a barrier between the gypsum cast and the denture during ocessing. The strip shall not adhere to denture or model, so that its moval is quick and easy when tested as specified in 4.4.3.

5 Finish. The strips shall be transparent and shall have a smooth, unbbled surface texture.

6 Workmanship. The workmanship shall be first class throughout. The rips shall be uniform in texture, and finish. They shall be free from emishes, pin holes, and other imperfections which may detract from their pearance or may impair their serviceability.

QUALITY ASSURANCE PROVISIONS

1 Responsibility for inspection. Unless otherwise specified in the contact or purchase order, the supplier is responsible for the performance of l inspection requirements as specified herein. Except as otherwise specified, e supplier may utilize his own facilities or any commercial laboratory ceptable to the Government. The Government reserves the right to perform y of the inspections set forth in the specification where such inspections e deemed necessary to assure supplies and services conform to prescribed quirements.

1.1 Inspection. Inspection, as used in this specification, is defined both examination (such as visual, auditory, etc., investigation without e use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

1.2 Certificates of quality. When available, certificates of quality, pplied by the manufacturer of the component or material, listing the ecified test method and test results obtained, may be furnished in lieu of tual performance of such testing by the contractor.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:38Z
Check the source to verify that this is the current version before use.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105.

4.2.2 For tests. Sampling for end item testing shall be conducted in accordance with MIL-STD-105 and as indicated in table II. The unit of product for inspection purposes shall be 1 package of plastic strip.

Table II. Sampling Criteria.

Characteristic	Requirements	Test Procedure	Inspection level	AQL (percent defective)
Density **	3.3	4.4.1	S2	*
Tensile strength ***	3.3	4.4.2	S2	*
Ultimate Elongation ***	3.3	4.4.2	S2	*
Working qualities ****	3.4	4.4.3	S1	*
Dimensions	3.2	SMI and 4.4.4	S2	
a. Thickness		4.4.4		2.5
b. Length and Width		SMI		4.0

* Acceptance number shall be zero.

** Three specimens shall be tested from each unit of product sampled. If the average of the three results does not comply, the item shall be rejected.

*** Five specimens shall be tested from each unit of product sampled. If the average of the five results does not comply, the item shall be rejected.

**** Two specimens shall be tested from each unit of product sampled.

4.2.3 Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

4.3 Examination. The plastic strips shall be examined to determine compliance with all requirements contained in this specification.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:38Z
Check the source to verify that this is the current version before use.

4.4.1 Density. Density shall be determined in accordance with American Society for Testing Materials Standard D-1505-63T.

4.4.2 Tensile strength and elongation. The tensile properties shall be determined in accordance with American Society for Testing Material Standard D-882-61T.

4.4.3 Working qualities. The strips shall be used in trial packing of an acrylic denture and as a barrier between the resin and the gypsum cast during curing in accordance with accepted dental laboratory procedures.

4.4.4 Thickness. The thickness shall be determined in accordance with L-P-378, except the tolerance shall be as specified in 3.2.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. Two hundred strips, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table III shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table III. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	12 units	144 units

5.1.2.1 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:38Z
Check the source to verify that this is the current version before use.

5.1.3 Level A. Unit package shall be a carton of appropriate size constructed in accordance with PPP-B-676, except that commercial colors shall be acceptable. The carton may be designed with cut outs, or constructed in such a manner as to serve as a dispensing unit. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a carton of appropriate size constructed in accordance with Federal Specification PPP-B-566 or PPP-B-676, except that commercial colors shall be acceptable. Closure shall be adequate to prevent spillage of contents under normal handling.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-636, type CF, class weather-resistant.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.1.3 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix, and waterproofing shall conform with 30.4 of PPP-B-6

5.2.1.4 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

NOTE: Strapping shall not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

Source: https://assist.dla.mil -- Downloaded: 20261O-21T08:38Z
Check the source to verify that this is the currentversion before use.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-636, type CF, class domestic and method I closure shall be utilized.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Polyethylene strips are suitable for use in the trial packing of dentures (see 3.4).

6.2 Ordering data. Procurement documents should specify the following:

(a) Number and date of this specification.
(b) Selection of applicable levels of packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:38Z
Check the source to verify that this is the current version before use.

6.3 This specification does not cover all types, classes, grades, or sizes of the commodity indicated by the title of this specification, or those which are commercially available, but is intended to cover the types whi are normally procured to meet requirements.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

N

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:38Z
Check the source to verify that this is the current version before use.