MIL-S-36456B
8 September 1986
SUPERSEDING
MIL-S-36456A
18 February 1976

MILITARY SPECIFICATION

SCISSORS, ORAL SURGICAL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.2 Scope. This specification covers scissors suitable for use in oral surgical procedures.

1.2 Classification. Scissors shall be of the following types as specified (see 6.1).

Type I - Curved

Type II - Angular (Dean)

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation.

AMSC N/A FSC 6520

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-RST, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

Federal

GG-I-526	- Instruments, Dental and Surgical; General Specifications.
ZZ-R-690	- Rubber Dam, Dental
PPP-B-566	- Boxes, Folding, Paperboard.
PPP-B-601	- Boxes, Wood, Cleated-Plywood.
PPP-B-621	- Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-676	- Boxes, Setup.

Military

MIL-P-116	- Preservation, Methods of.
MIL-L-10547	- Liners, Case and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

STANDARDS

Federal

FED-STD-151	- Metals; Test Methods.

Military

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.
MIL-STD-147	- Palletized Unit Loads.
MIL-STD-794	- Parts and Equipment, Procedures for Packaging of.

DRAWING

Defense Personnel Support Center (DPSC)

20458 Scissors, Oral Surgical

(Copies of specifications, standards, and drawings required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issue of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the non-government documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

E 18 - Standard Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials.

E 92 - Standard Test Method for Vickers Hardness of Metallic Materials.

F 899 - Standard Specification for Stainless Steel Billet, Bar and Wire for Surgical Instruments.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General requirements. The scissors shall be in accordance with the applicable requirements for class 4, type 420 stainless steel of GG-I-526, except for material (see 3.2), and with the additional options and requirements specified herein.

3.2 Material. Scissors shall be fabricated of class 4, Type 420B, 420X, 420C or 420F, as specified in ASTM F899, except the screw shall be fabricated of class 4, Type 416 material.

3.3 Style, design and dimensions.

3.3.1 Type I scissors. Type I scissors shall be curved, double-blunt surgical scissors suitable for use in oral surgery. Style, design and dimensions shall be in accordance with Defense Personnel Support Center (DPSC) Drawing 20458 for the applicable type.

3.3.2 Type II scissors. Type II scissors shall be of Dean design, angular, having double-sharp points, with uniform clean cut, saw-toothed blades and bowed shanks. Scissors shall be suitable for cutting the mucoperiosteal tissue in oral surgery and cartilage in orthopedic surgery. Style, design and dimensions shall be in accordance with DPSC Drawing 20458 for the applicable type.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

3.3.2.1 Drawings. The drawings forming a part of this specification are specification control drawings. The supplier shall be responsible for preparing his own shop drawings. Where tolerances prescribed could cumulatively result in improper design, the supplier shall provide a product with dimensions within the tolerances prescribed on the drawing to insure proper design, function, fit, assembly or operation of the item. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer.

3.4 Cutting edges. The scissors shall cut a continuous length of test material of at least 3/4 inch for Type I scissors and 1/2 inch for Type II scissors, when tested as specified in 4.4.2. The cutting requirement shall apply for the entire length of the cut specified herein, including the tips of the scissors. All three cuts made with each scissors tested shall meet the requirements of this specification.

3.5 Hardness. Scissors shall have a Rockwell hardness of C50 to C55, after proper stress relieving, except that if the screw is fabricated of class 4, Type 416 material, it shall have a minimum Rockwell hardness of C20.

3.6 Finish. Finish shall be entirely mirror, satin or matte, except the cutting edges and inside surfaces of blade shall have a crocus finish. Should the instrument be of mirror finish, the locks shall be polished smooth, but need not possess a mirror finish. The matte finish shall exhibit a uniform nondirectional surface texture equivalent to that produced by lightly blasting the prepared surface with a fine abrasive under pressure.

3.7 Identification marking. Each scissors shall be permanently and legibly marked in accordance with the requirements of GG-I-526. In addition, scissors of foreign manufacture shall also be marked "stainless".

3.8 Workmanship. The scissors shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the steel, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The Certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling for lot acceptance.

4.2.1 Sampling for examination. A random sample of scissors shall be selected from each lot offered to the Government in accordance with MIL-STD-105. The unit of product for examination purposes shall be one pair of scissors. The acceptable quality levels (AQLs) shall be as indicated in Table I.

Table I. Examination Criteria

Type defect	Inspection level	AQL (percent defective)
Major defects	II	1.0
Minor A	II	2.5
Minor B	S-2	4.0

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as indicated in table II. Sampling criteria for tests. The unit of product for test purposes shall be one instrument. Where feasible, the same unit of product shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

TABLE II. Sampling criteria for tests.

Characteristic	Requirement	Test Procedure	Inspection level	AQL
Material	3.2	4.4.1	See 4.2.2.1	-
Hardness	3.5 and GG-I-526	4.4.3	S-2	1.5
Cutting edges	3.4	4.4.2	II	1.0
Copper Sulfate test	GG-I-526	GG-I-526	S-2	1.0
Boil test	GG-I-526	GG-I-526	S-2	1.0

4.2.2.1 Sampling of raw material. A sufficient quantity from each lot of metal used in the construction of the scissors shall be used for composition analysis.

4.3 Examination. The scissors shall be examined to determine compliance with requirements contained in this specification. Examination shall be conducted as specified in table III. Any scissors in the sample containing one or more defects shall be rejected, and if the number of defective scissors in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected. The following listed defects indicate minimum inspection requirements.

Table III. Classification of defects

Categories	Defects
Major:	
101	Style and design not as specified for the applicable type.
102	Cutting action of scissors not free of excessive stiffness or looseness.
103	Screw in lock not permanently set in a fixed position.
104	Screw lock not properly assembled.
105	Cutting edges not free of nicks, feathers, and burrs.
106	Scissors not free of corrosion, discoloration, pits, and burrs.
107	Scissors not free of cracks.
108	Cutting edge of scissors not uniformly sharp.
109	Cutting edge of Type II scissors not uniformly saw toothed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

Table II. Classification of defects (cont.)

Categories	Defects
Minor A:	
201	Finish not mirror, satin or matte (excluding crocus - finished sharpened surfaces). applicable type.
202	Finish not free of coarse grind marks or scratched surface areas.
203	Identification marking not permanent, legible, or complete.
Minor B:	
251	Dimensions not within tolerance shown in drawing.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Chemical analysis. In the absence of certificates of quality for the raw material, chemical analysis shall be conducted in accordance with method 111 or method 112 of FED-STD-151. In case of dispute, method 111 shall govern.

4.4.2 Scissors performance test. The test material shall be dental rubber dam material, medium thickness (0.007 to 0.009 inch) and in accordance with ZZ-R-690. Scissors to be tested shall be cleaned prior to test performance. Three separate, consecutive tests shall be performed for each scissors. Each test shall consist of making one cut through three plies of test material. Each cut shall be made using the scissors in the normal manner (with the examiner's fingers in the finger rings of the instrument), except that no lateral pressure shall be exerted.

4.4.3 Hardness. Hardness shall be determined in accordance with ASTM Designation E 18 (Rockwell) or E 92 (Vickers or Diamond Pyramid).

4.4 Inspection of packaging. The sampling and inspection of the preservation and interior package marking shall be in accordance with groups A and B quality conformance inspection requirements of MIL-P-116. The sampling and inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C, as specified (see 6.1).

5.1.1 Level A.

5.1.1.1 Cleaning and drying. Scissors shall be cleaned and dried in accordance with MIL-P-116.

5.1.1.2 Preservative applications. Preservatives shall not be used.

5.1.1.3 Unit package. Each pair of scissors shall be packaged in accordance with MIL-P-116, method IC-1.

5.1.1.4 Intermediate package. Six unit packages containing scissors of one type only shall be packaged in a box conforming to PPP-B-566, PPP-B-636, class domestic or PPP-B-676. Closure shall be as specified in the applicable box specification.

5.1.2 Level C. The level C preservation for scissors shall conform to the MIL-STD-794 requirements for this level.

5.2 Packing. Packing shall be level A, B, or C as specified, (see 6.1).

5.2.1 Level A. Twenty-four (24) intermediate packages (144 units) containing scissors of one type only shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-601, overseas type, PPP-B-621, class 2 or PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall be as specified in the liner specification. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed as specified in PPP-B-636.

5.2.2 Level B. Twenty-four (24) intermediate packages (144 units) containing scissors of one type only shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-601, domestic type, PPP-B-621, class 1 or PPP-B-636, class domestic. Closure shall be as specified in the applicable box specification.

5.2.3 Level C. The level C packing for scissors shall conform to the MIL-STD-794 requirements for this level.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

5.2.4 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.2.5 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination equal 40 cubic feet or more. Loads shall be unitized on pallets conforming to MIL-STD-147. Quantities less than 40 cubic feet need not be unitized. Pallet loads including the pallet shall not exceed 43 inches in height, 48 inches in width, and 40 inches in length. Pallet shall conform to Type IV or Type V.

5.2.5.1 Levels A and B. Scissors packed as specified in 5.2.1 and 5.2.2, shall be unitized on pallets as specified in 5.2.5.

5.2.5.2 Level C. Scissors packed as specified in 5.2.3 shall be unitized as specified in MIL-STD-794.

5.3 Marking.

5.3.1 Levels A, B and C. Each unit pack, intermediate package, exterior container, and unitized load shall be marked as specified in MIL-STD-129.

5.4 General.

5.4.1 Exterior container. Exterior container (see 5.2.1, 5.2.2 and 5.2.3) shall be of minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

5.4.2 Packaging inspection. The inspection of these packaging requirements shall be accordance with 4.5.

6. NOTES

6.1 Ordering data.

6.1.1 Acquisition requirements. Acquisition documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type required (see 1.2).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

6.2 National Stock Number (NSN) coverage. This specification covers the following items appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6520-00-554-9150	SCISSORS, ORAL SURGICAL, Curved, 4-3/4 inch (12.06 cm).
6520-00-555-1150	SCISSORS, ORAL SURGICAL, Dean, Angular, 6-3/4 inch (17.14 cm).

6.3 Subject term (key word) listing.

Angular (Dean) Scissors
Curved Scissors
Oral Surgical Scissors

MILITARY INTERESTS

Custodians:

Army - MD
Navy - MS
Air Force - 03

Review Activities:

Army - MD
Navy - MS
Air Force - 03

Civil Agency Coordinating Activities:
VA-OSS
PHS
FDA-MPQAS

Preparing Activity:

DoD-MB

Agent:

DLA-DM

Project No. 6520-1920

49104

Location: NCR - DISK 3

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS In a continuing effort to make our standardization documents better, the DoD provides this form for use in bmitting comments and suggestions for improvements. All users of military standardization documents are invited to provide uggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

Fold along this line

Fold along this line

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO. 12062 WASHINGTON D.C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
Defense Personnel Support Center
ATTN: DPSC-RST
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:37Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-36456B	SCISSORS, ORAL SURGICAL

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* - Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* - Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* - Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426

Source: https://assist.dla.mil - Downloaded: 2026-10-21T08:37Z
Check the source to verify that this is the current version before use.