MILITARY SPECIFICATION

CLOTH, NONWOVEN, DISPOSABLE, SPUNBONDED POLYPROPYLENE

This specification is approved for use by the Navy Clothing and Textile Research Facility, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1. Scope This specification covers the requirements for one type of nonwoven disposable cloth made of spunbonded polypropylene.

2. APPLICABLE DOCUMENTS

2.1 Issue of documents The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATION

FEDERAL

PPP-P-1136 - Packaging and Packing of Coated (Plastic; Rubber) and Laminated Fabrics

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods
FED-STD-751 - Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be address to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Standard sample When a standard sample is available, the finished cloth shall be equal to or better than the sample with respect to all characteristics for which the standard sample is referenced (see 6.2).

3.2 First article When specified (see 6.2), the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.2).

3.3 Cloth, nonwoven The nonwoven cloth shall be fabricated of polypropylene fibers in mat form and bonded together with heat and pressure. The color shall be any shade of white. The cloth shall conform to the requirements specified in Table I when tested as specified in 4.5.

Table I - Physical requirements

Weight, oz/sq yd (maximum)	2.5
Breaking strength, lbs (minimum)	
Machine direction	23.0
Cross direction	30.0
Tearing strength, grams (minimum)	
Machine direction	450
Cross direction	450
Seam efficiency, %	80.0
Water resistance, inches (minimum)	6.0
Flame resistance	
Machine and cross directions	
After flame, seconds (maximum)	3.0
After glow, seconds (maximum)	3.0
Char length, inches (maximum)	9.0
Air permeability, cu ft/min (minimum)	80.0

3.4 Length, width and put up The cloth shall be put up on rolls as specified in PPP-P-1136. The length and width shall be as specified (see 6.2).

3.5 Workmanship The finished cloth shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable quality levels.

4. QUALITY ASSURANCE PROVISIONS

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

4.1 Responsibility for inspection Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements as specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 First article inspection The first article submitted in accordance with 3.2 shall be inspected as specified in 4.3.2 for compliance with construction, workmanship, and end item testing.

4.3 Inspection Sampling for inspection shall be in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated hereinafter.

4.3.1 Component and material inspection In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.3.2 Examination of the end item The end item shall be examined in accordance with the classification of defects and at the inspection levels and acceptable quality levels (AQL's) set forth below.

4.3.2.1 Yard-by-yard examination The required yardage of each roll shall be examined, and defects clearly noticeable at normal inspection distance (3 feet) shall be classified as listed. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the most serious defect shall be counted. A continuous defect shall be counted as one defect for each yard or fraction thereof in which it occurs. The sample unit shall be one linear yard. The acceptable quality level shall be 4.0 defects per 100 units for all defects listed. The sample size shall be in accordance with inspection level II of MIL-STD-105. The lot size shall be expressed in units of one yard each. The number of rolls selected shall be in accordance with Table II. An approximately equal number of yards shall be examined from each roll in the sample.

Defects
Any hole, cut or tear.
Any imedded foreign matter.
Any unbonded area of delamination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

4.3.2.2 Overall examination Each defect shall be counted not more than once in each roll examined. The sample unit shall be one roll. The sample size and the acceptance number shall be as shown in Table II.

Defects

Color not as specified.
Overall uncleanness.
Width less than specified.
Objectionable odor.

Table II - Sample size

Lot size (yards)	Sample size (rolls)	Acceptance number
Up thru 1200 1/	3	0
1201 thru 3200	5	0
3201 thru 10,000	8	0
10,001 thru 35,000	13	0
35,001 thru 150,000	20	1
150,001 and over	32	2

1/ If the lot contains fewer than 3 rolls, each piece in the lot shall be examined.

4.3.3 Examination for length

4.3.3.1 Individual rolls During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket, shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.3.3.2 Total yardage in sample The lot shall be unacceptable if the total of the actual length of rolls in the sample is less than the total of the lengths marked on the tickets.

4.4 Examination of packaging requirements An examination shall be made in accordance with the provisions of PPP-P-1136 to determine whether packaging, packing, and marking comply with Section 5 requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

4.5 Testing of the end item The methods of testing specified in FED-STD-191 wherever applicable and as listed in Table III shall be followed. The physical and chemical values specified in Section 3 shall apply to the results of the determination made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 2 yards full width of the cloth. The lot shall be unacceptable if one or more sample units fail to meet any requirement specified. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be as follows:

Lot size in yards	Sample size
800 or less	2
801 thru 22,000	3
22,001 and over	5

Table III - Test methods

Characteristic	Requirement Paragraph	Test Method
Weight	Table I	5041
Breaking strength	Table I	5100
Tearing strength	Table I	5132
Seam efficiency	Table I	5110 1/
Water resistance	Table I	5514
Flame resistance	Table I	5903
Air permeability	Table I	5450

1/ Except that the seam type shall be SSn or SSp and stitch type 504 or 505 as specified in FED-STD-751.

5. PACKAGING

5.1 Preservation-packaging Packaging shall be level A or C, as specified (see 6.2 and 6.2.1).

5.1.1 Levels A and C The cloth, put up as specified (see 3.4), shall be packaged in accordance with the applicable requirements of PPP-P-1136.

5.2 Packing Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Levels A, B, and C The cloth shall be packed in accordance with the applicable requirements of PPP-P-1136.

5.3 Marking In addition to any special marking required by the contract or order (see 6.2), shipments shall be marked in accordance with the applicable requirements of PPP-P-1136.

6. NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

6.1 Intended use The nonwoven cloth covered by this specification is intended primarily for use in the fabrication of general purpose type disposable clothing.

6.2 Ordering data Procurement documents should specify the following:

a. Title, number and date of this specification.
b. Requirements for the first article (see 3.2).
c. Length and width required (see 3.4).
d. Levels of packaging and packing required (see 5.1 and 5.2).

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives, as indicated in PPP-P-1136 may be exercised in packaging the cloth.

6.3 Standard sample For access to the standard sample, address the procuring activity issuing the invitation for bids.

6.4 Source of cloth Nonwoven cloth conforming to the requirements of this specification may be obtained from the Kimberly-Clark Corporation, Neenah, Wisconsin 54956 under their designation SB (SPF).

Custodian:
Navy - NU

Review activity:
DLA - CT

User activity:
Navy - SH

Preparing Activity:
Navy - NU

Project No. 8305-N771

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-C-87092(NU) Cloth, Nonwoven, Disposable, Spunbonded Polypropylene

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1426 1 OCT 76 Replaces edition of 1 Jan 72 which may be used. S/N 0102-LF-001-4260

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Officer In Charge
Navy Clothing and Textile Research Facility
21 Strathmore Road
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:43Z
Check the source to verify that this is the current version before use.