A-A-12
March 6, 1980

COMMERCIAL ITEM DESCRIPTION

FLOOR CLEANING AND POLISHING COMPOUND

The General Services Administration has authorized the use of this commercial item description in lieu of Federal Specification P-C-449.

This commercial item description covers a floor cleaning and polishing compound intended primarily for use on wood and cork tile floors. The product is to be used without dilution and applied by the use of a steel wool pad under a concentrated weight polishing machine or other suitable means. As this product may contain petroleum solvents, it should be used only with extreme care on other types of floor tile.

Salient characteristics:

The cleaning compound shall be free of extraneous matter, lumpiness, and separation of solvents.

Consistency. The cone penetration shall be in the range of 260 - 350 tenths of a millimeter when tested according to ASTM D 217.

Nonvolatile matter. Weigh to the nearest milligram approximately 2 g of the sample and place in a tared, dried flat bottom dish in a forced draft drying oven and heat at 105° - 110° C for 16 hours. Cool to room temperature in a desiccator and calculate the percent nonvolatile matter. The nonvolatile matter content of the cleaner shall be 20 to 30 percent.

Miscibility. Place 50 ± 2.5 g of the sample in 500 ml distilled water in an 800-ml beaker. Stir with a magnetic stirrer for 10 minutes. The sample shall be readily dispersed into a uniform emulsion. After 2 hours, there shall be no evidence of separation of the emulsion.

Gloss enhancement. Apply a coat of the cleaner-polish to a sealed planed wood panel. Allow the coat to dry for 2 hours and then polish with a No. 00 steel wool pad. Apply a second coat on the first coat and allow to dry for 18 hours. After polishing the second coat with a steel wool pad, measure 60 degree specular gloss. The specular gloss shall be not less than 10.

Static coefficient of friction. Using duplicate sealed and polished wood panels, determine the static coefficient of friction in accordance with ASTM D 2047. The coefficient shall be not less than 0.50.

The issues of ASTM D 217 and ASTM D 2047 in effect on the date of the solicitation shall be used to determine compliance with stated requirements.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices and is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Packaging, packing, and marking. The packaging and packing shall be in accordance with normal commercial practice and shall assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling, and storage. The shipping container shall be in compliance with the National Motor Freight Classification and Uniform Freight Classification. Marking shall be as specified in the contract or order.

Note: The ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 202610-24T02:56Z
Check the source to verify that this is the currentversion before use.