[METRIC]
A-A-13A
April 21, 1998
Superseding
A-A-13
June 22, 1982

COMMERCIAL ITEM DESCRIPTION

SWEEPING COMPOUND

The General Services Administration has authorized the use of this commercial item description, for all federal agencies.

1. Scope. This commercial item description covers three types of sweeping compounds for use in the maintenance of floors.

2. Types.

Type I Sawdust-sand-mineral oil
Type II Sawdust-sand-water wax emulsion
Type III Sawdust-wax base

3 Salient Characteristics:

3.1 The sweeping compound shall be a clean, homogeneous mixture free from lumps and caking, and conform to the following requirements:

Requirement (%)	Type I		Type II		Type III	
	Min.	Max.	Min.	Max.	Min.	Max.
Volatile matter at 105^{0}C, weight	---	12	---	12	---	12
Extractable Oil	10	26	---	---	---	---
Waxes & Emulsifiers, weight	---	---	15	20	30	45
Sand, weight	35	50	40	50	---	---
Sawdust, weight	22	---	18	---	43	70
Retained on No. 20 sieve, weight based on total sand content	---	1.0	---	1.0	---	1.0
Retained on No. 8 sieve, weight based on total sawdust content	---	1.0	---	1.0	---	1.0
Passing through No 40 sieve, weight based on total sawdust content	---	40.0	---	40.0	---	40.0
Ash content, weight	---	---	---	---	---	3.0

3.2 Matter volatile at 105^{0}C. Weigh 35 grams of the sample in a tared weighing bottle and heat with stopper removed for 2 hours in an oven at a temperature of 105 +/-2^{0}C. Insert stopper, cool in desiccator, and weigh. Repeat to a weight constant to within 0.1 gram. Calculate loss in weight as volatile matter. Save the dried sample for the extractable oil determination and for the waxes and emulsifiers determination.

Beneficial comments, recommendations, additions, deletions, clarification, etc., and any data which may improve this document, should be sent to: GSA, Paints and Chemicals Center, 400 15th Street, S.W., Auburn, WA 98001.

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026l0-24T02:56Z
Check the source to verify that this is the current version before use.

3.3 Extractable oil. Transfer, quantitatively. the dried sample mentioned above, to an extraction thimble. Pour 150 milliliters of ethyl ether, or Fluorocarbon 113 (Freon 113), into a tared 250 milliliter extraction flask. Assemble the extraction flask tube and condenser on a steam bath and extract for 10 cycles. Stop extraction process so as to retain the maximum volume of ether in the extraction flask. Connect extraction flask to a distilling condenser and distill off the ether using a steam bath. Remove the last trace of ether from the flask on the steam bath. Cool the flask in a dessicator, weigh and calculate the percentage of oil. Save the air-dried thimble residue for the sieve analysis.

3.4 Waxes and emulsifiers. The procedure and sample size, as specified above, should be used, except that chloroform shall be the extracting solvent instead of ether. The chloroform extract shall be in solid form at a temperature below 32^0C(90^0F.)

3.5 Sieve test. Using the thimble residue, test shall be made using a mechanical shaker which imparts to the sieves a rotary motion and tapping action of a uniform speed of 300 +/- gyrations and 150 +/- 10 taps of the striker per minute. Sieves shall conform to ASTM E 11.

3.6 Ashing procedure. Ash the material collected on each sieve separately and that which passed through the sieves. Ash the material to constant weight, cool in a desiccator, and record the weight of the ash in each sample. Calculate the percent of sand and sawdust. The sawdust content is the loss in weight during ashing.

3.7 Combustibility. The product shall not be permanently ignited and there shall be no spreading of flames on the product beyond an area of 1-1/2 inch radius from the center of the pan and shall cease within one minute after the pill is consumed when tested as follows: Loosely fill a 20 cm (8-inch) diameter metal container. such as a pie pan, to an even thickness of 13 to 19 mm (1/2 to 3/4 inch.) Place a standard methenamine pill in the center of the pan. Ignite the methenamine pill with a match in a draft free room.

3.8 Flash point. The flash point of the oil and waxes shall be a minimum of 125^0C (257^0F) when specified in ASTM D 93.

4. Product Conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices and be the same product offered for sale in the commercial market. The Government reserves the right to require proof of such conformance.

5. Notes.

5.1 The contractor may use his normal quality assurance procedures for manufacture of this product; however, should a disagreement arise between the Government and its customer or between the Government and the manufacturer concerning compliance to the salient characteristics of this commercial item description, the test methods and tests stated in this commercial item description will be used to determine compliance of the product.
5.2 ASTM standards are available from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

PREPARING ACTIVITY:
GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 202610-24T02:56Z
Check the source to verify that this is the current version before use.