COMMERCIAL ITEM DESCRIPTION

SCOURING POWDER (GLASS CLEANING)

The General Services Administration has authorized the use of this Commercial Item Description in lieu of Federal Specification P-S-320.

This commercial item description covers glass cleaning scouring powder used for safe cleaning of glass or other nitreous surfaces.

Salient characteristics.

Moisture and volatile matter at 105°C. The scouring powder shall contain not more than 4 percent by weight moisture and volatile matter when tested as specified in ASTM D 820, Sections 5-6.

Matter insoluble in water. The scouring powder shall contain not less than 85 percent by weight water-insoluble matter when tested according to ASTM D 820, Section 15. In addition, not more than one percent by weight of the matter insoluble in water shall be retained on a No. 100 U.S. Standard sieve.

Total alkali. The total alkali, calculated as Na_2O, shall be not more than 0.8 percent by weight when tested as specified in ASTM D 820, Sections 16-17.

Detergent. The scouring powder shall contain at least 4 percent by weight sum of soap and synthetic detergents when tested as specified in ASTM D 820, Sections 9-14, 35-41 and 46.

Odor. The scouring powder shall not have a strong or rancid odor.

Performance. When tested as follows the scouring powder shall remove all the test soil and not scratch the glass panel.

Make the soiling mixture by mixing the following ingredients to form a smooth paste:

Ingredient	Percent by weight
Lanolin, anhydrous	38.0
Asphalt (conforming to ASTM D 312, type II)	12.0
Turpentine	20.0
Lubricating oil, automotive, 30W, nondetergent	15.0
Lampblack (conforming to ASTM D 209)	15.0

Apply a thin, even film of the soiling mixture to one side of a clean, scratch-free 4 by 4 inch window-glass pane. Weigh out approximately 3 grams of scouring powder, spread on a wad of clean dampened cloth of soft material like unsized cotton and apply to the soiled glass panel with a circular hand motion. Let it dry, forming a film. Wipe the dried film off the glass panel with a clean dry cloth. The soiling mixture shall have been completely removed from the glass panel. There shall be no streaks or scratches on the glass. There shall be no fine abrasion of the glass surface which causes distortion or blurring of images seen through the glass panel.

The issues of the ASTM standards in effect on the date of the solicitation shall be used to determine compliance with the stated requirements.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices and is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Packaging, packing and marking. The packaging and packing shall be in accordance with normal commercial practice and shall assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling and storage. The shipping container shall be in compliance with the National Motor Freight Classification and Uniform Freight Classification. Marking shall be as specified in the contract or order.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103

FSC 7930

GSA-DC-81005508

Source: https://assist.dla.mil -- Downloaded: 202610-24T02:56Z
Check the source to verify that this is the current version before use.