INCH-POUND

A-A-50166A
August 30, 1994
SUPERSEDING
A-A-50166
May 12, 1988

COMMERCIAL ITEM DESCRIPTION

PADDING, COTTON, STITCHED ROVING

The General Services Administration has authorized the use of this commercial item description in preference to CCC-P-86.

1. SCOPE. This commercial item description covers the requirements for cotton padding to be used on flatwork ironers and pressing machines.

2. SALIENT CHARACTERISTICS. The padding shall be made of cleaned, natural color cotton roving, or a blend of 60 percent cotton/40 percent polyester roving which has been carded and drawn. The padding shall be fabricated to simulate a woven construction with the roving strands running widthwise and the stitching running lengthwise in row formation binding each roving strand in successive order. The padding shall be stitched with a single-needle chain stitch, at 6 to 8 stitches per inch with 2-ply combed cotton thread, ticket no. 60. The padding shall be furnished in rolls with continuous lengths of 45 to 55 yards. The finished padding shall conform to the physical requirements listed in Table I.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419.

AMSC N/A FSC 8320

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:40Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements

Characteristic	Requirement	Test Method
Thickness: inch 0.06	0.31 ± 0.06	ASTM D-1777
Weight: oz./sq. yd. (min.)	32.0	5040 1/ (full width short specimen method)
Width: inches (min.)	74.0	5020 1/ (short specimen method)
Strands of roving per inch	4 ± 1	5050 1/
Rows of stitching	4 ± 1	5050 1/

1/ Federal Standard 191 Test Method

2.1 Labels. The padding shall be labeled in accordance with commercial practices and shall contain the following information: contractor's name, contract number, and National Stock Number.

3. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. QUALITY ASSURANCE PROVISIONS

4.1 Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this commercial item description; conforms to the producer's own drawings, specifications, standards, and quality assurance practices; and is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.2 Market acceptability criteria. The item offered must have been sold to the commercial market or to the Government, and the contractor shall certify and provide supporting documentation as to its serviceability and the long term (five years) availability of all necessary maintenance and logistics support parts and materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:40Z
Check the source to verify that this is the current version before use.

4.3 Warranty. The item offered shall include the standard warranty given to the commercial market beginning with the date of delivery of the individual items.

4.4 Visual examination. Each roll of padding shall be examined for the defects listed below.

4.4.1 Defects. Any material with thin or weak places, cotton not natural color, or material not as specified; width not as specified; any discolorations; any cuts, tears, or holes; any stitching missing loose, broken, or wrong type; any permanent crease in cloth, shade bar, spot or stain; weight not as specified; label missing, illegible, or wrong legend; item not packaged as specified in the contract or purchase order.

4.5 Dimensional examination. The finished padding shall conform to the dimensions specified. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the roll ticket shall be considered a length defect. If the total of the actual lengths of the rolls is less than the total of the lengths marked on the roll tickets, the lot shall be rejected. The sample unit shall be one yard full width of the padding.

5. PACKAGING

5.1 Preservation, packing, and marking. The preservation, packing, and marking shall be as specified in the contract or purchase order.

6. NOTES.

6.1 Source of Government documents. Copies of military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

6.2 Source of non-Government documents

ASTM-D 1777 - Standard Method for Measuring Thickness of Textile Materials

(Applications for copies should be addressed to American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:40Z
Check the source to verify that this is the current version before use.

Custodians:
Army - GL
Navy - NU

Review Activities:
Army - MD
Navy - MC, MS
Air Force - 45

Civil Agency Coordinating Activity:
GSA - FSS

Preparing Activity:
DLA - CT

Project No. 8320-0104

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:40Z
Check the source to verify that this is the current version before use.