METRIC

MIL-PRF-8565/15A
14 July 2009
SUPERSEDING
MIL-B-8565/15
7 October 1994

PERFORMANCE SPECIFICATION SHEET

BATTERY, STORAGE, AIRCRAFT, MEDIUM-RATE, TYPE 1, MAINTENANCE-FREE, 24-VOLT, 35-AMPERE-HOUR

Reactivated after 14 July 2009 and may be used for new and existing designs and acquisitions.

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-8565.

REQUIREMENTS:

1. Part or identifying number. The part or identifying number (PIN) of the batteries covered by this specification sheet shall be D8565/15-1.

2. Dimensions and weight. The dimensions of the battery shall be as shown on figure 1. The weight of the battery shall be not greater than 40.82 kilograms (90.0 pounds) (see 3.8.3 and 4.5.3 of MIL-PRF-8565).

3. Capacity. The rated capacity of the battery shall be not less than 35 ampere-hours (Ah), based on its ability to conform to the life test final discharge (35.0 Ah/1 Hr/24°C/20.0 V). See 3.8.6, as modified by MIL-PRF-8565/15, and 4.5.7 and 6.10 of MIL-PRF-8565.

4. Service life. The battery's service life (useful life) in aircraft shall be not less than 4 years.

5. Qualification inspection and conformance inspection. Table I lists the required inspections.

6. MIL-PRF-8565 variance. The battery shall comply with MIL-PRF-8565 except as follows.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.

6.1 The following paragraphs are not applicable:

3.5.10 Heaters.
3.6.5 Marking for batteries with heaters.
3.8.16 Output performance.
3.8.17 Cold and hot temperature charge.
4.5.28 Output performance test.
4.5.29 Cold and hot temperature charge test.

6.2 Modify the following paragraphs:

6.2.1 Change "18.0 volts" to "20.0 volts" in the following paragraphs:
4.5.6 Electrical test preparation, first sentence.
4.5.7 Capacity discharge, second sentence.
4.5.11 Capacity discharge at 49°C (120°F), third sentence.
4.5.12 Charge and discharge test at low temperature, step c and step f, second sentence.
4.5.17 Temperature rise and float test, step e, second sentence.
4.5.22 Ground storage test, step d and i.
4.5.23 Physical integrity at high temperature test, step b and k.
4.5.26 Shelf life test, sixth sentence.
TABLE III Capacity performance requirements, requirements (1), (2), and (3).

6.2.2 Modify the following paragraphs as stated:

3.5.5 Receptacles. Add the following: "For D8565/15-1, the female receptacle (front view) shall be dimensionally equal to MS3509, style 1. The receptacle may be integrally molded in the container."

3.6.4 Battery caution marking. Delete MIL-PRF-8565 paragraph in its entirety and substitute the following: "Marking for Label 2 shown on figure 1 shall show the following with lettering height not less than 6.35mm (0.25 inch). The marking shall be in white or black print.

MAINTENANCE-FREE BATTERY

DO NOT REMOVE COVER

PROCESS THIS BATTERY IN ACCORDANCE WITH APPROVED PROCEDURES ONLY

SEE NAVAIR 17-15BAD-1 OR APPLICABLE SERVICE T.O."

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.

3.8.6 Capacity and electrical performance. Delete the entire text and insert: “The rated capacity of the battery shall not be less than 35 ampere-hours, based on its ability to conform to the life test final discharge. The battery shall produce not less than 20.0 volts at the C-rate for not less than 60 minutes at 24°C (35.0 Ah/1 Hr/24°C/20.0 V) after being tested in accordance with 4.5.7, as modified by MIL-PRF-8565/15. The discharge requirements and associated parameters shall be as shown in table III (see 6.10). Both table III and 6.10 are in MIL-PRF-8565. Battery capacity shall vary not greater than ± 5 percent within a given inspection lot. The tolerance of the discharge current shall be ± 1 percent of the specified value.

3.8.7 Constant voltage discharge. Delete the first sentence and insert: “The battery shall comply with the following requirements during the 14.0-volt constant voltage discharge:

Requirement	24°C	-26°C
a. Minimum Current at Peak Value (Time = 0+)	1300 amperes	800 amperes
b. Minimum Current after 15 seconds	1000 amperes	450 amperes
c. Minimum Capacity delivered after 60 seconds	13.67 ampere-hours	5.93 ampere-hours

Inability to deliver the specified minimum discharge current and capacity shall constitute a test failure.”

3.8.9 Cycling. In the first sentence, delete "100 cycles" and substitute "135 cycles".

3.8.13.3 Deep discharge recovery. Delete the second sentence and insert: “After such storage, the battery shall deliver not less than 35 ampere-hours after being tested in accordance with 4.5.27 of MIL-PRF-8565.”

4.4.2 Constant potential charging method. Delete MIL-PRF-8565 paragraph in its entirety and substitute the following: "Unless otherwise specified, the battery shall be charged at a constant potential of 28.5 ± 0.1 volts for 4.0 ± 0.1 hours with a power source having a current limit of 25 ± 1 amperes."

4.5.10 Cycling test. In the second sentence, delete "100 cycles" and substitute "135 cycles". In the third sentence, delete "2.0-hour" and substitute "4.0-hour".

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification inspection and conformance inspection of batteries.

Test number	Examinations and tests	Qualification inspection					Conformance inspection		
		Sample number			Requirement paragraph 1/	Test paragraph 1/	Group A sample 1 100%	Group B sample number	
		1	2	3				1	2
1	INCOMING INSPECTION	X	X	X	3.8.1(G)	4.5.1(G)	X	X	X
2	VISUAL AND MECHANICAL EXAMINATION	X	X	X	3.5 (S), 3.6 (S), 3.8.2 (G) table II (G)	4.5.2 (G)	X	X	X
3	DIMENSIONS AND WEIGHT	X	X	X	Reqmt 2 (N), 3.8.3 (G)	4.5.3 (G)	X 2/	X 2/	X
4	DIELECTRIC STRENGTH AND INSULATION RESISTANCE TEST	X	X	X	3.7 (G), 3.8.4 (G)	4.5.4 (G)	X 2/	X	X
5	STRENGTH OF VENT TUBES TEST	X	X	X	3.7 (G), 3.8.5 (G)	4.5.5 (G)	X 2/	X	X
6	ELECTRICAL TEST PREPARATION	X	X	X	--	4.5.6 (S)		X	X
7	CAPACITY DISCHARGE	X	X	X	Reqmt 3 (N), 3.8.6 (S), Reqmt 1 of table III (S)	4.5.7 (S)	X	X	X
8	CONSTANT VOLTAGE DISCHARGE	X	X		3.7 (G), 3.8.7 (S), Reqmt 4 of table III (G)	4.5.8 (G)	X	X	
9	STRENGTH OF RECEPTACLE TEST			X	3.7 (G), 3.8.8 (G)	4.5.9 (G)			
10	CYCLING TEST	X			Reqmt 4 (N), 3.8.9 (S), Reqmt 1 of table III (S)	4.5.10 (S)		X	
11	CAPACITY DISCHARGE AT 49 °C (120 °F)		X		3.8.6 (S), Reqmt 2 of table III (S)	4.5.11 (S)			
12	CHARGE AND DISCHARGE TEST AT LOW TEMPERATURE		X		3.8.6 (S), Reqmt 3 of table III (S)	4.5.12 (S)			X
13	DISCHARGE WHILE INVERTED		X		3.5.9 (G), Reqmt 5 of table III (G)	4.5.13 (G)			X
14	ALTITUDE TEST		X		3.5.9 (G), 3.7 (G), 3.8.10 (G)	4.5.14 (G)			X
15	SHOCK TEST (BASIC DESIGN)	X			3.7 (G), 3.8.10 (G)	4.5.15 (G)			
16	TEMPERATURE SHOCK TEST	X			3.7 (G) 3.8.10 (G)	4.5.16 (G)		X	
17	TEMPERATURE RISE AND FLOAT TEST		X		3.7 (G), 3.8.11 (G), Reqmt 1 of table III (S)	4.5.17 (S)			X
18	BATTERY GAS EMISSION TEST		X		3.8.10 (G), 3.8.12 (G)	4.5.18 (G)			

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification inspection and conformance inspection of batteries – Continued.

Test number	Examinations and tests	Qualification inspection					Conformance inspection		
		Sample number			Requirement paragraph 1/	Test paragraph 1/	Group A sample 1 100%	Group B sample number	
		1	2	3				1	2
19	VIBRATION TEST		X		3.7 (G), 3.8.10 (G)	4.5.19 (G)			
20	HUMIDITY TEST		X		3.7 (G), 3.8.10 (G)	4.5.20 (G)			X
21	SALT FOG TEST	X			3.7 (G) 3.8.10 (G)	4.5.21 (G)		X	
22	GROUND STORAGE TEST			X 3/	3.8.13.1 (G)	4.5.22 (S)			
23	DEEP DISCHARGE RECOVERY TEST			X	3.7 (G), 3.8.13.3 (S)	4.5.27 (G)			
24	PHYSICAL INTEGRITY AT HIGH TEMPERATURE TEST	X			3.7 (G), 3.8.10 (G), Reqmt 1 of table III (S)	4.5.23 (S)			
25	SHOCK TEST (CRASH SAFETY)	X			3.8.10 (G) 3.8.15 (G)	4.5.25 (G)			
26	IMPACT RESISTANCE TEST (NONMETALLIC BATTERY CONTAINER)		4/		3.8.14 (G)	4.5.24 (G)			
27	WORMGEAR RETAINING PIN HARDNESS		5/		3.5.5 (S)	4.5.30 (G)			
28	SHELF LIFE TEST			X	3.8.9 (S) 3.8.13.2 (G)	4.5.26 (S)			
29	FINAL EXAMINATION	X	X	X	3.7 (G), 3.8.4 (G)	4.5.31 (G)		X	X

1/ The notations in parentheses specify the source of the paragraph. "(G)" means the paragraph as shown in MIL-PRF-8565. "(S)" shows that the paragraph has been modified by this specification sheet. "(N)" indicates that a new paragraph or requirement has been added by MIL-PRF-8565/15(AS).


2/ See sample information in test paragraph.

3/ The manufacturer requesting qualification to this specification may submit an additional (fourth) test sample to expedite the qualification test program.

4/ For nonmetallic battery container designs, two outer nonmetallic battery containers shall be furnished for inspection.

5/ Five wormgear retaining pins shall be furnished for inspection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.




NOTES:

1. All dimensions are in millimeters.
2. Allow additional 4 mm width for cover.
3. Abbreviations used in this figure are maximum (MAX), minimum (MIN) and part identification number (PIN).

FIGURE 1. PIN D8565/15-1 dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.



NOTES:

1. All dimensions are in millimeters.
2. Allow additional 4 mm length for cover.
3. Abbreviations used in this figure are inside diameter (ID), outside diameter (OD), maximum (MAX), minimum (MIN) and radius (R).

FIGURE 1. PIN D8565/15-1 dimensions-Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.

6.19 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodian:
Navy - AS
Air Force - 84

Preparing activity:
Navy - AS
(Project 6140-2008-003)

Review activity:
DLA - GS

Agent:
Navy - SH

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:34Z
Check the source to verify that this is the current version before use.