INCH-POUND
MIL-B-18/250B
22 November 2010
SUPERSEDING
MIL-B-18/250A (ER)
28 May 1985

MILITARY SPECIFICATION SHEET

BATTERY, DRY, BA-399/U

INACTIVE FOR NEW DESIGN AFTER
10 AUGUST 1998 AND IS NO LONGER USED,
EXCEPT FOR REPLACEMENT PURPOSES.

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-B-18.



FIGURE 1. Battery dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:57Z
Check the source to verify that this is the current version before use.

Ltr	Inches		mm	
	Min	Max	Min	Max
A	.562	.625	14.27	15.88
B	.450	.563	11.43	14.30
C	.250	.313	6.35	7.95
D	.562	.625	14.27	15.88
E	.255	.270	6.48	6.86
F	.056	.111	1.42	2.82
G	.219	.229	5.56	5.82
H	.323	.378	8.20	9.60
J	1.875	1.938	47.63	49.23
K	.437	.500	11.10	12.70
L	3.062	3.125	77.77	79.38
M	.875	1.001	22.23	25.43

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.
3. Four holes to fit .094 inch (2.38 mm) pins.
4. Socket inset contacts are not required.
5. Socket opening in a non metallic jacket shall coincide with outer edge of battery on side shown.

FIGURE 1. Battery dimensions - Continued.

REQUIREMENTS:

Dimensions, marking, and configuration: See figure 1.

Nominal voltage: 15.0 volts.

Usual number and type of cells: 10 “R” cells.

Usual cell connection: Series.

Terminals: 4-hole socket.

Weight (maximum): 6.0 ounces.

Capacity tests: When the battery is tested in accordance with the methods of examination and test of this specification, the minimum capacity-test requirements shall be not less than the minimum time specified for SLD or SLT.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:57Z
Check the source to verify that this is the current version before use.

First article inspection in accordance with MIL-B-18:

Visual and mechanical (external).
Battery voltage.
Vibration test.
Mechanical-shock test in accordance with MIL-STD-202, method 213, test condition I.
Insulation resistance test in accordance with MIL-STD-202, method 302, test condition B, tolerance ±20 volts.
Capacity, D (without storage).
Jacket integrity test.

Conformance inspection in accordance with MIL-B-18:

Visual and mechanical (external).
Battery voltage.
Insulation resistance test in accordance with MIL-STD-202, method 302, test condition B, tolerance ±20 volts.
Vibration test.
Mechanical-shock test in accordance with MIL-STD-202, method 213, test condition I.
Jacket integrity test.
Electrode leakage.
Capacity, D and T.

Method of examination and test:

Capacity tests: See requirements for capacity specified herein.

Storage:

Test	Period
D	12 months
T	90 days

Discharge: The battery shall be discharged through a resistance of 100 ohms for 2 minutes, then remain on open circuit for 28 minutes. This cycle shall be repeated 5 days per week continuously to a test-end voltage of 10.0 volts.

Special marking on each unit package:

TO TEST THIS BATTERY WITH TS-183 ( )/U:

USE JACK NO.	MINIMUM PERMISSIBLE VOLTAGE
13	13.8

Unless expressly authorized, this test information shall apply to Army and Air Force applications only.

Part or Identifying Number (PIN): BA-399/U, see 1.2 of MIL-B-18.

Reference documents. In addition to MIL-B-18, this document references the following:

MIL-STD-202

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:57Z
Check the source to verify that this is the current version before use.

The margins of this specification are marked with vertical lines to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
DLA - CC

Preparing activity:
DLA - CC

(Project 6135-2010-064)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:57Z
Check the source to verify that this is the current version before use.