
MILITARY SPECIFICATION SHEET

BATTERY, DRY, BA-1086/U

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the dry battery described herein shall consist of this document and the latest issue of Specification MIL-B-18.



NOTES:

1. All dimensions shown on figure are in inches. Unless otherwise specified tolerance is ± 1/16 inch.

(A) denotes changes

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:58Z
Check the source to verify that this is the current version before use.

FSC 6135

NOTES: (Contd)

2. Metric equivalents specified in table are for general information only and are based upon 1 inch - 25.4 millimeters.

3. The cells making up the battery shall be made with a poly-vinyl-chloride barrier material or equivalent, and shall be sealed with a polyethylene seal or equivalent.

4. The polarity, voltage markings and jacket holes as indicated should be located in two places 180 degrees apart from each other.

5. Jacket hole opening of 1/4 ± 1/32 diameter for exposing cell case surface.

REQUIREMENTS:

Dimensions and configuration: See figure.

Nominal voltage: 11.7 volts
Tapped at: 2.6 volts.
Tapped at: 5.2 volts.

Usual number and type of cells: 9 "R-1R".

Usual cell connection: Series.

Terminals: Flat surface.

Weight (Maximum): 4.5 ounces.

(A) Capacity tests: When the battery is tested in accordance with the methods of examination and test of this Specification, the minimum capacity-test requirements shall be not less than the minimum time specified for SLD or SLT.

(A) First Article inspection:

Visual and mechanical (External).
Battery voltage.
Vibration test.
Mechanical-shock test per MIL-STD-202, method 213, test condition I.
Insulation resistance test per MIL-STD-202, method 302, test condition Letter B, tolerance ±20 volts.
Capacity, D (without storage).
Jacket integrity test.

(A) Quality conformance inspection:

Visual and mechanical (External).
Battery voltage.
Insulation-resistance test per MIL-STD-202, method 302, test condition Letter B, tolerance ±20 volts.
Vibration test.
Mechanical-shock test per MIL-STD-202, method 213, test condition I.
Jacket integrity test.
Electrode leakage.
Capacity, D & T.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:58Z
Check the source to verify that this is the current version before use.

Methods of examination and test:

Capacity tests: See requirements for capacity specified herein.

Storage -	Test	Period
	D	12 months
	T	90 days

Discharge - The battery shall be discharged through 315 ohms continuously to a test-end voltage of 8.1 volts.

Closed circuit voltage -

Special marking on each unit package:

TO TEST THIS BATTERY WITH TS-183 ( )/U:

USE JACK NO.	MINIMUM PERMISSIBLE VOLTAGE
11	9.0

Unless expressly authorized, this test information shall apply to Army and Air Force applications only.

Custodian:
Army - ER

Preparing activity:
Army - ER

Review activities:

Project Number: (6135-A-171-8)

User activities:
Army - ME, AV

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:58Z
Check the source to verify that this is the current version before use.