MILITARY SPECIFICATIONS

CLOTH, PLAIN WEAVE, NYLON

1. SCOPE

1.1 This specification covers the requirements for one type cloth, nylon, mesh, color black (see 6.4).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

CCC-T-191	Textile Test Methods
PPP-P-1133	Packaging and Packing of Synthetic Fiber and Silk Fabrics

STANDARDS

Federal

FED. STD. No. 4 Glossary of Fabric Imperfections

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

FEDERAL TRADE COMMISSION

Textile Fiber Products Identification Act, Effective March 3, 1960

(Copies may be obtained free of charge from the Federal Trade Commission, Washington 25, D. C.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Standard sample. The cloth shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Material

3.2.1 Yarn. The yarn for the warp and filling shall be monofilament nylon having a diameter of 0.008 plus or minus 0.001 inch.

*3.3 Color. The color of the cloth shall be lusterless black, shade 221.

3.3.1 Colorfastness. The finished cloth shall show fastness to perspiration and laundering equal to or better than the standard sample. When a standard sample is not established or not designated as applicable to colorfastness, the finished cloth shall show good fastness to perspiration and laundering when tested as specified in 4.4.

*3.3.2 Matching. The color of the fabric shall match the standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard shade under incandescent lamplight at 2800° Kelvin.

*3.4 Physical requirements. The finished cloth shall conform to the requirements specified in table I when tested as specified in 4.4.

*TABLE I. Physical requirements

Weight per square yard		Yarns per inch Minimum		Breaking strength Minimum		Weave
Ounces				Warp	Filling	
Min	Max	Warp	Filling	Pounds		----
4.8	5.2	50	35	200	175	Plain

3.4.1 Width. The finished minimum width of the cloth, inclusive of selvage, shall be as specified (see 6.2).

3.5 Finish. The cloth shall be heat treated at 350° ±5°F to achieve a stabilized cloth in accordance with the requirements specified in 3.6.

3.6 Shrinkage. The cloth shall not shrink more than 2.0 percent in the warp direction nor more than 1.5 percent in the filling direction when tested as specified in 4.4.

*3.7 Length. Unless otherwise specified (see 6.2), the cloth shall be in one continuous piece not less than 50 yards and shall be put up in rolls as specified in PPP-P-1133.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

3.8 Fiber identification. Each roll shall be ticketed, labeled, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act, Effective March 3, 1960.

3.9 Workmanship. The finished cloth shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the point level specified.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

*4.2 Examination of the end item. Examination shall be in accordance with the provisions of 4.2.1 through 4.2.4.

*4.2.1 Yard-by-yard examination. Thirty yards from each roll in the sample shall be examined on one side. The number of rolls from which the sample yardage shall be extracted shall be in accordance with the following:

Lot Size (Yards)	Sample Size (Rolls)
3200 or less	10
3201 up to and including 10,000	15
10,001 on over	25

An approximately equal number of yards shall be examined in each roll of the sample. The lot shall be unacceptable if the points per hundred yards exceed 30. Point computation shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Sample size (yards)} \times \text{contracted width of material (inches)}} = \text{Points per square yard.}$$

No more than one roll shall be taken from any shipping container unless the number of shipping containers in the lot is less than the required number of rolls, in which case all shipping containers shall be present in the sample. All defects, as defined in section III of Fed. Std. No. 4, that are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.2.1.1. No linear yard (increment of 1 yard on the measuring device of the inspection machine) shall be penalized more than 4 points.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects up to 3 inches in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

Note: The following defects, when present shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth

Width less than specified

Objectionable odor

Poor dye penetration, mottled, streaky, or cloudy.

4.2.2 Examination for length

4.2.2.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or two yards below the length marked on the ticket shall be considered a defect with regard to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets.

4.2.3 Examination for compliance with Textile Fiber Products Identification Act. During the yard-by-yard examination, each piece in the sample shall be examined for conformance to the Textile Fiber Products Identification Act. Each piece not labeled in accordance with this act shall be a defect. The lot shall be unacceptable if two or more of these defects occur.

4.2.4 Examination for shade. During the yard-by-yard examination, each roll shall be examined for shade. Two or more rolls in the sample off shade, shaded side to side, side to center, or end to end shall be cause for rejection of the entire lot represented by the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

4.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1133 to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation.

4.4 Tests. The method of testing specified in CCC-T-191, wherever applicable and as listed in table II shall be followed. The physical values specified in section 3 apply to the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 3 yards full width of the finished cloth. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. The sample size (number of sample units) and lot size expressed shall be in accordance with the following:

LOT SIZE (in yards)	SAMPLE SIZE
800 or less	2
801 to 22,000	3
22,001 and up	5

TABLE II. Test methods

Characteristic	Requirement reference	Test method
Yarn		
Monofilament	3.2.1	Visual 1/
Diameter	3.2.1	3
Fiber identification	3.2.1	3
Weave	Table I	Visual 1/
Yarns per inch	Table I	5050
Weight	Table I	5041
Breaking strength	Table I	5100
Colorfastness to:		
Perspiration	3.3.1	5680
Laundering	3.3.1	5614
Shrinkage	3.6	5556 2/

1/ One determination shall be made on each sample unit and the result reported as "pass" or "fail."

2/ Cotton laundering procedure in test method 5556 shall be used.

3/ The supplier shall submit a certificate of compliance for this characteristic. The certificate shall be accompanied by actual test, inspection, or other verifiable quality data.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

*5.1.1 Levels A and C. The cloth, put up as specified, shall be packaged in accordance with the applicable requirements of PPP-P-1133.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2 and 6.2.1).

*6.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1133.

*5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1133.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use as a stiffener for the brim and crown of the Hat and Insect Net HGU-18/P (MIL-H-38471).

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification

b. Width of cloth required (see 3.4.1)

c. Minimum length, when other than specified (see 3.7)

d. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2.1 In the preparation of contracts or purchase orders, it must be noted that various options, choices, and alternatives, as indicated in PPP-B-1133, may be exercised in the preparation for delivery of the cloth.

6.3 Standard sample. For access to standard sample address the procuring activity issuing the invitation for bids.

6.4 The cloth covered by this specification was previously procured under U. S. Army LP/P.DES 13-63.

Custodian:
Air Force - 11

Preparing activity:
Air Force - 11

Review Activities
Air Force - 82, 85

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)* | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT $

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)* | DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4883, WHICH IS OBSOLETE C-8279

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.

FOLD

SEG (SEPS)
WRIGHT-PATTERSON AFB, OHIO

POSTAGE AND FEES PAID

UNITED STATES AIR FORCE
OFFICIAL BUSINESS

Commander
Systems Engineering Group
ATTN: SEPS
Wright-Patterson AFB, Ohio

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T12:41Z
Check the source to verify that this is the current version before use.