MIL-C-83286B(USAF)
AMENDMENT 2
19 August 1980
SUPERSEDING
AMENDMENT 1
18 JUNE 1975

MILITARY SPECIFICATION

COATING, URETHANE, ALIPHATIC ISOCYANATE,
FOR AEROSPACE APPLICATIONS

This amendment forms a part of Military Specification MIL-C-83286B(USAF) dated 5 October 1973.

Page 2, paragraph 1.3b, add the following under specified columns:

FED-STD 595 Color number	Color name
36320	Compass Ghost Grey (Average visual reflectance 31.5%)
36375	Compass Ghost Grey (Average visual reflectance 38.5%)
37200	Aluminized

Page 6, paragraph 3.5.6. In line 2 change "0.50 percent" to "1.75 percent" and in line 4, change "0.75 percent" to "1.75 percent".

Page 6, paragraph 3.5.7, delete in its entirety and substitute:

"3.5.7 Viscosity, Stormer (Component I). The viscosity (consistency) of component I of the coating material for gloss colors shall be a maximum of 95 Kreb Units (KU) when tested in accordance with 4.8.3 and Table V. The viscosity (consistency) of component I of the coating material for camouflage colors shall be a maximum of 115 Kreb Units (KU) when tested in accordance with 4.8.3 and Table V."

Page 7, paragraph 3.6.2, line 3: Change "6 hours" to "7 hours".

Page 7, paragraph 3.6.3, delete in its entirety and substitute:

"3.6.3 Viscosity. The initial viscosity for all colors and gloss ranges of the freshly mixed material shall be 17 to 23 seconds in

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:45Z
Check the source to verify that this is the current version before use.

a number 2 Zahn cup, measured in accordance with 4.8.9 except for all gloss ranges of insignia red, insignia blue, clear and black which shall be 16 to 23 seconds in a number 2 Zahn cup when measured in accordance with 4.8.9. After standing for six hours in a closed container and if necessary with addition of a maximum of 20 percent by volume of thinner conforming to MIL-T-81772, the viscosity shall not increase greater than 6 seconds from the initial admixed viscosity."

Page 8, paragraph 3.7.1.2, Table II, under Camouflage Colors, delete: "Maximum of 12, Minimum of 7" and substitute: "Maximum of 7, Minimum of 0".

Page 10, paragraph 3.7.3.4, line 5, change "3/8-inch" to "1-inch" and line 9, change "1/2-inch" to "2-inch".

Page 12, paragraph 3.7.3.7, delete in its entirety and substitute:

"3.7.3.7 Resistance to taping. All colors and gloss ranges of the polyurethane coating, except insignia reds, insignia blues and blacks, shall be sufficiently cured after 6 hours drying time at standard conditions to permit taping without permanent marring of the painted surface. All gloss ranges of insignia reds and insignia blues shall be sufficiently cured after 7 hours drying time at standard conditions to permit taping without marring of the painted surface. All gloss ranges of the blacks shall be sufficiently cured after 16 hours drying time at standard conditions to permit taping without marring of the painted surface. Resistance to taping shall be tested in accordance with 4.8.10."

Page 15, paragraph 4.8.4, add the following new sentence:

"The above storage stability testing for one year at 70°F to 90°F is for qualification testing only and does not exempt the supplier from meeting the requirements of 3.5.8."

Page 17, paragraph 4.8.6, line 3, change "-65°C $\pm$ 3°F (-54° $\pm$ 1.5°C)" to "-65°F $\pm$ 3°F (-54°C $\pm$ 1.5°C)".

Page 21, paragraph 6.5, lines 2 and 4, change "1.2.b" to "1.3.b".

Source: https://assist.dla.mil -- Downloaded: 202610-23T07:45Z
Check the source to verify that this is the current version before use.

Custodian:
Air Force - 11

Reviewers:
Air Force - 99

Preparing activity
Air Force - 11

Project No. 8010-F183

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:45Z
Check the source to verify that this is the current version before use.