MIL-T-60394A(AR)
AMENDMENT 3
24 July 1988
SUPERSEDING
AMENDMENT 2
1 August 1978

MILITARY SPECIFICATION

TAPE-PRESSURE-SENSITIVE ADHESIVE FILM FOAM DOUBLE-COATED (FOR USE WITH AMMUNITION)

This amendment forms a part of Military Specification MIL-T-60394A(AR), dated 28 July 1967 and is approved for use within the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2: Add a new paragraph as follows:

"1.2 Classification. The tape covered by this specification shall be of the following types and classed as specified (see 6.1).

Type I - Regular
Type II - High Performance
Class 1 - High density-open cell
Class 2 - High density-closed cell"

PAGE 2

* 2.1: Delete reference to "Federal Test Method STD-101."

3.1: Delete in its entirety and substitute with the following:

"3.1 Construction. The tape shall consist of a high density, open or closed cell foam plastic backing, coated on both sides with a homogeneous, pressure-sensitive adhesive, applied in a smooth uniform layer throughout the length of the tape. The finished tape shall require no solvent, heat or other preparation prior to or after application to clean dry surfaces above freezing."

* 3.2 Delete Table I in its entirety and substitute with the new Table I included.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.

TABLE I

TYPE PROPERTY	I MINIMUM	I MAXIMUM	II MINIMUM	II MAXIMUM	TEST PARAGRAPH
Dynamic Normal Tensile Strength (Ungaged), Pounds Per Square Inch (psi)	15	--	25	--	4.4.1
Dynamic Normal Tensile Strength (Aged) Pound Per Square Inch (psi)	9	--	25	--	4.4.1
Caliper (w/o liner) inches	0.021	0.045	0.021	0.045	4.4.2
Peel Adhesion (Unaged) oz/inch width	45	--	45	--	4.4.3
Liner Removal (Unaged) oz/in	--	4.0	--	4.0	4.4.4
Liner Removal (Aged) oz/in	--	4.0	--	4.0	4.4.4
Holding Power (Unaged) minutes	2000	--	7000	--	4.4.5
Holding Power (Aged) minutes	2000	--	7000	--	4.4.5
Static "Normal" Tensile Strength hours	--	--	72	--	4.4.1
Compatibility (Reactivity) milliliters (see para. 6.3)	--	5	--	5	4.4.6

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.

PAGE 11

4.4.1: Delete "Code No. 04001, Major Defect" and substitute "Dynamic, Code No. 04001, Static. - Code No. 04002, Major Defects."

4.4.1.1: Add "e. Weights for static test, 2.5 kilograms each."

PAGE 12

4.4.1.3: Add the words "for Dynamic 'Normal' Tensile Strength" after the first word "Procedure" in the first line.

PAGE 14

4.4.1.4: Add new paragraph as follows:

"4.4.1.4 Procedure for static 'normal' tensile strength. The 'T' blocks shall be cleaned by immersing in the MEK for 10 minutes and the removed and wiped dry with surgical gauze. The test specimen shall be placed, liner side down, on a flat horizontal surface. The one-inch square face of the 'T' block shall be contact with the exposed adhesive surface of the specimen and pressed together. Using a razor or safety knife, the specimen shall be cut around the block so as to make the liner side of the specimen the exact dimensions of the block. The liner shall be removed and the 'T' block placed on its side with the 'T' section vertical. The other 'T' block shall be placed against the exposed adhesive, taking care that the two faces are in perfect alignment. The first mating is the only one possible, and once together the two blocks cannot be separated without damaging the specimen. If the first mating is not perfect, discard the specimen and repeat the above steps. Hang the mated 'T' blocks by the hole in one block so that it hangs free and add the 2.5 kilogram weight to the other block. Allow the loaded specimen to hang undisturbed. Time the specimen until the blocks separate due to failure of the tape. Remove the bulk of the foam from the blocks to place them in the MEK."

* 4.4.9: Delete in its entirety and substitute with the following:

"4.4.9 Bleeding of tape. (Major Defect) (See 6.6).

4.4.9.1: Apparatus. The apparatus shall consist of the following:

a. An air-circulating oven maintained at a temperature of 150° ± 2°F or otherwise specified temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.

b. Bedplate. A 1/4 inch-thick metal sheet, 3 ± 1/16 inches square, with a smooth, flat upper face.

c. Metal sheets, 3 ± 1/16 inches square, made from smooth, thin, flat aluminum.

d. Pressure block. A block of metal, 3 ± 1/16 inches square, weighing 4.5 ± 0.05 pounds, with a smooth, flat bottom surface.

e. Paper sheets, 3 inches square, of smooth, white-coated book paper.

4.4.9.2: Test specimens. Five (5) test specimens shall be used for this test. The specimens shall be strips of tape 1 ± 1/16 inch wide by 3 inches long. The exposure temperature shall be 150° ± 2°F.

4.4.9.3: Test procedures. Heat the test specimens, the 4.5 pound pressure block, bedplate, aluminum sheets and white book papers, before assembly, in an oven for at least 1 hour at 150° ± 2°F. After temperature conditioning, place each test specimen between two paper sheets to form a sandwich and use single aluminum sheets as a separator between each sandwich. Stack the resultant sandwiches with the aluminum separators squarely on an aluminum sheet and cap this stack with one aluminum sheet (NOTE: Not more than five specimens shall be placed in a stack). Place this stack on the bedplate and cover with the pressure bolck. Condition this assembly at 150° ± 2°F for a minimum of five (5) hours. Remove the assembly, separate the sandwiches, and examine the white paper for evidences of staining, disregard stains arising from the cut edges of the specimen.

PAGE 16

* 6.6: Add the new paragraph 6.6 as follows:

"6.6 Notes on bleeding of tape test method.

a. Bleeding is defined as the transfer by exudation of color or substance (such as pigment, asphalt, etc.) from the material under test to contiguous material.

b. Care should be taken that radiant heat does not raise the temperature of the assembly condiserably above the indicated temperature of the oven.

c. The size of the pressure blocks may depart from that specified, provided the pressure amounts to approximately 0.5 pounds per square inch."

Source: https://assist.dla.mil -- Downloaded: 202610-23T00:34Z
Check the source to verify that this is the currentversion before use.

The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1375-A402)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.