DDD-B-1199A
December 1, 1971
SUPERSEDING
Fed. Spec. DDD-B-1199
November 17, 1966

FEDERAL SPECIFICATION

BINDING TEXTILE, COTTON, BIAS-CUT

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers cotton, bias-cut binding used primarily for the binding of seams in wearing apparel.

1.2 Classification.

1.2.1 Types and classes. The bias-cut cotton binding shall be furnished in the following types, and classes, as specified (see 6.2).

Type I - Cambric.
Type II - Percale.
Type III - Sateen.
Type IV - Twill.
Class 1 - Bleached.
Class 2 - Dyed.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

V-T-276 - Thread, Cotton.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).
Fed. Std. No. 191 - Textile Test Methods.
Fed. Std. No. 751 - Stitches, Seams, and Stitching.

FSC 8315

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-W-43334 - Webbing and Tape, Textile, Packaging and Packing of.

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber

Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C. 20580.)

Color Association of the United States, Inc.

Standard Color Card of America

(Information regarding availability of copies of Color Cards or Cable Numbers may be obtained from the Color Association of the United States, Inc., 200 Madison Avenue, New York, N.Y. 10016.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Standard sample. When a standard sample is established, the dyed and finished binding shall match the standard sample for the shade and shall be equal to, or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Material.

3.2.1 Cloth. The cloth to be cut into bias binding shall be cotton, and shall conform to the requirements shown in table I for the type binding specified when tested as specified in 4.2.1. In addition, type I cloth shall contain sufficient sizing to produce a cambric finish.

TABLE I. Physical requirements

Type	Weight per square yard (minimum)	Yarns per inch (minimum)		Weave
	Ounces	Warp	Filling	
I	2.7	64	55	Plain
II	3.0	85	72	Plain
III	2.8	88	140	Satin
IV	3.2	76	112	1/2 Twill

3.3 Color. The cloth to be cut into bias binding shall be bleached or dyed the color specified (see 6.2). The use of dyes and compounds containing elementary or labile sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuffs shall be chosen and applied so that the dyed and finished binding shall show no more labile sulfur than shown by the standard sample when tested as specified in 4.2.1. When no standard sample is available, the dyed cloth shall show no more than a slight trace of labile sulfur as defined in the test method, when tested as specified in 4.2.1. Unless otherwise specified, when ordering red, blue, or green colors, all of the following numbers in each series of red, blue, and green cable numbers of the Standard Color Card of America are acceptable, and may be furnished at the option of the supplier.

Red	Blue	Green
No. 70180	No. 70216	No. 70167
No. 70081	No. 70085	No. 70168
	No. 70086	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

3.3.1 Matching. The color of the dyed and finished cloth to be cut into bias binding shall match the standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin, and shall be a good approximation to the standard shade under incandescent lamplight at 2800° Kelvin.

3.3.2 Colorfastness. The dyed and finished cloth to be cut into bias binding shall show colorfastness to combined laundering and bleaching, crocking, light, and perspiration equal to, or better than the standard sample. When no standard sample has been established, the finished binding shall show "good" colorfastness to combined laundering and bleaching, crocking, light, and perspiration when tested as specified in 4.2.1.

3.4 Thread. The thread shall be cotton, type IA2 or IA3, 3 ply, ticket No. 60, conforming to V-T-276. The thread shall be bleached or dyed to approximate the shade of the binding, as specified. When dyed, the thread shall show colorfastness to combined laundering and bleaching, light, and perspiration equal to, or better than the standard sample. When no standard sample has been established, the thread shall show good colorfastness to combined laundering and bleaching, light, and perspiration.

3.5 Construction. The cloth to be cut into bias binding shall have the selvages removed, and then shall be cut on an angle of 45° ± 5°. The binding shall then be joined together. The seam joining shall be securely sewn with not less than 10, nor more than 14 stitches per inch, using stitch type 301 and seam type SSa-1 of Fed. Std. No. 751, with seams pressed open. Types II and IV shall have the edges of the binding treated with sizing to prevent raveling. The sizing shall not affect the colorfastness requirements of the finished binding provided in 3.3.2.

3.6 Width. The width of the binding shall be as specified (see 6.2). A tolerance of plus or minus 1/32 of an inch will be permitted.

3.7 pH. The pH value of the water extract of the cloth to be cut into bias binding shall be no less than 5.5 nor more than 8.5 when tested as specified in 4.2.1.

3.8 Length. The binding shall be rolled on tubes of the same width as the binding. Unless otherwise specified, the length of the rolls shall be not less than 50, nor more than 100 yards, as specified (see 6.2).

3.9 Fiber identification. Each roll shall be labeled or ticketed for fiber content in accordance with the Textile Fiber Products Identification Act.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

3.10 Workmanship. The finished binding shall conform to the quality and grade of product established by this specification. Occurrence of defects shall not exceed the applicable acceptable quality levels (AQL).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection shall be in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents. In addition to the quality assurance provisions of the subsidiary specifications, the basic cloths shall be tested for the characteristics specified in accordance with the referenced test methods of Fed. Std. No. 191 as listed in table II. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. The lot size shall be expressed in units of one linear yard of cloth, full, width, before cutting. The sample unit for test purposes shall be two linear yards, full width. The lot shall be unacceptable if one or more units fail to meet any requirement specified. All test reports shall contain the individual values utilized in expressing the final result. The sample size shall be as follows:

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

TABLE II. Testing of components

Characteristic	Requirement reference	Test method
Weave	3.2.1	Visual 1/
Yarns per inch:		
Warp	3.2.1	5050
Filling	3.2.1	5050
Weight; ounces per square yard	3.2.1	5041
Identification of cotton	3.2.1	1200 2/
Colorfastness to:		
Combined laundering and bleaching	3.3.2	5605
Crocking	3.3.2	5651
Light	3.3.2	5660
Perspiration	3.3.2	5680
Sulfur	3.3	2020
pH	3.7	2811

1/ One determination per sample unit and results reported as "pass" or "fail".

2/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

4.2.2 Examination of the end item. The examination of the end item shall be in accordance with 4.2.2.1 through 4.2.2.3.2.

4.2.2.1 Yard-by-yard examination. The required yardage of each roll of binding shall be inspected for visual defects listed below. All defects found shall be counted, regardless of their proximity to each other, except when two or more defects represent a single local condition in which case only the more serious defect will be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit for this examination shall be 1 linear yard. Except when otherwise specified by civil government agencies, the sample size shall be in

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

accordance with inspection level I of MIL-STD-105. The AQL shall be 4.0 defects per 100 units (yards). The lot size shall be expressed in units of 1 yard each. An approximate equal number of yards shall be examined from each roll selected. The number of rolls from which the sample is to be selected shall be in accordance with table III.

Examine	Defects
Material defects	Hole, cut, tear, multiple float, smash - Any.
Abrasion marks	Resulting in a weak place.
Crease or wrinkle	Permanently embedded.
Stain, spot, or streak	Single, more than 1 inch in combined direction or multiple small spots within 9 linear inches clearly visible at normal inspection distance (approximately 3 feet).
Selvage	Not removed.
Seams and stitching	Any open seam. Stitches per inch more or less than specified. Insecurely stitched. Seams not pressed open. Wrong stitch or seam type.
	NOTE: A seam shall be classified "open" when one or more stitches joining a seam are broken or when two or more continuous skipped stitches occur.
Stitch tension	Loose tension resulting in a loosely secured seam. Tight tension - Stitches break when normal strain is applied to seam or stitching.
	NOTE: Puckering is evidence of tight tension. When evident, test seam by exerting moderate pull on seam.
Width	Not within specified tolerances.
Type I only	Finish not equal to standard.
Angle of bias	Less than 40˚. More than 50˚.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

TABLE III

Lot size in yards	Sample size in rolls	Maximum number of defects acceptable in sample (see 4.2.2.2 and 4.2.2.3.1)
1300 or less	3	0
1301 up to an including 3200	5	0
3201 up to and including 8000	7	0
8001 up to and including 22,000	10	0
22,001 up to and including 110,000	15	0
110,001 and over	25	1

4.2.2.2 Overall examination. Each defect listed below shall be counted not more than once in each roll examined. The sample unit for this examination shall be one roll. The sample size (same number of pieces as the yard-by-yard examination) and acceptance number shall be as shown in table III.

Defects

Off shade, not within established tolerance.
Uneven dyeing.
Poor penetration, mottled, or streaky throughout.
Overall uncleanness.

4.2.2.3 Length examination.

4.2.2.3.1 Examination for length of individual rolls. Each roll in the sample shall be examined for gross length. Any gross length found to be less than the specified minimum length or more than the maximum length permitted, or any gross length found to be more than 2 yards less than the gross length marked on the ticket, shall be considered a defect with respect to length. The sample unit for this examination shall be one roll. The sample size and acceptance number shall be as shown in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4.2.2.3.2 Examination for total yardage in sample. The lot shall be unacceptable if the total of the actual gross length of rolls in the sample is less than the total of the gross lengths marked on roll tickets.

4.2.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of MIL-W-43334 to determine whether the packaging, packing, and marking complies with the section 5 requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C (see 6.2).

5.1.1 Levels A, B, and C. Binding, put up as specified, shall be packaged in accordance with the applicable requirements of MIL-W-43334.

5.2 Packing. Packing shall be level A, B, or C (see 6.2).

5.2.1 Levels A, B, and C. Binding shall be packed in accordance with the applicable requirements of MIL-W-43334.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, shipment shall be marked in accordance with MIL-W-43334.

6. NOTES

6.1 Intended use. The cotton bias-cut binding covered by this specification is intended primarily for the binding of seams in wearing apparel.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and class of binding required (see 1.2.1).
(c) Color required (see 3.3).
(d) Width of binding (see 3.6).
(e) Length of rolls (see 3.8).
(f) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Sample. For access to standard sample for color, address the procuring office issuing the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

6.4 Level A packaging and level B packing shall be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipments will be made to ultimate consumers.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Air Force - 82

Preparing activity:

Army - GL

CIVIL AGENCY INTEREST:

GSA-FSS
VA-DMS
JUS-FPI

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price :ents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

BINDING TEXTILE, COTTON, BIAS-CUT DDD-B-1199A

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

U.S.MAIL

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.