AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

CUSHION, CARPET AND RUG

(HAIR FELT AND RUBBER COATED JUTE AND ANIMAL HAIR OR FIBER)

This amendment was developed by the Standardization Division, Federal Supply Service, General Services Administration, Washington, DC 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification DDD-C-001023(GSA-FSS) dated December 22, 1966.

PAGE 1

Paragraph 2.1 - Under "Federal Specifications" delete "C-F-202 - Felt Sheet (Hair) & Felt Roll (Hair)" and CCC-T-191 - Textile Test Methods". Also, under "Federal Standards" insert "Fed Test Method Std No 191 - Textile Test Methods".

PAGE 2

Paragraph 3.3.1 - Delete in its entirety and substitute paragraphs 3.3.1 through 3.3.1.6, as follows

"3.3.1 Type I - Hair felt. The hair felt material and construction shall be as specified in 3.3.1.1 through 3.3.1.6

3.3.1.1 Fiber The felt shall be made predominantly from washed cattle hair which shall be the main fiber constituent of the felt, but not to the exclusion of other animal hair. The fiber content of all felt shall be not less than 95 percent cattle hair, except for the core material specified in 3.3.1.2 Up to 9 percent adhesive material (based on weight of the hair felt) is permitted for binding the interliner material. Adhesive shall be nonsouring in the presence of moisture Chloroform and water extractable matter shall not exceed 16.0 percent by weight based on the bone dry weight of the specimen when tested as specified in 4.4 Animal hair shall be cleaned, washed, thoroughly sterilized, free from loading materials and foreign matter

3.3.1.2 Construction. The felt for the cushion shall be a matted fabric evenly felted on each side of an interliner by the needleloom (needle punched) process The interliner used for the reinforcement shall be burlap fabric weighing not less than 4.2 ounces per square yard or other open mesh or nonwoven material which will provide the necessary strength to eliminate shrink and stretch in both directions of the cushion at time of installation The felt shall be compressed into a threaded or waffled pattern of the thickness specified in 3.3.1.5. Edges of the cushion shall be evenly cut.

3.3.1.3 Color Unless otherwise specified (6.1), the felt shall be natural, i.e. the color resulting from the various shades of hair used.

3.3.1.4 Weight The finished weight of the cushion shall be 48 ounces per square yard A plus tolerance of 10 percent and a minus tolerance of 8 percent will be allowed.

3.3.1.5 Thickness. The thickness of the cushion shall be not less than 3/8 inch.

3.3.1.6 Flexibility. The cushion shall show no visible sign of cracking or splitting."

Paragraph 3.3.2.2 - Add sentence. "Taping of the finished edges is not required, however, unless specified (6.1)."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

PAGE 3

Paragraph 3.3.2.10 - After first sentence, insert new sentence, as follows: "When seaming is specified, pieces shall be securely seamed with tape applied to the underside of the cushion."

Paragraph 4.3.1 - After first sentence insert new sentence "For type I cushion, testing shall be performed for fiber identification, as specified in 3.3.1.1, and weight of core fabric, as applicable in 3.3.1.2, the fiber identification may be accepted based on contractor's certified laboratory test results and for the core fabric weight test method 5041 of Fed. Test Method Std. No. 191 shall be used." Also after second sentence, insert the following sentence "For type I and type II cushions, the contractor shall certify that the animal hair or fiber has been cleaned, washed, and sterilized as specified herein."

Table I - After column heading "Test method" insert footnote reference "2/". Also, under Table I insert footnote as follows "2/ Test methods referenced are applicable to Fed. Test Method Std. No. 191."

Paragraph 4.3.2 - Delete first sentence in its entirety. Also, in second sentence before "type II cushion" insert "type I and".

PAGE 4

Paragraph 4.3.2.1 - In "Defects" listing, after first, second, third, fourth, and twelfth defect, add "(type II)"

PAGE 5

Paragraph 4.4 - Delete first sentence in its entirety and substitute "For type I cushion, tests shall be performed for the characteristics specified in table V." Also, line 4, delete "CCC-T-191" and substitute "Fed. Test Method Std. No. 191".

Table III - After table heading "End item testing" add "(Type II cushion)".

After Table IV, insert new Table V, as follows

TABLE V. End item testing (Type I cushion)

Characteristic	Requirement Reference	Test Method
Quantitative analysis (not including core fabric)	3.3.1.1	2101 1/
Extractable material	3.3.1.1	2611 1/
Weight, cushion	3.3.1.4	5040 or 5041 2/
Thickness	3.3.1.5	5030
Flexibility	3.3.1.6	4.5.5

1/ May be accepted based on contractor's certified laboratory test results.
2/ When method 5041 is used, one specimen with an area of at least 16 square inches shall be used

After paragraph 4.5.4 add new paragraph 4.5.5 as follows

"4.5.5 Flexibility. A cushion specimen shall be bent 180 degrees over a rod approximately equal in diameter to the thickness of the sample. Any visible sign of cracking or splitting shall be considered a failure."

PAGE 6

Paragraph 6.1 - Add new subparagraphs (g) and (h) as follows

"(g) Color, if other than as specified (3.3.1.3).
(h) When taping of finished edges is required (3.3.2.2)."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.