DDD-C-450a
March 7, 1966

SUPERSEDING
Int. Fed. Spec. DDD-C-00450 (GSA-FSS)
September 29, 1964

FEDERAL SPECIFICATION

CLOTHS, POLISHING (FOR ELECTRICAL CONTACT SURFACES)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 This specification covers requirements for cotton cloths of one type and size primarily used for cleaning and polishing electrical contact surfaces (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids, or request for proposal form a part of the specification to the extent specified herein.

Federal Specifications:

CCC-T-191—Textile Test Methods.
PPP-B-636—Box, Fiberboard.

Federal Standard:

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained free of charge from the Federal Trade Commission, Washington, D. C., 20580.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Base cloth.* The cloth shall be woven, made from cotton which has been cleaned, carded or combed, and evenly spun into single yarns, when tested as specified in 4.2.4.

3.1.1.1 *Yarns per inch.* The number of yarns per inch in the warp direction shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

be 50 ± 2, and in the filling direction 38 ± 2, when tested as specified in 4.2.4.

3.1.1.2 *Breaking strength.* The minimum breaking strength shall be 25 pounds in the warp direction and 17 pounds in the filling direction when tested as specified in 4.2.4.

3.1.1.3 *Finish.* The base cloth shall have a soft finish and shall be lightly napped on both sides (see 4.2.2.1.1).

3.1.2 *Finishing compound.* The finishing compound shall be composed of a silica base suitable for the purpose intended when tested in accordance with 4.2.4.

3.1.3 *Finished cloth.* In addition to the requirements of 3.1.1 through 3.1.1.3, the following requirements apply to the finished cloth.

3.1.3.1 *Weight.* The finished cloths shall weigh not less than 7.0 ounces per square yard when tested in accordance with 4.2.4.

3.1.3.2 *Treatment.* The silica compound applied to the base cloth to obtain the desired finish shall be accomplished by a dipping process which shall thoroughly impregnate the cloth.

3.1.3.3 *Size.* The cloths in any one sample size shall average not less than 10.75 x 13.25 inches when measured in accordance with 4.2.2.1.2. A tolerance of minus 1/4 inch in either or both dimensions of the above size is permitted for individual cloths.

3.1.3.4 *Color.* The color of the cloths shall be white (bleached) (see 4.2.2.1.1).

3.1.3.5 *Edges.* All edges other than selvage edges shall be pinked (see 4.2.2.1.1).

3.2 Fiber identification. Each cloth shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act (see 2.2).

3.3 Preproduction sample. When specified, before production is commenced, a finished sample of the size cloth required by the specification shall be submitted to the contracting officer for approval. Approval of the preproduction sample authorizes production. Such production does not relieve the contractor of the responsibility for compliance with all provisions of this specification.

3.4 Workmanship. The cloths shall conform to the quality and grade of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels (AQL's).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated hereinafter. For purposes of sampling, an inspection lot for acceptance inspection and tests shall consist of all polishing cloths submitted for inspection and delivery at one time.

4.2.1 *Inspection of materials and components.* In accordance with 4.1, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

specification. In the event of conflict, this specification shall govern.

4.2.2 *Inspection of the end item.*

4.2.2.1 *Examination of the end item.* Examination of the end item shall be made in accordance with classification of defects, inspection levels, and AQL's set forth as follows. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of polishing cloths for examinations in 4.2.2.1.1 and 4.2.2.1.2.

4.2.2.1.1 *Examination of the end item for defects in appearance, construction, and workmanship.* The sample unit for this examination shall be one polishing cloth.

Examine	Defect
Appearance, construction, and workmanship	Any hole, cut, or tear. Spot, stain, or streak affecting serviceability. Lumps or embedded foreign matter. Edges not pinked, other than selvage edges. Not bleached white. Not woven. Not a soft finish and not lightly napped on both sides.

4.2.2.1.2 *Examination of the end item for defects in dimensions.* The sample unit for this examination shall be one polishing cloth.

Defects
Average size in any one sample size less than 142.0 square inches.
Any individual cloth varies more than minus 1/4 inch on either or both dimensions of the minimum size 10.75 x 13.25.

4.2.2.1.3 *Inspection levels and AQL's for examinations.* The inspection levels for determining the sample size, and the AQL's expressed in defects per 100 units shall be as follows:

Examination paragraph	Inspection level	AQL
4.2.2.1.1	S-4	2.5
4.2.2.1.2:		
Average unit	S-2	—
Individual unit	S-2	2.5

4.2.3 *Examination of preparation for delivery requirements.* An examination shall be made to determine that packaging, packing, and marking requirements comply with section 5. Defects shall be scored in accordance with the following list. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed as follows shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 4.0 defects per 100 units in accordance with MIL-STD-105.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, improper taping, loose strapping, inadequate stapling. Open and noncontinuous heat sealed seam of polyethylene bag. Omission of vent hole in polyethylene bag.
Content	Bulging or distortion of containers. Number per package and per container is more or less than required.

4.2.4 *Testing of the end item.* Testing of the end item shall be made for the applicable characteristics as indicated in table I for each lot presented for inspection. The lot size shall be expressed in units of polishing cloths. The sample unit shall be two polishing cloths. Five sample units randomly taken from throughout the lot shall be tested. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

TABLE I. *Test requirements.*

Characteristic	Requirement reference	Test method[1]	Number of determinations per individual sample unit[2]	Results reported as:
Fiber identification	3.1.1	1200	1	Pass or fail.
Ply of yarn	3.1.1	Visual	1	Pass or fail.
Yarns per inch	3.1.1	5050	3	Average of 3 determinations to nearest whole number.
Breaking strength	3.1.1	5100	3	Average of 3 determinations to nearest whole number.
Finishing compound	3.1.2	Certificate of compliance[3]	—	Pass or fail.
Weight	3.1.3.1	5041	3	Average of 3 determinations to nearest whole number.

[1] Tests shall be performed in accordance with methods of CCC-T-191, except that the stipulation as to the number of specimens to test, number of determinations to make, or number of results to report shall not apply.

[2] Test report shall include all values on which average results are based.

[3] A certificate of compliance shall be required from the manufacturer stating that his product meets the requirements for finishing compound.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 *Level A.* Each polishing cloth, compactly folded, shall be packaged in an end opening 40-pound kraft envelope. The open end shall be provided with a flap type closure. The flap shall have a reinforced hole, centered 5/8 ± 1/16 inch from the end of the flap. A metal clasp shall be secured in place on the envelope in a location so that when the envelope flap is folded, the clasp and hole will coincide.

5.1.1.1 When specified, twelve polishing cloths shall be neatly stacked and placed in a snug-fitting flat or square style clear polyethylene film bag of 0.00125 inch thickness (± 20 percent tolerance). The polyethylene bag shall be formed with heat sealed seams that are straight and continuous and shall be effected by heat sealing with the heat seal made as close as possible to the open end. A 1/4-inch diameter hole shall be made at one corner of each bag to allow excess air to escape. Alternatively, a mechanical tie (paper or plastic covered soft steel wire, aluminum band, etc.) shall be applied to close the bag opening (see 6.2).

5.1.2 *Level C.* Each polishing cloth shall be packaged in accordance with the supplier's commercial practice.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 *Level A.* Six hundred polishing cloths, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, V3c or V3s of PPP-B-636. Each shipping container shall be closed, waterproofed, and reinforced with flat steel strapping or tape banding in accordance with the appendix of the container specification.

5.2.2 *Level B.* Six hundred polishing cloths, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

container conforming to style RSC, type CF or SF, class domestic, grade 275 of PPP-B-636. Each container shall be closed method II in accordance with the appendix of the container specification.

5.2.3 *Level C.* Polishing cloths, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking.

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.3 *Polyethylene bagged packages.* Polyethylene bagged packages shall have the required information legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification. The bag or label shall indicate the following information:

STOCK NUMBER
NOMENCLATURE
QUANTITY

6. NOTES

6.1 Intended use. The cloths covered by this specification are intended for use in cleaning and burnishing electrical contact surfaces of metallic component parts and hardware such as telephone switchboard plugs and jacks, relays and relay housings, potentiometer housings, contactor rings, switches, etc.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Whether preproduction sample is required (see 3.3).
(*c*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(*d*) Whether packaging in polyethylene bags is required (see 5.1.1.1).

6.3 For civil agencies. Level A packaging and level B packing should be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipment will be made to ultimate consumers.

6.4 Transportation descriptions. The transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Cloths, polishing, cotton, treated with chemicals.
Carload minimum weight 20,000 pounds, subject to Rule 34, Uniform Freight Classification.

Motor:

Cloths, polishing, cotton, chemically treated.
Truckload minimum weight—Any quantity.

MILITARY CUSTODIANS:

Army—GL
Navy—SA
Air Force—69

Review activities:

Army—MD, GL
Navy—SA
Air Force—69

User activities:

Army—None
Navy—SH, MC
Air Force—None

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

Review and User information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing Of DOD Standardization Documents.

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.