DDD-C-491

JUNE 28, 1932

SUPERSEDING
F. S. No. 260
December 6, 1924

FEDERAL STANDARD STOCK CATALOGUE

Section IV

(Part 5)

FEDERAL SPECIFICATION

FOR

CLOTHS; WIPING

This specification was approved for promulgation by the [Federal Specification Board on June 28, 1932, for the use of the departments and independent establishments of the Government in the purchase of this commodity, and shall become mandatory for all departments and independent establishments of the Government not later than February 15, 1933. It may be put into effect, however, at any earlier date, after promulgation.

A. APPLICABLE FEDERAL SPECIFICATIONS.

A–1. The following Federal specification of the issue in effect on date of invitation for bids, shall form a part of this specification:

F. S. CCC–T–191. Textiles; Test Methods. Specification No. 345.

A–2. Any special requirements of the individual departments of the Government are noted in section H.

B. GRADES.

B–1. This specification covers one grade only.

C. MATERIAL AND WORKMANSHIP.

C–1. The cloths shall be new, selected, clean and free from starched and stiffened pieces. They shall be as free as practicable from seams. They shall be free from grit and dirt. They shall be soft, absorbent, light weight, and dry. They shall be free from toweling and heavily napped rags.

D. GENERAL REQUIREMENTS.

D–1. See Detail requirements.

E. DETAIL REQUIREMENTS.

E–1. *Size.*—The minimum size of cloths shall have an area of at least 2 square feet and a minimum width of 10 inches.

E–2. *Weight.*—The maximum weight of any cloth shall not exceed approximately 9 ounces per square yard.

Source: https://assist.dla.mil -- Check the source to verify that thi

E–3. *Requirement table.*—

Gross weight of bale (nominal)	Volume of bale (approximate)	Tare (maximum)
Pounds	*Cubic feet*	*Per cent*
50	3½	6
100	7	6
600	35	6

A variation of plus or minus 10 per cent from the nominal weight of individual bales will be permitted.

E–4. *Moisture and tare content.*—If the weight of wrapping, including hoops or ties, exceeds the amount specified in the requirment table, or if the moisture content exceeds 7 per cent, the excess weight shall be deducted at the same price per pound that is paid for the cloth; provided further that if the tare exceeds 10 per cent of the gross weight or the moisture content exceeds 10 per cent, the waste shall be rejected.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. Any requirements applicable to the individual departments are noted in section H.

F–2. *Sampling.*—Not less than one sample weighing 1 pound shall be taken at random from each 1,000 pounds, or fraction thereof, except when the shipment is over 10,000 pounds, in which case a sample shall be taken from each one-tenth of the shipment. In addition to the samples required for the regular tests, immediately after the total weight of the material is obtained, a sample approximately 1 to 1½ pounds shall be pulled out and weighed to the nearest one-eighth ounce. This sample shall be properly marked with identification and weight, wrapped in strong paper, and retained for test in case of dispute in regard to the moisture content.

F–3. *Testing.*—

F–3a. *Moisture content (umpire test).*—In the event of a dispute in regard to moisture content, the following procedure shall be used. The sample prepared for this purpose (see F–2) shall be shipped to a conditioning laboratory, where it shall be exposed for at least four hours to an atmosphere of 65 per cent relative humidity at 70° F., and then weighed with equivalent accuracy. When the moisture content exceeds 7 per cent, the entire shipment may be based on the corrected weight of the sample.

Weight of bale conditioned =

$$\frac{(\text{Weight of bale}) \times (\text{weight of sample conditioned})}{\text{Weight of sample as pulled out}}$$

F–3b. *Testing.*—Federal Specification CCC–T–191, identical with General Specifications for Textile Materials FSB No. 345, in effect on date of invitation for bids, wherever practicable, shall be followed.

Source: https://assist.dla.mil -- Dov
Check the source to verify that this is

the excess only will be deducted from the gross weight and payment made on the basis of these adjusted weights."

H–3c (3). Tare in excess of 10 percent of the gross weight, or moisture content in excess of 10 percent of the net weight, shall be considered cause for rejection of the wiping cloths.

H–4. *Post Office Department.*—Sampling, inspecting, and testing of cloths purchased by the Post Office Department shall be in accordance with the outline contained in its invitation for bids.

I. NOTES.

I–1. Purchasers should exercise choice of all options offered herein and should specify weight of bale and the type and class of cloths required. The larger bales conform to general commercial practice and should be purchased wherever practicable.

I–2. The cloths covered by this specification are intended for wiping purposes.

I–3. The method of test for moisture regains conforms in all essential requirements with Moisture Regains of Cotton yarns, Commercial Standard CS11–41.

I–4. It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no sample will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

I–5. Federal Specifications do not include all types, classes, grades, sizes, etc., of the commodities indicated by the titles of the specifications, or which are commercially available, but are intended to cover the types, etc., which are suitable for Federal Government requirements.

I–6. An Index of Federal Specifications may be purchased as noted in the paragraph below, price to be obtained from the Superintendent of Documents.

I–7. Copies of this specification and of CCC–T–191 and CS11–41 may be obtained upon application, accompanied by money order, coupon, or cash, to the Superintendent of Documents, Government Printing Office, Washington, D. C. Price 5 cents each.

Notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

Source: https://assistdocumi
Check the source to verify tha