DDD-D-00620(DSA-DM)
17 March 1965
SUPERSEDING
MIL-D-36152(BuMed)
24 May 1963

INTERIM FEDERAL SPECIFICATION

DRAPE, SURGICAL, PLASTIC, STERILE, 18 BY 36 INCHES, 10S

This interim Federal specification was developed by the Defense Medical Supply Center, Third Avenue and 29th Street, Brooklyn, New York 11232, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE

1.1 This specification covers one type of prepacked, disposable, sterile, drape, suitable for use in surgical procedures.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Boxes, Set-Up, Paperboard.

FSC 6530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards, as outlined under General Information in the Index of Federal Specifications and Standards, and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington D. C., 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards, and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

Military Standards:

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the currentversion before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials:

ASTM Designation D726-58	Standard Methods of Test for Resistance of Paper to Passage of Air (Method A).
ASTM Designation D882-61T	Tentative Methods of Test for Tensile Properties of Thin Plastic Sheeting (Method B).
ASTM Designation D1000-64	Standard Methods of Testing Pressure-Sensitive Adhesive Coated Tapes Used for Electrical Insulation.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia 3, Pa.)

U.S. Pharmacopoeial Convention, Inc.:

Pharmacopeia of the United States

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pa.)

3. REQUIREMENTS

3.1 Materials.

3.1.1 Backing. The backing shall be a translucent, uniform, polyethylene film. The surface of the film shall be matted to minimize reflections and eye strain. The test for the presence of polyethylene shall be conducted in accordance with 4.4.4.1. The backing shall be treated to reduce buildup of static electricity during handling or application. Both the adhesive-coated area and the uncoated area shall not produce a measurable voltage at 27 percent relative humidity when subjected to the static electricity test specified in 4.4.3.7.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the currentversion before use.

3.1.2 Adhesive. The adhesive shall be a transparent, synthetic, nonrubber copolymer, pressure-sensitive type. The adhesive shall indicate synthetic nonrubber characteristics, when tested as specified in 4.4.4.2. The adhesive shall require no heat, solvents, or moisture prior to application.

3.1.3 Facing. The facing shall be a smooth film, paper, or other material chemically inert to the adhesive.

3.1.4 Physical properties. The material for the drapes shall meet the requirements shown in table I, when tests are run on the adhesive-coated film areas after removal of the facing material, as specified in 4.4.3.

Table I.

Physical properties	Minimum	Maximum
Film tensile strength (pounds per square inch of width)	2.0	—
Film porosity, seconds	100	—
Film ultimate elongation, percent	100	—
Film thickness, inch	0.0012	0.0018
Drape thickness, inch	0.0025	0.0035
Drape adhesion to steel (ounces per inch of width)	10	—
Static electricity, volts	—	300
Adhesive transfer to facing, percent	—	5

3.1.5 Envelope. The envelope shall be heat-sealed polyethylene.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the current version before use.

3.2 Construction. Each drape shall be a rectangular sheet of plastic film with dimensions of 18 by 36 inches ± 10 percent, and shall have no splices, torn edges, perforations, or other defects. One side of the film sheet shall be coated with an adhesive except for a 6-inch strip across each end, so that the coated area shall be 18 by 24 inches ± 1/2 inch.

3.3 Design. The adhesive shall be pressure sensitive, and shall cause the drape to adhere immediately and firmly to clean, dry, human skin. The protective liner over the adhesive mass shall be easy to remove and shall not lift off any of the adhesive on removal. A starting tab shall be provided for easy removal of the facing material. Drapes shall be rolled on their own protective facing material. The drape shall be sufficiently transparent to permit a clear view of the operative and surrounding areas, and shall be suitable for use with X-ray equipment without removal. The drape shall be easily applied, adhere firmly, and permit incision directly through the drape. Each drape shall be sealed in an envelope. The resultant package shall permit easy opening under operating room conditions. The packaged drape shall be sterilized, according to 3.6.1, and shall maintain sterility until opened.

3.4 Stability. The drape, adhesive, and facing material shall show no evidence of deterioration or change in properties such as to make the drape unfit for use after 36 months of normal storage and handling.

3.5 Sensitivity and toxicity. The drapes shall meet the requirements of the Federal Food and Drug Administration for toxicity and skin sensitivity of pressure-sensitive adhesive products used on the human body.

3.6 Sterilization and certification.

3.6.1 Sterilization. Sterilization shall be accomplished by the ethylene oxide method or other suitable means which shall render the drape sterile in the final package (see 3.3), when tested as specified in 4.4.3.6.

3.6.2 Certificates of sterility. For destination inspection only (applicable to Defense Medical Supply Center procurement only). A certificate of sterility, listing all sterility lot or control numbers, shall state that samples from each sterility lot or control have been tested for sterility, as required in 3.6.1 and 4.4.3.6, and have been found to be sterile. The certificate shall reference the method used in determining sterility. One copy of the certificate of sterility shall be submitted by the contractor directly to the Chief, Quality Control Division, Directorate of Technical Operations, Attn: Code TQ, Defense Medical Supply Center, Third Avenue and 29th Street, Brooklyn, New York 11232, and one copy shall be forwarded with each shipment to the consignee.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

3.7 Identification marking. Each envelope shall bear, permanently and legibly, the name or registered trademark of the manufacturer.

3.8 Instructions. Each envelope shall bear or contain the manufacturer's printed instructions for opening the drape to maintain sterility.

3.9 Workmanship. Workmanship shall be first class throughout. Drapes shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual, auditory, etc., investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The unit of product for inspection purposes shall be the individual drape.

	Inspection level	AQL (percent defective)
For visual examination		
Major A defects	II	1.0
Total (major and minor combined) defects	II	4.0
For dimensional examination	II	2.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105. The unit of product for inspection purposes shall be the individual drape.

Component (unit of product)	Characteristic	Requirement	Test procedure	Inspection level	AQL
Plastic film	Material identification	3.1.1	4.4.4.1	**	
	Tensile strength	3.1.4	4.4.3.1	S-2	*
	Elongation	3.1.4	4.4.3.1	S-2	*
	Thickness	3.1.4	4.4.3.2	S-2	*
	Porosity	3.1.4	4.4.3.5	S-2	*
Synthetic adhesive	Material identification	3.1.2	4.4.4.2		
Drape	Static electricity	3.1.1	4.4.3.7	S-2	*
	Adhesion to steel	3.1.4	4.4.3.3	S-2	*
	Adhesion to facing material	3.1.4	4.4.3.4	S-2	*
	Sterility	3.6.1	4.4.3.6	As required by U.S.P.	

* Acceptance number shall be zero for all sample sizes.
** Sufficient sample shall be taken from each lot to perform tests for the identity of the material.

4.2.3 Where possible, the same sample unit shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4.3 Examination. The drapes shall be examined to determine compliance with all requirements contained in this specification.

4.3.1 Classification of defects. Examination shall be conducted in accordance with the following classification of defects:

Categories and defects*

Major A
101 Adhesive coating not uniform and continuous (free of breaks).
102 Facing material does not properly protect the adhesive coated area.
103 Tab on facing strip missing.
104 Facing strip not free of tears, cuts, and holes.
105 Individual envelope not free of tears, cuts, and openings in heat-sealed closures.

Major B
151 Drape not free of cuts, tears, holes, blisters, and perforations.
152 Drape not one piece (free of splices).
153 Surface not smooth and not free of embedded particles and foreign matter.
154 Drape not free of surface dirt.

*Examination shall not be restricted to the classified possible defects listed above.

4.3.2 Dimensional examination. The drapes shall be examined for defects in dimensions. Any dimension not within the tolerance specified herein shall be classified as a defect.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Conditioning. The samples selected for all tests except static electricity test, shall be conditioned for not less than 24 hours at 73° Fahrenheit (F.) ± 3.5° F. and 50 ± 2 percent relative humidity, and shall be tested under these conditions. Static electricity test shall be conditioned at 27 ± 2 percent relative humidity.

4.4.2 Specimens. In all tests where sterility is a factor, the drapes shall be removed from the envelope in accordance with the manufacturer's instructions regarding aseptic technique.

4.4.3 Physical tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4.4.3.1 Tensile strength and ultimate elongation of film. Tensile strength and ultimate elongation of film shall be determined in accordance with ASTM Designation D882-61T, Method B, with 1-inch jaw separation, 12-inch movement per minute. Three specimens from each sample in each direction shall be selected for test. The report shall be the average of the size results obtained.

4.4.3.2 Film thickness. Thickness of film shall be determined in accordance with ASTM Designation D1000-64. Each sample shall be measured at five points.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

5 PREPARATION FOR DELIVERY

4.4.3.3 Adhesion to steel. A pendulum-type tensile-testing machine, consisting of two clamps whose centers shall be in the same plane parallel with the direction of the motion of the stressing clamp, and so aligned that they shall hold the test panel and tape specimen wholly in one plane, shall be used. A pendulum shall be so attached to one clamp as to balance the load applied to the specimen accurately. A device shall indicate, on a graduated scale or chart, the load applied to the specimen. A means for moving the stressing clamp at a uniform rate shall be provided. A 5- by 2- by 1/16-inch corrosion-resisting steel plate, AISI 302 or 304, polished to a No. 4 finish (commercial polish ground), shall be used. A mechanically-operated roller, 3.25 ± 0.1 inches in total diameter and 2.5 ± 0.05 inches in width, covered with rubber approximately 1/4 inch thick and having a durometer hardness of 70 to 80, shall be used. The weight of the roller proper, which applies pressure to the specimen, shall be 4.5 ± 0.1 pounds. The roller shall be so constructed that the weight of the handle shall not be added to the weight of the roller during use. The cylindrical surface of the roller shall be a true surface void of any concave or convex deviations, so that the roller shall apply uniform pressure across the width of its entire surface. The facing material from the adhesive area shall be removed and discarded. A 10-inch-long by 1-inch-wide specimen shall be cut from the adhesive-covered area. The strip shall be known as "the tape" in this test. Before each test, panels shall be cleaned using a three-phase cleaning technique: (1) Panels shall be scrubbed using surgical gauze saturated with a suitable solvent such as diacetone alcohol; (2) Panels shall be scrubbed using surgical gauze saturated with one of the following solvents: heptane, methyl-ethyl-ketone, isopropyl alcohol, or methyl alcohol; (3) Solvent shall be allowed to evaporate, and then the panels shall be dry-wiped with surgical gauze. Care shall be exercised so as not to contaminate the test area with fingerprints. A 5-inch portion of the tape shall be applied, adhesive side down, to the polished surface of the panel by passing the roller twice over its surface, once in each direction, at the rate of 12 inches per minute, using only the weight of the roller in applying the tape to the panel. Care shall be exercised to insure that no air bubbles are entrapped. However, should this condition arise, the specimen shall be discarded and a new one prepared. Each specimen shall be prepared individually and tested immediately (within 1 minute) before preparing a subsequent sample. Five specimens shall be tested from each drape, and the report shall be the average of the five results obtained. The test itself shall be conducted essentially as follows: The free end of the tape shall be double backed at an angle of 180° and 1 inch of the tape shall be peeled off the plate at the folded end. The end of the plate from which the tape was just removed shall be clamped into the lower jaw of the pendulum-type tensile-testing machine and the free end of the tape into the upper jaw. The pawls on the pendulum arm shall be taped back in an open position. After the machine has started, the values obtained while the first inch of tape is removed mechanically shall be disregarded. The minimum pull value obtained during the removal of the next 2 inches from the plate shall be taken as the adhesion value. Any values obtained in removal of the final 1 inch shall be disregarded. The test shall be made with the stressing jaw moving at a speed of 12 inches per minute. The tensile tester shall be of such capacity that the test values shall be read when the pendulum hangs between 9° and 45° from the vertical.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4.4.3.4 Adhesion to facing material. A strip of drape, completely covered with adhesive and facing material, shall be cut 1/2 inch wide and 10 inches long. The facing material shall be peeled back from the drape a distance of 1 inch. The one end of the drape exposed shall be inserted in the upper jaw of the machine described in 4.4.3.3. The facing material shall be inserted in the lower jaw. The balance of the test shall be conducted as adhesion to steel (4.4.3.3), except that the maximum value shall be recorded. Five specimens shall be tested from each drape, and the report shall be the average of the five results obtained.

4.4.3.5 Porosity. (ASTM Designation D726-58, Method A). A Gurley densometer or similar instrument shall be used. A representative section of the drape without adhesive or facing material shall be inserted in the clamp. The cylinder shall be released and after 20 seconds, there shall be no further perceptible movement of the cylinder for an additional 100 seconds.

4.4.3.6 Sterility. Sterility shall be determined in accordance with the applicable test for solids specified in the current edition of the Pharmacopeia of the United States.

4.4.3.7 Static electricity test. A 1000-volt static voltmeter shall be connected in series between a ground and an insulated 12-inch corrosion-resisting steel basin. The basin shall be insulated by placing it on a glass or ceramic plate and elevating it not less than 4 inches from any item of large capacitance. A sample of drape having an area between 100 and 300 square inches, shall be rubbed vigorously for 5 seconds against a piece of clean catskin and then dropped into the basin. The voltage shall be recorded. Each sample shall be tested three times and the average reported. The test shall be run on adhesive-coated material areas after removal of the facing material.

4.4.4 Material identification tests.

4.4.4.1 Polyethylene. The presence of polyethylene film shall be determined as follows: A sample of the film shall be ignited. The film shall be allowed to burn freely. The presence of polyethylene shall be indicated by a wax-like dripping from the burning area accompanied by the odor of melted paraffin.

4.4.4.2 Synthetic adhesive. The method for determining the synthetic non-rubber adhesive shall be as follows: The adhesive shall be removed from a strip of the drape 1 inch by 5 inches with toluene. The toluene shall be dried off. The adhesive shall be placed in a beaker containing 50 milliliters of methyl ethyl ketone and heated gently to boiling. Caution is imperative, since a highly flammable solvent is being utilized. The synthetic adhesive shall become semisolid, and the mixture shall remain water clear. The rubber adhesive shall "ball up", become opaque, and shall not dissolve. After boiling for 15 minutes, the solid or semi-solid adhesive shall be removed and dried. A rubber adhesive shall be indicated by a non-pressure-sensitive ball of rubber. A synthetic adhesive shall dry to its pressure-sensitive form.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. Ten (10) drapes, as specified, constitute one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table II shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table II. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	4 units	12 units

5.1.2.1 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Ten (10) individually packaged drapes, (1 unit) shall be packaged in a carton of appropriate size, constructed in accordance with PPP-B-676, except that commercial colors shall be acceptable. Closure of carton shall be adequate to prevent spillage of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a carton of appropriate size constructed in accordance with PPP-B-636 or PPP-B-676. Commercial colors shall be acceptable when carton conforming to PPP-B-676 is utilized. Closure shall be adequate to prevent spillage of contents under normal handling.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 3 use; PPP-B-601, table II, using type III, class 1 plywood; PPP-B-621, table III; or PPP-B-636, type CF, class weather-resistant.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.1.3 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix, and waterproofing shall conform to 30.4, of PPP-B-636.

5.2.1.4 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

NOTE: Strapping shall not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall conform to PPP-B-601, table I, using type III, class 1 plywood; or shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 2 use; PPP-B-621, table I; or PPP-B-636, type CF, class domestic and method I closure shall be utilized.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown. In addition, sterilization report number shall be shown on the unit package.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Number and date of this specification.
(b) Selection of applicable level of packing (see 5.2).

6.2 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Federal Government requirements.

Military Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

FOLD UNDER

DEFENSE SUPPLY AGENCY
DEFENSE MEDICAL SUPPLY CENTER
3RD AVENUE AND 29TH STREET
BROOKLYN, N.Y., 11232

POSTAGE FEES PAID
DEFENSE SUPPLY AGENCY

OFFICIAL BUSINESS

DEFENSE SUPPLY AGENCY

DEFENSE MEDICAL SUPPLY CENTER

ATTN: DIRECTORATE OF TECHNICAL OPERATIONS (CODE T:5)

3RD AVENUE AND 29TH STREET

BROOKLYN, N.Y., 11232

FOLD

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:35Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the ification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION: DRAPE, SURGICAL, PLASTIC, STERILE, 18 BY 36 INCHES, 10S
INTERIM FEDERAL SPECIFICATION DDD-D-00620(DSA-DM) Dated 17 March 1965

ORGANIZATION *(Of submitter)*

CITY AND STATE

CONTRACT NO.

QUANTITY OF ITEMS PROCURED

DOLLAR AMOUNT
$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*

DATE

DD FORM 1426.

SMD FPSO 12302

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the current version before use.