DDD-L-1257A
October 12, 1972
SUPERSEDING
Int. Fed. Spec. DDD-L-001257
November 24, 1967

FEDERAL SPECIFICATION

LINER, LAUNDRY BASKET FRAME

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers a nylon type of liner in one size, and a vinyl-nylon type of liner in various sizes and colors, which are inserted into laundry basket frames.

1.2 Classification. The liners shall be in the following types, sizes and colors, as specified (see 6.2):

Type I. Nylon
Size 1.

Type II. Vinyl-Nylon
Size 1 - 12 bushel capacity.
2 - 14 bushel capacity.
3 - 16 bushel capacity.
4 - 18 bushel capacity.

Color A - Red.
B - Blue.
C - White.
D - Yellow.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

V-T-285 - Thread, Polyester.
V-T-295 - Thread, Nylon.
PPP-B-636 - Box, Fiberboard.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).
Fed. Std. No. 191 - Textile Test Methods.
Fed. Std. No. 751 - Stitches, Seams and Stitchings.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables of Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

Military Specification:

MIL-C-43006 - Cloth, Laminated, Vinyl-Nylon, Hight Strength, Flexible.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENT

3.1 Material.

3.1.1 Nylon. Nylon for the fabrication of the liner shall be of plain weave, of either continuous filament nylon or spun nylon, or a combination of both, having not less than 60 warp yarns per inch and not less than 44 filling yarns per inch providing the aggregate of warp and filling yarns is not less than 110. The weight shall be not less than 3.4 ounces per square yard. The flammability rating shall be self-extinguishing.

3.1.1.1 Shrinkage. The finished nylon cloth shall be preshrunk and shall have not more than 10 percent residual shrinkage in either the direction of the warp or of the filling.

3.1.1.2 Breaking strength. The minimum breaking strength shall be not less than 200 pounds in either the direction of the warp or of the filling.

3.1.1.3 Color. Unless otherwise specified, (see 6.2) the basic cloth shall be the undyed natural-white color of the nylon.

3.1.2 Vinyl-nylon. Vinyl-nylon for the fabrication of the liner shall be the Type I, class 1 of MIL-C-43006, having a flammability rating of self-extinguishing.

3.2 Design and construction.

3.2.1 Type I, size 1. The liner shall be constructed to conform to the design, shape and dimensions shown on figure 1. A tolerance of plus 1 inch is permitted.

3.2.1.1 Thread. Thread for the stitching shall be natural white and shall conform to letter size B, type I, class 1 of V-T-295.

3.2.2 Stitches, seams and stitching, type I. The types of stitches, seams and stitching specified for the operations listed in table (II) shall be in accordance with Fed. Std. No. 751.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE I. Stitch types, seam and stitching types

Operation	Stitch type	Seam and Stitching type
Attaching flaps to side of liner	301 or 401	LSd-3
Finishing flap edges	301 or 401	EFb-1

3.2.3 Type II. Type II liners shall be of dimensions as specified in Table II.

TABLE II. Dimensions

Size	Capacity/Bushels	Length/Inches	Width/Inches	Depth/Inches
1	12	35	26-1/2	31
2	14	38-3/4	28	31-3/4
3	16	39-1/4	28-1/4	33-1/2
4	18	41-1/2	30	33-3/4

3.2.3.1 Thread. Thread for the stitching shall be natural white and shall conform to letter size B, type I, class 1 of V-T-285, or letter size B, type I, class 1 of V-T-295.

3.2.3.2 Stitches, seams and stitching, type II. The type of stitches and seams and stitching specified for the operations listed in table (II) shall be in accordance with Fed. Std. No. 751.

TABLE III. Stitch types, seam and stitching types

Operation	Stitch type	Seam and Stitching type
Joining two ends of material to form body (Vertical seam)	301 to 401	LSc-2
Finishing top of body	301 to 401	EFb-2

3.2.3.3 Cord. Cord shall be solid braided nylon or solid braided polypropelene with heat sealed ends.

3.2.3.4 Grommets. The liner shall have a single or double row of grommets or eyelets located at the top edge of the liner. A cord (see 3.2.3.3) shall be laced through the grommets or eyelets to secure the liner.

3.3 Marking. The body of the liner shall be marked with the manufacturers name or trademark in easily visible letters, as specified (see 6.2).

3.4 Workmanship. Liners shall be clean, free from tears, holes, cuts, weak spots, puckers, loose threads, exposed raw edges or any defect that might affect function or serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to the prescribed requirements.

4.2 Sampling.

4.2.1 Lot. Unless otherwise specified (see 6.2), a lot shall consist of all liners of the same type offered for inspection at one time.

4.2.2 Visual examination of end item. Sampling for these characteristics shall be according to level S-3 in MIL-STD-105. The Acceptable Quality Levels (AQL's) for defects listed in table IV shall be 2.5 percent defective for major defects and 4.0 percent defective for minor defects.

4.2.3 Sampling for tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

4.2.3.1 Fabric. Not less than one piece, at least 1 yard long and the full width, from the same lot used in the fabrication of the liners shall be furnished by the contractor and taken at random by the Government inspector for test purposes.

4.3 Examination.

4.3.1 End item. Liners selected in accordance with 4.2.2 shall be examined for defects listed in table IV.

TABLE IV. Classification of defects, end item

Defects	Major	Minor
Dimensions not as specified	X	
Thread not as specified	X	
Hole, cut or tear	X	
Stitches, seams and stitching not as specified	X	
Weak spots, puckers	X	
Loose threads, exposed raw edges		X
Marking illegible or missing		X
Damage or defects affecting function or serviceability	X	
Damage or defects not affecting function or serviceability		X

4.3.2 Examination of preparation for delivery. An inspection shall be made to determine that the packing and marking comply with the requirements in section 5 of this specification. Defects shall be scored in accordance with table V. Sampling shall be in accordance with MIL-STD-105. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units.

TABLE V. Classification of preparation for delivery defects

Examine	Defects
Markings	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Material	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling, or distortion of container.
Contents	Net weight exceeds the requirements of the box specification.

4.4 Tests.

4.4.1 Fabric. The methods specified in Fed. Test Method No. 191, whenever applicable, and as listed in table IV, shall be followed for testing the fabric. Any test failure shall be cause for rejection of the entire lot submitted for inspection.

TABLE V. Test methods

Test	Reference paragraph	Test method
Identification if nylon.	3.1.1	1530
Identification if polyester.	3.1.2	1600
Yarns per inch.	3.1.1	5050
Weight of cloth.	3.1.1	5041
Breaking strength.	3.1.1	5100
Shrinkage.	3.1.1	5552

4.4.2 Certificates. Manufacturer's certificates of compliance with denier and filament requirments will be accepted.

4.4.3 Vinyl-nylon. The methods specified in MIL-C-43006, whenever applicable, shall be followed for testing of the vinyl-nylon.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.1.1 Level A. Twelve liners shall be packed in a close-fitting box conforming to PPP-B-636, class weather resistant. The box shall be closed, waterproofed, and reinforced in accordance with the appendix of PPP-B-636.

5.1.2 Level B. Twelve liners shall be packed in a close-fitting box conforming to PPP-B-636, class domestic. The box shall be closed in accordance with the appendix of PPP-B-636.

5.1.3 Level C. The liners shall be packed to assure carrier acceptance and safe delivery at destination in compliance with Uniform Freight Classification rules or National Motor Freight Classification rules.

5.2 Marking. Marking shall be in accordance with 5.2.1 or 5.2.2 (see 6.2).

5.2.1 Civil agencies. In addition to markings required by the contract or order, the shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.2.2 Military agencies. In addition to markings required by the contract or order, the shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Liners covered by this specification are for use over laundry basket frames for transporting clean and soiled hospital linen.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type, size and color of liner required (see 1.2).
(c) Size of lot, if different from 4.2.1.
(d) Selection of applicable level of packing required (see 5.1).
(e) Whether civilian or military marking is required (see 5.2).

MILITARY INTERESTS:

Army - GL
Navy - YD
Air Force - 85

Preparing activity:

GSA-FSS

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.