DDD-R-591A
October 20, 1976
SUPERSEDING
Fed. Spec. DDD-R-591
January 13, 1936

FEDERAL SPECIFICATION

ROBES; BATH

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for two types of cotton bathrobes.

1.2 Classification. The bathrobes shall be first quality and of two types.

Type I - Flannelette
Type II - Terry cloth

Sizes:
1 - Small
2 - Medium
3 - Large
4 - Extra-Large

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

V-T-276 - Thread, Cotton.
UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-B-636 - Box, Shipping, Fiberboard.

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).
Fed. Test Method Std. No. 191 - Textile Test Methods.
Fed. Std. No. 751 - Stitches; Seams, and Stitching.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Laws and Regulation:

Rules and Regulations Under the Textile Fiber Products Indentification Act 16 CFR 303.

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for issuance thereof).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza., Chicago, IL 60606.)

3. REQUIREMENTS

3.1 General requirements (Type I and type II).

3.1.1 Shrinkage. Shrinkage greater than 5 percent shall be cause for rejection (see table II).

3.1.2 Colorfastness. The colorfastness to light and colorfastness to laundering of finished robes shall not be less than good (see table II).

3.1.3 Stitching. All stitches shall run not less than ten (10) to the inch and shall conform to stitch types 301 or 401, of Fed. Std. No. 751. Where double stitching is called for the gage shall be 3/16 to 5/16 inch.

3.1.4 Thread. The thread used in fabrication shall be cotton, type 1a3, 4-cord, no. 30 machine, soft finish, color, as shown in table I, V-T-276. The thread color shall match the robe fabric.

3.1.5 Seams. All seams shall conform to type 301-LSc-2 or 401-LSc-2, latest revision of Fed. Std. No. 751.

3.1.6 Hems. All hems shall have raw edges turned well under and shall be neatly sewed and finished.

3.1.7 Buttons. Bathrobes shall be without buttons and without buttonholes unless called for in the invitation for bids. (See 6.2.)

3.1.8 Sizes. Bathrobes shall be made in four sizes: small, medium, large, and extra-large to conform to measurements shown in the following table: (See 6.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

	Small	Medium	Large	Extra-large
	Inches	Inches	Inches	Inches
Neck	16	17	18	18.5
Chest measure, including overlap, pleats, etc-	48	51	54	57
Sleeve, length from center of back	33	34	35	36
Length of garment measured down middle of the back from the collar seam to the lower end of the bottom hem	45	46	47	48
Width of bottom (or length of bottom hem)	55	58	61	65

3.1.9 Tolerances. A plus or minus tolerance of not more than 1/8 inch in the hems and pleats, 1/2 inch in the length and width, 1/2 inch in the chest, and 1/4 inch in other measurements shall be permitted.

3.1.10 Tags. A tag of suitable material, indelibly marked, shall be securely attached at the inside junction of the collar and the body of the garment bearing the following information:

"Small", "Medium", "Large" or "Extra-large" (as the case may be).

3.1.11 Content label. Each bath robe shall be labeled in accordance with the textile fiber product identification act.

3.1.12 Hangers. Each garment shall be provided with a hanger which shall conform to the color of the robe. The hanger shall be made of cotton tape 1/2 inch in width with a tensile strength of 45 pounds. It shall be folded under at the ends and sewed with a double row of stitches at each end. The hanger shall be placed on the inside of the garment at the midposition of the junction of the body with the collar.

3.1.13 Colors. Unless otherwise specified (see 6.2) the bathrobes shall be white.

3.2 Type I. Type I bathrobes shall be made entirely of all cotton outing flannel.

3.2.1 Tensile strength. The tensile strength (grab method) for type I material shall not be less than 40 pounds in the warp and not less than 25 lbs in the filling. (See table II.)

3.2.2 Weight. Material shall weigh not less than 4.5 ounces per square yard.

3.2.3 Description. Type I garments shall be made of the same material throughout including the collar, belt and pockets. The material shall be matched in the garment according to the standard trade practice. The robe shall have what is known to the trade as a shawl collar and the body of the garment shall be made in three pieces; that is, one in the back and a right piece and a left piece in the front. The garment shall have one pocket on the right side. A belt of the same material, double thickness, shall be permanently attached with two rows of stitching running the full width of the belt and placed at the middle of the back.

3.2.4 Collar. The collar shall be double thickness. The front hem on both side pieces in the body of the garment shall be 3 inches in width from the bottom of the garment to a point 4 inches below the level with the bottom of the armholes where it shall widen gradually to 5 inches in the lapel part of the collar and again narrowing to 4 inches at the middle of the back in a manner to give the shawl collar a well-tailored effect.

3.2.5 Sleeves. The armholes shall be 24 inches in circumference. Except for cuffs, the sleeves shall be made of not more than two pieces of material. The width of the sleeve at the elbow (11 inches above wrist opening) shall be 9-1/4 inches wide, and the width at the wrist opening shall be 7 inches. The sleeves shall have a 3-inch cuff. Sleeve shall fit the armhole of the garment neatly and shall altogether present a well-tailored effect. Sleeves and bottom of cuff shall be double stitched, 3/16- to 5/16-inch gage.

3.2.6 Pocket. The pocket shall be sewed on the right side of the garment. The upper rear corner of the pocket shall be placed approximately 10 inches below the bottom of the right armhole and approximately 1/2-inch forward of the right seam on the right side of the garment; the pocket shall be vertical. The pocket shall measure 7-1/4 inches high and 6-3/4 inches wide; the top edge of the pocket shall be finished with a 1-1/2-inch hem. Double stitching 3/16- to 5/16-inch gage shall be used, and top corners shall be bar-tacked.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

3.2.7 Belt. A belt 2 inches wide and 74 inches long made of two thicknesses of material shall pass through two loops each placed approximately 6-1/4 inches below the bottom of the armholes. Loops shall be made of double thickness material and shall be 1/2-inch wide and of proper length for the width of the belt. Both ends of each loop shall be stitched to the garment with double rows of stitches. Both edges and ends of the belt shall be turned in and sewed. The midpoint of the belt shall be permanently attached to the garment by means of a double row of stitching placed in the middle of the back and running the width of the belt.

3.2.8 Hems. There shall be a 3-inch hem on both sides of the front. This hem shall extend and be of uniform width from the bottom edge of the garment to the points where it shall widen gradually into the lapel as described herein under "Collar". The bottom of the garment shall be fully finished with a 1-inch hem. The open edge of the pocket shall be finished with a 1-inch hem. Double stitching 3/16- to 5/16-inch gage shall be used.

3.3 Type II. Type II bathrobes shall be made entirely of all cotton terry cloth or a polyester-cotton blend containing not less than 85 percent cotton.

3.3.1 Description. Type II garments shall be made of the same material throughout, including collar, belt, and pockets. The material shall be matched in the garment according to standard trade practice. The robe shall have what is known to the trade as a "round collar" and the body of the garment shall be made in two pieces. There shall be one pocket on the right side and one on the left. There shall be a 1-1/4-inch hem on both sides of the front. The bottom of the garment and sleeves shall be finished with a 1-inch hem. The opening of the pocket shall be finished with a 1-inch hem.

3.3.2 Tensile strength. The tensile strength of the material shall be not less than 36 pounds in the warp and not less than 38 pounds in the filling. (See table II.)

3.3.3 Weight. The material shall weigh not less than 9 ounces per square yard. (See table II.)

3.3.4 Weave. The fabric shall have a terry weave. Both the ground warp and loop (top) warp shall be of two-ply yarn. The filling shall be of one-ply yarn.

3.3.5 Collar. The collar shall be of double thickness 4-1/2 inches wide. The upper surface shall be of one piece. Not more than two pieces shall be used on the under surface.

3.3.6 Tie. The tie shall be of a white tie cord, two ply, 36 inch in length excluding tassels, running through the collar and firmly fastened in center of back and also at points where it emerges from the collar.

3.3.7 Sleeves. The armholes shall be 24 inches in circumference. The width of the sleeve at the elbow (11 inches above wrist opening) shall be 9-1/4 inches, and the width at the wrist opening shall be 7 inches. Sleeves shall fit the armhole of the garment neatly and shall altogether present a well-tailored effect. Armholes shall be piped with durable white tape.

3.3.8 Pockets. A pocket shall be sewed on each side of the garment. The upper rear corners shall be placed approximately 10 inches below the bottom of the armholes and approximately 7 inches from the front edge. Pockets shall be vertical and shall measure 7-1/2 inches deep and 7 inches wide; the top edge shall be finished with a 1-inch hem. Double stitching of 3/16- to 5/16-inch gage shall be used and top corners shall be bar-tacked.

3.3.9 Belts. A belt 2-inches wide and 76 inches long, made of two thicknesses of material, shall pass through two loops each placed approximately 6 inches below the bottom of the armholes. Loops shall be made of double thickness material and shall be 1/2 inch wide and of proper length for the width of the belt. Both ends of each loop shall be turned under and stitched to the garment with double rows of stitches. The edges and ends of the belt shall be turned in and stitched along the edges. The midpoint of the belt shall be permanently attached to the garment by means of a double row of stitching placed in the middle of the back and running the width of the belt.

3.4 Workmanship. The garment shall be free from defects which may affect the appearance or serviceability of the garment. Garments shall show no raw edges of fabric or loose ends of the thread. The garments shall be well tailored and finished according to the best practice of the trade. The warp shall run in the direction of the length of the garment or any part thereof, except the warp shall run lengthwise of the belt.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection lot. Unless otherwise specified in the invitation for bids, all robes of one type and size submitted at one time shall be considered a lot for purposes of inspection and tests.

4.1.2 Inspection. Inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.1.3 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.2 Examination of preparation for delivery requirements. An examination shall be made to determine that packaging, packing, and marking requirements comply with section 5. Defects shall be scored in accordance with the following list. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed as follows shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-3 and the AQL shall be 4.0 defects per 100 units in accordance with MIL-STD-105.

Examine	Defect
Marking (exterior and interior	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, improper taping, loose strapping, inadequate stapling. Open and noncontinuous heat sealed seam of polyethylene bag. Omission of vent hole in polyethylene bag.
Content	Bulging or distortion of containers. Number per container is more or less than required.

4.3 Examination of the end item. For the purpose of visual and dimensional inspection, the sample unit shall be one bathrobe, and shall be examined for the defects listed in table I. Sampling shall be in accordance with inspection Level I of MIL-STD-105. The acceptable quality level shall be 2.5 for majors and 6.5 for minors measured in percent defectives.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

TABLE I. Visual and dimensional defects

	Major	Minor
Any weakening defect such as a smash, multiple float or loose slub in the materia	X	
Shade difference, unsightly slub, finishing and or dye streaks	X	
Hole, cut, tear, visible mend, burn, or a needle chew that may develop into a hole	X	
Spot, stains, or soiled areas	X	
Any component part or assembly omitted	X	
Any component not made in accordance with specification requirements	X	
Part of garment caught in any unrelated operation or stitching	X	
Any raw edges or loose threads		X
Bartack in secure or misplaced		X
Label missing		X
Pocket set on crookedly or poorly shaped affecting appearance		X
Puckered or loose seams	X	
Improper stitching or missing stitches		X
Dimensions not within tolerance as specified in para. 3.1.9	X	
Correct size	X	
Correct color	X	

4.4 Testing of the end item. Whenever applicable, and as listed in table II, Fed. Std. 191 shall be followed. All test reports shall contain the individual values utilized in expressing the final results. Where certificates of compliance or report of anlaysis are submitted, the government reserves the right to check test such items to determine the validity of the certificate or analysis.

4.4.1 For the purpose of end item testing, the sample unit shall be one bathrobe, and shall be tested for the defects tested in table II. Sampling shall be in accordance with inspection level S-1 of MIL-STD-105. The AQL shall be 4.0 measured in percent defectives.

TABLE II. Test methods

Characteristic	Requirement	FED-STD-191 Test method
Yarn identification (cotton)	3.2 and 3.3	1200
Weight per square yd	3.2.1 and 3.3.3	5040
Breaking strength	3.2.1 and 3.3.2	5100
Colorfastness to light	3.1.2	5660
Colorfastness to laundering	3.1.2	5612
Shrinkage test	3.1.1	7550

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B or C as specified (see 6.2).

5.1.1 Level A and B. Unless otherwise specified (see 6.2) each robe shall be pressed, folded and tied in bundles of ten. Each bundle of robes of like description, shall be wrapped with kraft paper conforming to UU-P-268; type I, Grade B. Bundles shall be secured with twine or tape.

5.1.2 Level C. The robes shall be packaged in accordance with the supplier's commercial practice.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

5.2.1 Level A. Robes of like description shall be packed in a close fitting box conforming to PPP-B-636, class weather resistant. The box when filled of its content shall be of such dimension as to climinate avoid. The box shall be closed and waterproofed with tape in accordance with the appendix to the box specification.

5.2.2 Level B. Robes of like description shall be packed in a close-fitting box conforming to PPP-B-636, class domestic. The box when filled of its content, shall be of such dimensions as to eliminate avoid. The box shall be closed in accordance with the appendix to the box specification.

5.2.3 Level C. Of like description shall be packed in containers that comply with the National Motor Freight Classification Rules or the Uniform Freight Classification Rules, as applicable.

5.3 Marking. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123 or MIL-STD-129, as applicable.

6. NOTES

6.1 Intended use. This item is intended for wear by hospital patients.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type required (see 1.2) and size required (see 3.1.8).
(c) Color (see 3.1.13).
(d) Selection of applicable level of packaging and packing (see 5.1).
(e) Size requirements (see 1.2 and 3.1.8).
(f) Button requirements (see 3.1.7).

Preparing activity:

GSA-FSS

CIVIL AGENCY COORDINATING ACTIVITY:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 30 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.