DDD-T-511D
December 21, 1970
SUPERSEDING
Fed. Spec. DDD-T-511C
April 7, 1966

FEDERAL SPECIFICATION

TOWELS, DISH AND DISHCLOTHS (CRASH, COTTON, AND COTTON AND LINEN-MIXED): CLOTH, CRASH, COTTON

This specification was approved by the Commissioner, Federal Supply Service, General Services Admistration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers unbleached cotton and linen-mixed crash towels; bleached cotton crash towels; and bleached cotton toweling, either plain or with a woven colored stripe along each selvage edge.

1.2 Classification.

1.2.1 Types, classes, and sizes. The cloth shall be of the following types, classes, and sizes, as specified (see 6.2):

Type I - Towel or dishcloth.

Class 1 - Cotton warp and linen filling (unbleached).
Class 2 - All cotton (bleached).

Size 1 - 17 by 30 inches.
Size 2 - 17 by 36 inches.
Size 3 - 17 by 14-1/2 inches.

Type II - Cloth, crash, cotton (bleached).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

FSC 7210
8305

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the current version before use.

Federal Specifications:

V-T-276 - Thread, Cotton.
PPP-B-636 - Box, Fiberboard.
PPP-F-320 - Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes.
PPP-P-1134 - Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics).

Federal Standards:

FED-STD-4 - Glossary of Fabric Imperfections.
FED-STD-123 - Marking for Domestic Shipment (Civil Agencies).
FED-STD-191 - Textile Test Methods.
FED-STD-751 - Stitches, Seams and Stitchings.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-B-17757 - Boxes, Fiberboard, Corrugated (Modular Sizes).

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580.)

Technical Manual of the American Association of Textile Chemists and Colorists

(Copies may be obtained from the AATCC National Headquarters, P.O. Box 12215, Research Triangle Park, NC 27709.)

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc., Agent, 1616 P Street N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification

(Application for copies shall be addressed to the Uniform Classification Committee, Tariff Publishing Officer, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Yarn.

3.1.1.1 Cotton. The yarn for the warp of the type I, class 1 towels and the warp and filling of the type I, class 2 towels and type II cloth shall be cotton, tested as specified in 4.4.

3.1.1.2 Linen. The yarn for the filling of the type I, class 1 towels shall be linen, tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the current version before use.

3.1.2 Thread. The cotton thread for hemming shall conform to type IA1 for type I, class 1 towels and type IA2 for type I, class 2 towels, of V-T-276. The thread used with stitch type 301 shall be ticket No. 50, 3 ply. The thread used with stitch type 401 shall be ticket No. 50, 3 ply for the needle and ticket No. 70, 2 ply for the looper.

3.2 Physical requirement. The type I towels and type II cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

TABLE I. Physical requirements

	Weight per square yard, ounces (minimum)	Yarns per inch (minimum)		Breaking strength, pounds, (minimum)		Weave
		Warp	Filling	Warp	Filling	
Type I class 1	6.0	28	22	45	35	Plain
Type I, class 2; and type II	5.8	38	30	50	40	Plain

3.2.1 Finish.

3.2.1.1 Type I, class 1. The cloth for the type I, class 1 towels shall be scoured and unbleached.

3.2.1.2 Type I, class 2, and type II. The type II cloth and the cloth for the type I, class 2 towels shall be scoured and bleached.

3.2.2 Stripes. When specified (see 6.2), the type I towels and type II cloth shall have woven, colored stripes, 3/16 to 5/16 inch wide, located 7/16 to 9/16 inch from each selvage edge.

3.2.2.1 Colorfasteness (stripes). The stripes shall show "good" colorfastness to combined laundering and bleaching when tested as specified in 4.4.

3.2.3 Nonfibrous material. The starch and protein content, including chloroform-soluble and water-soluble material of the finished type I towels and type II cloth shall not exceed 5.0 percent when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

3.2.4 Rate of absorbency. The height of the rise of the colored water shall be a minimum of 6 centimeters in 5 minutes in both warp and filling direction for both type I towels and type II cloth when tested as specified in 4.4.

3.3 Hems and selvages. The finished towel shall be hemmed at each end. The sides of the towel or cloth shall have two fast selvages, or one fast selvage and one hemmed side or two hemmed sides. There shall be no raw edges showing on the finished towel.

3.3.1 End hems. The hem at each end of the towel shall be 1/4 to 3/8 inch wide. Stitching shall be 1/16 to 1/8 inch from the turned edges, 10 to 12 stitches per inch using stitch type 301 and seam type EFb-1 of FED-STD-751. At the beginning and at the end of each hem, the hem shall be backstitched at least 1/2 inch.

3.3.2 Side hems. When side hems are used, they shall be 1/4 to 3/8 inch wide. Stiching shall be 1/16 to 1/8 inch from the turned edges, 10 to 12 stitches per inch using stitch type 301 or 401 and seam type EFb-1 of FED-STD-751.

3.4 Size. The finished measurements of the towels shall be as follows:

Type	Size	Length (inches)	Width (inches) 1/
		Minimum	
I	1	30	17
I	2	36	17
I	3	14-1/2	17
II	-	See 3.6.1	17

1/ The width shall be inclusive of selvages, and a tolerance of ± 1/2 inch will be permitted.

3.5 Marking for identification (civil agencies). When identification marking is required by civil agencies on type I towels, the marking requirement shall be as specified (see 6.2).

3.6 Type II, put-up.

3.6.1 Civil agencies (bolt put-up). Bolts of 50 ± 2-1/2 yards of cloth shall be put up at the suppliers's option by winding into rolls on a flat chipboard or cardboard insert of not less than 1/8 inch in thickness by 12 inches wide, or by folding open width in one yard flat folds.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:35Z
Check the source to verify that this is the current version before use.

3.6.2 Military requirements. Unless otherwise specified (see 6.2), the cloth shall be put up on rolls as specified in PPP-P-1134.

3.7 Fiber identification. Each type I towel, and each roll or bolt or type II cloth shall be labeled, ticketed, or invoiced for fiber content in accordance with the rules and regulations Under the Textile Fiber Products Identification Act.

3.8 Workmanship. The finished towels and cloth shall conform to the quality established by this specification. The occurrence of defects for the type I towels shall not exceed the applicable acceptable quality levels (AQLs) specified. For type II cloth, the points per 100 square yards, when calculated as specified in section 4, shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection and acceptance shall be performed in accordance with MIL-STD-105 except when otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be tested in accordance with all requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.2.2 Examination of the type I towel. Defects found during this examination shall be classified in accordance with 4.2.2.1 through 4.2.2.4. The sample unit shall be one towel. The lot size shall be expressed in units of one towel each. The inspection levels and AQL shall be as specified in 4.2.2.3 and 4.2.2.4.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the current version before use.

4.2.2.1 Visual examination. The towels shall be visually examined for defects listed in table II. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition in the towel, in which case only the most serious shall be counted.

TABLE II. Classification of defects

Examine	Defect	Classification	
		Major	Minor
Quality of material	Cut, hole or tear	X	
	Smash	X	
	Float and skip:		
	- Multiple 3/4 inch or more in combined directions	X	
	- multiple more than 1/4 inch but less than 3/4 inch in combined directions		X
	- Single 4 inches or more in length		X
	Broken or missing yarn:		
	- Two or more contiguous	X	
	- Single 4 inches or more in length		X
	Fine or light filling bar or light place	X	
	Hitchback:		
	Opening between yarns 1/16 inch or more at widest place		X
	Slub, slug, or gout, jerked-in filling or slough off more than 1/8 inch in thickness		X
	Spot, stain, or streak over 1/8 inch in longest dimension clearly visible when viewed at a normal inspection distance (approximately 3 feet)		X
	Selvage:		
	- Cut, torn, broken, or omitted	X	
	- Curled, scalloped, or folded		X
	Type I, class 2 towel not bleached		X
	Color of stripes, when applicable, other than specified		X
	Stripes, when applicable less than 3/16 inch or more than 5/16 inch wide		X
	Stripes, when applicable, located less than 7/16 inch or more than 9/16 inch from selvage edge		X
	Objectionable odor.		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects (cont'd)

Examine	Defect	Classification Major	Minor
Workmanship	Hem less than 1/4 inch or more than 3/8 inch wide		X
	Hem omitted	X	
	Raw edge showing stitching less than 1/16 inch or more than 1/8 inch from turned edge		X
	Less than 10 or more than 12 stitches per inch		X
	Wrong stitch or stitching type		X
	Open seam over 1 inch in length	X	
	Open seam up to and including 1 inch in length		X
	Loose stitch tension resulting in loosely secured seam		X
	Tight stitch tension (stitches break when strain is applied to seam or stitching)		X
	Backstitching at beginning and end of end hems omitted or less than 1/2 inch		X
	Needle chew		X
Marking (when specified)	Omitted, incomplete, illegible, incorrect, or misplaced		X

4.2.2.2 Towel quality inspection. Each towel in the sample size shall be designated as first or second quality, for inspection purposes only, in accordance with 4.2.2.2.1 and 4.2.2.2.2.

4.2.2.2.1 A first quality towel shall be defined as follows:

Contains no major defects listed.
Contains not more than two minor defects listed.

4.2.2.2.2 A second quality towel shall be defined as follows:

Contains no hole, cut, tear, or smash.
Contains not more than two major defects listed.
Contains not more than five total defects (major and minor combined) listed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

4.2.2.3 Inspection level and AQL. The inspection level shall be level I of MIL-STD-105 and the AQL for first quality towels shall be 4.0 percent defective (seconds). Any towel in the sample that does not meet the criteria for first or second quality towels (see 4.2.2.2.1 and 4.2.2.2.2) shall be cause for rejection of the lot.

4.2.2.4 Dimensional examination. Any finished length or width, inclusive of selvages, less than specified, shall be classified as a defect. The AQL shall be 4.0 percent defective and the inspection level shall be S-3 of MIL-STD-105.

4.2.3 Examination of the type II cloth. Defects found during this examination shall be classified in accordance with 4.2.3.1 through 4.2.3.3.

4.2.3.1 Yard-by-yard examination. Each roll in the sample shall be examined on one side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects as defined in Section I of FED-STD-4 which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.2.3.1.1, except that only those slubs and knots which exceed the limits shown on figure 1 of FED-STD-4 shall be scored. No linear yard (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 40 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceed 60 points. If one roll exceeds 60 points per 100 square yards, a second sample of 20 rolls shall be examined only for individual roll quality examination. The lot shall be unacceptable if one or more rolls in the second sample exceeds 60 points per 100 square yards. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 square yards}$$

4.2.3.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

The following defects, when present, shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth.
Width less than specified.
Not bleached.
Stripes (when applicable):
Not color specified.
Less than 3/16 inch or more than 5/16 inch wide.
Located less than 7/16 or more than 9/16 inch from selvage edge.

4.2.3.2 Examination for length.

4.2.3.2.1 Individual roll (or piece). During the yard-by-yard examination, each roll (or piece) in the sample shall be examined for length. Any length found to be less than the minimum specified, more than the maximum specified (when applicable, or more than 2 yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls (or pieces) in the sample are defective in respect to length.

4.2.3.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual length of rolls (or pieces) in the sample is less than the total of the lengths marked on the tickets.

4.2.3.3 Examination for compliance with Rules and Regulations Under the Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll (or piece) in the sample shall be examined for compliance with Rules and Regulations Under the Textile Fiber Products Identification Act. Each roll (or piece) not labeled in accordance with this act shall be a defect. The lot shall be unacceptable if two or more of these defects occur.

4.3 Examination of preparation for delivery requirements.

4.3.1 Type I. An examination shall be made to determine that packaging, packing and marking comply with the section 5 requirements of this specification. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery, with the exception that it need not be sealed. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadquate application of components, such as: incomplete closure of container flap; loose strapping; inadequate stapling. Bulged or distorted container. Inadequate securing or sealing of wrapping materials and containers. Open and non-continuous heat sealed seam and closure of polyethylene bag. Omission of vent hole in polyethylene bag.
Content	Number of packages per shipping container is more or less than required. Towels of different class in same package 1/. Number of towels per package not as required 1/.

1/ Three packages from each shipping container in the sample shall be examined.

4.3.2 Type II. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing and marking comply with the section 5 requirements of this specification.

4.4 Testing of the end item. The methods of testing specified in FED-STD-191, wherever applicable and as listed in table IV shall be followed. The physical and chemical values specified in section 3 apply to the results of determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit for testing shall be as follows:

Type I, classes 1 and 2:
(a) Sizes 1 and 2 - 2 towels each.
(b) Size 3 - 4 towels.

Type II, 3 continuous yards full width of the finished cloth. The sample size (number of sample units) shall be as shown below. The lot size shall be expressed in units of 1 yard, or one towel, as applicable. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. All test reports shall contain the individual values utilized in expressing the final result.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE IV. Test methods

Characteristic	Requirement paragraph	Test method
Cotton yarn identification	3.1.1.1	1200 1/
Linen yarn identification	3.1.1.2	1210 1/
Weight per square yard	3.2	5041
Yarns per inch:		
Warp	3.2	5050
Filling	3.2	5050
Breaking strength		
Warp	3.2	5100
Filling	3.2	5100
Weave	3.2	Visual 2/
Colorfastness (stripes) to:		
Combined laundering and bleaching	3.2.2.1	5605
Nonfibrous material	3.2.3	2611
Rate of absorbency:		
Warp	3.2.4	4.4.1
Filling	3.2.4	4.4.1

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ One determination per sample unit and the results reported as "pass" or "fail".

4.4.1 Absorbency test. Samples of cloth 2 cm. wide and not less than 15 cm. long shall be cut from both the warp direction and the filling direction of the cloth. The specimens shall be suspended vertically so that approximately 3 cm. of the specimen is immersed in a dye solution of Acid Red 87 (color index No. 45380 of the Technical Manual of the American Association of Textile Chemists and Colorists) and distilled water. The dye solution shall be of sufficient intensity as to allow ready identification of the water level and rise of the solution in the fabric. Small weights shall be fastened to the end of the specimen to keep it immersed through the test. The measurement of the rise of the solution shall be made from the level of the liquid. The rate of absorbency shall be measured as the distance traversed by the liquid in the specimen during the five minute interval. The time shall be recorded from the instant the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

specimen end is in contact with the solution. The rate of absorbency of the sample unit shall be the average of the results obtained from the five specimens in each of the warp and filling directions and shall be reported separately to the nearest 0.1 cm.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Towels or dishcloths (type I). Towels or dishcloths of one description only shall be packaged in bundles of twelve each with every six reversed. Six towels shall be laid flat, one on top of the other, and be folded to approximate demensions of 14-1/2 by 7-1/2 inches. Each bundle of twelve towels shall be secured with cotton tape or twine and then be placed in a close-fitting clear polyethylene film bag. The bag shall be fabricated from polyethylene film having a thickness of 0.0015-inch (± 20 percent tolerance). The polyethylene bag shall be formed with heat sealed seams that are straight, continuous, and parallel to each other and the formed edges of the bag. The bag closure shall be effected by heat sealing with the heat seal made as close as possible to the open end. A 1/4-inch diameter hole shall be made at one corner of each bag to allow excess air to escape. Alternatively, a mechanical tie (paper of vinyl plastic covered soft steel wire, aluminum band, etc.) shall be applied to close the bag opening.

5.1.1.2 Cloth (type II). Cloth, put-up in rolls as specified in 3.6.2 shall be packaged in accordance with the applicable level A requirements of PPP-P-1134.

5.1.2 Level C. Towels or dishcloths (type I) and cloth (type II) shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing. Packing shall be level A, B, or c as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Towels or dishcloths (type I). Two hundred and eighty-eight towels or dishcloths of one description only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container assembled, closed, and reinforced conforming to class weather-resistant, grade V2s, size 3A of MIL-B-17757. The fiberboard for the box liner shall conform to type CF, class weather-resistant, variety DW, grade V15c of MIL-B-17757. Level A packages shall be packed flat, three in length, one in width, and eight in depth within a shipping container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

5.2.1.2 Cloth (type II). Cloth, packaged as specified in 5.1, shall be packed in accordance with the applicable level A requirements of PPP-P-1134.

5.2.2 Level B.

5.2.2.1 Towels or dishcloths (type I).

5.2.2.1.1 Military requirements. Two hundred and eighty-eight towels or dishcloths of one description only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container assembled and closed conforming to class domestic, grade 275, size 3A of MIL-B-17757. The fiberboard for the box liner shall conform to type CF, class domestic, variety DW, grade 275 of MIL-B-17757. Level A packages shall be packed flat, three in length, one in width, and eight in depth within a shipping container.

5.2.2.1.1.1 When specified (see 6.2), the shipping container shall be a grade V3c or V3s fiberboard box fabricated in accordance with MIL-B-17757 and closed in accordance with the appendix of the box specification. The shipping container material may also be grade V4s of PPP-F-320.

5.2.2.1.2 Civil agencies. Three hundred towels or dishcloths of one description only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each container shall be fitted with a taped box liner conforming to class domestic, variety DW, grade 275 of PPP-B-636. Inside dimensions of each shipping container packed with size 1 or 2 towels shall approximate 24 inches in length, 14 inches in width, and 19 inches in depth. Approximate dimensions are furnished as a guide only. Inside dimensions of each shipping container packed with size 3 towels shall be determined by the supplier to insure a snug-fit of the contents to be packed therein. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.2 Cloth (type II). Cloth, packaged as specified in 5.1, shall be packed in accordance with the applicable level B requirements of PPP-P-1134.

5.2.3 Level C. Towels or dishcloths (type I) and cloth (type II), packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.

5.3.1 Towels or dishcloths (type I).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

5.3.1.1 Civil agencies. In addition to any special marking required by contract or order, interior packages and shipping containers shall be marked in accordance with FED-STD-123.

5.3.1.2 Military requirements. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.1.3 Polyethylene bagged packages. Polyethylene bagged packages shall have the required identification information listed below, legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification. The bag or label shall indicate only the following information:

STOCK NUMBER
ITEM DESCRIPTION
TYPE, CLASS, AND SIZE
QUANTITY

5.3.2 Cloth (type II). In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirement of PPP-P-1134.

6. NOTES

6.1 Intended use. The towels and towel cloth are intended for use by civil and military agencies of the Government.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Type, class and size required (see 1.2.1).
(c) Color of stripes, if required (see 3.2.2).
(d) When identification marking for civil agencies is required (see 3.5).
(e) Length of type II cloth put up on rolls for military requirements if other than specified (see 3.6.2).
(f) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(g) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1.1.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:35Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 82

Review activities:

Army - MD
Navy - MS
Air Force - 45

User activities:

Army - SM
Navy - MC

Preparing activity:

Army - GL

CIVIL AGENCIES INTEREST:

GSA-FSS
HEW
JUS-FPI
VA-DMS

Project No. 7210-0137

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:35Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION DDD-T-511D; Towels, Dish and Dishcloths (Crash, Cotton, and Cotton and Linen-Mixed); Cloth, Crash, Cotton

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:35Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:35Z
Check the source to verify that this is the current version before use.