L-F-475A
Interim Amendment-3
September 24, 1982
Superseding
Interim Amendment-2
February 9, 1971

INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

FLOOR COVERING VINYL, SURFACE (TILE AND ROLL), WITH BACKING

This interim amendment was developed by the Furniture Commodity Center, Office of Personal Property, General Services Administration, Washington, D.C., 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification L-F-475A, dated March 11, 1965.

The approved item name for this document is TILE, VINYL RESIN

Paragraph 1.1, delete in its entirety and substitute:

1.1 Scope. This specification covers floor covering having a vinyl plastic wearing surface on an organic or inorganic or filled fibrous composition (non-abestos formulated) backing.

Paragraph 1.2.1, change the Overall thickness, inches, minimum column to read as follows:

Grade	Overall
A	0.080
B	0.060
C	0.050

Paragraph 2.1, delete in its entirety and substitute:

2.1 The following documents of the issue in effect on the date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

Under Federal Standards add the following:

"Fed. Test Method Std. 501 - Floor Coverings, Resilient, Nontexile: Sampling and Testing."

Delete the paragraph beginning "Single copies of this specification, etc." and substitute:

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:10Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, MA; New York, NY; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Denver, CO; San Francisco, IL; Los Angeles, CA; and Seattle, WA.)

Add the following paragraph:

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies shall be addressed to the National Motor Freight Traffic Association, Inc., Agent, 1616 P Street, N.W., Washington, D.C. 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Traffic Publishing Officer, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, Illinois 60606.)

Paragraph 3.2, delete the first sentence and substitute:

"The wearing surface shall be a vinyl plastic wear layer consisting of a binder and, if included, fillers and pigments, stabilized against heat and light deterioration."

Paragraph 3.3. delete in its entirety and substitute:

Paragraph 3.3 Backing. The backing shall be fabricated of organic fibers, inorganic fibers or filled fibrous composition (non-asbestos formulated) as specified (see 6.2). Organic fibers shall be felt treated with a resin or asphalt saturant. Inorganic fibers shall be saturated with an alkali and moisture-resistant polymeric material. Filled fibrous compositions (non-asbestos formulated) shall be saturated with an alkali and moisture-resistant polymeric material. The backing shall be bonded to the wearing surface. When an attempt is made to pull the wearing surface from the back by hand, the backing shall delaminate or break before the bonding fails. The exposed side of the backing shall not mar the wearing surface or cause sticking where they have been in contact."

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:10Z
Check the source to verify that this is the current version before use.

Paragraph 3.4, delete in its entirety and substitute:

3.4 Color and pattern. The color and pattern of the wearing surface shall be as specified (see 6.2 and 6.3). In through-surface patterns the color and pattern shall extend throughout the thickness of the wearing surface. In surface pattern products the color and pattern need not extend throughout the entire thickness of the wearing surface (see 6.2).

Paragraph 3.5.2, change the Overall thickness, inches, minimum column to read as follows:

Grade	Overall
A	0.080
B	0.060
C	0.050

PAGE 3

Paragraph 3.9, line 12, insert this sentence before the last sentence:

"The scratch width requirement shall not apply to embossed areas nor to textured surfaces."

Paragraph 3.10, line 2, delete "smooth and".

Table I, under the column titled "Defect" delete "Not smooth" and the "X" under "Minor".

PAGE 4

Paragraph 4.5, add the following sentences:

"The sample unit for Type II shall be taken from the end of the roll; only one sample unit shall be taken from any given roll. The rolls for the tests on Type II material shall be determined at random as required in MIL-STD-105."

Paragraph 4.6.1, delete lines 5 and 6 and following the word "humidity" in line 4 insert the following: "and at a temperature of 23.0° ± 1.1°C. (73.4° ± 2°F.) for a period of not less than 16 hours.

Paragraph 4.6.2, line 10, delete the last three sentences and substitute:

"The wearlayer thickness and overall thickness of embossed or textured patterns may be determined by the above method if the pattern consists of substantially flat areas larger than the micrometer foot. For patterns that do not contain suitable flat areas, thickness of the wearlayer should be determined by Method 2151 of Fed. Test Method Std. 501, at randomly selected points in the specimen. At least 5 points should be measured and averaged.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

The thickness of the backing should be measured by Method 2151 and added to the average obtained for the wearlayer to obtain overall thickness. In cases of dispute the thickness of the wearlayer should be determined by measuring the volume of a 6" x 6" section of the specimen and dividing by the area of the specimen to obtain the average overall thickness. Thickness of the backing shall be determined by using Method 2151 and this value subtracted from the overall thickness to obtain the average wearlayer thickness."

PAGE 8

Paragraph 4.6.7.2.3, line 24, insert this sentence after "of the test.":

"The scratch shall be made in smooth areas only. Embossed and textured areas shall be avoided."

Paragraph 6.1, delete the last sentence and substitute:

"For on-grade and below-grade floors, inorganic backing or filled fibrous composition (non-asbestos formulated) backing should be specified (see 3.3 and 6.2)."

Paragraph 6.2(c), delete in its entirety and substitute:

6.2(c) Whether backing shall be organic, inorganic, or filled fibrous composition (non-asbestos formulated) (see 3.3 and 6.1)

Paragraph 6.2, change 6.2(e) to read: "Through-surface pattern required (see 3.4, 6.3, and 6.6)." Reletter the present 6.2(e) and the following items under 6.2 accordingly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.